

ASX Announcement

ASX Code: RVR

24 June 2015

Liontown Deposit JORC 2012 Resource Estimate

Highlights:

- JORC 2012 Resource estimate for the Liontown deposit of 2.3Mt @ 8.4% Zn Eq.
- Total Thalanga Operations JORC 2012 Resource estimate of 5.0Mt @ 12.4% Zn Eq.
- Liontown contains a substantial higher grade core (up to 20% Zn Eq.) – open at depth
- More work will be undertaken to further define the higher grade core
- Liontown is not currently included in the Thalanga Restart Plan, however may be at a later point

Zinc developer Red River Resources Ltd (“Red River” or the “Company”) is pleased to announce updated mineral resource estimates for the Liontown deposit, part of its Thalanga Project, 60km south-west of Charters Towers in Central Queensland. The resource estimate, based on historical data, was independently completed by Mining One Consultants Pty Ltd (Mining One) in June 2015.

Table 1 Liontown Project Resources (>5% Zn Eq.) (30 May 2015)

| Resource Category | Type | Tonnage (kt) | Cu (%) | Pb (%) | Zn (%) | Au (g/t) | Ag (g/t) | Zn Eq. (%) |
|-------------------|--------------------|--------------|------------|------------|------------|------------|-----------|------------|
| Indicated | Fresh | 334 | 0.4 | 1.9 | 4.6 | 1.2 | 20 | 8.3 |
| | Transition | 34 | 0.5 | 1.3 | 4.0 | 1.4 | 29 | 7.6 |
| | Oxide | 36 | 0.7 | 1.5 | 4.4 | 1.7 | 31 | 9.0 |
| | Sub Total | 403 | 0.5 | 1.8 | 4.6 | 1.3 | 21 | 8.3 |
| Inferred | Fresh | 1,586 | 0.5 | 1.5 | 4.6 | 0.8 | 28 | 8.2 |
| | Transition | 85 | 0.7 | 1.7 | 5.4 | 0.4 | 15 | 9.4 |
| | Oxide | 184 | 1.0 | 1.3 | 4.7 | 0.8 | 12 | 9.3 |
| | Sub Total | 1,855 | 0.5 | 1.5 | 4.6 | 0.8 | 26 | 8.4 |
| Total | All | 2,258 | 0.5 | 1.6 | 4.6 | 0.8 | 25 | 8.4 |
| Total | Fresh/Trans | 2,038 | 0.5 | 1.6 | 4.6 | 0.8 | 26 | 8.3 |

Tonnages and grades are rounded. Discrepancies in totals may exist due to rounding.

Zinc equivalent (Zn Eq.) has been calculated using the metal selling prices, recoveries and other assumptions contained in Table 2 of this announcement. It is Red River’s opinion that all elements included in the metal equivalent calculation have a reasonable potential to be recovered and sold.

The resource estimates for the Liontown deposit have been classified in accordance with the JORC Code (JORC 2012) and supersedes the JORC 2004 resource estimates for Liontown released by Liontown Resources Limited (ASX:LTR) (2 April 2008, Upgraded Resource Statement for the Liontown Deposit).

Zinc equivalent (Zn Eq.) calculation parameters are listed in Table 2. The metallurgical recoveries are derived from historical metallurgical recoveries from test work carried out on Liontown samples and the Thalanga deposit. The Liontown deposit is related to and of a similar style of mineralisation to the Thalanga Operations and it is appropriate to apply similar recoveries. It is Red River's opinion that all elements included in the metal equivalent calculation have a reasonable potential to be recovered and sold.


Table 2 Zinc Equivalent Calculation Factors

| Metal | Price | Unit | Recoveries | Zn Eq. Factors |
|------------------------|-----------|---------|------------|----------------|
| Copper | US\$3.00 | US\$/lb | 80% | 3.3 |
| Lead | US\$0.90 | US\$/lb | 70% | 0.9 |
| Zinc | US\$1.00 | US\$/lb | 88% | 1.0 |
| Gold | US\$1,200 | US\$/oz | 15% | 0.05 |
| Silver | US\$17.00 | US\$/oz | 65% | 0.025 |
| FX Rate: A\$0.85:US\$1 | | | | |

1. Background

Red River acquired the Thalanga project located in Northern Queensland Australia in late 2014. Red River subsequently engaged Mining One to complete a JORC 2012 compliant Resource estimate covering the Liontown deposit. The deposit is located within EM14161 controlled by Red River Resources. The Liontown deposit is approximately 40km south of the regional center of Charters Towers in Queensland, Australia.

Figure 1 Liontown Location Plan




Diamond and Reverse Circulation drilling has been completed over multiple drill campaigns within the Liontown deposit area. The Liontown deposit is classified as a volcanogenic-massive-sulphide type (VHMS) where copper, zinc, lead and silver mineralisation is found associated with a suite of sulphide minerals including sphalerite, galena, chalcopyrite, pyrite and other minor sulphide assemblages.

The source drilling and sampling data was supplied by Red River whereby a 3D interpretation of the mineralised domain was constructed by Mining One using sectional interpretation strings to build the domain wireframes.

A historical resource estimate was completed by McDonald Speijers in 2008 that used a 2D method of assigning gold, silver and base metal grades to sectional interpretation of the deposit. The report compiled in 2008 contained detailed information on the QAQC protocols, drilling campaigns and overall geological interpretation of the deposit. Mining One has used this information to guide aspects of this 2015 resource estimate.

An ordinary kriged estimate was run to estimate copper, zinc, lead, silver and gold grades into the block model. The resources have been reported above a 5% Zn Eq cut-off into inferred and indicated categories. The Zn Eq. % grade tonnage curve is shown below.

Figure 2 Liontown Project Resources – Zn Eq. (%) Grade Tonnage Curve



Source: Resource Estimation of Liontown Deposit (Mining One, June 2015)


2. Higher Grade Core at Lontown

A review of the Lontown block model (Figure 3) has indicated that an east plunging higher grade core (10-20% Zn Eq.) exists and is open at depth.

Mineable Shape Optimiser (which produces optimized stope designs) work has commenced to understand whether this high grade core can be mined, and if so, work will then start on more detailed mine design and scheduling.

The objective is to complete a mine design for Lontown, so there is a clearly identified scenario (capital expenditure, timeline and commodity price / foreign exchange rate) which will allow the deposit to be mined.

Figure 3 Lontown Resource Blocks (All Domains)




Source: Resource Estimation of Lontown Deposit (Mining One, June 2015)

The primary target to increase the Lontown resource position is to complete extensional drilling down plunge of the domains 6, 7, 8 (Figure 4). There exists a higher grade zone of base metal mineralization within these domains that shows a 70 plunge towards the east.

Although data is not sufficient at depth to accurately quantify the resource upside targets it is clear that the mineralized system does extend down dip and down plunge towards the east. Additional drilling will provide confirmation of these interpreted targets.

Work has commenced on a resource definition drilling program to seek to confirm the interpreted targets and increase the high grade resource at Lontown.

Figure 4 Liontown Resource Upside Potential



Source: Resource Estimation of Liontown Deposit (Mining One, June 2015)

3. Drilling Data

The drill database supplied to Mining One was named “DH_LiontownWaterloo.mdb”, and contained a total of 200 holes that were used for the purposes of the resource estimate. The drilling dataset is comprised of diamond and reverse circulation holes drilled from surface locations.

Drilling has been completed within the project area since the 1950’s, a summary of drilling phases was compiled in the 2008 resource report for Liontown, a summary of these phases is shown in Table 3 below, details of the holes used to estimate resources are summarised in Table 4.

Table 3 Historical Drilling Phases (2008 Resource Report)

| Drillholes | Hole Type | Number of Holes | Time Period | Company |
|-------------------|-----------|-----------------|-------------|--------------------|
| LLD001-060 | DDH | 60 | 1970-1973 | Nickel Mines |
| LLD101-127 | DDH | 27 | 1982-1983 | Esso |
| LRC001-050 | RC | 50 | 1987 | Great Mines |
| LLD128-137 | DDH | 10 | 1994 | Pancontinental |
| LLRC065-076, >090 | RC | 33 | 1994-1995 | Pancontinental |
| LTD001-016 | DDH | 16 | 2007 | Liontown Resources |
| LTD017-030 | DDH | 14 | 2007 | Liontown Resources |

Table 4 Historical Drilling Summary – Resource Estimation

| Deposit | Hole Type | No. Holes | Metres (m) | Ave Depth (m) |
|----------|---------------------|-----------|------------|---------------|
| Liontown | Diamond | 99 | 21,209.32 | 214.23 |
| | Reverse Circulation | 121 | 17,273.10 | 142.75 |
| | Totals | 220 | 38,482.42 | 175 |

4. Combined Thalanga Operations Mineral Resource Estimate

The combined Thalanga Operations Mineral Resource Estimate is broken down on a deposit by deposit basis as per Table 5.

Table 5 Thalanga Operations Mineral Resource Estimate by Deposit

| Project | Resource Class | Tonnage (kt) | Cu (%) | Pb (%) | Zn (%) | Au (g/t) | Ag (g/t) | Zn Eq. (%) |
|--|------------------|--------------|------------|------------|-------------|------------|-----------|-------------|
| West 45⁽¹⁾ | Measured | - | - | - | - | - | - | - |
| | Indicated | 585 | 0.6 | 3.6 | 8.3 | 0.3 | 70 | 15.3 |
| | Inferred | 6 | 0.9 | 0.8 | 3.7 | 0.1 | 15 | 7.8 |
| | Sub Total | 591 | 0.6 | 3.5 | 8.3 | 0.3 | 69 | 15.2 |
| Thalanga Far West⁽²⁾ | Measured | 73 | 1.8 | 1.6 | 5.3 | 0.2 | 41 | 13.7 |
| | Indicated | 494 | 1.6 | 1.6 | 5.3 | 0.2 | 40 | 13.0 |
| | Inferred | 591 | 1.7 | 2.1 | 6.3 | 0.3 | 57 | 15.2 |
| | Sub Total | 1,158 | 1.7 | 1.9 | 5.8 | 0.2 | 49 | 14.4 |
| Orient⁽³⁾ | Measured | - | - | - | - | - | - | - |
| | Indicated | 496 | 0.9 | 1.8 | 7.7 | 0.2 | 44 | 13.4 |
| | Inferred | 44 | 0.8 | 1.8 | 10.9 | 0.2 | 46 | 16.2 |
| | Sub Total | 540 | 0.9 | 1.8 | 7.9 | 0.2 | 44 | 13.6 |
| Waterloo⁽⁴⁾ | Measured | - | - | - | - | - | - | - |
| | Indicated | 406 | 2.7 | 2.1 | 13.4 | 1.4 | 68 | 24.6 |
| | Inferred | 301 | 0.9 | 0.9 | 7.9 | 0.4 | 20 | 8.8 |
| | Sub Total | 707 | 1.9 | 1.6 | 11.0 | 1.0 | 48 | 17.8 |
| Liontown⁽⁵⁾ | Measured | - | - | - | - | - | - | - |
| | Indicated | 367 | 0.5 | 1.8 | 4.6 | 1.3 | 21 | 8.3 |
| | Inferred | 1,671 | 0.5 | 1.5 | 4.6 | 0.8 | 26 | 8.4 |
| | Sub Total | 2,038 | 0.5 | 1.6 | 4.6 | 0.8 | 25 | 8.4 |
| Thalanga Project | Measured | 73 | 1.8 | 1.6 | 5.3 | 0.2 | 41 | 13.7 |
| | Indicated | 2,348 | 1.2 | 2.3 | 7.8 | 0.6 | 50 | 14.9 |
| | Inferred | 2,613 | 0.8 | 1.6 | 5.5 | 0.6 | 33 | 10.1 |
| | Total | 5,034 | 1.0 | 1.9 | 6.6 | 0.6 | 41 | 12.4 |

Tonnages and grades are rounded. Discrepancies in totals may exist due to rounding.

Zinc equivalent (Zn Eq) has been calculated using the metal selling prices, recoveries and other assumptions contained in the announcements referred to below. It is Red River's opinion that all elements included in the metal equivalent calculation have a reasonable potential to be recovered and sold.

(1) Stuart Hutchin, Mining One Consultants, 31 Jan 2015. ASX Release: Thalanga Project – Updated Mineral Resource Estimate (11 February 2015)

(2) Resource Estimation of the Thalanga Far West Deposit, Mining One Consultants, 21 January 2015. ASX Release: Red River Delivers Thalanga Far West Maiden JORC 2012 Resource of 1.2Mt @ 14.3% Zinc Equivalent (27 January 2015)


(3) Stuart Hutchin, Mining One Consultants, 31 Jan 2015. ASX Release: Thalanga Project – Updated Mineral Resource Estimate (11 February 2015)

(4) Stuart Hutchin, Mining One Consultants, 7 Feb 2015. ASX Release: Waterloo Deposit – Updated Mineral Resource Estimate (24 April 2015)

(5) Stuart Hutchin, Mining One Consultants, 30 May 2015. Table 2 of ASX Release: Liontown Deposit JORC 2012 Resource Estimate (24 June 2015)

Waterloo and Liontown resource estimates exclude oxide material

On behalf of the board



Donald Garner
Managing Director
Red River Resources Limited

End.

For further information please visit Red River's website www.redriverresources.com.au or contact us:

Donald Garner
Managing Director
dgarner@redriverresources.com.au
M: +61 438 338 496

Paul Hart
Non-Executive Director
phart@redriverresources.com.au
M: +61 421 051 474

Nathan Ryan
NWR Communications
nathan.ryan@nwrcommunications.com.au
M: +61 420 582 887



ACN 100 796 754

Competent Person Statement

The information in this report that relates to the estimation and reporting of the West 45 and Orient Resources is based on and fairly represents, information and supporting documentation compiled by Mr Stuart Hutchin who is a Member of The Australasian Institute of Mining and Metallurgy, Member of the Australian Institute of Geoscientists and a full time employee of Mining One Consultants Pty Ltd.

Mr Hutchin has sufficient experience relevant to the style of mineralisation and type of deposit under consideration and to the activity which he is undertaking to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'.

JORC Code, 2012 Edition – Table 1 (Liontown Deposit)

Section 1 Sampling Techniques and Data

| Criteria | JORC Code explanation | Commentary |
|------------------------------|---|---|
| <i>Sampling techniques</i> | <ul style="list-style-type: none"> <i>Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.</i> <i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</i> <i>Aspects of the determination of mineralisation that are Material to the Public Report.</i> <i>In cases where ‘industry standard’ work has been done this would be relatively simple (eg ‘reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay’). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</i> | <ul style="list-style-type: none"> The deposit was primarily sampled via half core samples based on geological considerations within diamond drill holes drilled on a 20m x 20m up to a 100m x 100m pattern through the deposit. The RC samples were typically taken on 1m intervals through the deposit. The holes were orientated to ensure drill intersections were approximately perpendicular to the dip and strike of the ore lenses and overall geological package. Diamond core and reverse circulation drill samples were crushed and assayed for Cu, Pb, Zn, Ag, Fe and Au via Aqua Regia via the ICP25 method for the base metals and fire assay with an AAS finish for gold. |
| <i>Drilling techniques</i> | <ul style="list-style-type: none"> <i>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</i> | <ul style="list-style-type: none"> A total of 220 drillholes have been used to estimate the Liontown Resources, of these a total of 99 were surface diamond holes and 121 were reverse circulation holes. The diamond core size drilled was predominately with standard tube NQ2 sized core. All diamond core was orientated. |
| <i>Drill sample recovery</i> | <ul style="list-style-type: none"> <i>Method of recording and assessing core and chip sample recoveries and results assessed.</i> <i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i> <i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i> | <ul style="list-style-type: none"> The diamond core drill recovery was monitored using a combination of the drillers run sheets, core block markings and manual piecing together of core and measurement.. Any core loss was noted within the logging sheets. Core recovery averaged >95% through the ore intervals. The majority of the resource is based on diamond drilling, the deposit predominately consists of copper, zinc and lead mineralization, there are no concerns regarding loss of fine material during the core sampling process for this deposit. |

| Criteria | JORC Code explanation | Commentary |
|--|--|--|
| Logging | <ul style="list-style-type: none"> Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography. The total length and percentage of the relevant intersections logged. | <ul style="list-style-type: none"> All diamond core and reverse circulation chips were logged for geological and geotechnical characteristics. Rock type, alteration style and sulphide mineral content were logged by a site geologist. The logging was sufficient to enable creation of detailed geological model that supports the resource estimate. |
| Sub-sampling techniques and sample preparation | <ul style="list-style-type: none"> If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled. | <ul style="list-style-type: none"> NQ2 sized diamond core was marked up and cut in half with a diamond core saw. The right side of the core as sampled according to the geological intervals selected by the site Geologist. The RC samples were poured through a riffle splitter after the sample was circulated from the drill face through a cyclone and into a large plastic bag. The methodology of selecting half core via geological intervals guarantees that the core samples are representative. The reverse circulation drilling samples are collected on 1m intervals so there is no selectivity bias with these. The sample sizes vary from material sourced from the core samples given the varying sample lengths. The RC samples are generally 5-10 kg. The sample sizes are appropriate given the relatively even distribution of base metal grades within the deposit |
| Quality of assay data and laboratory tests | <ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc. Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established. | <ul style="list-style-type: none"> The ALS laboratory completed analysis of the 2007 diamond drilling samples, details of the assaying of earlier historical samples is not available. Standard and blank samples were inserted into the 2007 drilling program sample batches. The results of these samples indicate that there are no known material biases in the original Lioontown assay dataset in relation to the base metal assays. The gold and silver assays were however not used for the resource estimate from the Nickel Mines series of drilling. |

| Criteria | JORC Code explanation | Commentary |
|---|--|---|
| Verification of sampling and assaying | <ul style="list-style-type: none"> The verification of significant intersections by either independent or alternative company personnel. The use of twinned holes. Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols. Discuss any adjustment to assay data. | <ul style="list-style-type: none"> A series of twin holes were completed by Esso although the limited quantity of holes did not allow a meaningful comparison. Hole intercepts exist within 10m spacing in some areas of the resource that do confirm base metal and precious metal grades within the ore structures. Data was entered into a central database and then validated by a series of validation checks to ensure erroneous data was not saved into the resource database. |
| Location of data points | <ul style="list-style-type: none"> Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation. Specification of the grid system used. Quality and adequacy of topographic control. | <ul style="list-style-type: none"> The MGA94 grid system was used as the grid reference for the Lontown deposit. All holes were surveyed using a differential GPS survey system. The topography surface is represented by a wireframe file that has been edited over time by various project operators. The surface covers the complete Lontown deposit area. The surface is an accurate representation of the actual topographic surface at the site. |
| Data spacing and distribution | <ul style="list-style-type: none"> Data spacing for reporting of Exploration Results. Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied. Whether sample compositing has been applied. | <ul style="list-style-type: none"> The Lontown deposit has been drilled on an average spacing of 50m x 25m along the strike of the ore domains. This drill spacing provides evidence of mineralized zone continuity for the purposes of resource estimation. No sampling compositing was necessary in the initial diamond drilling however compositing of raw assay data was completed in preparation for the resource estimation process. |
| Orientation of data in relation to geological structure | <ul style="list-style-type: none"> Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type. If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material. | <ul style="list-style-type: none"> The majority of diamond holes were orientated to provide an approximate perpendicular intersection angle with the main mineralized zones. No sampling bias is assessed as been caused by the drilling orientation. |
| Sample security | <ul style="list-style-type: none"> The measures taken to ensure sample security. | <ul style="list-style-type: none"> Samples were supervised by either the drill crew, field assistant or geologist and at all times. Given the base metal nature of the deposit sample security was not assessed as a significant risk. |
| Audits or reviews | <ul style="list-style-type: none"> The results of any audits or reviews of sampling techniques and data. | <ul style="list-style-type: none"> A review of the assay data was completed by McDonald Speijers Consultants in 2008. A due diligence review of the resource estimation was also completed by Mining One Consultants was completed in November 2013. |

Section 2 Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section.)

| Criteria | JORC Code explanation | Commentary |
|---|---|---|
| Mineral tenement and land tenure status | <ul style="list-style-type: none"> Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area. | <ul style="list-style-type: none"> A 1.5% NSR is payable to FTI Consulting in addition to the standard Queensland government royalty. The license area is current. |
| Exploration done by other parties | <ul style="list-style-type: none"> Acknowledgment and appraisal of exploration by other parties. | <ul style="list-style-type: none"> Exploration activities have been carried out by Nickel Mines (1970-1973), Esso (1982-1983), Great Mines (1987), Pancontinental (1994-1995) and Lione Resources (2007) |
| Geology | <ul style="list-style-type: none"> Deposit type, geological setting and style of mineralisation. | <ul style="list-style-type: none"> The deposit consists of stratiform sulphide lenses and stringer zones developed within quartz eye volcanoclastics located between a dacite hangingwall and rhyolite footwall. |
| Drill hole Information | <ul style="list-style-type: none"> A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul style="list-style-type: none"> easting and northing of the drill hole collar elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar dip and azimuth of the hole down hole length and interception depth hole length. If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. | <ul style="list-style-type: none"> A list of each resource drillhole location and downhole survey is located as an appendices 2 & 3 to this table, see below. |

| Criteria | JORC Code explanation | Commentary |
|--|---|--|
| Data aggregation methods | <ul style="list-style-type: none"> In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated. | <ul style="list-style-type: none"> The exploration results reported for the Liofentown deposit were included as weighted average assay intervals for Zn, Cu, Ag and Pb. No cutting of high grades was completed when reporting as exploration results |
| Relationship between mineralisation widths and intercept lengths | <ul style="list-style-type: none"> These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known'). | <ul style="list-style-type: none"> The typical drill sample interval is 1m in length, the average thickness of the mineralized zone is 5m, there are no issues with reporting the results based on this. The drillholes intercepted the mineralized lenses at an approximately perpendicular angle. All exploration results were reported as downhole thicknesses. |
| Diagrams | <ul style="list-style-type: none"> Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views. | <ul style="list-style-type: none"> See Appendix 2 for a location plan of all drill collars used in the resource estimate. |
| Balanced reporting | <ul style="list-style-type: none"> Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results. | <ul style="list-style-type: none"> N/A |
| Other substantive exploration data | <ul style="list-style-type: none"> Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances. | <ul style="list-style-type: none"> Not Applicable |

| Criteria | JORC Code explanation | Commentary |
|--------------|---|---|
| Further work | <ul style="list-style-type: none"> The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive. | <ul style="list-style-type: none"> Further infill drilling will be required within the deposit area with a view to defining additional resources. Collection of additional density measurements is also recommended. |

Section 3 Estimation and Reporting of Mineral Resources

(Criteria listed in section 1, and where relevant in section 2, also apply to this section.)

| Criteria | JORC Code explanation | Commentary |
|---------------------------|---|--|
| Database integrity | <ul style="list-style-type: none"> Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes. Data validation procedures used. | <ul style="list-style-type: none"> The survey, sampling and logging data was electronically imported into the resource database.. A visual check was also made of the drill traces, assay and logging data in the 3D environment of Surpac to ensure that results correlated between drillholes and were inline with the geological interpretation and mineralization continuity. |
| Site visits | <ul style="list-style-type: none"> Comment on any site visits undertaken by the Competent Person and the outcome of those visits. If no site visits have been undertaken indicate why this is the case. | <ul style="list-style-type: none"> A site visit was completed by Stuart Hutchin on 16/10/2013 where The Lione town site and historical workings were inspected. |
| Geological interpretation | <ul style="list-style-type: none"> Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit. Nature of the data used and of any assumptions made. The effect, if any, of alternative interpretations on Mineral Resource estimation. The use of geology in guiding and controlling Mineral Resource estimation. The factors affecting continuity both of grade and geology. | <ul style="list-style-type: none"> The confidence in the overall geological interpretation is moderate given that Lione town exhibits a similar geological setting and mineralization style as other well-known deposits in the Thalanga project area. The dacite, quartz eye volcanoclastics and rhyolite geological units have been logged and are used to define general areas of rock types within the deposit. The mineralized zones typically occur within the quartz eye volcanoclastics. The mineralized lenses occur within the quartz eye volcanoclastic package, they are discrete pods of massive sulphide and stringer mineralization, some fault control on these zones is evident with further drilling required to full quantify. |
| Dimensions | <ul style="list-style-type: none"> The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource. | <ul style="list-style-type: none"> The strike length of the main lens modelled is approximately 1000m individual mineralized pods ranges from 40m to 400m, thickness of the zone ranges from 2m to 20m. The resource domain is located from 5m below the surface topography and extends to a depth of 450m below surface. |

| Criteria | JORC Code explanation | Commentary |
|-------------------------------------|---|--|
| Estimation and modelling techniques | <ul style="list-style-type: none"> The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used. The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data. The assumptions made regarding recovery of by-products. Estimation of deleterious elements or other non-grade variables of economic significance (eg sulphur for acid mine drainage characterisation). In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed. Any assumptions behind modelling of selective mining units. Any assumptions about correlation between variables. Description of how the geological interpretation was used to control the resource estimates. Discussion of basis for using or not using grade cutting or capping. The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available. | <ul style="list-style-type: none"> The resource model was constructed using Surpac software. Mineralised domain wireframes were constructed using a nominal 2% Zn Eq boundary with the geological logging also used to determine the mineralized envelope. A minimum domain thickness of 2m was used, this corresponds to the minimum practical mining width within an underground operation. High grade Zn, Cu, Pb, Ag and Au top cuts were applied using a combination of the 95% confidence interval, histograms and cumulative probability plots. This generally cut <1% of composite values. A composite file was created using a composite length of 1m. The median sample length within the assay dataset is also 1m. Variograms for each metal were created for all modelled domains with the results of these used to assist with estimation of resources. An ordinary kriged estimate run. This method is deemed to be suitable given the style and orientation of the mineralization and type of data support. The estimation process was validated by comparing global block grades with the average composite grades, visual checks comparing block grades with raw assay data, volume checks of the ore domain wireframe vs the block model volume and comparison of the ordinary kriged results with an inverse distance estimate. The validation steps taken indicate that the block estimates are a realistic representation of the source assay data and that they block model volumes are valid in comparison to the modelled interpretation. |
| Moisture | <ul style="list-style-type: none"> Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content. | <ul style="list-style-type: none"> The resource tonnages have been estimated on a dry basis |
| Cut-off parameters | <ul style="list-style-type: none"> The basis of the adopted cut-off grade(s) or quality parameters applied. | <ul style="list-style-type: none"> A cut – off using 5% Zn Eq has been used to report resources. This was chosen as the lower limit of potentially economically extractable material within an underground mining operation in this style of deposit. |

| Criteria | JORC Code explanation | Commentary |
|--------------------------------------|--|---|
| Mining factors or assumptions | <ul style="list-style-type: none"> Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. | <ul style="list-style-type: none"> The resources have been estimated using a minimum thickness of 2m for each of the domain shapes, this minimum thickness therefore accounts for any dilution in zones that are less than this thickness. The proposed mining method is via underground long hole stoping techniques, the model parameters are therefore deemed to be suitable for this type of potential mining operation. |
| Metallurgical factors or assumptions | <ul style="list-style-type: none"> The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made. | <ul style="list-style-type: none"> The ore is planned to be crushed and a concentrate containing Zn, Pb, Ag and Cu produced, metallurgical test work will need to be completed to confirm the processing metrics of the ore material. The ore would likely be processed at the existing Thalanga processing facility. |
| Environmental factors or assumptions | <ul style="list-style-type: none"> Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a greenfields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not been considered this should be reported with an explanation of the environmental assumptions made. | <ul style="list-style-type: none"> The tailings produced during the creation of the concentrate would be disposed of at the currently permitted Thalanga tailings facility. Waste rock from the mine will be placed on the existing waste dump locations. Government approvals would need to be obtained for mining at Lontown. |

| Criteria | JORC Code explanation | Commentary |
|-------------------|--|---|
| Bulk density | <ul style="list-style-type: none"> Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples. The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit. Discuss assumptions for bulk density estimates used in the evaluation process of the different materials. | <ul style="list-style-type: none"> The bulk densities for the ore and waste rock types were estimated using the Archimedes method, that is (Dry Weight / (Dry Weight – Wet Weight)). A density of 2.64 was assigned to the fresh ore material. These density values were derived from average densities taken from historical readings taken by previous operators. |
| Classification | <ul style="list-style-type: none"> The basis for the classification of the Mineral Resources into varying confidence categories. Whether appropriate account has been taken of all relevant factors (ie relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data). Whether the result appropriately reflects the Competent Person's view of the deposit. | <ul style="list-style-type: none"> The resources have been classified according to the drill density and the modelled continuity of both the thickness and grade of the mineralized zones in the view of the competent geologist. Indicated and inferred blocks have been reported for the resource. The resource classification is deemed appropriate in relation to the drill spacing and geological continuity of the mineralized domains. |
| Audits or reviews | <ul style="list-style-type: none"> The results of any audits or reviews of Mineral Resource estimates. | <ul style="list-style-type: none"> Stuart Hutchin has visited the Lione town site within the last two years. The review involved a high level assessment of the exploration potential. |

| Criteria | JORC Code explanation | Commentary |
|--|---|--|
| Discussion of relative accuracy/confidence | <ul style="list-style-type: none"> Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate. The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used. These statements of relative accuracy and confidence of the estimate should be compared with production data, where available. | <ul style="list-style-type: none"> The resource estimate is deemed to be an accurate reflection of both the geological interpretation and tenure of mineralization within the deposit. Small scale historical underground mining activities confirm the existence of mineralised lodes within the deposit area. |

LIONTOWN APPENDIX 1

DRILLHOLE COLLAR LOCATIONS

| HoleID | MGA_E | MGA_N | RL | Hole_Depth | Hole Type | Lease | Company |
|---------|----------|---------|---------|------------|-----------|----------|---------|
| LLD001 | 402154.5 | 7742915 | 291.574 | 50.3 | DDH | ML10277 | NMIN |
| LLD002 | 402164.4 | 7742899 | 291.86 | 126.03 | DDH | ML10277 | NMIN |
| LLD003 | 402193.2 | 7742896 | 292.969 | 68.58 | DDH | ML10277 | NMIN |
| LLD004 | 402210.4 | 7742897 | 293.624 | 81.7 | DDH | ML10277 | NMIN |
| LTD0039 | 402224 | 7742762 | 292.364 | 300.4 | DDH | ML10277 | LTR |
| LLD006 | 402224.1 | 7742892 | 293.995 | 119.9 | DDH | ML10277 | NMIN |
| LLD005 | 402225.4 | 7742897 | 294.229 | 59.7 | DDH | ML10277 | NMIN |
| LLD007 | 402228 | 7742865 | 293.34 | 208.5 | DDH | ML10277 | NMIN |
| LTD0034 | 402233.6 | 7742798 | 292.319 | 291.3 | DDH | ML10277 | LTR |
| LLD008 | 402240.2 | 7742894 | 294.668 | 121.92 | DDH | ML10277 | NMIN |
| LLD010 | 402253 | 7742890 | 295.018 | 121.01 | DDH | ML10277 | NMIN |
| LLD009 | 402254.4 | 7742896 | 295.39 | 51.82 | DDH | ML10277 | NMIN |
| LLD011 | 402269.2 | 7742892 | 295.917 | 121.92 | DDH | ML10277 | NMIN |
| LLD013 | 402283.8 | 7742887 | 296.593 | 121.92 | DDH | ML10277 | NMIN |
| LLD012 | 402285.3 | 7742893 | 296.885 | 54 | DDH | ML10277 | NMIN |
| LLD014 | 402299 | 7742889 | 297.648 | 119.2 | DDH | ML10277 | NMIN |
| LLD015 | 402316.7 | 7742883 | 298.619 | 115.9 | DDH | ML10277 | NMIN |
| LLD016 | 402345.6 | 7742881 | 299.725 | 126.5 | DDH | ML10277 | NMIN |
| LTD0038 | 402346.7 | 7742702 | 292.203 | 315.4 | DDH | EPM14161 | LTR |
| LLD017 | 402352.3 | 7742770 | 293.561 | 228.3 | DDH | ML10277 | NMIN |
| LLD018 | 402375.6 | 7742880 | 300.393 | 122.4 | DDH | ML10277 | NMIN |
| LTD0037 | 402404.1 | 7742693 | 290.253 | 339.5 | DDH | EPM14161 | LTR |
| LLD019 | 402404.4 | 7742877 | 301.195 | 121.62 | DDH | ML10277 | NMIN |
| LTD0040 | 402412 | 7742747 | 292.091 | 224.8 | DDH | ML10277 | LTR |
| LTD0003 | 402433.4 | 7742773 | 293.293 | 213 | DDH | ML10277 | LTR |
| LTD0002 | 402433.6 | 7742774 | 293.482 | 138 | DDH | ML10277 | LTR |
| LLD022 | 402436.3 | 7742874 | 301.664 | 122.83 | DDH | ML10277 | NMIN |
| LLD021 | 402436.7 | 7742879 | 302.05 | 121.62 | DDH | ML10277 | NMIN |
| LLD023 | 402467.2 | 7742872 | 301.153 | 216.71 | DDH | ML10277 | NMIN |
| LLD039 | 402479.2 | 7743033 | 298.086 | 31.4 | DDH | ML10277 | NMIN |
| LTD0035 | 402494.5 | 7742537 | 288.588 | 529.6 | DDH | EPM14161 | LTR |
| LLD024 | 402497.1 | 7742869 | 300.408 | 140.51 | DDH | ML10277 | NMIN |
| LTD0036 | 402509.7 | 7742721 | 291.707 | 297.3 | DDH | EPM14161 | LTR |
| LLD025 | 402521 | 7742867 | 299.982 | 120.7 | DDH | ML10277 | NMIN |

| HoleID | MGA_E | MGA_N | RL | Hole_Depth | Hole Type | Lease | Company |
|---------|----------|---------|---------|------------|-----------|----------|---------|
| LLD027 | 402551.7 | 7742862 | 299.573 | 121.62 | DDH | ML10277 | NMIN |
| LLD026 | 402553.2 | 7742869 | 300.35 | 124.7 | DDH | ML10277 | NMIN |
| LLD033 | 402555.1 | 7742706 | 291.583 | 303 | DDH | EPM14161 | NMIN |
| LLD028 | 402568.9 | 7742863 | 300.201 | 146.91 | DDH | ML10277 | NMIN |
| LLD032 | 402572.6 | 7742779 | 293.937 | 234.6 | DDH | ML10277 | NMIN |
| LLD030 | 402584.6 | 7742859 | 300.175 | 123.44 | DDH | ML10277 | NMIN |
| LTD0007 | 402584.7 | 7742757 | 292.972 | 219 | DDH | EPM14161 | LTR |
| LLD029 | 402585.1 | 7742865 | 301.135 | 125.9 | DDH | ML10277 | NMIN |
| LLD031 | 402585.8 | 7742754 | 292.779 | 228 | DDH | EPM14161 | NMIN |
| LLD036 | 402598.7 | 7742860 | 300.68 | 121.92 | DDH | ML10277 | NMIN |
| LTD0006 | 402600.6 | 7742846 | 298.727 | 150 | DDH | ML10277 | LTR |
| LLD038 | 402611.5 | 7742856 | 300.425 | 125 | DDH | ML10277 | NMIN |
| LLD037 | 402612 | 7742863 | 301.816 | 120.4 | DDH | ML10277 | NMIN |
| LTD0026 | 402630.6 | 7742735 | 293.772 | 317.7 | DDH | EPM14161 | LTR |
| LLD041 | 402644.7 | 7742858 | 301.289 | 119.5 | DDH | ML10277 | NMIN |
| LLD040 | 402645.1 | 7742864 | 302.522 | 90.83 | DDH | ML10277 | NMIN |
| LTD0030 | 402651.2 | 7742483 | 287.389 | 624.2 | DDH | EPM14161 | LTR |
| LLD042 | 402659.9 | 7742861 | 301.814 | 122.22 | DDH | ML10277 | NMIN |
| LTD0017 | 402668.7 | 7742620 | 292.181 | 360.5 | DDH | EPM14161 | LTR |
| LTD0023 | 402671.8 | 7742742 | 295.339 | 287.7 | DDH | EPM14161 | LTR |
| LLD050 | 402673.7 | 7742696 | 298.208 | 51.82 | DDH | EPM14161 | NMIN |
| LTD0008 | 402674.2 | 7742780 | 295.838 | 231.05 | DDH | EPM14161 | |
| LLD044 | 402675 | 7742861 | 301.563 | 123.44 | DDH | ML10277 | NMIN |
| LLD043 | 402675.4 | 7742867 | 302.35 | 96.8 | DDH | ML10277 | NMIN |
| LLD045 | 402690.3 | 7742864 | 301.429 | 92.1 | DDH | ML10277 | NMIN |
| LLD049 | 402691.5 | 7742786 | 296.876 | 341.1 | DDH | EPM14161 | NMIN |
| LTD0009 | 402693.9 | 7742688 | 298.013 | 327 | DDH | EPM14161 | LTR |
| LLD047 | 402705.1 | 7742861 | 300.477 | 121.92 | DDH | ML10277 | NMIN |
| LLD046 | 402705.6 | 7742867 | 300.836 | 117.4 | DDH | ML10277 | NMIN |
| LLD048 | 402718.5 | 7742866 | 300.323 | 115.2 | DDH | ML10277 | NMIN |
| LTD0001 | 402729.8 | 7742862 | 300.072 | 174 | DDH | EPM14161 | LTR |
| LLD052 | 402733.3 | 7742862 | 300.187 | 95.1 | DDH | EPM14161 | NMIN |
| LTD0021 | 402737.3 | 7742570 | 289.864 | 389 | DDH | EPM14161 | LTR |
| LTD0020 | 402751.4 | 7742699 | 296.752 | 389.5 | DDH | EPM14161 | LTR |
| LTD0019 | 402752.7 | 7742760 | 301.283 | 269.3 | DDH | EPM14161 | LTR |
| LTD0018 | 402754.1 | 7742794 | 301.344 | 221.9 | DDH | EPM14161 | LTR |
| LLD135 | 402758.2 | 7742842 | 300.969 | 165 | DDH | EPM14161 | PAN |
| LLD053 | 402767.8 | 7742868 | 302.859 | 122.83 | DDH | EPM14161 | NMIN |
| LLD136 | 402781.8 | 7742823 | 301.096 | 219 | DDH | EPM14161 | PAN |
| LTD0025 | 402806.6 | 7742424 | 286.976 | 624 | DDH | EPM14161 | LTR |
| LTD0005 | 402811 | 7742872 | 303.845 | 135 | DDH | EPM14161 | LTR |
| LTD0016 | 402815.6 | 7742518 | 288.404 | 454.2 | DDH | EPM14161 | LTR |
| LTD0015 | 402818.1 | 7742556 | 289.147 | 449 | DDH | EPM14161 | LTR |

| HoleID | MGA_E | MGA_N | RL | Hole_Depth | Hole Type | Lease | Company |
|---------|----------|---------|---------|------------|-----------|----------|---------|
| LTD0014 | 402822.8 | 7742626 | 291.811 | 333.1 | DDH | EPM14161 | LTR |
| LLD055 | 402823.4 | 7742874 | 303.543 | 111.3 | DDH | EPM14161 | NMIN |
| LTD0013 | 402829.2 | 7742711 | 296.084 | 309.2 | DDH | EPM14161 | LTR |
| LLD054 | 402831.1 | 7742924 | 306.619 | 155.2 | DDH | EPM14161 | NMIN |
| LTD0012 | 402832.8 | 7742758 | 300.686 | 264 | DDH | EPM14161 | LTR |
| LTD0010 | 402835.5 | 7742797 | 302.901 | 216.15 | DDH | EPM14161 | LTR |
| LTD0011 | 402837.9 | 7742832 | 303.188 | 186.16 | DDH | EPM14161 | LTR |
| LLD137 | 402839.3 | 7742787 | 302.465 | 339 | DDH | EPM14161 | PAN |
| LLD056 | 402892.1 | 7742813 | 302.416 | 205.82 | DDH | EPM14161 | NMIN |
| LTD0024 | 402928.7 | 7742415 | 286.839 | 892.8 | DDH | EPM14161 | LTR |
| LLD057 | 402944.1 | 7742880 | 302.874 | 146.61 | DDH | EPM14161 | NMIN |
| LTD0029 | 402945.6 | 7742667 | 292.966 | 534.2 | DDH | EPM14161 | LTR |
| LTD0022 | 402950.9 | 7742729 | 295.606 | 383.6 | DDH | EPM14161 | LTR |
| LLD134 | 402961.2 | 7742876 | 303.042 | 111 | DDH | EPM14161 | PAN |
| LTD0027 | 403062.5 | 7742813 | 297.78 | 510.4 | DDH | EPM14161 | LTR |
| LTD0033 | 403070.6 | 7742730 | 293.165 | 375.55 | DDH | EPM14161 | LTR |
| LLD059 | 403150.6 | 7742824 | 296.191 | 164.44 | DDH | EPM14161 | NMIN |
| LTD0031 | 403195.8 | 7742782 | 293.115 | 390.3 | DDH | EPM14161 | LTR |
| LTD0028 | 403199.5 | 7742845 | 294.125 | 252.3 | DDH | EPM14161 | LTR |
| LTD0032 | 403203.1 | 7742893 | 296.11 | 159.4 | DDH | EPM14161 | LTR |
| LLD060 | 403224.5 | 7742901 | 296.179 | 31.4 | DDH | EPM14161 | NMIN |
| LLD117 | 402117.3 | 7742851 | 290.708 | 247.8 | RC | EPM14161 | ESSO |
| LRC016 | 402172.1 | 7742912 | 292.192 | 66 | RC | ML10277 | GREAT |
| LRC015 | 402173.2 | 7742927 | 292.933 | 50 | RC | ML10277 | GREAT |
| LLD108 | 402210.1 | 7742741 | 291.88 | 394.5 | RC | ML10277 | ESSO |
| LRC018 | 402222.3 | 7742913 | 294.709 | 53 | RC | ML10277 | GREAT |
| LRC017 | 402223.4 | 7742928 | 294.173 | 50 | RC | ML10277 | GREAT |
| LLD105 | 402229.4 | 7742863 | 293.34 | 192.8 | RC | ML10277 | ESSO |
| LLD106 | 402230.5 | 7742895 | 294.303 | 187.5 | RC | ML10277 | ESSO |
| LLD109 | 402237.3 | 7742966 | 292.936 | 218.3 | RC | ML10277 | ESSO |
| LRC019 | 402272.5 | 7742915 | 297.063 | 70 | RC | ML10277 | GREAT |
| LLRC075 | 402301 | 7742889 | 297.777 | 96 | RC | ML10277 | PAN |
| LRC020 | 402322.3 | 7742911 | 299.468 | 47 | RC | ML10277 | GREAT |
| LLD113 | 402360.1 | 7742840 | 297.656 | 256 | RC | ML10277 | ESSO |
| LRC023 | 402370.8 | 7742912 | 301.927 | 50 | RC | ML10277 | GREAT |
| LRC022 | 402372.5 | 7742932 | 301.164 | 50 | RC | ML10277 | GREAT |
| LLRC164 | 402374.2 | 7743523 | 293.359 | 93 | RC | EPM14161 | RGC |
| LLRC165 | 402374.3 | 7743323 | 291.596 | 90 | RC | EPM14161 | RGC |
| LLRC166 | 402374.3 | 7743223 | 290.039 | 60 | RC | EPM14161 | RGC |
| LRC021 | 402375.4 | 7742950 | 300.295 | 50 | RC | ML10277 | GREAT |
| LLD125 | 402377.1 | 7742600 | 290.099 | 385.6 | RC | EPM14161 | ESSO |
| LRC001 | 402426.1 | 7742908 | 302.659 | 85 | RC | ML10277 | GREAT |
| LRC002 | 402427.4 | 7742928 | 301.829 | 65 | RC | ML10277 | GREAT |

| HoleID | MGA_E | MGA_N | RL | Hole_Depth | Hole Type | Lease | Company |
|---------|----------|---------|---------|------------|-----------|----------|---------|
| LLD130 | 402428.8 | 7742728 | 291.653 | 232 | RC | EPM14161 | PAN |
| LLD116 | 402433.1 | 7742778 | 293.901 | 320.7 | RC | ML10277 | ESSO |
| LRC004 | 402475.9 | 7742905 | 302.277 | 80 | RC | ML10277 | GREAT |
| LLD112 | 402480 | 7742863 | 300.469 | 181.2 | RC | ML10277 | ESSO |
| LRC003 | 402480 | 7742924 | 302.005 | 60 | RC | ML10277 | GREAT |
| LRC046 | 402495.6 | 7742883 | 302.081 | 69 | RC | ML10277 | GREAT |
| LRC050 | 402496.5 | 7742898 | 302.8 | 48 | RC | ML10277 | GREAT |
| LLRC090 | 402498.6 | 7742849 | 299.306 | 100 | RC | ML10277 | PAN |
| LRC044 | 402499.1 | 7742918 | 302.142 | 80 | RC | ML10277 | GREAT |
| LLD121 | 402503.6 | 7742672 | 290.553 | 490.5 | RC | EPM14161 | ESSO |
| LLD115 | 402515 | 7742801 | 295.727 | 271.8 | RC | ML10277 | ESSO |
| LRC025 | 402515.1 | 7742831 | 298.131 | 50 | RC | ML10277 | GREAT |
| LRC040 | 402515.7 | 7742887 | 303.091 | 85 | RC | ML10277 | GREAT |
| LRC024 | 402516.7 | 7742851 | 299.284 | 50 | RC | ML10277 | GREAT |
| LRC042 | 402516.9 | 7742872 | 300.882 | 88 | RC | ML10277 | GREAT |
| LRC005 | 402518.8 | 7742901 | 303.961 | 80 | RC | ML10277 | GREAT |
| LLRC076 | 402520.4 | 7742872 | 300.477 | 90 | RC | ML10277 | PAN |
| LRC006 | 402533.3 | 7742920 | 297.659 | 50 | RC | ML10277 | GREAT |
| LRC048 | 402551.3 | 7742914 | 297.31 | 68 | RC | ML10277 | GREAT |
| LRC049 | 402552.9 | 7742892 | 295.373 | 78 | RC | ML10277 | GREAT |
| LLRC161 | 402555.4 | 7743597 | 295.859 | 84 | RC | EPM14161 | PAN |
| LRC041 | 402568.2 | 7742847 | 292.821 | 80 | RC | EPM14161 | GREAT |
| LRC008 | 402569.7 | 7742902 | 296.518 | 80 | RC | ML10277 | GREAT |
| LRC039 | 402570 | 7742872 | 294.059 | 84 | RC | ML10277 | GREAT |
| LRC037 | 402571.1 | 7742887 | 295.14 | 90 | RC | ML10277 | GREAT |
| LRC035 | 402571.4 | 7742912 | 296.624 | 81 | RC | ML10277 | GREAT |
| LRC007 | 402571.5 | 7742923 | 296.859 | 50 | RC | ML10277 | GREAT |
| LRC033 | 402574.9 | 7742937 | 298.533 | 78 | RC | ML10277 | GREAT |
| LLD107 | 402576.1 | 7742776 | 293.844 | 187.5 | RC | ML10277 | ESSO |
| LLD102 | 402588.9 | 7742862 | 300.614 | 220.5 | RC | ML10277 | ESSO |
| LLRC162 | 402593.4 | 7743477 | 295.321 | 90 | RC | EPM14161 | PAN |
| LRC043 | 402593.6 | 7742852 | 293.536 | 80 | RC | EPM14161 | GREAT |
| LRC038 | 402596.4 | 7742890 | 295.994 | 93 | RC | ML10277 | GREAT |
| LRC036 | 402597.6 | 7742905 | 296.665 | 93 | RC | ML10277 | GREAT |
| LLRC091 | 402598.2 | 7742840 | 297.858 | 140 | RC | ML10277 | PAN |
| LLD129 | 402607.4 | 7742694 | 294.636 | 284.9 | RC | EPM14161 | PAN |
| LLD118 | 402607.4 | 7742664 | 294.311 | 388.5 | RC | EPM14161 | ESSO |
| LRC047 | 402616.5 | 7742824 | 293.38 | 74 | RC | EPM14161 | GREAT |
| LRC045 | 402619.5 | 7742863 | 294.357 | 93 | RC | EPM14161 | GREAT |
| LRC034 | 402620.5 | 7742914 | 297.247 | 26 | RC | ML10277 | GREAT |
| LRC010 | 402622.2 | 7742903 | 297.193 | 80 | RC | ML10277 | GREAT |
| LRC009 | 402624 | 7742924 | 298.057 | 50 | RC | ML10277 | GREAT |
| LLRC092 | 402638.6 | 7742843 | 299.126 | 140 | RC | ML10277 | PAN |

| HoleID | MGA_E | MGA_N | RL | Hole_Depth | Hole Type | Lease | Company |
|---------|----------|---------|---------|------------|-----------|----------|---------|
| LLD132 | 402670.8 | 7742880 | 305.7 | 120.6 | RC | ML10277 | PAN |
| LLD133 | 402671 | 7742883 | 305.309 | 102.2 | RC | ML10277 | PAN |
| LRC011 | 402672.1 | 7742919 | 299.628 | 60 | RC | ML10277 | GREAT |
| LRC012 | 402672.3 | 7742900 | 298.237 | 80 | RC | ML10277 | GREAT |
| LLRC068 | 402674.4 | 7742920 | 306.076 | 100 | RC | ML10277 | PAN |
| LLRC067 | 402677.4 | 7742960 | 306.634 | 100 | RC | EPM14161 | PAN |
| LRC026 | 402677.9 | 7742939 | 301.393 | 59 | RC | ML10277 | GREAT |
| LLRC093 | 402678.5 | 7742840 | 299.946 | 140 | RC | ML10277 | PAN |
| LLRC066 | 402681.1 | 7743010 | 303.739 | 100 | RC | EPM14161 | PAN |
| LLRC065 | 402684.8 | 7743059 | 301.491 | 100 | RC | EPM14161 | PAN |
| LLD104 | 402691.7 | 7742692 | 298.153 | 333.4 | RC | EPM14161 | ESSO |
| LLD124 | 402692.6 | 7742689 | 298.054 | 406 | RC | EPM14161 | ESSO |
| LLD114 | 402697.5 | 7742786 | 297.264 | 293.8 | RC | EPM14161 | ESSO |
| LLD101 | 402701.7 | 7742864 | 300.802 | 215.5 | RC | ML10277 | ESSO |
| LLD103 | 402717.7 | 7742995 | 305.692 | 287.1 | RC | EPM14161 | ESSO |
| LLRC094 | 402719.4 | 7742851 | 299.114 | 140 | RC | ML10277 | PAN |
| LRC014 | 402721.9 | 7742911 | 299.585 | 80 | RC | ML10277 | GREAT |
| LRC013 | 402724.3 | 7742919 | 299.542 | 50 | RC | ML10277 | GREAT |
| LLD128 | 402743.1 | 7742632 | 292.121 | 399.3 | RC | EPM14161 | PAN |
| LLRC082 | 402758.6 | 7742839 | 300.411 | 162 | RC | EPM14161 | PAN |
| LLRC069 | 402761.6 | 7742879 | 303.443 | 103 | RC | EPM14161 | PAN |
| LRC028 | 402772.7 | 7742902 | 300.608 | 50 | RC | EPM14161 | GREAT |
| LRC027 | 402774.2 | 7742922 | 304.216 | 47 | RC | EPM14161 | GREAT |
| LLRC072 | 402801.8 | 7742880 | 304.574 | 100 | RC | EPM14161 | PAN |
| LLD110 | 402810.4 | 7742699 | 295.718 | 325.5 | RC | EPM14161 | ESSO |
| LLD119 | 402814.7 | 7742773 | 301.894 | 252.5 | RC | EPM14161 | ESSO |
| LLD111 | 402821.1 | 7742865 | 303.025 | 235 | RC | EPM14161 | ESSO |
| LRC029 | 402824.8 | 7742928 | 302.865 | 50 | RC | EPM14161 | GREAT |
| LLD126 | 402825.4 | 7742598 | 290.273 | 439.5 | RC | EPM14161 | ESSO |
| LLRC085 | 402839.1 | 7742842 | 302.998 | 150 | RC | EPM14161 | PAN |
| LLRC095 | 402840.6 | 7742862 | 302.513 | 132 | RC | EPM14161 | PAN |
| LLRC070 | 402842 | 7742882 | 303.804 | 103 | RC | EPM14161 | PAN |
| LRC032 | 402873.9 | 7742915 | 303.464 | 60 | RC | EPM14161 | GREAT |
| LRC031 | 402875.4 | 7742934 | 303.316 | 47 | RC | EPM14161 | GREAT |
| LLRC073 | 402882.2 | 7742882 | 304.137 | 100 | RC | EPM14161 | PAN |
| LLD131 | 402897.7 | 7742563 | 289.517 | 419.5 | RC | EPM14161 | PAN |
| LLD127 | 402911.8 | 7742524 | 288.143 | 721.3 | RC | EPM14161 | ESSO |
| LLD120 | 402914.5 | 7742791 | 300.455 | 260.5 | RC | EPM14161 | ESSO |
| LLRC096 | 402920.6 | 7742860 | 305.114 | 132 | RC | EPM14161 | PAN |
| LLRC071 | 402922.1 | 7742880 | 303.303 | 109 | RC | EPM14161 | PAN |
| LLRC080 | 402959.3 | 7742841 | 301.323 | 144 | RC | EPM14161 | PAN |
| LLRC097 | 402960.8 | 7742861 | 303.666 | 120 | RC | EPM14161 | PAN |
| LLRC074 | 402962.3 | 7742881 | 302.571 | 90 | RC | EPM14161 | PAN |

| HoleID | MGA_E | MGA_N | RL | Hole_Depth | Hole Type | Lease | Company |
|---------|----------|---------|---------|------------|-----------|----------|---------|
| LLRC098 | 402965.7 | 7742926 | 306.055 | 100 | RC | EPM14161 | PAN |
| LLRC099 | 402999.2 | 7742838 | 299.559 | 140 | RC | EPM14161 | PAN |
| LLRC081 | 403000.7 | 7742858 | 300.484 | 126 | RC | EPM14161 | PAN |
| LLRC100 | 403039.6 | 7742842 | 297.277 | 168 | RC | EPM14161 | PAN |
| LLRC083 | 403042.6 | 7742882 | 300.895 | 104 | RC | EPM14161 | PAN |
| LLD122 | 403067.2 | 7742806 | 297.551 | 295.3 | RC | EPM14161 | ESSO |
| LLRC101 | 403081 | 7742859 | 297.403 | 120 | RC | EPM14161 | PAN |
| LLRC084 | 403082.5 | 7742879 | 299.177 | 90 | RC | EPM14161 | PAN |
| LLRC086 | 403120.9 | 7742856 | 297.947 | 120 | RC | EPM14161 | PAN |
| LLRC087 | 403205.2 | 7742910 | 296.981 | 100 | RC | EPM14161 | PAN |
| LLRC088 | 403287.9 | 7742944 | 295.945 | 100 | RC | EPM14161 | PAN |
| LLD123 | 403311.9 | 7742836 | 290.555 | 243 | RC | EPM14161 | ESSO |

APPENDIX 2

LIONTOWN DOWNHOLE SURVEY INFORMATION

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-----|-----------|--------|-------|-------|-----------|--------|--------|-----|-----------|
| LLD001 | 0 | -45 | 7.8 | LLD015 | 0 | -68 | 7.8 | LLD027 | 0 | -68 | 7.8 |
| LLD001 | 50 | -45 | 7.8 | LLD015 | 115.9 | -60 | 7.8 | LLD027 | 120 | -60 | 7.8 |
| LLD002 | 0 | -68 | 7.8 | LLD016 | 0 | -68 | 7.8 | LLD028 | 0 | -68 | 7.8 |
| LLD002 | 120 | -60 | 7.8 | LLD016 | 120 | -60 | 7.8 | LLD028 | 20 | -66 | 7.8 |
| LLD003 | 0 | -68 | 7.8 | LLD017 | 0 | -60 | 7.8 | LLD028 | 140 | -58 | 7.8 |
| LLD003 | 60 | -64 | 7.8 | LLD017 | 220 | -46 | 354.8 | LLD029 | 0 | -68 | 7.8 |
| LLD004 | 0 | -68 | 7.8 | LLD018 | 0 | -68 | 7.8 | LLD029 | 10 | -68 | 7.8 |
| LLD005 | 0 | -68 | 7.8 | LLD018 | 120 | -60 | 7.8 | LLD029 | 125 | -60 | 7.8 |
| LLD006 | 0 | -68 | 7.8 | LLD019 | 0 | -68 | 7.8 | LLD030 | 0 | -68 | 7.8 |
| LLD006 | 110 | -60 | 7.8 | LLD019 | 120 | -60 | 7.8 | LLD030 | 120 | -60 | 7.8 |
| LLD007 | 0 | -72 | 7.8 | LLD020 | 0 | -68 | 350.8 | LLD031 | 0 | -75 | 7.8 |
| LLD007 | 25 | -74 | 10.8 | LLD020 | 5 | -67.5 | 350.8 | LLD031 | 10 | -73 | 3.8 |
| LLD007 | 200 | -50 | 7.8 | LLD020 | 70 | -62 | 350.8 | LLD031 | 220 | -46 | 3.8 |
| LLD008 | 0 | -68 | 7.8 | LLD020 | 120 | -60 | 350.8 | LLD032 | 0 | -68 | 7.8 |
| LLD008 | 120 | -60 | 7.8 | LLD021 | 0 | -68 | 349.8 | LLD032 | 230 | -46 | 7.8 |
| LLD009 | 0 | -68 | 7.8 | LLD021 | 4 | -69 | 349.8 | LLD033 | 0 | -68 | 7.8 |
| LLD009 | 50 | -66 | 7.8 | LLD021 | 120 | -60 | 349.8 | LLD033 | 300 | -40 | 7.8 |
| LLD010 | 0 | -68 | 7.8 | LLD022 | 0 | -68 | 7.8 | LLD034 | 0 | -90 | 0 |
| LLD010 | 120 | -60 | 7.8 | LLD022 | 120 | -60 | 7.8 | LLD035 | 0 | -90 | 0 |
| LLD011 | 0 | -68 | 7.8 | LLD023 | 0 | -68 | 7.8 | LLD035 | 160 | -90 | 0 |
| LLD011 | 120 | -60 | 7.8 | LLD023 | 200 | -48 | 7.8 | LLD036 | 0 | -68 | 7.8 |
| LLD012 | 0 | -68 | 7.8 | LLD024 | 0 | -68 | 7.8 | LLD036 | 121.92 | -60 | 7.8 |
| LLD012 | 50 | -66 | 7.8 | LLD024 | 140 | -58 | 7.8 | LLD037 | 0 | -68 | 7.8 |
| LLD013 | 0 | -68 | 7.8 | LLD025 | 0 | -68 | 7.8 | LLD037 | 120 | -60 | 7.8 |
| LLD013 | 120 | -60 | 7.8 | LLD025 | 120 | -60 | 7.8 | LLD038 | 0 | -68 | 7.8 |
| LLD014 | 0 | -68 | 7.8 | LLD026 | 0 | -68 | 7.8 | LLD038 | 120 | -60 | 7.8 |
| LLD014 | 110 | -60 | 7.8 | LLD026 | 120 | -60 | 7.8 | LLD039 | 0 | -68 | 7.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-----|-----------|--------|-------|-----|-----------|--------|-------|-----|-----------|
| LLD040 | 0 | -68 | 7.8 | LLD054 | 0 | -90 | 0 | LLD103 | 280 | -53 | 185.8 |
| LLD040 | 90 | -60 | 7.8 | LLD054 | 150 | -90 | 0 | LLD104 | 0 | -62 | 4.8 |
| LLD041 | 0 | -68 | 7.8 | LLD055 | 0 | -68 | 7.8 | LLD104 | 59 | -62 | 3.8 |
| LLD041 | 110 | -60 | 7.8 | LLD055 | 100 | -60 | 7.8 | LLD104 | 176 | -57 | 358.8 |
| LLD042 | 0 | -68 | 7.8 | LLD056 | 0 | -75 | 7.8 | LLD104 | 248 | -55 | 358.8 |
| LLD042 | 120 | -60 | 7.8 | LLD056 | 200 | -48 | 7.8 | LLD104 | 256 | -53 | 354.8 |
| LLD043 | 0 | -68 | 7.8 | LLD057 | 0 | -68 | 7.8 | LLD104 | 300 | -51 | 353.8 |
| LLD043 | 90 | -60 | 7.8 | LLD057 | 140 | -58 | 7.8 | LLD105 | 0 | -60 | 4.8 |
| LLD044 | 0 | -68 | 7.8 | LLD059 | 0 | -68 | 7.8 | LLD105 | 60 | -58 | 2.8 |
| LLD044 | 120 | -60 | 7.8 | LLD059 | 160 | -53 | 7.8 | LLD105 | 120 | -57 | 0.8 |
| LLD045 | 0 | -68 | 7.8 | LLD060 | 0 | -50 | 347.8 | LLD105 | 150 | -56 | 358.8 |
| LLD045 | 90 | -60 | 7.8 | LLD101 | 0 | -65 | 4.8 | LLD105 | 180 | -55 | 358.8 |
| LLD046 | 110 | -60 | 7.8 | LLD101 | 47 | -61 | 352.8 | LLD106 | 0 | -60 | 4.8 |
| LLD047 | 0 | -68 | 7.8 | LLD101 | 75 | -60 | 351.8 | LLD106 | 60 | -60 | 3.8 |
| LLD047 | 120 | -60 | 7.8 | LLD101 | 105 | -59 | 348.8 | LLD106 | 120 | -58 | 4.8 |
| LLD048 | 0 | -68 | 7.8 | LLD101 | 135 | -57 | 347.8 | LLD106 | 150 | -57 | 4.8 |
| LLD048 | 110 | -60 | 7.8 | LLD101 | 177 | -54 | 347.8 | LLD106 | 180 | -57 | 5.8 |
| LLD049 | 0 | -68 | 7.8 | LLD101 | 213 | -52 | 348.8 | LLD107 | 0 | -60 | 4.8 |
| LLD049 | 340 | -36 | 7.8 | LLD102 | 0 | -65 | 4.8 | LLD107 | 95 | -62 | 3.8 |
| LLD050 | 0 | -68 | 7.8 | LLD102 | 52 | -61 | 3.8 | LLD107 | 125 | -62 | 2.8 |
| LLD050 | 50 | -66 | 7.8 | LLD103 | 0 | -60 | 184.8 | LLD107 | 155 | -59 | 357.8 |
| LLD051 | 0 | -90 | 0 | LLD103 | 35 | -60 | 179.8 | LLD107 | 185 | -57 | 354.8 |
| LLD051 | 140 | -90 | 0 | LLD103 | 80 | -60 | 181.8 | LLD108 | 0 | -60 | 4.8 |
| LLD052 | 0 | -68 | 7.8 | LLD103 | 130 | -59 | 182.8 | LLD108 | 132 | -61 | 352.8 |
| LLD052 | 95 | -60 | 7.8 | LLD103 | 166.4 | -57 | 182.8 | LLD108 | 168 | -59 | 351.8 |
| LLD053 | 0 | -45 | 7.8 | LLD103 | 210 | -55 | 183.8 | LLD108 | 204 | -57 | 350.8 |
| LLD053 | 120 | -45 | 7.8 | LLD103 | 240 | -54 | 185.8 | LLD108 | 251 | -54 | 351.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-----|-----------|--------|-------|-----|-----------|--------|-------|-----|-----------|
| LLD108 | 300 | -51 | 347.8 | LLD113 | 240 | -58 | 358.8 | LLD119 | 0 | -59 | 4.8 |
| LLD108 | 310 | -43 | 347.8 | LLD114 | 0 | -60 | 2.8 | LLD119 | 100 | -58 | 1.8 |
| LLD108 | 330 | -47 | 347.8 | LLD114 | 110 | -60 | 357.8 | LLD119 | 180 | -55 | 357.8 |
| LLD108 | 360 | -44 | 347.8 | LLD114 | 160 | -58 | 357.8 | LLD120 | 0 | -60 | 4.8 |
| LLD109 | 0 | -60 | 184.8 | LLD114 | 220 | -54 | 355.8 | LLD120 | 65 | -67 | 4.8 |
| LLD109 | 80 | -59 | 182.8 | LLD114 | 280 | -52 | 354.8 | LLD120 | 150 | -64 | 3.8 |
| LLD109 | 110 | -57 | 183.8 | LLD115 | 0 | -60 | 4.8 | LLD120 | 203 | -63 | 0.8 |
| LLD109 | 140 | -52 | 187.8 | LLD115 | 150 | -60 | 2.8 | LLD120 | 255 | -62 | 358.8 |
| LLD109 | 170 | -47 | 191.8 | LLD115 | 200 | -57 | 2.8 | LLD121 | 0 | -60 | 4.8 |
| LLD109 | 200 | -45 | 192.8 | LLD115 | 250 | -53 | 1.8 | LLD121 | 40 | -64 | 2.8 |
| LLD110 | 0 | -60 | 4.8 | LLD116 | 0 | -60 | 4.8 | LLD121 | 52 | -65 | 2.8 |
| LLD110 | 40 | -59 | 2.8 | LLD116 | 150 | -60 | 357.8 | LLD121 | 72 | -66 | 1.8 |
| LLD110 | 151 | -51 | 0.8 | LLD116 | 205 | -58 | 357.8 | LLD121 | 189 | -63 | 357.8 |
| LLD110 | 182 | -51 | 357.8 | LLD116 | 246 | -54 | 357.8 | LLD121 | 220 | -62 | 355.8 |
| LLD110 | 218 | -50 | 352.8 | LLD116 | 300 | -51 | 356.8 | LLD121 | 266 | -60 | 353.8 |
| LLD110 | 235 | -42 | 350.8 | LLD117 | 0 | -60 | 4.8 | LLD121 | 310 | -60 | 352.8 |
| LLD110 | 290 | -48 | 350.8 | LLD117 | 78 | -55 | 358.8 | LLD121 | 400 | -57 | 354.8 |
| LLD110 | 318.5 | -29 | 350.8 | LLD117 | 120 | -54 | 358.8 | LLD121 | 442 | -55 | 354.8 |
| LLD111 | 0 | -60 | 4.8 | LLD117 | 180 | -54 | 358.8 | LLD121 | 486 | -54 | 354.8 |
| LLD111 | 235 | -48 | 350.8 | LLD117 | 240 | -50 | 357.8 | LLD122 | 0 | -60 | 4.8 |
| LLD112 | 0 | -60 | 4.8 | LLD118 | 0 | -61 | 4.8 | LLD122 | 111 | -66 | 358.8 |
| LLD112 | 121 | -56 | 353.8 | LLD118 | 50 | -70 | 2.8 | LLD122 | 200 | -63 | 353.8 |
| LLD112 | 151 | -53 | 353.8 | LLD118 | 100 | -74 | 0.8 | LLD122 | 290 | -58 | 347.8 |
| LLD112 | 181 | -47 | 353.8 | LLD118 | 200 | -70 | 355.8 | LLD123 | 0 | -60 | 4.8 |
| LLD113 | 0 | -60 | 2.8 | LLD118 | 290 | -65 | 351.8 | LLD123 | 75 | -65 | 353.8 |
| LLD113 | 80 | -60 | 359.8 | LLD118 | 336 | -61 | 347.8 | LLD123 | 150 | -64 | 359.8 |
| LLD113 | 160 | -59 | 357.8 | LLD118 | 386 | -57 | 347.8 | LLD123 | 200 | -63 | 354.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-----|-----------|--------|-------|-------|-----------|--------|-------|-------|-----------|
| LLD123 | 242 | -60 | 352.8 | LLD127 | 190 | -75 | 4.8 | LLD129 | 170 | -57 | 10.8 |
| LLD124 | 0 | -75 | 7.8 | LLD127 | 259 | -71.5 | 354.8 | LLD129 | 200 | -56.2 | 9.8 |
| LLD124 | 80 | -78 | 2.8 | LLD127 | 291 | -70.5 | 356.8 | LLD129 | 230 | -55.5 | 7.8 |
| LLD124 | 130 | -77 | 356.8 | LLD127 | 355 | -70 | 352.8 | LLD129 | 284 | -55.5 | 7.8 |
| LLD124 | 178 | -76 | 356.8 | LLD127 | 400 | -68.5 | 349.8 | LLD130 | 0 | -60 | 6.8 |
| LLD124 | 232 | -71 | 346.8 | LLD127 | 454.3 | -67.5 | 347.8 | LLD130 | 6 | -63 | 7.8 |
| LLD124 | 280 | -70 | 342.8 | LLD127 | 495.6 | -66.5 | 344.8 | LLD130 | 26 | -63.7 | 9.3 |
| LLD124 | 333 | -68 | 341.8 | LLD127 | 568.3 | -64 | 343.8 | LLD130 | 52 | -63.2 | 11.3 |
| LLD124 | 386 | -64 | 341.8 | LLD127 | 612 | -63.5 | 342.8 | LLD130 | 90 | -58.2 | 17.8 |
| LLD124 | 406 | -64 | 340.8 | LLD127 | 718.3 | -64.5 | 337.8 | LLD130 | 120 | -57.6 | 14.3 |
| LLD125 | 0 | -60 | 7.8 | LLD128 | 0 | -60 | 7.8 | LLD130 | 150 | -54.5 | 9.8 |
| LLD125 | 82 | -58 | 12.8 | LLD128 | 24 | -60 | 7.8 | LLD130 | 180 | -53.5 | 6.8 |
| LLD125 | 97 | -58 | 11.8 | LLD128 | 50 | -60 | 7.8 | LLD130 | 210 | -53 | 5.8 |
| LLD125 | 174 | -54 | 11.8 | LLD128 | 80 | -61 | 15.8 | LLD130 | 230 | -52.5 | 6.3 |
| LLD125 | 220 | -50 | 9.8 | LLD128 | 120 | -60 | 19.8 | LLD131 | 0 | -60 | 4.8 |
| LLD125 | 301 | -46 | 7.8 | LLD128 | 150 | -60 | 19.8 | LLD131 | 18 | -60 | 4.8 |
| LLD125 | 385.6 | -39 | 1.8 | LLD128 | 180 | -58.5 | 17.8 | LLD131 | 36 | -60 | 4.8 |
| LLD126 | 0 | -60 | 7.8 | LLD128 | 210 | -55 | 12.8 | LLD131 | 51 | -60 | 4.8 |
| LLD126 | 87.5 | -64 | 11.8 | LLD128 | 240 | -53 | 9.8 | LLD131 | 136 | -60 | 4.8 |
| LLD126 | 157 | -62 | 10.8 | LLD128 | 270 | -53 | 9.8 | LLD131 | 153 | -60 | 3.8 |
| LLD126 | 247 | -59 | 3.8 | LLD128 | 300 | -51.8 | 6.8 | LLD131 | 189 | -60 | 4.8 |
| LLD126 | 307 | -57 | 357.8 | LLD128 | 330 | -51.5 | 8.8 | LLD131 | 213 | -60 | 4.8 |
| LLD126 | 374 | -55 | 355.8 | LLD128 | 360 | -50.5 | 5.8 | LLD131 | 243 | -60 | 4.8 |
| LLD126 | 409 | -54 | 355.8 | LLD128 | 399.3 | -50 | 4.8 | LLD131 | 273 | -59 | 4.8 |
| LLD126 | 439.4 | -53 | 355.8 | LLD129 | 0 | -60 | 5.8 | LLD131 | 303 | -59 | 3.8 |
| LLD127 | 0 | -72 | 4.8 | LLD129 | 112 | -63 | 20.8 | LLD131 | 315 | -58.5 | 2.8 |
| LLD127 | 103 | -77 | 7.8 | LLD129 | 140 | -60.5 | 14.8 | LLD131 | 333 | -58.3 | 2.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-------|-----------|--------|-------|-------|-----------|--------|-------|-----|-----------|
| LLD131 | 363 | -58.3 | 2.3 | LLD136 | 90 | -69.9 | 4.8 | LLR201 | 0 | -90 | 0 |
| LLD131 | 393 | -57 | 1.8 | LLD136 | 102 | -70.1 | 5.8 | LLR202 | 0 | -90 | 0 |
| LLD131 | 419 | -56.7 | 1.8 | LLD136 | 132 | -70 | 3.8 | LLR203 | 0 | -90 | 0 |
| LLD132 | 0 | -70 | 4.8 | LLD136 | 143.8 | -68.7 | 1.8 | LLR204 | 0 | -90 | 0 |
| LLD132 | 5 | -70 | 4.8 | LLD136 | 192 | -67.8 | 0.8 | LLR205 | 0 | -90 | 0 |
| LLD132 | 18 | -69 | 2.8 | LLD136 | 219 | -67.4 | 0.3 | LLR206 | 0 | -90 | 0 |
| LLD132 | 42.6 | -68 | 2.8 | LLD137 | 0 | -70 | 4.8 | LLR207 | 0 | -90 | 0 |
| LLD132 | 66.6 | -67.5 | 1.8 | LLD137 | 49 | -71 | 4.8 | LLR208 | 0 | -90 | 0 |
| LLD132 | 90.6 | -67.5 | 2.8 | LLD137 | 69 | -70.7 | 4.8 | LLR209 | 0 | -90 | 0 |
| LLD132 | 120.6 | -67 | 0.8 | LLD137 | 105 | -70.2 | 16.8 | LLR210 | 0 | -90 | 0 |
| LLD133 | 0 | -50 | 4.8 | LLD137 | 147 | -67.5 | 10.8 | LLR211 | 0 | -90 | 0 |
| LLD133 | 12 | -49.5 | 4.8 | LLD137 | 180 | -67.1 | 10.8 | LLR212 | 0 | -90 | 0 |
| LLD133 | 18 | -49.2 | 2.8 | LLD137 | 222 | -66 | 11.3 | LLR213 | 0 | -90 | 0 |
| LLD133 | 42.2 | -49 | 0.8 | LLD137 | 261 | -64.7 | 10.8 | LLR214 | 0 | -90 | 0 |
| LLD133 | 66.2 | -49 | 1.3 | LLD137 | 303 | -63.7 | 11.8 | LLR215 | 0 | -90 | 0 |
| LLD133 | 102 | -48.5 | 0.8 | LLD137 | 339 | -62.9 | 11.8 | LLR216 | 0 | -90 | 0 |
| LLD134 | 0 | -70 | 4.8 | LLD138 | 0 | -60 | 4.8 | LLR217 | 0 | -90 | 0 |
| LLD134 | 81 | -72 | 1.8 | LLD138 | 30 | -62.5 | 4.8 | LLR218 | 0 | -90 | 0 |
| LLD134 | 111 | -72.2 | 0.8 | LLD138 | 60 | -61.5 | 4.8 | LLR219 | 0 | -90 | 0 |
| LLD135 | 0 | -70 | 4.8 | LLD138 | 90 | -60.5 | 4.8 | LLR220 | 0 | -90 | 0 |
| LLD135 | 48 | -68.9 | 4.8 | LLD138 | 120.4 | -58.5 | 5.8 | LLR221 | 0 | -90 | 0 |
| LLD135 | 90 | -68.7 | 4.8 | LLD138 | 150.4 | -56.5 | 5.8 | LLR222 | 0 | -90 | 0 |
| LLD135 | 117 | -63.5 | 9.8 | LLD138 | 180.4 | -56 | 3.8 | LLR223 | 0 | -90 | 0 |
| LLD135 | 150 | -62.1 | 5.8 | LLD138 | 210.4 | -55 | 2.8 | LLR224 | 0 | -90 | 0 |
| LLD135 | 165 | -61.9 | 5.8 | LLD138 | 240.4 | -53.5 | 2.8 | LLR225 | 0 | -90 | 0 |
| LLD136 | 0 | -70 | 4.8 | LLD138 | 270.4 | -53 | 4.8 | LLR226 | 0 | -90 | 0 |
| LLD136 | 48 | -68.8 | 4.8 | LLD138 | 300.4 | -52.5 | 2.8 | LLR227 | 0 | -90 | 0 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-----|-----------|---------|-------|-----|-----------|---------|-------|-----|-----------|
| LLR228 | 0 | -90 | 0 | LLRC013 | 0 | -60 | 4.8 | LLRC026 | 80 | -60 | 4.8 |
| LLR229 | 0 | -90 | 0 | LLRC013 | 73 | -60 | 4.8 | LLRC027 | 0 | -60 | 4.8 |
| LLR230 | 0 | -90 | 0 | LLRC014 | 0 | -60 | 4.8 | LLRC027 | 80 | -60 | 4.8 |
| LLR231 | 0 | -90 | 0 | LLRC014 | 57 | -60 | 4.8 | LLRC028 | 0 | -60 | 4.8 |
| LLR232 | 0 | -90 | 0 | LLRC015 | 0 | -60 | 4.8 | LLRC028 | 80 | -60 | 4.8 |
| LLR233 | 0 | -90 | 0 | LLRC015 | 100 | -60 | 4.8 | LLRC029 | 0 | -60 | 4.8 |
| LLR234 | 0 | -90 | 0 | LLRC016 | 0 | -60 | 4.8 | LLRC029 | 80 | -60 | 4.8 |
| LLR235 | 0 | -90 | 0 | LLRC016 | 103 | -60 | 4.8 | LLRC030 | 0 | -60 | 4.8 |
| LLR236 | 0 | -90 | 0 | LLRC017 | 0 | -60 | 4.8 | LLRC030 | 100 | -60 | 4.8 |
| LLR237 | 0 | -90 | 0 | LLRC017 | 100 | -60 | 4.8 | LLRC031 | 0 | -60 | 4.8 |
| LLRC001 | 0 | -60 | 4.8 | LLRC018 | 0 | -60 | 4.8 | LLRC031 | 100 | -60 | 4.8 |
| LLRC002 | 0 | -60 | 4.8 | LLRC018 | 91 | -60 | 4.8 | LLRC032 | 0 | -60 | 4.8 |
| LLRC003 | 0 | -60 | 4.8 | LLRC019 | 0 | -60 | 4.8 | LLRC032 | 100 | -60 | 4.8 |
| LLRC004 | 0 | -60 | 4.8 | LLRC019 | 96 | -60 | 4.8 | LLRC033 | 0 | -60 | 4.8 |
| LLRC005 | 0 | -60 | 4.8 | LLRC020 | 0 | -60 | 4.8 | LLRC033 | 100 | -60 | 4.8 |
| LLRC006 | 0 | -60 | 4.8 | LLRC020 | 97 | -60 | 4.8 | LLRC034 | 0 | -60 | 4.8 |
| LLRC007 | 0 | -60 | 4.8 | LLRC021 | 0 | -60 | 4.8 | LLRC034 | 100 | -60 | 4.8 |
| LLRC008 | 0 | -60 | 4.8 | LLRC021 | 97 | -60 | 4.8 | LLRC035 | 0 | -60 | 4.8 |
| LLRC008 | 88 | -60 | 4.8 | LLRC022 | 0 | -50 | 185.8 | LLRC035 | 100 | -60 | 4.8 |
| LLRC009 | 0 | -60 | 4.8 | LLRC022 | 120 | -50 | 182.8 | LLRC036 | 0 | -60 | 4.8 |
| LLRC009 | 88 | -60 | 4.8 | LLRC023 | 0 | -60 | 4.8 | LLRC036 | 100 | -60 | 4.8 |
| LLRC010 | 0 | -60 | 4.8 | LLRC023 | 91 | -60 | 4.8 | LLRC037 | 0 | -60 | 4.8 |
| LLRC010 | 100 | -60 | 4.8 | LLRC024 | 0 | -60 | 4.8 | LLRC037 | 100 | -60 | 4.8 |
| LLRC011 | 0 | -60 | 4.8 | LLRC024 | 80 | -60 | 4.8 | LLRC038 | 0 | -60 | 4.8 |
| LLRC011 | 63 | -60 | 4.8 | LLRC025 | 0 | -60 | 4.8 | LLRC038 | 100 | -60 | 4.8 |
| LLRC012 | 0 | -60 | 4.8 | LLRC025 | 80 | -60 | 4.8 | LLRC039 | 0 | -60 | 4.8 |
| LLRC012 | 85 | -60 | 4.8 | LLRC026 | 0 | -60 | 4.8 | LLRC039 | 100 | -60 | 4.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-----|-----------|---------|-------|-----|-----------|---------|-------|------------|-----------|
| LLRC040 | 0 | -60 | 4.8 | LLRC053 | 100 | -60 | 4.8 | LLRC067 | 0 | -60 | 4.8 |
| LLRC040 | 98 | -60 | 4.8 | LLRC054 | 0 | -60 | 4.8 | LLRC067 | 100 | -60 | 4.8 |
| LLRC041 | 0 | -60 | 4.8 | LLRC054 | 100 | -60 | 4.8 | LLRC068 | 0 | -60 | 4.8 |
| LLRC041 | 100 | -60 | 4.8 | LLRC055 | 0 | -60 | 4.8 | LLRC068 | 100 | -60 | 4.8 |
| LLRC042 | 0 | -60 | 4.8 | LLRC055 | 100 | -60 | 4.8 | LLRC069 | 0 | -70 | 4.8 |
| LLRC042 | 100 | -60 | 4.8 | LLRC056 | 0 | -60 | 4.8 | LLRC069 | 26 | -69.5 | 4.8 |
| LLRC043 | 0 | -60 | 4.8 | LLRC056 | 100 | -60 | 4.8 | LLRC069 | 61 | - 68.75 | 4.8 |
| LLRC043 | 89 | -60 | 4.8 | LLRC057 | 0 | -60 | 4.8 | LLRC069 | 97 | -67.5 | 4.8 |
| LLRC044 | 0 | -60 | 4.8 | LLRC057 | 100 | -60 | 4.8 | LLRC070 | 0 | -70 | 4.8 |
| LLRC044 | 100 | -60 | 4.8 | LLRC058 | 0 | -60 | 4.8 | LLRC070 | 103 | -68 | 4.8 |
| LLRC045 | 0 | -60 | 4.8 | LLRC058 | 100 | -60 | 4.8 | LLRC071 | 0 | -70 | 4.8 |
| LLRC045 | 100 | -60 | 4.8 | LLRC059 | 0 | -60 | 4.8 | LLRC071 | 102 | - 67.25 | 4.8 |
| LLRC046 | 0 | -60 | 4.8 | LLRC059 | 102 | -60 | 4.8 | LLRC072 | 0 | -70 | 4.8 |
| LLRC046 | 100 | -60 | 4.8 | LLRC060 | 0 | -60 | 4.8 | LLRC072 | 100 | -68 | 4.8 |
| LLRC047 | 0 | -60 | 4.8 | LLRC060 | 100 | -60 | 4.8 | LLRC073 | 0 | -70 | 4.8 |
| LLRC047 | 100 | -60 | 4.8 | LLRC061 | 0 | -60 | 4.8 | LLRC073 | 100 | -68 | 4.8 |
| LLRC048 | 0 | -60 | 4.8 | LLRC061 | 100 | -60 | 4.8 | LLRC074 | 0 | -70 | 4.8 |
| LLRC048 | 100 | -60 | 4.8 | LLRC062 | 0 | -60 | 4.8 | LLRC074 | 90 | -71.8 | 4.8 |
| LLRC049 | 0 | -60 | 4.8 | LLRC062 | 102 | -60 | 4.8 | LLRC075 | 0 | -70 | 4.8 |
| LLRC049 | 100 | -60 | 4.8 | LLRC063 | 0 | -60 | 4.8 | LLRC075 | 96 | -64 | 4.8 |
| LLRC050 | 0 | -60 | 4.8 | LLRC063 | 100 | -60 | 4.8 | LLRC076 | 0 | -70 | 4.8 |
| LLRC050 | 72 | -60 | 4.8 | LLRC064 | 0 | -60 | 4.8 | LLRC076 | 45 | -65 | 4.8 |
| LLRC051 | 0 | -60 | 4.8 | LLRC064 | 100 | -60 | 4.8 | LLRC076 | 90 | -60 | 4.8 |
| LLRC051 | 114 | -60 | 4.8 | LLRC065 | 0 | -60 | 4.8 | LLRC077 | 0 | -60 | 4.8 |
| LLRC052 | 0 | -60 | 4.8 | LLRC065 | 100 | -60 | 4.8 | LLRC077 | 90 | -60 | 4.8 |
| LLRC052 | 100 | -60 | 4.8 | LLRC066 | 0 | -60 | 4.8 | LLRC078 | 0 | -60 | 4.8 |
| LLRC053 | 0 | -60 | 4.8 | LLRC066 | 100 | -60 | 4.8 | LLRC078 | 90 | - 57.25 | 4.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-------|-----------|---------|-------|-------|-----------|---------|-------|-------|-----------|
| LLRC079 | 0 | -60 | 4.8 | LLRC087 | 0 | -70 | 4.8 | LLRC097 | 60 | -70.4 | 4.8 |
| LLRC079 | 90 | -55 | 4.8 | LLRC087 | 100 | -71.7 | 4.8 | LLRC097 | 120 | -64.9 | 4.8 |
| LLRC080 | 0 | -70 | 4.8 | LLRC088 | 0 | -70 | 4.8 | LLRC098 | 0 | -70 | 184.8 |
| LLRC080 | 42 | -71 | 4.8 | LLRC088 | 100 | -70 | 4.8 | LLRC098 | 100 | -64.3 | 184.8 |
| LLRC080 | 80 | -68.5 | 4.8 | LLRC089 | 0 | -70 | 4.8 | LLRC099 | 0 | -70 | 4.8 |
| LLRC080 | 120 | -60 | 4.8 | LLRC089 | 72 | -70 | 4.8 | LLRC099 | 60 | -70.9 | 4.8 |
| LLRC080 | 144 | -51 | 4.8 | LLRC090 | 0 | -70 | 4.8 | LLRC099 | 140 | -61.1 | 4.8 |
| LLRC081 | 0 | -70 | 4.8 | LLRC090 | 100 | -62.5 | 4.8 | LLRC100 | 0 | -70 | 4.8 |
| LLRC081 | 78 | -72.5 | 4.8 | LLRC091 | 0 | -70 | 4.8 | LLRC100 | 72 | -68 | 4.8 |
| LLRC081 | 126 | -69.5 | 4.8 | LLRC091 | 61 | -68.3 | 4.8 | LLRC100 | 168 | -59 | 4.8 |
| LLRC082 | 0 | -70 | 4.8 | LLRC091 | 140 | -64.4 | 4.8 | LLRC101 | 0 | -70 | 4.8 |
| LLRC082 | 54 | -69.5 | 4.8 | LLRC092 | 0 | -70 | 4.8 | LLRC101 | 60 | -76 | 4.8 |
| LLRC082 | 96 | -68 | 4.8 | LLRC092 | 61 | -66 | 4.8 | LLRC101 | 120 | -75 | 4.8 |
| LLRC082 | 126 | -64.5 | 4.8 | LLRC092 | 140 | -54.8 | 4.8 | LLRC102 | 0 | -60 | 4.8 |
| LLRC082 | 162 | -61.5 | 4.8 | LLRC093 | 0 | -70 | 4.8 | LLRC102 | 111 | -60 | 4.8 |
| LLRC083 | 0 | -70 | 4.8 | LLRC093 | 61 | -65.1 | 4.8 | LLRC103 | 0 | -60 | 4.8 |
| LLRC083 | 104 | -71.5 | 4.8 | LLRC093 | 140 | -50.5 | 4.8 | LLRC103 | 112 | -60 | 4.8 |
| LLRC084 | 0 | -70 | 4.8 | LLRC094 | 0 | -70 | 4.8 | LLRC104 | 0 | -60 | 4.8 |
| LLRC084 | 90 | -67 | 4.8 | LLRC094 | 61 | -69.1 | 4.8 | LLRC104 | 112 | -60 | 4.8 |
| LLRC085 | 0 | -70 | 4.8 | LLRC094 | 140 | -49.9 | 4.8 | LLRC105 | 0 | -60 | 4.8 |
| LLRC085 | 66 | -68.5 | 4.8 | LLRC095 | 0 | -70 | 4.8 | LLRC105 | 100 | -60 | 4.8 |
| LLRC085 | 102 | -68 | 4.8 | LLRC095 | 61 | -69.3 | 4.8 | LLRC106 | 0 | -60 | 4.8 |
| LLRC085 | 150 | -68 | 4.8 | LLRC095 | 120 | -67 | 4.8 | LLRC106 | 84 | -60 | 4.8 |
| LLRC086 | 0 | -70 | 4.8 | LLRC096 | 0 | -70 | 4.8 | LLRC107 | 0 | -60 | 4.8 |
| LLRC086 | 42 | -70.8 | 4.8 | LLRC096 | 60 | -67.8 | 4.8 | LLRC107 | 118 | -60 | 4.8 |
| LLRC086 | 84 | -70.6 | 4.8 | LLRC096 | 120 | -64.9 | 4.8 | LLRC108 | 0 | -60 | 4.8 |
| LLRC086 | 120 | -68 | 4.8 | LLRC097 | 0 | -70 | 4.8 | LLRC108 | 105 | -60 | 4.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-----|-----------|---------|-------|-----|-----------|---------|-------|-----|-----------|
| LLRC109 | 0 | -60 | 4.8 | LLRC122 | 100 | -60 | 4.8 | LLRC137 | 0 | -60 | 4.8 |
| LLRC109 | 118 | -60 | 4.8 | LLRC123 | 0 | -60 | 4.8 | LLRC137 | 84 | -60 | 4.8 |
| LLRC110 | 0 | -60 | 4.8 | LLRC123 | 100 | -60 | 4.8 | LLRC138 | 0 | -60 | 4.8 |
| LLRC110 | 130 | -60 | 4.8 | LLRC124 | 0 | -60 | 4.8 | LLRC138 | 80 | -60 | 4.8 |
| LLRC111 | 0 | -60 | 4.8 | LLRC124 | 72 | -60 | 4.8 | LLRC139 | 0 | -60 | 4.8 |
| LLRC111 | 109 | -60 | 4.8 | LLRC125 | 0 | -60 | 4.8 | LLRC139 | 101 | -60 | 4.8 |
| LLRC112 | 0 | -60 | 4.8 | LLRC125 | 114 | -60 | 4.8 | LLRC140 | 0 | -60 | 4.8 |
| LLRC112 | 124 | -60 | 4.8 | LLRC127 | 0 | -60 | 4.8 | LLRC140 | 100 | -60 | 4.8 |
| LLRC113 | 0 | -60 | 4.8 | LLRC127 | 96 | -60 | 4.8 | LLRC141 | 0 | -60 | 4.8 |
| LLRC113 | 106 | -60 | 4.8 | LLRC128 | 0 | -60 | 4.8 | LLRC141 | 60 | -60 | 4.8 |
| LLRC114 | 0 | -60 | 4.8 | LLRC128 | 79 | -60 | 4.8 | LLRC142 | 0 | -90 | 0 |
| LLRC114 | 46 | -60 | 4.8 | LLRC129 | 0 | -60 | 4.8 | LLRC142 | 40 | -90 | 0 |
| LLRC115 | 0 | -60 | 4.8 | LLRC129 | 111 | -60 | 4.8 | LLRC143 | 0 | -60 | 4.8 |
| LLRC115 | 106 | -60 | 4.8 | LLRC130 | 0 | -60 | 4.8 | LLRC143 | 71 | -60 | 4.8 |
| LLRC116 | 0 | -60 | 4.8 | LLRC130 | 108 | -60 | 4.8 | LLRC144 | 0 | -60 | 4.8 |
| LLRC116 | 100 | -60 | 4.8 | LLRC131 | 0 | -60 | 4.8 | LLRC144 | 39 | -60 | 4.8 |
| LLRC117 | 0 | -60 | 4.8 | LLRC131 | 79 | -60 | 4.8 | LLRC145 | 0 | -90 | 0 |
| LLRC117 | 100 | -60 | 4.8 | LLRC132 | 0 | -60 | 4.8 | LLRC145 | 84 | -90 | 0 |
| LLRC118 | 0 | -60 | 4.8 | LLRC132 | 66 | -60 | 4.8 | LLRC146 | 0 | -60 | 4.8 |
| LLRC118 | 94 | -60 | 4.8 | LLRC133 | 0 | -60 | 4.8 | LLRC147 | 0 | -90 | 0 |
| LLRC119 | 0 | -60 | 4.8 | LLRC133 | 96 | -60 | 4.8 | LLRC148 | 0 | -90 | 0 |
| LLRC119 | 64 | -60 | 4.8 | LLRC134 | 0 | -60 | 4.8 | LLRC149 | 0 | -90 | 0 |
| LLRC120 | 0 | -60 | 4.8 | LLRC134 | 59 | -60 | 4.8 | LLRC150 | 0 | -60 | 4.8 |
| LLRC120 | 118 | -60 | 4.8 | LLRC135 | 0 | -60 | 4.8 | LLRC150 | 66 | -60 | 4.8 |
| LLRC121 | 0 | -60 | 4.8 | LLRC135 | 84 | -60 | 4.8 | LLRC151 | 0 | -60 | 4.8 |
| LLRC121 | 94 | -60 | 4.8 | LLRC136 | 0 | -60 | 4.8 | LLRC151 | 72 | -60 | 4.8 |
| LLRC122 | 0 | -60 | 4.8 | LLRC136 | 108 | -60 | 4.8 | LLRC152 | 0 | -60 | 4.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-----|-----------|---------|-------|-----|-----------|--------|-------|-------|-----------|
| LLRC152 | 48 | -60 | 4.8 | LLRC166 | 60 | -60 | 7.8 | LMR205 | 0 | -90 | 0 |
| LLRC153 | 0 | -90 | 0 | LLRC167 | 0 | -60 | 2.8 | LMR206 | 0 | -90 | 0 |
| LLRC154 | 0 | -60 | 4.8 | LLRC167 | 129 | -60 | 2.8 | LMR207 | 0 | -90 | 0 |
| LLRC154 | 88 | -60 | 4.8 | LLRC168 | 0 | -60 | 2.8 | LPD001 | 0 | -50 | 4.8 |
| LLRC155 | 0 | -60 | 4.8 | LLRC168 | 111 | -60 | 2.8 | LPD001 | 6 | -53.5 | 4.8 |
| LLRC155 | 84 | -60 | 4.8 | LLRC169 | 0 | -60 | 4.8 | LPD001 | 25 | -54.5 | 7.8 |
| LLRC156 | 0 | -60 | 359.8 | LLRC169 | 87 | -60 | 4.8 | LPD001 | 50 | -51.8 | 6.8 |
| LLRC156 | 60 | -60 | 359.8 | LLRC170 | 0 | -60 | 4.8 | LPD001 | 101 | -45.8 | 4.3 |
| LLRC157 | 0 | -60 | 359.8 | LLRC170 | 99 | -60 | 4.8 | LPD001 | 130 | -38.8 | 2.8 |
| LLRC157 | 94 | -60 | 359.8 | LLRC171 | 0 | -60 | 4.8 | LPD001 | 160 | -38 | 2.3 |
| LLRC158 | 0 | -60 | 359.8 | LLRC171 | 120 | -60 | 4.8 | LPD001 | 190 | -37.8 | 0.8 |
| LLRC158 | 90 | -60 | 359.8 | LLRC172 | 0 | -60 | 4.8 | LPD001 | 220 | -38 | 359.8 |
| LLRC159 | 0 | -60 | 311.8 | LLRC172 | 87 | -60 | 4.8 | LPD001 | 250 | -36.5 | 0.8 |
| LLRC159 | 66 | -60 | 311.8 | LLRC173 | 0 | -60 | 4.8 | LPD001 | 280 | -32.5 | 357.8 |
| LLRC160 | 0 | -60 | 311.8 | LLRC173 | 78 | -60 | 4.8 | LRC001 | 0 | -60 | 4.8 |
| LLRC160 | 90 | -60 | 311.8 | LLRC174 | 0 | -60 | 4.8 | LRC001 | 85 | -60 | 4.8 |
| LLRC161 | 0 | -60 | 311.8 | LLRC174 | 96 | -60 | 4.8 | LRC002 | 0 | -60 | 4.8 |
| LLRC161 | 84 | -60 | 311.8 | LLRC175 | 0 | -60 | 4.8 | LRC002 | 65 | -60 | 4.8 |
| LLRC162 | 0 | -60 | 347.8 | LLRC175 | 120 | -60 | 4.8 | LRC003 | 0 | -60 | 4.8 |
| LLRC162 | 90 | -60 | 347.8 | LLRC176 | 0 | -60 | 4.8 | LRC003 | 60 | -60 | 4.8 |
| LLRC163 | 0 | -60 | 311.8 | LLRC176 | 80 | -60 | 4.8 | LRC004 | 0 | -60 | 4.8 |
| LLRC163 | 66 | -60 | 311.8 | LLRC177 | 0 | -60 | 4.8 | LRC004 | 80 | -60 | 4.8 |
| LLRC164 | 0 | -60 | 277.8 | LLRC177 | 234 | -60 | 4.8 | LRC005 | 0 | -60 | 4.8 |
| LLRC164 | 93 | -60 | 277.8 | LMR201 | 0 | -90 | 0 | LRC005 | 80 | -60 | 4.8 |
| LLRC165 | 0 | -60 | 7.8 | LMR202 | 0 | -90 | 0 | LRC006 | 0 | -60 | 4.8 |
| LLRC165 | 90 | -60 | 7.8 | LMR203 | 0 | -90 | 0 | LRC006 | 50 | -60 | 4.8 |
| LLRC166 | 0 | -60 | 7.8 | LMR204 | 0 | -90 | 0 | LRC007 | 0 | -60 | 4.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-----|-----------|--------|-------|-----|-----------|--------|-------|-----|-----------|
| LRC007 | 50 | -60 | 4.8 | LRC021 | 0 | -60 | 4.8 | LRC034 | 26 | -60 | 4.8 |
| LRC008 | 0 | -60 | 4.8 | LRC021 | 50 | -60 | 4.8 | LRC035 | 0 | -60 | 4.8 |
| LRC008 | 80 | -60 | 4.8 | LRC022 | 0 | -60 | 4.8 | LRC035 | 81 | -60 | 4.8 |
| LRC009 | 0 | -60 | 4.8 | LRC022 | 50 | -60 | 4.8 | LRC036 | 0 | -60 | 4.8 |
| LRC009 | 50 | -60 | 4.8 | LRC023 | 0 | -60 | 4.8 | LRC036 | 93 | -60 | 4.8 |
| LRC010 | 0 | -60 | 4.8 | LRC023 | 50 | -60 | 4.8 | LRC037 | 0 | -60 | 4.8 |
| LRC010 | 80 | -60 | 4.8 | LRC024 | 0 | -60 | 4.8 | LRC037 | 90 | -60 | 4.8 |
| LRC011 | 0 | -60 | 4.8 | LRC024 | 50 | -60 | 4.8 | LRC038 | 0 | -60 | 4.8 |
| LRC011 | 60 | -60 | 4.8 | LRC025 | 0 | -60 | 4.8 | LRC038 | 93 | -60 | 4.8 |
| LRC012 | 0 | -60 | 4.8 | LRC025 | 50 | -60 | 4.8 | LRC039 | 0 | -60 | 4.8 |
| LRC012 | 80 | -60 | 4.8 | LRC026 | 0 | -60 | 4.8 | LRC039 | 84 | -60 | 4.8 |
| LRC013 | 0 | -60 | 4.8 | LRC026 | 59 | -60 | 4.8 | LRC040 | 0 | -60 | 4.8 |
| LRC013 | 50 | -60 | 4.8 | LRC027 | 0 | -60 | 4.8 | LRC040 | 85 | -60 | 4.8 |
| LRC014 | 0 | -60 | 4.8 | LRC027 | 47 | -60 | 4.8 | LRC041 | 0 | -60 | 4.8 |
| LRC014 | 80 | -60 | 4.8 | LRC028 | 0 | -60 | 4.8 | LRC041 | 80 | -60 | 4.8 |
| LRC015 | 0 | -60 | 4.8 | LRC028 | 50 | -60 | 4.8 | LRC042 | 0 | -60 | 4.8 |
| LRC015 | 50 | -60 | 4.8 | LRC029 | 0 | -60 | 4.8 | LRC042 | 88 | -60 | 4.8 |
| LRC016 | 0 | -60 | 4.8 | LRC029 | 50 | -60 | 4.8 | LRC043 | 0 | -60 | 4.8 |
| LRC016 | 66 | -60 | 4.8 | LRC030 | 0 | -60 | 4.8 | LRC043 | 80 | -60 | 4.8 |
| LRC017 | 0 | -60 | 4.8 | LRC030 | 65 | -60 | 4.8 | LRC044 | 0 | -60 | 4.8 |
| LRC017 | 50 | -60 | 4.8 | LRC031 | 0 | -60 | 4.8 | LRC044 | 80 | -60 | 4.8 |
| LRC018 | 0 | -60 | 4.8 | LRC031 | 47 | -60 | 4.8 | LRC045 | 0 | -60 | 4.8 |
| LRC018 | 53 | -60 | 4.8 | LRC032 | 0 | -60 | 4.8 | LRC045 | 93 | -60 | 4.8 |
| LRC019 | 0 | -60 | 4.8 | LRC032 | 60 | -60 | 4.8 | LRC046 | 0 | -60 | 4.8 |
| LRC019 | 70 | -60 | 4.8 | LRC033 | 0 | -60 | 4.8 | LRC046 | 69 | -60 | 4.8 |
| LRC020 | 0 | -60 | 4.8 | LRC033 | 78 | -60 | 4.8 | LRC047 | 0 | -60 | 4.8 |
| LRC020 | 47 | -60 | 4.8 | LRC034 | 0 | -60 | 4.8 | LRC047 | 74 | -60 | 4.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-----|-----------|--------|-------|-----|-----------|---------|-------|-----|-----------|
| LRC048 | 0 | -60 | 4.8 | LRD124 | 0 | -90 | 0 | LRD151 | 0 | -90 | 0 |
| LRC048 | 68 | -60 | 4.8 | LRD125 | 0 | -90 | 0 | LRD152 | 0 | -90 | 0 |
| LRC049 | 0 | -60 | 4.8 | LRD126 | 0 | -90 | 0 | LRD153 | 0 | -90 | 0 |
| LRC049 | 78 | -60 | 4.8 | LRD127 | 0 | -90 | 0 | LRD154 | 0 | -90 | 0 |
| LRC050 | 0 | -50 | 4.8 | LRD128 | 0 | -90 | 0 | LRD155 | 0 | -90 | 0 |
| LRC050 | 48 | -50 | 4.8 | LRD129 | 0 | -90 | 0 | LSR201 | 0 | -90 | 0 |
| LRD103 | 0 | -90 | 0 | LRD130 | 0 | -90 | 0 | LSR202 | 0 | -90 | 0 |
| LRD104 | 0 | -90 | 0 | LRD131 | 0 | -90 | 0 | LSR203 | 0 | -90 | 0 |
| LRD105 | 0 | -90 | 0 | LRD132 | 0 | -90 | 0 | LSR204 | 0 | -90 | 0 |
| LRD106 | 0 | -90 | 0 | LRD133 | 0 | -90 | 0 | LSR205 | 0 | -90 | 0 |
| LRD107 | 0 | -90 | 0 | LRD134 | 0 | -90 | 0 | LSR206 | 0 | -90 | 0 |
| LRD108 | 0 | -90 | 0 | LRD135 | 0 | -90 | 0 | LTD0001 | 0 | -63 | 7.8 |
| LRD109 | 0 | -90 | 0 | LRD136 | 0 | -90 | 0 | LTD0001 | 42 | -61 | 7.8 |
| LRD110 | 0 | -90 | 0 | LRD137 | 0 | -90 | 0 | LTD0001 | 69 | -61 | 6.8 |
| LRD111 | 0 | -90 | 0 | LRD138 | 0 | -90 | 0 | LTD0001 | 108 | -60 | 7.3 |
| LRD112 | 0 | -90 | 0 | LRD139 | 0 | -90 | 0 | LTD0001 | 144 | -59 | 6.8 |
| LRD113 | 0 | -90 | 0 | LRD140 | 0 | -90 | 0 | LTD0001 | 174 | -59 | 7.8 |
| LRD114 | 0 | -90 | 0 | LRD141 | 0 | -90 | 0 | LTD0002 | 0 | -60 | 7.8 |
| LRD115 | 0 | -90 | 0 | LRD142 | 0 | -90 | 0 | LTD0002 | 12 | -60 | 7.8 |
| LRD116 | 0 | -90 | 0 | LRD143 | 0 | -90 | 0 | LTD0002 | 51 | -51 | 7.8 |
| LRD117 | 0 | -90 | 0 | LRD144 | 0 | -90 | 0 | LTD0002 | 87 | -49 | 7.8 |
| LRD118 | 0 | -90 | 0 | LRD145 | 0 | -90 | 0 | LTD0002 | 93 | -49 | 7.8 |
| LRD119 | 0 | -90 | 0 | LRD146 | 0 | -90 | 0 | LTD0002 | 111 | -49 | 7.8 |
| LRD120 | 0 | -90 | 0 | LRD147 | 0 | -90 | 0 | LTD0002 | 138 | -49 | 7.8 |
| LRD121 | 0 | -90 | 0 | LRD148 | 0 | -90 | 0 | LTD0003 | 0 | -60 | 7.8 |
| LRD122 | 0 | -90 | 0 | LRD149 | 0 | -90 | 0 | LTD0003 | 60 | -55 | 7.8 |
| LRD123 | 0 | -90 | 0 | LRD150 | 0 | -90 | 0 | LTD0003 | 111 | -55 | 7.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-----|-----------|---------|-------|-------|-----------|---------|-------|-------|-----------|
| LTD0003 | 147 | -55 | 7.8 | LTD0009 | 0 | -64 | 4.8 | LTD0012 | 60 | -56.8 | 5.5 |
| LTD0003 | 174 | -55 | 7.8 | LTD0009 | 96 | -63 | 7.8 | LTD0012 | 90 | -55.6 | 5.5 |
| LTD0003 | 201 | -54 | 7.8 | LTD0009 | 123 | -62 | 7.8 | LTD0012 | 120 | -51.5 | 7.2 |
| LTD0004 | 0 | -70 | 7.8 | LTD0009 | 177 | -60.3 | 0.6 | LTD0012 | 144 | -49.3 | 7.2 |
| LTD0004 | 84 | -74 | 7.8 | LTD0009 | 207 | -59.3 | 359.5 | LTD0012 | 174 | -43.5 | 7.2 |
| LTD0004 | 123 | -73 | 7.8 | LTD0009 | 237 | -58.9 | 359.9 | LTD0012 | 204 | -42.5 | 8.1 |
| LTD0004 | 153 | -74 | 6.8 | LTD0009 | 243 | -58.6 | 0.5 | LTD0012 | 234 | -41.5 | 8.7 |
| LTD0005 | 0 | -70 | 7.8 | LTD0009 | 267 | -58.6 | 359.9 | LTD0012 | 264 | -40.5 | 8.6 |
| LTD0005 | 81 | -71 | 6.8 | LTD0009 | 297 | -58.4 | 0.8 | LTD0013 | 0 | -60 | 4.8 |
| LTD0005 | 111 | -71 | 7.8 | LTD0009 | 327 | -58.2 | 0.3 | LTD0013 | 30 | -61.2 | 6 |
| LTD0005 | 135 | -71 | 7.8 | LTD0010 | 0 | -60 | 4.8 | LTD0013 | 60 | -60.7 | 6 |
| LTD0006 | 0 | -58 | 7.8 | LTD0010 | 30 | -60.9 | 7.8 | LTD0013 | 90 | -60.3 | 6 |
| LTD0006 | 69 | -55 | 8.8 | LTD0010 | 60 | -59 | 5.5 | LTD0013 | 120 | -60.3 | 6.1 |
| LTD0006 | 99 | -55 | 8.8 | LTD0010 | 90 | -56.4 | 5.8 | LTD0013 | 150 | -60.5 | 6.7 |
| LTD0006 | 129 | -54 | 8.8 | LTD0010 | 120 | -50.8 | 7 | LTD0013 | 183 | -59.9 | 4.7 |
| LTD0006 | 150 | -54 | 8.3 | LTD0010 | 150 | -46.3 | 7 | LTD0013 | 210 | -58.7 | 3.3 |
| LTD0007 | 0 | -65 | 9.8 | LTD0010 | 180 | -45.2 | 7 | LTD0013 | 243 | -57.6 | 1.8 |
| LTD0007 | 99 | -65 | 7.8 | LTD0010 | 210 | -44.3 | 6.7 | LTD0013 | 273 | -56.4 | 359.7 |
| LTD0007 | 129 | -60 | 7.8 | LTD0011 | 0 | -60 | 4.8 | LTD0014 | 0 | -60 | 4.8 |
| LTD0007 | 159 | -60 | 7.8 | LTD0011 | 60 | -60.5 | 3.3 | LTD0014 | 174 | -57.7 | 11.8 |
| LTD0007 | 189 | -60 | 7.8 | LTD0011 | 90 | -64.1 | 3.3 | LTD0014 | 204 | -56.4 | 12.1 |
| LTD0007 | 219 | -60 | 7.8 | LTD0011 | 108 | -54.2 | 3.3 | LTD0014 | 234 | -56.8 | 10.9 |
| LTD0008 | 0 | -56 | 11.8 | LTD0011 | 126 | -53.5 | 5 | LTD0014 | 267 | -56.7 | 10.4 |
| LTD0008 | 106 | -46 | 7.8 | LTD0011 | 156 | -52.6 | 5 | LTD0014 | 297 | -56.1 | 9.9 |
| LTD0008 | 141 | -44 | 7.8 | LTD0011 | 186 | -51.4 | 4.3 | LTD0015 | 0 | -60 | 4.8 |
| LTD0008 | 174 | -43 | 8.8 | LTD0012 | 0 | -60 | 4.8 | LTD0015 | 101 | -61.5 | 7.8 |
| LTD0008 | 201 | -43 | 7.8 | LTD0012 | 30 | -60.1 | 5.5 | LTD0015 | 350 | -52.9 | 356.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-------|-----------|---------|-------|-------|-----------|---------|-------|-------|-----------|
| LTD0015 | 380 | -52 | 356.8 | LTD0018 | 0 | -60 | 4.8 | LTD0021 | 132 | -61 | 2.8 |
| LTD0015 | 409 | -51.5 | 356.8 | LTD0018 | 86 | -63.5 | 9.8 | LTD0021 | 162.7 | -59.5 | 1.8 |
| LTD0015 | 446 | -50 | 355.8 | LTD0018 | 116.9 | -63 | 7.8 | LTD0021 | 192 | -58.5 | 1.8 |
| LTD0016 | 0 | -60 | 4.8 | LTD0018 | 146.9 | -62 | 4.8 | LTD0021 | 222.7 | -56.8 | 3.8 |
| LTD0016 | 115.2 | -61.5 | 5.3 | LTD0018 | 158.9 | -61 | 4.8 | LTD0021 | 252 | -55.5 | 1.8 |
| LTD0016 | 140 | -61 | 5.8 | LTD0018 | 176.9 | -61 | 3.8 | LTD0021 | 282.7 | -52.1 | 1.8 |
| LTD0016 | 181.2 | -58.5 | 4.8 | LTD0018 | 197.9 | -61 | 3.8 | LTD0021 | 312 | -50 | 358.8 |
| LTD0016 | 230 | -55 | 3.8 | LTD0019 | 0 | -60 | 4.8 | LTD0021 | 342.7 | -49 | 358.8 |
| LTD0016 | 262.2 | -54 | 3.3 | LTD0019 | 71 | -60 | 7.8 | LTD0021 | 372.7 | -47.5 | 358.8 |
| LTD0016 | 292.2 | -56 | 359.8 | LTD0019 | 110 | -60 | 7.8 | LTD0022 | 0 | -60 | 4.8 |
| LTD0016 | 322 | -51 | 3.8 | LTD0019 | 149.3 | -58 | 7.3 | LTD0022 | 120 | -62.2 | 1 |
| LTD0016 | 348 | -48.5 | 1.8 | LTD0019 | 182 | -56 | 3.3 | LTD0022 | 150 | -62.3 | 0.4 |
| LTD0016 | 382 | -46 | 359.8 | LTD0019 | 209.3 | -55 | 2.8 | LTD0022 | 180 | -62.2 | 359.1 |
| LTD0016 | 412 | -44 | 1.8 | LTD0019 | 239 | -54 | 1.8 | LTD0022 | 210 | -61.2 | 357 |
| LTD0016 | 432 | -43.5 | 1.8 | LTD0019 | 269 | -53.5 | 0.8 | LTD0022 | 240 | -60.3 | 354.9 |
| LTD0016 | 454.2 | -42.5 | 1.8 | LTD0020 | 0 | -60 | 4.8 | LTD0022 | 270 | -59.9 | 355.6 |
| LTD0017 | 0 | -60 | 4.8 | LTD0020 | 74.2 | -61 | 7.3 | LTD0022 | 300 | -58.8 | 354.4 |
| LTD0017 | 90.5 | -62 | 2.3 | LTD0020 | 104 | -60 | 7.8 | LTD0022 | 330 | -58.2 | 355.3 |
| LTD0017 | 120 | -62 | 1.8 | LTD0020 | 131 | -60 | 7.8 | LTD0022 | 360 | -57.3 | 354.7 |
| LTD0017 | 150 | -61 | 359.8 | LTD0020 | 176.5 | -59 | 4.8 | LTD0022 | 383.6 | -56.8 | 354.5 |
| LTD0017 | 180 | -58.5 | 359.8 | LTD0020 | 206 | -58 | 5.8 | LTD0023 | 0 | -60 | 4.8 |
| LTD0017 | 210 | -57.1 | 356.8 | LTD0020 | 236 | -57 | 4.8 | LTD0023 | 63 | -60.5 | 6.8 |
| LTD0017 | 240 | -56.5 | 356.8 | LTD0020 | 266 | -56 | 5.8 | LTD0023 | 90 | -60 | 6.8 |
| LTD0017 | 270 | -56 | 356.8 | LTD0020 | 296 | -55 | 6.8 | LTD0023 | 120 | -60 | 4.8 |
| LTD0017 | 300 | -55 | 357.8 | LTD0020 | 356 | -53 | 4.8 | LTD0023 | 150 | -59 | 3.8 |
| LTD0017 | 330 | -54 | 356.8 | LTD0020 | 383.5 | -51 | 4.8 | LTD0023 | 180 | -57 | 0.8 |
| LTD0017 | 360 | -52 | 357.8 | LTD0021 | 0 | -60 | 4.8 | LTD0023 | 210 | -56 | 358.8 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-------|-----------|---------|-------|--------|-----------|---------|-------|-------|-----------|
| LTD0023 | 240 | -55 | 358.8 | LTD0024 | 810.4 | -43.8 | 9.3 | LTD0025 | 555 | -39 | 356.8 |
| LTD0023 | 269.6 | -53 | 358.8 | LTD0024 | 840.4 | -42 | 9.4 | LTD0025 | 570 | -38 | 356.8 |
| LTD0023 | 287.7 | -53 | 358.8 | LTD0024 | 870.4 | -41 | 9.9 | LTD0025 | 585 | -37.5 | 356.8 |
| LTD0024 | 0 | -60 | 4.8 | LTD0025 | 0 | -60 | 4.8 | LTD0025 | 600 | -37.1 | 356.8 |
| LTD0024 | 120 | -59.4 | 356.5 | LTD0025 | 120 | -57 | 10.8 | LTD0025 | 615 | -37 | 356.8 |
| LTD0024 | 150 | -58.6 | 356.5 | LTD0025 | 150 | -56 | 355.8 | LTD0026 | 0 | -60 | 4.8 |
| LTD0024 | 180 | -58.5 | 358.5 | LTD0025 | 180 | -56 | 9.8 | LTD0026 | 90 | -62.5 | 1.8 |
| LTD0024 | 210 | -58.5 | 359.5 | LTD0025 | 210 | -54 | 7.8 | LTD0026 | 120 | -62 | 359.8 |
| LTD0024 | 240 | -58.3 | 0.4 | LTD0025 | 240 | -53.25 | 18.8 | LTD0026 | 149 | -60.5 | 357.8 |
| LTD0024 | 270 | -58.2 | 0.5 | LTD0025 | 269.4 | -51.25 | 7.8 | LTD0026 | 150 | -60.5 | 357.8 |
| LTD0024 | 300 | -57.7 | 0.5 | LTD0025 | 285 | -50.8 | 7.8 | LTD0026 | 180 | -59.5 | 357.8 |
| LTD0024 | 330 | -57.3 | 0.6 | LTD0025 | 312 | -50.1 | 6.8 | LTD0026 | 210 | -59 | 356.8 |
| LTD0024 | 360 | -57.6 | 1.5 | LTD0025 | 327 | -50 | 6.8 | LTD0026 | 239.7 | -59 | 356.8 |
| LTD0024 | 390 | -57.2 | 3.2 | LTD0025 | 342 | -49.99 | 6.8 | LTD0026 | 269.7 | -58.8 | 356.8 |
| LTD0024 | 420 | -56.4 | 4.5 | LTD0025 | 361 | -49 | 5.8 | LTD0026 | 302 | -55 | 356.8 |
| LTD0024 | 450 | -55.6 | 6.2 | LTD0025 | 375 | -48.5 | 6.8 | LTD0026 | 317 | -55 | 356.8 |
| LTD0024 | 480 | -54.9 | 8.8 | LTD0025 | 390 | -47.9 | 4.8 | LTD0027 | 0 | -60 | 4.8 |
| LTD0024 | 510 | -54.6 | 9.4 | LTD0025 | 405 | -47 | 4.8 | LTD0027 | 60 | -61.2 | 4.5 |
| LTD0024 | 540 | -53.7 | 10.5 | LTD0025 | 420 | -46 | 2.8 | LTD0027 | 90 | -62 | 3.4 |
| LTD0024 | 570 | -53 | 11 | LTD0025 | 435 | -43.8 | 1.8 | LTD0027 | 120 | -62.2 | 2.2 |
| LTD0024 | 600 | -52.7 | 12 | LTD0025 | 450 | -41.5 | 356.8 | LTD0027 | 150 | -62.3 | 1.3 |
| LTD0024 | 630 | -52.1 | 12 | LTD0025 | 465 | -41 | 357.8 | LTD0027 | 180 | -62.3 | 0.5 |
| LTD0024 | 660 | -51.4 | 10.4 | LTD0025 | 480 | -41 | 356.8 | LTD0027 | 210 | -61.9 | 0 |
| LTD0024 | 690 | -49.4 | 8.8 | LTD0025 | 495 | -40.5 | 356.8 | LTD0027 | 240 | -61.7 | 359.1 |
| LTD0024 | 720 | -47.9 | 8.1 | LTD0025 | 510 | -40 | 356.8 | LTD0027 | 270 | -61.6 | 359.8 |
| LTD0024 | 750 | -46.8 | 8.4 | LTD0025 | 525 | -40 | 357.8 | LTD0027 | 300 | -61.3 | 0.7 |
| LTD0024 | 780 | -46.8 | 8.7 | LTD0025 | 540 | -40 | 356.8 | LTD0027 | 330 | -61 | 1.2 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-------|-----------|---------|-------|-------|-----------|---------|-------|-------|-----------|
| LTD0027 | 360 | -60.5 | 0.9 | LTD0030 | 190 | -54.6 | 4.9 | LTD0032 | 120 | -63.4 | 2.2 |
| LTD0027 | 390 | -60.2 | 0 | LTD0030 | 220 | -54.2 | 4.5 | LTD0032 | 159.4 | -63.2 | 1.1 |
| LTD0027 | 420 | -59.6 | 3.1 | LTD0030 | 250 | -53.9 | 5.1 | LTD0033 | 0 | -63 | 4.8 |
| LTD0027 | 450 | -58.8 | 2.9 | LTD0030 | 280 | -52.4 | 4.5 | LTD0033 | 150 | -59.6 | 10.8 |
| LTD0027 | 480 | -58 | 3.9 | LTD0030 | 309 | -51.9 | 5.1 | LTD0033 | 180 | -59.5 | 15 |
| LTD0027 | 510 | -57.3 | 5.4 | LTD0030 | 340 | -51.5 | 3.9 | LTD0033 | 210 | -58.6 | 12.8 |
| LTD0028 | 0 | -60 | 4.8 | LTD0030 | 399 | -50.5 | 6 | LTD0033 | 240 | -57.9 | 11.8 |
| LTD0028 | 90.3 | -60.7 | 1.8 | LTD0030 | 430 | -50 | 7.2 | LTD0033 | 270 | -57.1 | 12.5 |
| LTD0028 | 120 | -60.4 | 0.2 | LTD0030 | 460 | -49.2 | 7.4 | LTD0033 | 300 | -56.2 | 13.4 |
| LTD0028 | 150 | -59.8 | 358.3 | LTD0030 | 490 | -48.6 | 8 | LTD0033 | 330 | -55.1 | 19.4 |
| LTD0028 | 180 | -59.5 | 359.6 | LTD0030 | 520 | -48.5 | 7.4 | LTD0033 | 375 | -53.3 | 14.8 |
| LTD0028 | 207 | -58.6 | 359.8 | LTD0030 | 550 | -47.2 | 7.4 | LTD0034 | 0 | -60 | 4.8 |
| LTD0029 | 0 | -60 | 4.8 | LTD0030 | 580 | -45.8 | 7.4 | LTD0034 | 90 | -59.8 | 5.8 |
| LTD0029 | 120 | -60 | 0 | LTD0030 | 612 | -44.7 | 7.3 | LTD0034 | 120 | -58.7 | 5.9 |
| LTD0029 | 150 | -59.2 | 359.1 | LTD0031 | 0 | -60 | 4.8 | LTD0034 | 150 | -57.9 | 4.9 |
| LTD0029 | 180 | -58.9 | 359.2 | LTD0031 | 90 | -65.8 | 3.8 | LTD0034 | 180 | -57 | 1.7 |
| LTD0029 | 210 | -58.4 | 359 | LTD0031 | 120 | -65.2 | 2.3 | LTD0034 | 210 | -56.1 | 4.2 |
| LTD0029 | 240 | -57.8 | 358.8 | LTD0031 | 150 | -65.2 | 2.6 | LTD0034 | 240 | -55.5 | 5.5 |
| LTD0029 | 270 | -56.8 | 9.9 | LTD0031 | 180 | -64.2 | 0.8 | LTD0034 | 270 | -54 | 6.7 |
| LTD0029 | 300 | -56.9 | 359.6 | LTD0031 | 210 | -63.3 | 357.9 | LTD0034 | 290 | -53.8 | 6.8 |
| LTD0029 | 330 | -56.2 | 359.3 | LTD0031 | 240 | -63.5 | 356.5 | LTD0035 | 0 | -60 | 4.8 |
| LTD0029 | 360 | -55.5 | 0.2 | LTD0031 | 270 | -63.1 | 356.9 | LTD0035 | 90 | -58.3 | 4.6 |
| LTD0029 | 420 | -54.3 | 1.7 | LTD0031 | 330 | -62.6 | 356 | LTD0035 | 120 | -57.3 | 5.3 |
| LTD0029 | 450 | -52.9 | 3.6 | LTD0031 | 360 | -62.1 | 353.9 | LTD0035 | 150 | -62.2 | 4.8 |
| LTD0030 | 0 | -60 | 4.8 | LTD0031 | 390 | -62.3 | 354.2 | LTD0035 | 180 | -61.1 | 2.1 |
| LTD0030 | 130 | -55.8 | 4.2 | LTD0032 | 0 | -63 | 4.8 | LTD0035 | 210 | -60 | 1 |
| LTD0030 | 160 | -55 | 4.9 | LTD0032 | 90 | -64.4 | 4.6 | LTD0035 | 240 | -57.3 | 357.1 |

| HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 | HoleID | Depth | Dip | AzimMGA94 |
|---------|-------|-------|-----------|---------|-------|-------|-----------|--------|-------|-----|-----------|
| LTD0035 | 270 | -55.6 | 355.5 | LTD0038 | 120 | -61.7 | 13.5 | LTR208 | 0 | -90 | 0 |
| LTD0035 | 300 | -54.2 | 354.1 | LTD0039 | 0 | -60 | 11.8 | LTR209 | 0 | -90 | 0 |
| LTD0035 | 330 | -51.8 | 353.4 | LTD0039 | 60 | -70.1 | 8.8 | LTR210 | 0 | -90 | 0 |
| LTD0035 | 360 | -50 | 352.6 | LTD0039 | 90 | -70 | 7.6 | LTR211 | 0 | -90 | 0 |
| LTD0035 | 390 | -49.4 | 352.6 | LTD0039 | 120 | -69.1 | 6.7 | LTR212 | 0 | -90 | 0 |
| LTD0035 | 420 | -48.5 | 352.3 | LTD0039 | 180 | -67.6 | 3.2 | LTR213 | 0 | -90 | 0 |
| LTD0035 | 450 | -47 | 351 | LTD0039 | 210 | -67.7 | 3 | LTR214 | 0 | -90 | 0 |
| LTD0035 | 480 | -45.8 | 351 | LTD0039 | 240 | -67.3 | 1 | LTR215 | 0 | -90 | 0 |
| LTD0035 | 510 | -44.3 | 351.9 | LTD0039 | 270 | -66.8 | 0.6 | LTR216 | 0 | -90 | 0 |
| LTD0035 | 529.6 | -43.9 | 351.6 | LTD0039 | 300 | -66.1 | 359.8 | LTR217 | 0 | -90 | 0 |
| LTD0036 | 0 | -60 | 4.8 | LTD0040 | 0 | -50 | 7.8 | LTR218 | 0 | -90 | 0 |
| LTD0036 | 180 | -55.1 | 5 | LTD0040 | 130 | -44 | 3.5 | LTR219 | 0 | -90 | 0 |
| LTD0036 | 210 | -54.5 | 5.6 | LTD0040 | 190 | -40.4 | 3.5 | LTR220 | 0 | -90 | 0 |
| LTD0036 | 240 | -53.5 | 5.8 | LTD0040 | 220 | -39.2 | 3.2 | LTR221 | 0 | -90 | 0 |
| LTD0036 | 270 | -52 | 7.2 | LTD0041 | 0 | -60 | 17.8 | LTR222 | 0 | -90 | 0 |
| LTD0036 | 297 | -55.1 | 7.7 | LTD0041 | 80 | -57.5 | 18 | LTR223 | 0 | -90 | 0 |
| LTD0037 | 0 | -60 | 11.8 | LTD0041 | 110 | -56.5 | 16 | LTR224 | 0 | -90 | 0 |
| LTD0037 | 90 | -59.5 | 14.8 | LTD0041 | 140 | -55.7 | 15.9 | LTR225 | 0 | -90 | 0 |
| LTD0037 | 120 | -59 | 14.6 | LTD0041 | 170 | -55.6 | 14.2 | LTR226 | 0 | -90 | 0 |
| LTD0037 | 150 | -58.5 | 13.7 | LTD0041 | 200 | -55.1 | 14 | LTR227 | 0 | -90 | 0 |
| LTD0037 | 180 | -57.8 | 13.3 | LTR201 | 0 | -90 | 0 | LTR228 | 0 | -90 | 0 |
| LTD0037 | 210 | -57.3 | 13.7 | LTR202 | 0 | -90 | 0 | LTR229 | 0 | -90 | 0 |
| LTD0037 | 240 | -56.7 | 13.3 | LTR203 | 0 | -90 | 0 | LTR230 | 0 | -90 | 0 |
| LTD0037 | 270 | -56.9 | 14.1 | LTR204 | 0 | -90 | 0 | LTR231 | 0 | -90 | 0 |
| LTD0037 | 300 | -56.5 | 16.1 | LTR205 | 0 | -90 | 0 | LTR232 | 0 | -90 | 0 |
| LTD0038 | 0 | -60 | 11.8 | LTR206 | 0 | -90 | 0 | LTR233 | 0 | -90 | 0 |
| LTD0038 | 90 | -61.8 | 15.9 | LTR207 | 0 | -90 | 0 | LTR234 | 0 | -90 | 0 |

| HoleID | Depth | Dip | AzimMGA94 |
|--------|-------|-----|-----------|
| LTR235 | 0 | -90 | 0 |
| LTR236 | 0 | -90 | 0 |
| LTR237 | 0 | -90 | 0 |
| LTR238 | 0 | -90 | 0 |
| LTR239 | 0 | -90 | 0 |
| LTR240 | 0 | -90 | 0 |
| LTR241 | 0 | -90 | 0 |
| LTR242 | 0 | -90 | 0 |
| LTR243 | 0 | -90 | 0 |
| LTR244 | 0 | -90 | 0 |
| LTR245 | 0 | -90 | 0 |
| LTR246 | 0 | -90 | 0 |
| LTR247 | 0 | -90 | 0 |
| LTR248 | 0 | -90 | 0 |
| LTR249 | 0 | -90 | 0 |
| LTR250 | 0 | -90 | 0 |
| LTR251 | 0 | -90 | 0 |
| LTR252 | 0 | -90 | 0 |
| LTR253 | 0 | -90 | 0 |
| LTR254 | 0 | -90 | 0 |

APPENDIX 3

LIONTOWN DRILLHOLE ASSAY INTERVALS

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD124 | 338 | 339 | 3 | 0.055 | 0.13 | 0.41 | 2.57 | 3.45 | 12 |
| LLD124 | 339 | 340 | 22 | 0.187 | 0.37 | 3.86 | 21.20 | 26.45 | 12 |
| LLD124 | 340 | 341 | 5 | 0.037 | 0.11 | 0.15 | 0.79 | 1.42 | 12 |
| LTD0017 | 325 | 326 | 2.9 | 0.04 | 0.13 | 0.37 | 2.18 | 3.00 | 12 |
| LTD0017 | 326 | 327 | 24.3 | 0.09 | 1.11 | 1.83 | 11.65 | 17.57 | 12 |
| LTD0017 | 327 | 328 | 13.1 | 0.06 | 1.15 | 0.83 | 7.32 | 12.20 | 12 |
| LTD0017 | 328 | 329 | 4.3 | 0.05 | 0.31 | 0.13 | 2.15 | 3.41 | 12 |
| LTD0017 | 329 | 330 | 3.1 | 0.04 | 0.01 | 0.09 | 0.20 | 0.39 | 12 |
| LTD0017 | 330 | 331 | 4.2 | 0.03 | 0.10 | 0.18 | 1.15 | 1.73 | 12 |
| LTD0017 | 331 | 332 | 6.4 | 0.03 | 0.62 | 0.13 | 0.45 | 2.77 | 12 |
| LTD0030 | 492.08 | 493 | 34 | 0.1 | 2.18 | 3.99 | 14.40 | 26.04 | 12 |
| LTD0030 | 493 | 494 | 20 | 0.07 | 1.38 | 0.90 | 6.20 | 12.07 | 12 |
| LTD0030 | 494 | 495 | 0 | 0.02 | 0.00 | 0.02 | 0.08 | 0.09 | 12 |
| LLD031 | 204.52 | 206.81 | | | 0.03 | 0.50 | 2.12 | 2.68 | 11 |
| LLD031 | 206.81 | 208.03 | | | 0.02 | 0.16 | 0.26 | 0.47 | 11 |
| LLD031 | 208.03 | 209.09 | | | 3.20 | 0.08 | 3.00 | 13.63 | 11 |
| LLD031 | 209.09 | 209.85 | | | 0.68 | 0.07 | 0.24 | 2.54 | 11 |
| LLD033 | 248.41 | 249.94 | | | 0.01 | 0.01 | 0.28 | 0.32 | 11 |
| LLD033 | 249.94 | 251.46 | | | 0.02 | 0.01 | 0.58 | 0.64 | 11 |
| LLD033 | 251.46 | 252.98 | | | 0.01 | 0.01 | 0.33 | 0.37 | 11 |
| LLD118 | 339.2 | 340.2 | 1 | 0.035 | 0.01 | 0.08 | 1.36 | 1.48 | 11 |
| LLD118 | 340.2 | 341.2 | 1 | 0.033 | 0.03 | 0.06 | 0.84 | 1.03 | 11 |
| LLD118 | 341.2 | 342.2 | 1 | 0.02 | 0.00 | 0.01 | 0.40 | 0.44 | 11 |
| LLD118 | 342.2 | 343.2 | 1 | 0.037 | 0.05 | 0.01 | 1.41 | 1.61 | 11 |
| LLD118 | 343.2 | 344.2 | 4 | 0.06 | 0.78 | 0.41 | 4.38 | 7.43 | 11 |
| LTD0007 | 208 | 209 | 0.5 | 0.04 | 0.01 | 0.02 | 0.33 | 0.39 | 11 |
| LTD0007 | 209 | 210 | 0.2 | 0.04 | 0.01 | 0.02 | 0.50 | 0.56 | 11 |
| LTD0036 | 199 | 200 | 58 | 0.14 | 4.82 | 1.25 | 7.16 | 25.65 | 11 |
| LTD0036 | 200 | 201 | 9 | 0.07 | 1.10 | 0.07 | 0.35 | 4.27 | 11 |
| LTD0036 | 201 | 202 | 7 | 0.05 | 0.45 | 0.20 | 0.68 | 2.50 | 11 |
| LTD0036 | 202 | 203 | 51 | 1.95 | 0.47 | 0.54 | 7.69 | 11.08 | 11 |
| LTD0036 | 203 | 204 | 70 | 0.1 | 2.41 | 1.07 | 2.66 | 13.33 | 11 |
| LLD027 | 6.1 | 7.62 | | | 0.13 | 0.16 | 0.28 | 0.84 | 9 |
| LLD027 | 7.62 | 9.14 | | | 0.20 | 0.22 | 0.56 | 1.39 | 9 |
| LLD027 | 9.14 | 10.67 | | | 0.19 | 0.18 | 0.56 | 1.34 | 9 |
| LLD027 | 10.67 | 12.19 | | | 0.45 | 0.33 | 0.62 | 2.39 | 9 |
| LLD027 | 12.19 | 13.72 | | | 0.49 | 0.96 | 0.66 | 3.14 | 9 |
| LLD027 | 13.72 | 15.24 | | | 0.45 | 0.73 | 0.22 | 2.34 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD027 | 15.24 | 18.29 | | | 0.40 | 1.31 | 0.22 | 2.70 | 9 |
| LLD027 | 18.29 | 19.81 | | | 0.16 | 0.36 | 0.15 | 1.00 | 9 |
| LLD029 | 31.35 | 33.53 | 0 | 0 | 0.05 | 0.12 | 0.10 | 0.38 | 9 |
| LLD029 | 33.53 | 36.58 | | | 0.06 | 0.06 | 0.12 | 0.35 | 9 |
| LLD029 | 36.58 | 37.89 | | | 0.06 | 0.01 | 0.16 | 0.38 | 9 |
| LLD030 | 37.53 | 38.1 | 0 | 0 | 0.08 | 0.03 | 0.26 | 0.54 | 9 |
| LLD030 | 38.1 | 39.62 | | | 0.05 | 0.05 | 0.16 | 0.36 | 9 |
| LLD030 | 39.62 | 39.78 | | | 0.07 | 0.11 | 0.19 | 0.51 | 9 |
| LLD030 | 39.78 | 41.15 | | | 0.05 | 0.04 | 0.13 | 0.33 | 9 |
| LLD030 | 41.15 | 42.67 | | | 0.05 | 0.05 | 0.16 | 0.37 | 9 |
| LLD030 | 42.67 | 44.2 | | | 0.05 | 0.05 | 0.16 | 0.38 | 9 |
| LLD030 | 44.2 | 45.42 | | | 0.06 | 0.03 | 0.19 | 0.42 | 9 |
| LLD030 | 45.42 | 45.72 | | | 0.12 | 0.04 | 0.34 | 0.77 | 9 |
| LLD030 | 45.72 | 46.69 | | | 0.08 | 0.03 | 0.20 | 0.51 | 9 |
| LLD031 | 151.18 | 152.7 | | | 0.08 | 0.48 | 7.50 | 8.20 | 9 |
| LLD031 | 152.7 | 153.7 | | | 0.10 | 0.23 | 6.00 | 6.53 | 9 |
| LLD031 | 153.7 | 155.68 | | | 0.62 | 0.60 | 19.75 | 22.34 | 9 |
| LLD031 | 155.68 | 156.51 | | | 0.06 | 0.56 | 3.25 | 3.97 | 9 |
| LLD031 | 156.51 | 158.04 | | | | | | 0.00 | 9 |
| LLD031 | 158.04 | 160.32 | | | 0.02 | 0.07 | 0.15 | 0.26 | 9 |
| LLD031 | 160.32 | 162.15 | | | 0.12 | 0.34 | 3.75 | 4.45 | 9 |
| LLD031 | 162.15 | 163.37 | | | | | | 0.00 | 9 |
| LLD031 | 163.37 | 164.9 | | | 0.16 | 1.90 | 11.50 | 13.74 | 9 |
| LLD031 | 164.9 | 166.42 | | | 0.13 | 3.00 | 12.50 | 15.62 | 9 |
| LLD031 | 166.42 | 167.94 | | | 0.08 | 1.90 | 13.00 | 14.96 | 9 |
| LLD031 | 167.94 | 169.47 | | | 0.08 | 0.82 | 4.05 | 5.05 | 9 |
| LLD031 | 169.47 | 170.99 | | | 0.02 | 0.35 | 0.26 | 0.62 | 9 |
| LLD031 | 170.99 | 172.52 | | | 0.02 | 0.58 | 2.95 | 3.54 | 9 |
| LLD031 | 172.52 | 174.8 | | | 0.02 | 0.66 | 2.82 | 3.48 | 9 |
| LLD031 | 174.8 | 176.33 | | | 0.03 | 0.50 | 2.12 | 2.68 | 9 |
| LLD031 | 176.33 | 178.23 | | | 0.06 | 0.76 | 5.50 | 6.38 | 9 |
| LLD031 | 178.23 | 180.37 | | | 0.72 | 0.50 | 10.30 | 13.12 | 9 |
| LLD032 | 112.96 | 114.3 | 0 | 0 | 0.13 | 0.65 | 2.29 | 3.30 | 9 |
| LLD032 | 114.3 | 115.82 | | | 0.12 | 0.64 | 1.72 | 2.69 | 9 |
| LLD032 | 115.82 | 117.35 | | | 0.43 | 3.06 | 6.02 | 10.19 | 9 |
| LLD032 | 117.35 | 118.87 | | | 0.68 | 5.68 | 10.48 | 17.84 | 9 |
| LLD032 | 118.87 | 120.4 | | | 0.46 | 3.59 | 6.77 | 11.52 | 9 |
| LLD032 | 120.4 | 121.92 | | | 0.44 | 3.42 | 6.37 | 10.90 | 9 |
| LLD032 | 121.92 | 123.44 | | | 0.03 | 0.20 | 0.38 | 0.66 | 9 |
| LLD032 | 123.44 | 124.05 | | | 0.09 | 0.55 | 0.95 | 1.74 | 9 |
| LLD032 | 124.05 | 124.36 | | | 0.43 | 1.30 | 6.46 | 9.05 | 9 |
| LLD032 | 124.36 | 124.66 | | | 0.35 | 3.18 | 5.10 | 9.12 | 9 |
| LLD032 | 124.66 | 124.97 | | | 0.30 | 3.05 | 4.79 | 8.53 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD032 | 124.97 | 125.27 | | | 0.32 | 2.81 | 4.53 | 8.12 | 9 |
| LLD032 | 125.27 | 125.58 | | | 0.29 | 1.17 | 3.66 | 5.67 | 9 |
| LLD032 | 125.58 | 125.88 | | | 0.18 | 1.68 | 2.26 | 4.37 | 9 |
| LLD032 | 125.88 | 126.19 | | | 0.14 | 1.17 | 1.92 | 3.44 | 9 |
| LLD032 | 126.19 | 126.49 | | | 0.29 | 1.91 | 3.01 | 5.69 | 9 |
| LLD032 | 126.49 | 126.8 | | | 0.30 | 1.56 | 4.14 | 6.53 | 9 |
| LLD032 | 126.8 | 127.1 | | | 0.56 | 5.32 | 10.46 | 17.10 | 9 |
| LLD032 | 127.1 | 127.41 | | | 0.39 | 5.71 | 7.74 | 14.17 | 9 |
| LLD032 | 127.41 | 127.71 | | | 0.38 | 5.39 | 6.28 | 12.39 | 9 |
| LLD032 | 127.71 | 128.02 | | | 0.47 | 5.81 | 7.77 | 14.55 | 9 |
| LLD032 | 128.02 | 128.32 | | | 0.54 | 6.26 | 9.71 | 17.13 | 9 |
| LLD032 | 128.32 | 128.63 | | | 0.76 | 3.86 | 13.24 | 19.22 | 9 |
| LLD032 | 128.63 | 128.93 | | | 0.72 | 7.92 | 10.85 | 20.35 | 9 |
| LLD032 | 128.93 | 129.24 | | | 1.04 | 8.89 | 17.83 | 29.26 | 9 |
| LLD032 | 129.24 | 129.54 | | | 1.18 | 7.16 | 21.46 | 31.80 | 9 |
| LLD032 | 129.54 | 129.84 | | | 0.93 | 5.93 | 15.01 | 23.42 | 9 |
| LLD032 | 129.84 | 130.15 | | | 1.13 | 7.28 | 18.32 | 28.60 | 9 |
| LLD032 | 130.15 | 130.45 | | | 1.16 | 6.41 | 19.62 | 29.22 | 9 |
| LLD032 | 130.45 | 130.76 | | | 1.00 | 5.85 | 18.10 | 26.67 | 9 |
| LLD032 | 130.76 | 131.06 | | | 0.99 | 5.20 | 15.43 | 23.38 | 9 |
| LLD032 | 131.06 | 131.37 | | | 1.15 | 2.76 | 16.77 | 23.05 | 9 |
| LLD032 | 131.37 | 131.67 | | | 0.95 | 2.15 | 11.36 | 16.43 | 9 |
| LLD032 | 131.67 | 131.98 | | | 0.80 | 3.08 | 13.51 | 18.92 | 9 |
| LLD032 | 131.98 | 132.28 | | | 1.43 | 3.80 | 23.88 | 32.02 | 9 |
| LLD032 | 132.28 | 132.59 | | | 0.68 | 3.34 | 14.94 | 20.19 | 9 |
| LLD032 | 132.59 | 132.89 | | | 1.34 | 3.44 | 20.15 | 27.67 | 9 |
| LLD032 | 132.89 | 133.2 | | | 0.83 | 3.36 | 12.20 | 17.96 | 9 |
| LLD032 | 133.2 | 133.5 | | | 0.36 | 2.59 | 6.33 | 9.85 | 9 |
| LLD032 | 133.5 | 133.81 | | | 0.12 | 1.52 | 1.91 | 3.67 | 9 |
| LLD032 | 133.81 | 134.11 | | | 0.18 | 0.41 | 1.09 | 2.05 | 9 |
| LLD032 | 134.11 | 134.42 | | | 0.12 | 0.48 | 1.94 | 2.77 | 9 |
| LLD032 | 134.42 | 134.72 | | | 0.37 | 2.04 | 8.86 | 11.92 | 9 |
| LLD032 | 134.72 | 135.03 | | | 0.12 | 0.32 | 2.00 | 2.68 | 9 |
| LLD032 | 135.03 | 135.33 | | | 0.18 | 1.77 | 2.64 | 4.83 | 9 |
| LLD032 | 135.33 | 135.64 | | | 0.05 | 0.67 | 0.87 | 1.64 | 9 |
| LLD033 | 191.62 | 192.24 | 0 | 0 | 0.29 | 1.25 | 5.20 | 7.28 | 9 |
| LLD033 | 192.24 | 192.94 | | | | | | | 9 |
| LLD033 | 192.94 | 193.24 | | | 0.06 | 0.26 | 0.48 | 0.91 | 9 |
| LLD033 | 193.24 | 193.55 | | | 0.06 | 0.58 | 1.15 | 1.87 | 9 |
| LLD033 | 193.55 | 193.85 | | | 0.10 | 1.05 | 2.87 | 4.14 | 9 |
| LLD033 | 193.85 | 194.16 | | | 0.23 | 2.87 | 11.10 | 14.44 | 9 |
| LLD033 | 194.16 | 194.46 | | | 0.08 | 0.75 | 2.08 | 3.02 | 9 |
| LLD033 | 194.46 | 194.77 | | | 0.02 | 0.23 | 0.50 | 0.76 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|------|--------|------------|
| LLD033 | 194.77 | 195.07 | | | 0.03 | 0.45 | 0.83 | 1.32 | 9 |
| LLD033 | 195.07 | 195.38 | | | 0.06 | 1.20 | 2.08 | 3.36 | 9 |
| LLD033 | 195.38 | 195.68 | | | 0.34 | 0.50 | 1.68 | 3.25 | 9 |
| LLD033 | 195.68 | 195.99 | | | 0.09 | 0.30 | 0.70 | 1.26 | 9 |
| LLD033 | 195.99 | 196.29 | | | 0.04 | 0.30 | 1.18 | 1.57 | 9 |
| LLD033 | 196.29 | 196.6 | | | 0.11 | 0.36 | 2.76 | 3.44 | 9 |
| LLD033 | 196.6 | 196.9 | | | 0.14 | 1.25 | 4.65 | 6.24 | 9 |
| LLD033 | 196.9 | 197.21 | | | 0.31 | 1.65 | 5.55 | 8.06 | 9 |
| LLD033 | 197.21 | 197.51 | | | 0.06 | 0.36 | 1.55 | 2.06 | 9 |
| LLD033 | 197.51 | 197.82 | | | 0.22 | 0.66 | 1.73 | 3.04 | 9 |
| LLD033 | 197.82 | 198.12 | | | 0.04 | 0.23 | 1.03 | 1.38 | 9 |
| LLD033 | 198.12 | 198.42 | | | 0.02 | 0.16 | 1.24 | 1.46 | 9 |
| LLD033 | 198.42 | 198.73 | | | 0.03 | 0.36 | 1.21 | 1.62 | 9 |
| LLD033 | 198.73 | 199.03 | | | 0.02 | 0.26 | 1.15 | 1.45 | 9 |
| LLD033 | 199.03 | 199.34 | | | 0.09 | 2.50 | 6.00 | 8.55 | 9 |
| LLD033 | 199.34 | 199.64 | | | 0.07 | 1.08 | 3.95 | 5.17 | 9 |
| LLD033 | 199.64 | 199.95 | | | 0.02 | 0.33 | 0.87 | 1.22 | 9 |
| LLD033 | 199.95 | 200.25 | | | 0.02 | 0.19 | 0.58 | 0.81 | 9 |
| LLD033 | 200.25 | 200.56 | | | 0.02 | 0.20 | 0.89 | 1.13 | 9 |
| LLD033 | 200.56 | 200.86 | | | 0.02 | 0.21 | 0.45 | 0.71 | 9 |
| LLD033 | 200.86 | 201.17 | | | 0.05 | 0.29 | 1.88 | 2.31 | 9 |
| LLD033 | 201.17 | 201.47 | | | 0.14 | 0.27 | 2.00 | 2.71 | 9 |
| LLD033 | 201.47 | 201.78 | | | 0.04 | 0.08 | 0.48 | 0.67 | 9 |
| LLD033 | 201.78 | 202.08 | | | 0.04 | 0.07 | 0.69 | 0.89 | 9 |
| LLD033 | 202.08 | 202.39 | | | 0.07 | 0.83 | 2.64 | 3.60 | 9 |
| LLD033 | 202.39 | 202.69 | | | 0.17 | 1.00 | 4.35 | 5.82 | 9 |
| LLD033 | 202.69 | 203 | | | 0.03 | 0.20 | 0.74 | 1.02 | 9 |
| LLD033 | 203 | 203.3 | | | 0.01 | 0.13 | 0.45 | 0.60 | 9 |
| LLD033 | 203.3 | 203.61 | | | 0.01 | 0.08 | 0.35 | 0.44 | 9 |
| LLD033 | 203.61 | 203.91 | | | 0.01 | 0.13 | 0.48 | 0.63 | 9 |
| LLD033 | 203.91 | 204.22 | | | 0.03 | 0.96 | 2.28 | 3.25 | 9 |
| LLD033 | 204.22 | 204.52 | | | 0.20 | 1.29 | 3.40 | 5.22 | 9 |
| LLD033 | 204.52 | 204.83 | | | 0.13 | 1.65 | 4.80 | 6.72 | 9 |
| LLD033 | 204.83 | 205.13 | | | 0.02 | 0.20 | 0.58 | 0.83 | 9 |
| LLD033 | 205.13 | 205.44 | | | 0.06 | 0.09 | 0.19 | 0.47 | 9 |
| LLD033 | 205.44 | 205.74 | | | 0.06 | 0.17 | 1.31 | 1.67 | 9 |
| LLD033 | 205.74 | 205.96 | | | 0.04 | 0.08 | 0.23 | 0.43 | 9 |
| LLD036 | 31.21 | 32 | 0 | 0 | 0.19 | 0.07 | 0.04 | 0.74 | 9 |
| LLD036 | 32 | 33.53 | | | 0.17 | 0.07 | 0.12 | 0.75 | 9 |
| LLD036 | 33.53 | 35.05 | | | 0.10 | 0.05 | 0.09 | 0.45 | 9 |
| LLD036 | 35.05 | 37.19 | | | 0.16 | 0.05 | 0.16 | 0.75 | 9 |
| LLD036 | 37.19 | 37.43 | | | 0.07 | 0.02 | 0.21 | 0.45 | 9 |
| LLD038 | 29.35 | 30.48 | 0 | 0 | 0.12 | 0.08 | 0.02 | 0.50 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|------|--------|------------|
| LLD038 | 30.48 | 31.76 | | | 0.16 | 0.05 | 0.02 | 0.60 | 9 |
| LLD040 | 47.24 | 48.77 | | | 1.73 | 0.08 | 0.20 | 5.98 | 9 |
| LLD040 | 48.77 | 50.29 | | | 0.68 | 0.05 | 0.10 | 2.39 | 9 |
| LLD041 | 53.34 | 54.86 | | | 0.31 | 0.02 | 0.16 | 1.18 | 9 |
| LLD041 | 54.86 | 56.39 | | | 0.16 | 0.04 | 0.30 | 0.86 | 9 |
| LLD047 | 51.82 | 52.12 | | | 0.52 | 0.49 | 4.98 | 7.13 | 9 |
| LLD047 | 52.12 | 53.34 | | | 0.20 | 0.46 | 2.07 | 3.13 | 9 |
| LLD047 | 53.34 | 54.86 | | | 0.14 | 0.25 | 0.47 | 1.15 | 9 |
| LLD047 | 54.86 | 56.39 | | | 0.18 | 0.37 | 1.99 | 2.91 | 9 |
| LLD047 | 56.39 | 57.91 | | | 0.31 | 0.08 | 3.36 | 4.46 | 9 |
| LLD047 | 57.91 | 59.44 | | | 0.21 | 0.12 | 1.92 | 2.71 | 9 |
| LLD047 | 59.44 | 60.35 | | | 0.16 | 0.13 | 1.78 | 2.44 | 9 |
| LLD047 | 60.35 | 60.66 | | | 0.12 | 0.24 | 0.86 | 1.48 | 9 |
| LLD047 | 60.66 | 60.96 | | | 0.11 | 0.13 | 0.95 | 1.43 | 9 |
| LLD047 | 60.96 | 62.18 | | | 0.07 | 0.51 | 0.72 | 1.41 | 9 |
| LLD047 | 62.18 | 62.48 | | | 0.72 | 0.29 | 3.51 | 6.14 | 9 |
| LLD047 | 62.48 | 62.79 | | | 0.77 | 0.17 | 2.84 | 5.52 | 9 |
| LLD047 | 62.79 | 63.09 | | | 0.29 | 0.24 | 1.69 | 2.85 | 9 |
| LLD047 | 63.09 | 63.4 | | | 0.12 | 0.41 | 1.18 | 1.93 | 9 |
| LLD047 | 63.4 | 63.7 | | | 0.18 | 0.19 | 1.86 | 2.62 | 9 |
| LLD047 | 63.7 | 64.01 | | | 0.19 | 0.24 | 1.43 | 2.27 | 9 |
| LLD047 | 64.01 | 64.31 | | | 0.18 | 0.02 | 1.06 | 1.67 | 9 |
| LLD047 | 64.31 | 64.62 | | | 0.22 | 0.27 | 1.33 | 2.29 | 9 |
| LLD047 | 64.62 | 64.92 | | | 0.38 | 0.07 | 1.84 | 3.15 | 9 |
| LLD047 | 64.92 | 65.23 | | | 0.23 | 0.15 | 1.28 | 2.18 | 9 |
| LLD047 | 65.23 | 65.53 | | | 0.16 | 0.29 | 1.20 | 1.99 | 9 |
| LLD047 | 65.53 | 65.84 | | | 0.13 | 0.22 | 1.46 | 2.08 | 9 |
| LLD047 | 65.84 | 66.14 | | | 0.07 | 0.39 | 0.77 | 1.36 | 9 |
| LLD048 | 44.69 | 48.77 | 0 | 0 | 0.45 | 0.10 | 0.07 | 1.65 | 9 |
| LLD048 | 48.77 | 51.82 | | | 0.13 | 0.05 | 0.12 | 0.59 | 9 |
| LLD048 | 51.82 | 52.72 | | | 0.04 | 0.03 | 0.21 | 0.36 | 9 |
| LLD049 | 123.39 | 123.44 | 0 | 0 | 0.02 | 0.01 | 0.02 | 0.09 | 9 |
| LLD049 | 123.44 | 123.75 | | | 0.01 | 0.02 | 0.03 | 0.09 | 9 |
| LLD049 | 123.75 | 124.05 | | | 0.02 | 0.02 | 0.02 | 0.08 | 9 |
| LLD049 | 124.05 | 124.36 | | | 0.02 | 0.01 | 0.02 | 0.09 | 9 |
| LLD049 | 124.36 | 124.66 | | | 0.01 | 0.01 | 0.01 | 0.04 | 9 |
| LLD049 | 124.66 | 124.97 | | | 0.01 | 0.01 | 0.01 | 0.04 | 9 |
| LLD049 | 124.97 | 125.27 | | | 0.01 | 0.01 | 0.01 | 0.06 | 9 |
| LLD049 | 125.27 | 125.58 | | | 0.03 | 0.01 | 0.02 | 0.11 | 9 |
| LLD049 | 125.58 | 125.88 | | | 0.01 | 0.01 | 0.01 | 0.06 | 9 |
| LLD049 | 125.88 | 126.19 | | | 0.04 | 0.18 | 0.20 | 0.49 | 9 |
| LLD049 | 126.19 | 126.49 | | | 0.05 | 0.22 | 0.59 | 0.95 | 9 |
| LLD049 | 126.49 | 126.8 | | | 0.04 | 0.28 | 0.75 | 1.15 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD049 | 126.8 | 127.1 | | | 0.20 | 2.19 | 4.80 | 7.43 | 9 |
| LLD049 | 127.1 | 127.41 | | | 0.11 | 1.54 | 2.76 | 4.52 | 9 |
| LLD049 | 127.41 | 127.71 | | | 0.02 | 0.30 | 0.77 | 1.12 | 9 |
| LLD049 | 127.71 | 128.02 | | | 0.03 | 0.31 | 0.70 | 1.07 | 9 |
| LLD049 | 128.02 | 128.32 | | | 0.04 | 0.37 | 0.92 | 1.38 | 9 |
| LLD049 | 128.32 | 128.63 | | | 0.23 | 1.59 | 3.75 | 5.95 | 9 |
| LLD049 | 128.63 | 128.93 | | | 0.07 | 0.62 | 1.31 | 2.09 | 9 |
| LLD049 | 128.93 | 129.24 | | | 0.02 | 0.06 | 0.12 | 0.23 | 9 |
| LLD049 | 129.24 | 129.54 | | | 0.01 | 0.02 | 0.03 | 0.10 | 9 |
| LLD049 | 129.54 | 129.84 | | | 0.03 | 0.28 | 0.29 | 0.62 | 9 |
| LLD049 | 129.84 | 130.15 | | | 0.04 | 0.28 | 0.62 | 1.00 | 9 |
| LLD049 | 130.15 | 130.45 | | | 0.03 | 0.14 | 3.40 | 3.61 | 9 |
| LLD049 | 130.45 | 130.76 | | | 0.01 | 0.04 | 0.11 | 0.20 | 9 |
| LLD049 | 130.76 | 131.06 | | | 0.03 | 0.54 | 1.03 | 1.62 | 9 |
| LLD049 | 131.06 | 131.37 | | | 0.21 | 1.20 | 2.37 | 4.14 | 9 |
| LLD049 | 131.37 | 131.67 | | | 0.10 | 0.36 | 1.88 | 2.52 | 9 |
| LLD049 | 131.67 | 131.98 | | | | | | 0.00 | 9 |
| LLD049 | 131.98 | 132.28 | | | 0.20 | 1.86 | 4.35 | 6.67 | 9 |
| LLD049 | 132.28 | 132.59 | | | 0.19 | 1.29 | 0.25 | 2.03 | 9 |
| LLD052 | 41.15 | 42.67 | | | 0.25 | 0.06 | 0.09 | 0.96 | 9 |
| LLD052 | 42.67 | 44.2 | | | 0.59 | 0.05 | 0.06 | 2.04 | 9 |
| LLD052 | 44.2 | 45.72 | | | 0.59 | 0.01 | 0.11 | 2.06 | 9 |
| LLD052 | 45.72 | 47.24 | | | 0.28 | 0.01 | 0.12 | 1.04 | 9 |
| LLD052 | 47.24 | 48.77 | | | 0.15 | 0.01 | 0.44 | 0.94 | 9 |
| LLD052 | 48.77 | 50.29 | | | 0.14 | 0.04 | 0.93 | 1.41 | 9 |
| LLD102 | 35.8 | 36.8 | 8 | 0.035 | 0.04 | 0.04 | 0.06 | 0.43 | 9 |
| LLD102 | 36.8 | 37.8 | 4 | 0.068 | 0.06 | 0.06 | 0.14 | 0.50 | 9 |
| LLD102 | 37.8 | 38.8 | 4 | 0.038 | 0.06 | 0.06 | 0.19 | 0.53 | 9 |
| LLD102 | 38.8 | 39.8 | 39 | 0.033 | 0.07 | 0.02 | 0.15 | 1.38 | 9 |
| LLD102 | 39.8 | 40.8 | 6 | 0.04 | 0.06 | 0.02 | 0.19 | 0.55 | 9 |
| LLD102 | 40.8 | 41.8 | 3 | 0.027 | 0.05 | 0.02 | 0.13 | 0.38 | 9 |
| LLD102 | 41.8 | 42.8 | 6 | 0.013 | 0.04 | 0.02 | 0.10 | 0.41 | 9 |
| LLD102 | 42.8 | 43.8 | 133 | 0.012 | 0.04 | 0.02 | 0.06 | 3.55 | 9 |
| LLD102 | 43.8 | 44.8 | 112 | 0.013 | 0.03 | 0.03 | 0.06 | 3.00 | 9 |
| LLD104 | 214.03 | 214.3 | 84 | 0.177 | 0.42 | 3.14 | 6.70 | 13.02 | 9 |
| LLD104 | 214.3 | 215.3 | 149 | 0.322 | 0.48 | 3.21 | 9.53 | 17.74 | 9 |
| LLD104 | 215.3 | 216.3 | 258 | 0.963 | 0.25 | 0.78 | 1.98 | 10.01 | 9 |
| LLD104 | 216.3 | 217.3 | 63 | 0.304 | 0.06 | 0.56 | 1.17 | 3.46 | 9 |
| LLD104 | 217.3 | 218.3 | 13 | 0.148 | 0.15 | 0.51 | 0.81 | 2.10 | 9 |
| LLD104 | 218.3 | 219.3 | 56 | 0.387 | 1.17 | 4.40 | 9.72 | 18.96 | 9 |
| LLD104 | 219.3 | 220.3 | 68 | 0.3 | 0.32 | 1.00 | 1.52 | 5.19 | 9 |
| LLD104 | 220.3 | 221.3 | 73 | 0.35 | 0.41 | 2.48 | 5.35 | 10.78 | 9 |
| LLD104 | 221.3 | 222.3 | 61 | 0.322 | 0.94 | 6.25 | 17.40 | 27.67 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|------|--------|------------|
| LLD104 | 222.3 | 223.3 | 16 | 0.123 | 0.11 | 1.68 | 4.05 | 6.33 | 9 |
| LLD104 | 223.3 | 224.3 | 6 | 0.035 | 0.04 | 0.11 | 0.49 | 0.87 | 9 |
| LLD104 | 224.3 | 225.3 | 1 | 0.038 | 0.00 | 0.03 | 0.12 | 0.18 | 9 |
| LLD104 | 225.3 | 226.3 | 0 | 0.035 | 0.00 | 0.02 | 0.15 | 0.15 | 9 |
| LLD104 | 226.3 | 227.3 | 0 | 0.027 | 0.00 | 0.01 | 0.05 | 0.04 | 9 |
| LLD104 | 227.3 | 227.5 | 0 | 0.025 | 0.00 | 0.01 | 0.28 | 0.27 | 9 |
| LLD107 | 113.5 | 114.5 | 168 | 0.465 | 0.14 | 0.69 | 2.83 | 8.14 | 9 |
| LLD107 | 114.5 | 115.5 | 98 | 0.798 | 0.44 | 2.55 | 7.05 | 13.29 | 9 |
| LLD107 | 115.5 | 116.5 | 9 | 0.112 | 0.05 | 0.32 | 0.94 | 1.62 | 9 |
| LLD107 | 116.5 | 117.5 | 31 | 0.183 | 0.45 | 3.56 | 7.50 | 12.97 | 9 |
| LLD107 | 117.5 | 118.5 | 13 | 0.098 | 0.13 | 0.94 | 1.85 | 3.45 | 9 |
| LLD107 | 118.5 | 119.5 | 11 | 0.137 | 0.16 | 1.48 | 3.11 | 5.25 | 9 |
| LLD107 | 119.5 | 120.5 | 20 | 0.14 | 0.15 | 1.16 | 2.41 | 4.46 | 9 |
| LLD107 | 120.5 | 121.5 | 7 | 0.077 | 0.11 | 1.31 | 2.51 | 4.23 | 9 |
| LLD107 | 121.5 | 122.5 | 7 | 0.073 | 0.09 | 2.26 | 3.85 | 6.36 | 9 |
| LLD107 | 122.5 | 123.5 | 4 | 0.062 | 0.07 | 0.92 | 1.94 | 3.10 | 9 |
| LLD107 | 123.5 | 124.5 | 11 | 0.063 | 0.26 | 3.01 | 6.05 | 9.90 | 9 |
| LLD107 | 124.5 | 125.5 | 16 | 0.07 | 0.25 | 0.29 | 0.89 | 2.38 | 9 |
| LLD107 | 125.5 | 126.5 | 12 | 0.058 | 0.12 | 0.17 | 0.65 | 1.50 | 9 |
| LLD107 | 126.5 | 127.5 | 25 | 0.147 | 1.89 | 1.93 | 9.45 | 18.06 | 9 |
| LLD107 | 127.5 | 128.5 | 24 | 0.068 | 2.74 | 0.29 | 2.18 | 12.09 | 9 |
| LLD107 | 128.5 | 129.5 | 23 | 0.07 | 2.57 | 0.40 | 5.80 | 15.22 | 9 |
| LLD107 | 129.5 | 130.5 | 13 | 0.048 | 1.85 | 0.14 | 2.85 | 9.41 | 9 |
| LLD107 | 130.5 | 131.5 | 13 | 0.048 | 1.15 | 0.13 | 3.28 | 7.52 | 9 |
| LLD107 | 131.5 | 132.5 | 8 | 0.023 | 0.60 | 0.06 | 0.88 | 3.12 | 9 |
| LLD107 | 132.5 | 133.5 | 3 | 0.012 | 0.20 | 0.04 | 0.72 | 1.49 | 9 |
| LLD107 | 133.5 | 134.5 | 2 | 0.028 | 0.07 | 0.02 | 0.15 | 0.43 | 9 |
| LLD107 | 134.5 | 135.5 | 3 | 0.048 | 0.20 | 0.06 | 1.44 | 2.22 | 9 |
| LLD110 | 230.2 | 231.2 | 1 | 0.047 | 0.01 | 0.08 | 0.75 | 0.87 | 9 |
| LLD110 | 231.2 | 232.2 | 0 | 0.018 | 0.00 | 0.13 | 0.48 | 0.58 | 9 |
| LLD110 | 232.2 | 233.2 | 3 | 0.047 | 0.18 | 0.27 | 6.40 | 7.30 | 9 |
| LLD110 | 233.2 | 234.2 | 2 | 0.037 | 0.01 | 0.25 | 1.96 | 2.26 | 9 |
| LLD110 | 234.2 | 235.2 | 1 | 0.035 | 0.17 | 0.15 | 1.79 | 2.51 | 9 |
| LLD110 | 235.2 | 236.2 | 0 | 0.02 | 0.00 | 0.05 | 0.19 | 0.21 | 9 |
| LLD110 | 236.2 | 237.2 | 0 | 0.015 | 0.00 | 0.05 | 0.23 | 0.25 | 9 |
| LLD110 | 237.2 | 238.2 | 0 | 0.024 | 0.00 | 0.07 | 0.31 | 0.36 | 9 |
| LLD110 | 238.2 | 239.2 | 1 | 0.042 | 0.10 | 0.11 | 1.45 | 1.91 | 9 |
| LLD114 | 120.8 | 121.8 | 4 | 0.032 | 0.42 | 0.26 | 9.05 | 10.77 | 9 |
| LLD114 | 121.8 | 122.8 | 3 | 0.047 | 0.02 | 0.37 | 0.85 | 1.33 | 9 |
| LLD114 | 122.8 | 123.8 | 5 | 0.043 | 0.28 | 2.23 | 4.14 | 7.20 | 9 |
| LLD114 | 123.8 | 124.8 | 9 | 0.063 | 0.41 | 1.62 | 5.55 | 8.59 | 9 |
| LLD114 | 124.8 | 125.8 | 1 | 0.057 | 0.01 | 0.15 | 0.42 | 0.62 | 9 |
| LLD114 | 125.8 | 126.8 | 7 | 0.065 | 0.36 | 1.25 | 3.10 | 5.57 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD114 | 126.8 | 127.8 | 2 | 0.068 | 0.06 | 0.46 | 1.05 | 1.72 | 9 |
| LLD115 | 83.4 | 85.4 | 94 | 3.07 | 3.17 | 9.85 | 10.20 | 32.03 | 9 |
| LLD115 | 85.4 | 86.4 | 31 | 0.617 | 0.60 | 0.46 | 1.42 | 4.62 | 9 |
| LLD115 | 86.4 | 87.4 | 33 | 0.078 | 5.05 | 0.54 | 9.21 | 27.19 | 9 |
| LLD116 | 91.2 | 93.75 | 258 | 0.258 | 1.65 | 2.18 | 28.40 | 42.27 | 9 |
| LLD116 | 93.75 | 95.75 | 24 | 0.081 | 0.34 | 3.76 | 14.40 | 19.51 | 9 |
| LLD116 | 95.75 | 97.5 | 12 | 0.117 | 0.23 | 2.78 | 7.15 | 10.70 | 9 |
| LLD116 | 97.5 | 101.8 | 4 | 0.098 | 0.02 | 0.49 | 4.95 | 5.55 | 9 |
| LLD116 | 101.8 | 102.7 | 0 | 0.028 | 0.00 | 0.04 | 0.58 | 0.60 | 9 |
| LLD116 | 102.7 | 104.05 | 1 | 0.043 | 0.00 | 0.06 | 1.17 | 1.26 | 9 |
| LLD118 | 294.2 | 295.2 | 152 | 1.85 | 0.51 | 4.35 | 7.60 | 17.09 | 9 |
| LLD118 | 295.2 | 296.2 | 147 | 0.904 | 0.46 | 3.08 | 5.65 | 13.66 | 9 |
| LLD118 | 296.2 | 297.2 | 54 | 0.127 | 0.03 | 0.09 | 0.35 | 1.89 | 9 |
| LLD118 | 297.2 | 298.2 | 8 | 0.065 | 0.01 | 0.05 | 0.11 | 0.39 | 9 |
| LLD118 | 298.2 | 299.2 | 77 | 0.141 | 0.04 | 0.22 | 0.36 | 2.61 | 9 |
| LLD118 | 299.2 | 300.2 | 98 | 0.16 | 0.05 | 0.36 | 0.50 | 3.46 | 9 |
| LLD119 | 146 | 147 | 1 | 0.052 | 0.00 | 0.11 | 0.69 | 0.82 | 9 |
| LLD119 | 147 | 148 | 1 | 0.067 | 0.01 | 0.15 | 0.35 | 0.56 | 9 |
| LLD119 | 148 | 149 | 1 | 0.045 | 0.04 | 0.13 | 0.73 | 1.00 | 9 |
| LLD119 | 149 | 150 | 1 | 0.037 | 0.02 | 0.25 | 0.96 | 1.27 | 9 |
| LLD119 | 150 | 151 | 1 | 0.027 | 0.01 | 0.11 | 0.35 | 0.49 | 9 |
| LLD119 | 151 | 152 | 1 | 0.043 | 0.04 | 0.12 | 1.20 | 1.47 | 9 |
| LLD121 | 236.2 | 237.2 | 6 | 0.108 | 0.04 | 0.27 | 1.58 | 2.11 | 9 |
| LLD121 | 237.2 | 238.2 | 21 | 0.085 | 0.29 | 2.36 | 10.00 | 13.61 | 9 |
| LLD121 | 238.2 | 239.2 | 83 | 0.448 | 0.40 | 4.24 | 10.30 | 17.53 | 9 |
| LLD121 | 239.2 | 240.2 | 31 | 0.295 | 0.13 | 0.03 | 0.11 | 1.34 | 9 |
| LLD121 | 240.2 | 241.2 | 48 | 0.327 | 0.13 | 0.26 | 0.31 | 2.17 | 9 |
| LLD126 | 348.2 | 349.2 | 8 | 0.106 | 0.08 | 2.55 | 3.80 | 6.55 | 9 |
| LLD126 | 349.2 | 350.2 | 140 | 0.678 | 0.23 | 2.26 | 4.88 | 11.19 | 9 |
| LLD126 | 350.2 | 351.2 | 317 | 1.05 | 0.49 | 2.53 | 6.44 | 18.30 | 9 |
| LLD126 | 351.2 | 352.2 | 211 | 0.574 | 0.69 | 7.68 | 16.50 | 30.99 | 9 |
| LLD126 | 352.2 | 353.2 | 13 | 0.296 | 0.03 | 0.29 | 0.63 | 1.33 | 9 |
| LLD126 | 353.2 | 354.2 | 7 | 0.266 | 0.01 | 0.30 | 0.72 | 1.20 | 9 |
| LLD126 | 354.2 | 355.2 | 12 | 0.193 | 0.26 | 2.48 | 4.36 | 7.77 | 9 |
| LLD126 | 355.2 | 356.2 | 8 | 0.078 | 0.33 | 2.63 | 4.50 | 8.16 | 9 |
| LLD126 | 356.2 | 357.2 | 7 | 0.078 | 0.13 | 1.10 | 3.26 | 4.85 | 9 |
| LLD126 | 357.2 | 358.2 | 4 | 0.073 | 0.04 | 0.77 | 2.08 | 2.99 | 9 |
| LLD128 | 297.65 | 298.85 | 4 | 0.81 | 0.18 | 0.08 | 1.66 | 2.46 | 9 |
| LLD128 | 298.85 | 299.85 | 3 | 0.11 | 0.04 | 0.73 | 1.32 | 2.20 | 9 |
| LLD128 | 299.85 | 300.85 | 3 | 0.36 | 0.08 | 0.31 | 1.58 | 2.20 | 9 |
| LLD128 | 300.85 | 301.85 | 3 | 0.11 | 0.04 | 0.18 | 0.64 | 1.01 | 9 |
| LLD128 | 301.85 | 302.85 | 3 | 0.13 | 0.13 | 0.56 | 3.29 | 4.29 | 9 |
| LLD128 | 302.85 | 303.85 | 4 | 0.04 | 0.07 | 0.33 | 3.14 | 3.76 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD128 | 303.85 | 304.85 | 3 | 0.06 | 0.04 | 0.27 | 1.04 | 1.50 | 9 |
| LLD128 | 304.85 | 305.85 | 1 | 0.06 | 0.03 | 0.28 | 0.68 | 1.05 | 9 |
| LLD128 | 305.85 | 306.85 | 2 | 0.4 | 0.13 | 0.61 | 1.37 | 2.40 | 9 |
| LLD128 | 306.85 | 307.85 | 4 | 0.32 | 0.88 | 4.72 | 9.21 | 16.48 | 9 |
| LLD128 | 307.85 | 308.85 | 9 | 0.46 | 0.95 | 5.86 | 10.30 | 18.96 | 9 |
| LLD128 | 308.85 | 309.85 | 12 | 1.01 | 1.08 | 0.89 | 5.74 | 10.46 | 9 |
| LLD128 | 309.85 | 310.6 | 4 | 0.54 | 0.29 | 0.58 | 5.86 | 7.47 | 9 |
| LLD128 | 310.6 | 311.6 | 5 | 0.18 | 0.12 | 0.27 | 2.46 | 3.22 | 9 |
| LLD128 | 311.6 | 312.72 | 3 | 0.13 | 0.11 | 0.70 | 2.54 | 3.61 | 9 |
| LLD128 | 312.72 | 313.2 | 3 | 0.14 | 0.12 | 1.56 | 5.90 | 7.78 | 9 |
| LLD129 | 217.65 | 218.45 | 19 | 2.26 | 0.40 | 4.85 | 11.30 | 17.58 | 9 |
| LLD129 | 218.45 | 219 | 54 | 1.3 | 0.11 | 0.04 | 0.67 | 2.47 | 9 |
| LLD129 | 219 | 220 | 15 | 0.93 | 0.36 | 0.10 | 3.73 | 5.44 | 9 |
| LLD129 | 220 | 221 | 70 | 0.58 | 0.73 | 0.30 | 5.97 | 10.43 | 9 |
| LLD129 | 221 | 222 | 19 | 0.23 | 0.36 | 0.93 | 6.21 | 8.72 | 9 |
| LLD129 | 222 | 223 | 5 | 0.08 | 0.37 | 0.32 | 0.95 | 2.59 | 9 |
| LLD129 | 223 | 224 | 5 | 0.06 | 0.14 | 0.49 | 1.65 | 2.70 | 9 |
| LLD129 | 224 | 225 | 7 | 0.03 | 0.12 | 0.97 | 2.05 | 3.49 | 9 |
| LLD129 | 225 | 226 | 8 | 0.06 | 0.41 | 3.30 | 5.64 | 10.16 | 9 |
| LLD129 | 226 | 226.7 | 4 | 0.02 | 0.05 | 1.26 | 1.72 | 3.12 | 9 |
| LLD129 | 226.7 | 227.2 | 8 | 0.07 | 0.30 | 0.98 | 5.39 | 7.46 | 9 |
| LLD129 | 227.2 | 228.2 | 9 | 0.09 | 0.77 | 0.31 | 9.94 | 12.99 | 9 |
| LLD129 | 228.2 | 228.8 | 12 | 0.1 | 0.27 | 2.78 | 5.58 | 9.29 | 9 |
| LLD129 | 228.8 | 229.4 | 9 | 0.13 | 0.32 | 4.24 | 7.68 | 12.77 | 9 |
| LLD129 | 229.4 | 230.4 | 4 | 0.06 | 0.07 | 1.02 | 2.30 | 3.56 | 9 |
| LLD129 | 230.4 | 231.4 | 2 | 0.04 | 0.06 | 0.10 | 2.01 | 2.34 | 9 |
| LLD129 | 231.4 | 232 | 5 | 0.11 | 0.59 | 0.92 | 5.57 | 8.47 | 9 |
| LLD129 | 232 | 233.2 | 3 | 0.11 | 0.07 | 0.03 | 1.02 | 1.35 | 9 |
| LLD130 | 145.45 | 146.2 | 25 | 0.63 | 0.06 | 0.40 | 4.50 | 5.73 | 9 |
| LLD130 | 146.2 | 147 | 9 | 0.1 | 0.01 | 0.03 | 0.11 | 0.39 | 9 |
| LLD130 | 147 | 148 | 11 | 0.09 | 0.02 | 0.06 | 0.23 | 0.62 | 9 |
| LLD130 | 148 | 149 | 15 | 0.09 | 0.03 | 0.09 | 0.89 | 1.46 | 9 |
| LLD130 | 149 | 150 | 16 | 0.26 | 0.06 | 0.10 | 4.20 | 4.92 | 9 |
| LLD130 | 150 | 151.1 | 107 | 1.09 | 0.41 | 3.25 | 8.25 | 15.24 | 9 |
| LLD130 | 151.1 | 153 | | | | | | 0.00 | 9 |
| LLD130 | 153 | 154 | 2 | 0.005 | 0.06 | 0.02 | 0.31 | 0.59 | 9 |
| LLD130 | 154 | 154.5 | 2 | 0.01 | 0.01 | 0.01 | 0.33 | 0.43 | 9 |
| LLD130 | 154.5 | 155.5 | 2 | 0.005 | 0.03 | 0.00 | 0.46 | 0.61 | 9 |
| LLD130 | 155.5 | 156 | 1 | 0.01 | 0.01 | 0.00 | 0.05 | 0.09 | 9 |
| LLD130 | 156 | 157 | 1 | 0.03 | 0.02 | 0.01 | 0.14 | 0.26 | 9 |
| LLD130 | 157 | 158 | 1 | 0.02 | 0.00 | 0.00 | 0.02 | 0.06 | 9 |
| LLD130 | 158 | 159 | 1 | 0.02 | 0.01 | 0.02 | 0.05 | 0.14 | 9 |
| LLD130 | 159 | 159.55 | 3 | 0.09 | 0.07 | 0.21 | 0.41 | 0.91 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD130 | 159.55 | 160.55 | 69 | 0.41 | 0.62 | 5.30 | 10.70 | 19.26 | 9 |
| LLD130 | 160.55 | 161.55 | 25 | 0.47 | 0.38 | 3.90 | 5.31 | 10.71 | 9 |
| LLD130 | 161.55 | 162.15 | 7 | 0.54 | 0.55 | 6.10 | 12.00 | 19.50 | 9 |
| LLD130 | 162.15 | 162.65 | 14 | 0.12 | 0.19 | 2.79 | 4.21 | 7.70 | 9 |
| LLD130 | 162.65 | 163.35 | 24 | 0.12 | 0.20 | 3.30 | 5.14 | 9.37 | 9 |
| LLD130 | 163.35 | 164.35 | 17 | 0.16 | 0.07 | 0.30 | 2.61 | 3.55 | 9 |
| LLD130 | 164.35 | 165 | 10 | 0.1 | 0.03 | 0.36 | 2.26 | 2.93 | 9 |
| LLD136 | 78 | 81 | 1 | 0.005 | 0.01 | 0.01 | 0.66 | 0.73 | 9 |
| LLD136 | 81 | 84 | 4 | 0.02 | 0.01 | 0.10 | 0.98 | 1.19 | 9 |
| LLD136 | 84 | 87 | 6 | 0.02 | 0.02 | 0.29 | 1.44 | 1.93 | 9 |
| LLD137 | 173 | 174 | 4 | 0.04 | 0.12 | 0.51 | 2.88 | 3.85 | 9 |
| LLD137 | 174 | 175 | 1 | 0.02 | 0.05 | 0.07 | 1.44 | 1.68 | 9 |
| LLD137 | 175 | 176 | 3 | 0.06 | 0.09 | 0.14 | 3.28 | 3.78 | 9 |
| LLD137 | 176 | 177 | 1 | 0.005 | 0.05 | 0.29 | 1.68 | 2.13 | 9 |
| LLD137 | 177 | 178 | 5 | 0.01 | 1.67 | 0.02 | 0.36 | 6.01 | 9 |
| LLD137 | 178 | 179 | | | | | | 0.00 | 9 |
| LLD137 | 179 | 180 | 1 | 0.005 | 0.03 | 0.00 | 0.05 | 0.18 | 9 |
| LLD137 | 180 | 182 | | | | | | 0.00 | 9 |
| LLD137 | 182 | 183 | 8 | 0.06 | 4.43 | 0.06 | 2.40 | 17.28 | 9 |
| LLD137 | 183 | 184 | 6 | 0.04 | 3.25 | 0.04 | 0.79 | 11.70 | 9 |
| LLD137 | 184 | 185 | 1 | 0.02 | 0.22 | 0.01 | 0.29 | 1.07 | 9 |
| LLRC090 | 22.65 | 23 | 6 | 11.9 | 0.50 | 6.27 | 0.13 | 8.18 | 9 |
| LLRC090 | 23 | 24 | 6 | 0.5 | 0.04 | 4.12 | 0.20 | 4.22 | 9 |
| LLRC090 | 24 | 25 | 16 | 1.29 | 0.65 | 6.88 | 0.32 | 9.11 | 9 |
| LLRC090 | 25 | 26 | 7 | 0.81 | 0.39 | 1.58 | 0.14 | 3.07 | 9 |
| LLRC090 | 26 | 27 | 6 | 0.23 | 0.15 | 0.47 | 0.08 | 1.17 | 9 |
| LLRC091 | 61 | 62 | 13 | 0.2 | 0.87 | 0.02 | 0.75 | 3.97 | 9 |
| LLRC091 | 62 | 63 | 14 | 0.94 | 1.76 | 0.03 | 0.71 | 6.94 | 9 |
| LLRC091 | 63 | 64 | 4 | 0.28 | 0.42 | 0.02 | 0.17 | 1.69 | 9 |
| LLRC091 | 64 | 65 | 3 | 0.03 | 0.12 | 0.02 | 0.39 | 0.88 | 9 |
| LLRC091 | 65 | 66 | 4 | 0.07 | 0.48 | 0.03 | 0.57 | 2.29 | 9 |
| LLRC091 | 66 | 67 | 6 | 0.1 | 0.32 | 0.02 | 0.87 | 2.09 | 9 |
| LLRC091 | 67 | 68 | 8 | 0.21 | 0.95 | 0.01 | 0.17 | 3.51 | 9 |
| LLRC092 | 63 | 64 | 3 | 0.08 | 0.06 | 0.05 | 3.17 | 3.49 | 9 |
| LLRC092 | 64 | 65 | 2 | 0.05 | 0.04 | 0.02 | 1.14 | 1.33 | 9 |
| LLRC092 | 65 | 66 | 3 | 0.06 | 0.08 | 0.04 | 0.91 | 1.28 | 9 |
| LLRC092 | 66 | 67 | 2 | 0.03 | 0.02 | 0.03 | 0.57 | 0.72 | 9 |
| LLRC092 | 67 | 68 | 2 | 0.02 | 0.05 | 0.01 | 0.99 | 1.22 | 9 |
| LLRC092 | 68 | 69 | 4 | 0.04 | 0.52 | 0.02 | 1.22 | 3.06 | 9 |
| LLRC093 | 59.48 | 60 | 1 | 0.08 | 0.08 | 0.09 | 0.08 | 0.47 | 9 |
| LLRC093 | 60 | 61 | 1 | 0.1 | 0.12 | 0.19 | 0.11 | 0.71 | 9 |
| LLRC093 | 61 | 62 | 1 | 0.55 | 0.11 | 0.28 | 0.14 | 0.82 | 9 |
| LLRC093 | 62 | 63 | 10 | 0.26 | 0.86 | 0.23 | 0.15 | 3.46 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|-------|-------|------|--------|------------|
| LLRC093 | 63 | 64 | 2 | 0.11 | 0.24 | 0.08 | 0.25 | 1.17 | 9 |
| LLRC093 | 64 | 64.13 | 1 | 0.05 | 0.02 | 0.06 | 0.26 | 0.41 | 9 |
| LLRC094 | 59.62 | 60 | 5 | 0.07 | 0.23 | 0.04 | 3.93 | 4.85 | 9 |
| LLRC094 | 60 | 61 | 13 | 0.12 | 0.32 | 0.06 | 8.08 | 9.51 | 9 |
| LLRC094 | 61 | 62 | 2 | 0.03 | 0.03 | 0.25 | 1.26 | 1.62 | 9 |
| LLRC094 | 62 | 63 | 1 | 0.02 | 0.01 | 0.13 | 0.40 | 0.57 | 9 |
| LLRC094 | 63 | 64 | 2 | 0.02 | 0.02 | 0.12 | 0.71 | 0.94 | 9 |
| LLRC094 | 64 | 65 | 1 | 0.03 | 0.04 | 0.05 | 0.86 | 1.06 | 9 |
| LLRC094 | 65 | 66 | 1 | 0.01 | 0.01 | 0.05 | 0.43 | 0.54 | 9 |
| LLRC094 | 66 | 67 | 1 | 0.005 | 0.01 | 0.01 | 0.35 | 0.41 | 9 |
| LLRC094 | 67 | 68 | 2 | 0.005 | 0.02 | 0.01 | 0.78 | 0.92 | 9 |
| LLRC094 | 68 | 69 | 1 | 0.01 | 0.12 | 0.01 | 0.71 | 1.12 | 9 |
| LLRC094 | 69 | 69.79 | 1 | 0.005 | 0.05 | 0.00 | 0.62 | 0.80 | 9 |
| LRC024 | 12 | 13 | 2 | 0.45 | 0.07 | 0.90 | 0.07 | 1.19 | 9 |
| LRC024 | 13 | 14 | 3 | 0.4 | 0.07 | 0.70 | 0.08 | 1.03 | 9 |
| LRC024 | 14 | 15 | 5 | 0.25 | 0.08 | 2.00 | 0.11 | 2.32 | 9 |
| LRC024 | 15 | 16 | 6 | 0.5 | 0.06 | 1.41 | 0.06 | 1.69 | 9 |
| LRC024 | 16 | 17 | 4 | 0.7 | 0.08 | 1.42 | 0.26 | 1.94 | 9 |
| LRC024 | 17 | 18 | 4 | 3.2 | 0.21 | 1.41 | 0.17 | 2.39 | 9 |
| LRC024 | 18 | 19 | 5 | 2.7 | 0.24 | 2.34 | 0.29 | 3.45 | 9 |
| LRC025 | 42 | 43 | 8 | 0.8 | 0.50 | 3.62 | 0.30 | 5.45 | 9 |
| LRC025 | 43 | 44 | 236 | 1.55 | 26.40 | 15.60 | 0.48 | 107.62 | 9 |
| LRC025 | 44 | 45 | 21 | 0.55 | 0.44 | 5.10 | 0.11 | 6.71 | 9 |
| LRC025 | 45 | 46 | 7 | 0.3 | 0.10 | 1.53 | 0.04 | 1.93 | 9 |
| LRC041 | 30 | 31 | 5 | 0.35 | 0.20 | 0.11 | 0.23 | 1.12 | 9 |
| LRC041 | 31 | 32 | 11 | 0.6 | 0.20 | 0.12 | 0.24 | 1.31 | 9 |
| LRC041 | 32 | 33 | 6 | 0.35 | 0.15 | 0.06 | 0.23 | 0.92 | 9 |
| LRC041 | 33 | 34 | 8 | 0.3 | 0.12 | 0.06 | 0.14 | 0.80 | 9 |
| LRC041 | 34 | 35 | 10 | 0.65 | 0.20 | 0.11 | 0.22 | 1.26 | 9 |
| LRC041 | 35 | 36 | 7 | 0.25 | 1.40 | 0.10 | 0.08 | 4.98 | 9 |
| LRC043 | 47 | 48 | 8 | 0.25 | 0.20 | 0.03 | 0.06 | 0.95 | 9 |
| LRC043 | 48 | 49 | 8 | 0.3 | 0.19 | 0.07 | 0.07 | 0.98 | 9 |
| LRC043 | 49 | 50 | 6 | 0.2 | 0.04 | 0.04 | 0.12 | 0.45 | 9 |
| LRC043 | 50 | 51 | 14 | 0.2 | 0.05 | 0.05 | 0.10 | 0.65 | 9 |
| LRC043 | 51 | 52 | 29 | 0.7 | 0.07 | 0.06 | 0.10 | 1.13 | 9 |
| LRC043 | 52 | 53 | 35 | 0.1 | 0.05 | 0.04 | 0.08 | 1.15 | 9 |
| LRC043 | 53 | 54 | 56 | 0.1 | 0.06 | 0.04 | 0.12 | 1.74 | 9 |
| LRC043 | 54 | 55 | 22 | 0.1 | 0.06 | 0.06 | 0.12 | 0.94 | 9 |
| LRC043 | 55 | 56 | 13 | 0.05 | 0.05 | 0.10 | 0.12 | 0.70 | 9 |
| LRC043 | 56 | 57 | 114 | 0.1 | 0.06 | 0.14 | 0.14 | 3.31 | 9 |
| LRC043 | 57 | 58 | 51 | 0.15 | 0.04 | 0.11 | 0.10 | 1.60 | 9 |
| LRC043 | 58 | 59 | 20 | 0.15 | 0.03 | 0.10 | 0.14 | 0.83 | 9 |
| LRC043 | 59 | 60 | 12 | 0.15 | 0.10 | 0.03 | 0.10 | 0.75 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|-------|--------|------------|
| LRC047 | 50 | 51 | 19 | 0.3 | 0.36 | 0.76 | 0.48 | 2.84 | 9 |
| LRC047 | 51 | 52 | 13 | 0.2 | 0.29 | 0.52 | 2.25 | 4.01 | 9 |
| LRC047 | 52 | 53 | 4 | 0.15 | 1.13 | 1.81 | 6.00 | 11.47 | 9 |
| LRC047 | 53 | 54 | 5 | 0.15 | 0.90 | 1.58 | 2.20 | 6.72 | 9 |
| LRC047 | 54 | 55 | 4 | 0.15 | 0.62 | 1.07 | 1.45 | 4.57 | 9 |
| LRC047 | 55 | 56 | 2 | 0.15 | 0.28 | 0.29 | 0.29 | 1.53 | 9 |
| LRC047 | 56 | 57 | 4 | 0.15 | 0.20 | 0.35 | 0.32 | 1.40 | 9 |
| LRC047 | 57 | 58 | 3 | 0.2 | 0.41 | 0.57 | 0.24 | 2.19 | 9 |
| LTD0001 | 41.06 | 42 | 1.2 | 0.02 | 0.11 | 0.05 | 0.08 | 0.51 | 9 |
| LTD0001 | 42 | 43 | 2.5 | 0.04 | 0.50 | 0.12 | 0.20 | 2.03 | 9 |
| LTD0001 | 43 | 44 | 2.6 | 0.03 | 0.20 | 0.19 | 0.02 | 0.90 | 9 |
| LTD0001 | 44 | 45 | 1.5 | 0.01 | 0.38 | 0.07 | 0.02 | 1.36 | 9 |
| LTD0001 | 45 | 46 | 3 | 0.01 | 0.47 | 0.08 | 0.05 | 1.76 | 9 |
| LTD0001 | 46 | 47 | 0.7 | -0.01 | 0.05 | 0.03 | 0.27 | 0.48 | 9 |
| LTD0001 | 47 | 48 | 0.6 | 0.01 | 0.01 | 0.03 | 0.43 | 0.49 | 9 |
| LTD0001 | 48 | 48.64 | 1.6 | 0.01 | 0.09 | 0.02 | 0.47 | 0.82 | 9 |
| LTD0002 | 84 | 85 | 4.6 | 0.04 | 0.07 | 0.23 | 3.80 | 4.36 | 9 |
| LTD0002 | 85 | 86 | 9.4 | 0.03 | 0.30 | 0.92 | 10.05 | 12.10 | 9 |
| LTD0002 | 86 | 87 | 4.9 | 0.03 | 0.14 | 0.45 | 15.85 | 16.86 | 9 |
| LTD0002 | 87 | 88 | 1.4 | 0.02 | 0.06 | 0.39 | 18.60 | 19.18 | 9 |
| LTD0002 | 88 | 89 | 95.3 | 0.44 | 0.59 | 2.86 | 19.45 | 26.38 | 9 |
| LTD0002 | 89 | 90 | 4 | 0.01 | 0.04 | 0.44 | 0.89 | 1.52 | 9 |
| LTD0002 | 90 | 91 | 4.2 | 0.01 | 0.08 | 0.32 | 0.46 | 1.12 | 9 |
| LTD0002 | 91 | 92 | 6.9 | -0.01 | 0.21 | 0.58 | 0.26 | 1.64 | 9 |
| LTD0002 | 92 | 93 | 7.4 | -0.01 | 0.42 | 0.48 | 0.35 | 2.34 | 9 |
| LTD0002 | 93 | 94 | 13.2 | 0.04 | 0.55 | 0.91 | 1.91 | 4.88 | 9 |
| LTD0002 | 94 | 95 | 2 | -0.01 | 0.07 | 0.74 | 0.94 | 1.89 | 9 |
| LTD0002 | 95 | 96 | 1.4 | 0.04 | 0.02 | 0.67 | 0.61 | 1.32 | 9 |
| LTD0002 | 96 | 97 | 1.4 | -0.01 | 0.02 | 0.31 | 1.34 | 1.73 | 9 |
| LTD0002 | 97 | 98 | 5.6 | 0.01 | 0.07 | 1.16 | 3.17 | 4.59 | 9 |
| LTD0002 | 98 | 99 | 1.5 | -0.01 | 0.02 | 0.21 | 0.53 | 0.82 | 9 |
| LTD0002 | 99 | 102 | 27.8 | 0.14 | 0.37 | 4.06 | 25.90 | 31.47 | 9 |
| LTD0002 | 102 | 105 | 16.6 | 0.26 | 0.42 | 3.80 | 27.20 | 32.42 | 9 |
| LTD0002 | 105 | 108 | 5.9 | 0.01 | 0.19 | 0.85 | 7.58 | 9.12 | 9 |
| LTD0002 | 108 | 111 | 2.5 | 0.01 | 0.04 | 0.32 | 1.18 | 1.66 | 9 |
| LTD0003 | 91 | 92 | 1.3 | 0.1 | 0.07 | 0.10 | 4.40 | 4.76 | 9 |
| LTD0003 | 92 | 93 | 1 | 0.13 | 0.11 | 0.18 | 5.49 | 6.05 | 9 |
| LTD0003 | 93 | 94 | 0.9 | 0.08 | 0.18 | 0.79 | 13.30 | 14.63 | 9 |
| LTD0003 | 94 | 95 | 8.7 | 0.19 | 0.14 | 4.76 | 16.40 | 21.37 | 9 |
| LTD0003 | 95 | 96 | 20.7 | 0.21 | 0.11 | 3.83 | 10.90 | 15.23 | 9 |
| LTD0003 | 96 | 97 | 17.3 | 0.12 | 0.21 | 1.31 | 12.75 | 15.05 | 9 |
| LTD0003 | 97 | 98 | 8.4 | 0.08 | 0.17 | 1.91 | 23.00 | 25.48 | 9 |
| LTD0003 | 98 | 99 | 14.5 | 0.08 | 0.20 | 3.93 | 13.90 | 18.46 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|-------|-------|--------|------------|
| LTD0003 | 99 | 99.5 | 5.2 | 0.05 | 0.15 | 0.77 | 2.26 | 3.56 | 9 |
| LTD0003 | 99.5 | 100 | 5.9 | 0.08 | 0.09 | 2.96 | 5.13 | 8.25 | 9 |
| LTD0003 | 100 | 101 | 8.8 | 0.06 | 0.13 | 0.89 | 2.57 | 4.04 | 9 |
| LTD0003 | 101 | 102 | 6.1 | 0.07 | 0.03 | 0.69 | 2.27 | 3.16 | 9 |
| LTD0003 | 102 | 103 | 3.8 | 0.06 | 0.03 | 0.35 | 2.18 | 2.68 | 9 |
| LTD0003 | 103 | 104 | 3.3 | 0.04 | 0.05 | 0.20 | 3.34 | 3.76 | 9 |
| LTD0003 | 104 | 105 | 3.6 | 0.06 | 0.03 | 0.10 | 2.02 | 2.30 | 9 |
| LTD0003 | 105 | 106 | 2.2 | 0.04 | 0.03 | 0.17 | 1.50 | 1.82 | 9 |
| LTD0003 | 106 | 107 | 1.5 | 0.03 | 0.03 | 0.15 | 1.54 | 1.80 | 9 |
| LTD0003 | 107 | 108 | 1.8 | 0.04 | 0.03 | 0.12 | 2.11 | 2.37 | 9 |
| LTD0003 | 108 | 109 | 0.7 | 0.04 | 0.01 | 0.01 | 1.14 | 1.19 | 9 |
| LTD0003 | 109 | 109.5 | 2.2 | 0.02 | 0.01 | 0.08 | 3.00 | 3.15 | 9 |
| LTD0003 | 109.5 | 111 | 4 | 0.04 | 0.04 | 0.08 | 12.55 | 12.84 | 9 |
| LTD0003 | 111 | 111.5 | 3 | 0.02 | 0.09 | 0.03 | 4.32 | 4.72 | 9 |
| LTD0003 | 111.5 | 112 | 0.9 | -0.01 | 0.00 | 0.02 | 0.69 | 0.74 | 9 |
| LTD0003 | 112 | 113 | 2.1 | 0.02 | 0.02 | 0.04 | 4.27 | 4.44 | 9 |
| LTD0003 | 113 | 114 | 5.5 | 0.07 | 0.21 | 0.26 | 1.33 | 2.38 | 9 |
| LTD0003 | 114 | 115 | 5.7 | 0.09 | 0.19 | 0.14 | 0.28 | 1.18 | 9 |
| LTD0003 | 115 | 115.4 | 2.3 | 0.03 | 0.05 | 0.05 | 0.11 | 0.39 | 9 |
| LTD0003 | 115.4 | 115.8 | 11.5 | 0.06 | 0.27 | 0.95 | 0.57 | 2.61 | 9 |
| LTD0003 | 115.8 | 116.2 | 6.3 | 0.04 | 0.27 | 0.14 | 0.54 | 1.71 | 9 |
| LTD0003 | 116.2 | 117 | 3.4 | 0.04 | 0.46 | 0.04 | 2.24 | 3.89 | 9 |
| LTD0003 | 117 | 117.5 | 7.6 | 0.04 | 0.96 | 0.77 | 5.00 | 9.03 | 9 |
| LTD0003 | 117.5 | 118 | 33 | 0.14 | 3.94 | 1.80 | 16.65 | 32.10 | 9 |
| LTD0006 | 38.7 | 40 | 2.2 | 0.24 | 0.08 | 0.10 | 0.05 | 0.46 | 9 |
| LTD0006 | 40 | 44 | 3.3 | 0.05 | 0.06 | 0.03 | 0.05 | 0.35 | 9 |
| LTD0006 | 44 | 44.8 | 4.3 | 0.05 | 0.09 | 0.06 | 0.10 | 0.58 | 9 |
| LTD0007 | 137 | 138 | 2.8 | 0.05 | 0.02 | 0.10 | 1.14 | 1.37 | 9 |
| LTD0007 | 138 | 138.9 | 11.6 | 0.14 | 0.12 | 0.71 | 3.42 | 4.75 | 9 |
| LTD0007 | 138.9 | 139.5 | 77.2 | 0.2 | 0.18 | 2.28 | 3.73 | 8.30 | 9 |
| LTD0007 | 139.5 | 139.9 | 71.8 | 0.66 | 0.25 | 3.51 | 6.36 | 12.16 | 9 |
| LTD0007 | 139.9 | 140.7 | 147 | 1.48 | 0.64 | 5.89 | 11.00 | 22.15 | 9 |
| LTD0007 | 140.7 | 141.5 | 48.2 | 0.36 | 0.16 | 2.82 | 6.46 | 10.75 | 9 |
| LTD0007 | 141.5 | 142 | 34.4 | 0.33 | 0.17 | 0.89 | 2.47 | 4.70 | 9 |
| LTD0007 | 142 | 143 | 16.5 | 0.68 | 0.04 | 0.14 | 0.45 | 1.14 | 9 |
| LTD0007 | 143 | 144 | 15.7 | 0.08 | 0.05 | 0.19 | 0.52 | 1.25 | 9 |
| LTD0007 | 144 | 145 | 7 | 0.05 | 0.10 | 0.63 | 1.66 | 2.74 | 9 |
| LTD0007 | 145 | 146 | 32.1 | 0.11 | 0.55 | 4.64 | 8.35 | 15.15 | 9 |
| LTD0007 | 146 | 146.5 | 65.8 | 0.15 | 0.80 | 11.25 | 20.50 | 34.90 | 9 |
| LTD0007 | 146.5 | 147.5 | 25.4 | 0.06 | 0.12 | 5.34 | 5.54 | 11.38 | 9 |
| LTD0007 | 147.5 | 148 | | 0.1 | 0.22 | 5.90 | 9.78 | 15.82 | 9 |
| LTD0007 | 148 | 149 | 7.8 | 0.03 | 0.21 | 2.52 | 3.87 | 7.02 | 9 |
| LTD0007 | 149 | 150 | 10.5 | 0.05 | 0.38 | 3.78 | 6.16 | 11.09 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LTD0007 | 150 | 151 | 10.1 | 0.08 | 0.25 | 5.12 | 6.30 | 11.99 | 9 |
| LTD0007 | 151 | 152 | 7.7 | 0.05 | 0.15 | 0.77 | 5.73 | 7.10 | 9 |
| LTD0007 | 152 | 153 | 4.7 | 0.05 | 0.12 | 0.58 | 3.98 | 5.01 | 9 |
| LTD0007 | 153 | 154 | 1.5 | 0.05 | 0.03 | 0.10 | 1.19 | 1.42 | 9 |
| LTD0007 | 154 | 155 | 4.7 | 0.03 | 0.02 | 0.23 | 2.51 | 2.91 | 9 |
| LTD0007 | 155 | 156 | 3.7 | 0.03 | 0.05 | 0.16 | 2.28 | 2.68 | 9 |
| LTD0007 | 156 | 157 | 5 | 0.04 | 0.09 | 0.35 | 1.99 | 2.72 | 9 |
| LTD0007 | 157 | 157.6 | 5.8 | 0.04 | 0.14 | 0.36 | 2.09 | 3.01 | 9 |
| LTD0007 | 157.6 | 158.6 | 18.9 | 0.08 | 2.88 | 1.63 | 4.78 | 16.23 | 9 |
| LTD0007 | 158.6 | 159 | 1.1 | 0.01 | 0.02 | 0.21 | 0.29 | 0.57 | 9 |
| LTD0007 | 159 | 160 | 0.5 | 0.01 | 0.01 | 0.09 | 0.30 | 0.42 | 9 |
| LTD0007 | 160 | 161 | 1.8 | 0.02 | 0.02 | 0.30 | 1.62 | 2.01 | 9 |
| LTD0007 | 161 | 162 | 1.4 | 0.03 | 0.01 | 0.26 | 1.12 | 1.41 | 9 |
| LTD0008 | 108.5 | 109.1 | 1.4 | -0.01 | 0.03 | 0.08 | 0.93 | 1.13 | 9 |
| LTD0008 | 109.1 | 110 | 23.3 | 0.23 | 0.86 | 1.46 | 15.35 | 20.08 | 9 |
| LTD0008 | 110 | 111 | 15.8 | 0.23 | 0.21 | 0.96 | 11.40 | 13.35 | 9 |
| LTD0008 | 111 | 112 | 0.8 | 0.02 | 0.00 | 0.08 | 0.21 | 0.31 | 9 |
| LTD0008 | 112 | 113 | 2.1 | 0.04 | 0.03 | 0.30 | 2.00 | 2.43 | 9 |
| LTD0008 | 113 | 114 | 2.1 | 0.04 | 0.04 | 0.31 | 1.79 | 2.27 | 9 |
| LTD0008 | 114 | 115 | 6 | 0.06 | 0.24 | 0.24 | 2.51 | 3.68 | 9 |
| LTD0009 | 225.43 | 226 | 4 | 0.14 | 0.09 | 0.36 | 0.58 | 1.31 | 9 |
| LTD0009 | 226 | 227 | 4 | 0.16 | 0.08 | 0.39 | 1.05 | 1.77 | 9 |
| LTD0009 | 227 | 228 | 38.4 | 0.5 | 0.62 | 3.87 | 7.10 | 13.62 | 9 |
| LTD0009 | 228 | 229 | 12.2 | 0.19 | 0.51 | 2.68 | 4.91 | 9.33 | 9 |
| LTD0009 | 229 | 230 | 13.6 | 0.16 | 0.21 | 1.90 | 2.22 | 4.98 | 9 |
| LTD0009 | 230 | 231 | 33.9 | 0.11 | 0.61 | 3.65 | 5.73 | 11.89 | 9 |
| LTD0009 | 231 | 232 | 28 | 0.17 | 0.71 | 2.81 | 17.40 | 22.97 | 9 |
| LTD0009 | 232 | 233 | 17.4 | 0.1 | 0.62 | 0.84 | 5.37 | 8.62 | 9 |
| LTD0009 | 233 | 234 | 60.3 | 0.37 | 0.98 | 4.57 | 17.60 | 26.48 | 9 |
| LTD0009 | 234 | 235 | 1.7 | 0.09 | 0.01 | 0.12 | 0.42 | 0.61 | 9 |
| LTD0009 | 235 | 236 | 4.2 | 0.07 | 0.05 | 0.22 | 1.06 | 1.55 | 9 |
| LTD0009 | 236 | 237 | 16.6 | 0.06 | 0.37 | 1.96 | 10.65 | 14.06 | 9 |
| LTD0009 | 237 | 238 | 16.3 | 0.05 | 0.58 | 2.13 | 5.02 | 9.27 | 9 |
| LTD0009 | 238 | 239 | 3.1 | 0.02 | 0.04 | 0.25 | 0.73 | 1.18 | 9 |
| LTD0009 | 239 | 239.2 | 4.5 | 0.06 | 0.49 | 0.08 | 2.22 | 4.01 | 9 |
| LTD0009 | 239.2 | 239.6 | 4.6 | 0.02 | 0.38 | 0.03 | 2.69 | 4.09 | 9 |
| LTD0012 | 170.71 | 171 | 0.3 | 0.02 | 0.00 | 0.01 | 0.05 | 0.07 | 9 |
| LTD0012 | 171 | 172 | 0.5 | 0.01 | 0.02 | 0.00 | 0.11 | 0.17 | 9 |
| LTD0012 | 172 | 173 | -0.2 | 0.02 | 0.00 | 0.00 | 0.04 | 0.05 | 9 |
| LTD0012 | 173 | 174.25 | 0.3 | 0.04 | 0.00 | 0.01 | 0.08 | 0.10 | 9 |
| LTD0012 | 174.25 | 175 | 1.4 | 0.44 | 0.00 | 0.01 | 0.05 | 0.13 | 9 |
| LTD0012 | 175 | 176 | 5.1 | 0.09 | 0.09 | 0.06 | 0.24 | 0.71 | 9 |
| LTD0012 | 176 | 176.38 | 1 | 0.07 | 0.03 | 0.01 | 0.06 | 0.19 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|------|--------|------------|
| LTD0013 | 242 | 243 | 2.4 | 0.03 | 0.03 | 0.18 | 0.69 | 1.01 | 9 |
| LTD0013 | 243 | 244 | 0.8 | 0.02 | 0.01 | 0.06 | 0.19 | 0.31 | 9 |
| LTD0013 | 244 | 245 | 0.8 | 0.03 | 0.05 | 0.02 | 0.19 | 0.38 | 9 |
| LTD0013 | 245 | 246 | 4.8 | 0.05 | 0.30 | 0.08 | 0.71 | 1.90 | 9 |
| LTD0014 | 315.27 | 316 | -0.2 | 0.01 | 0.00 | 0.00 | 0.00 | 0.00 | 9 |
| LTD0014 | 316 | 317 | -0.2 | -0.01 | 0.00 | 0.00 | 0.01 | 0.00 | 9 |
| LTD0014 | 317 | 318 | -0.2 | 0.01 | 0.00 | 0.00 | 0.00 | 0.00 | 9 |
| LTD0014 | 318 | 319 | -0.2 | -0.01 | 0.00 | 0.00 | 0.01 | 0.00 | 9 |
| LTD0014 | 319 | 319.7 | 0.2 | -0.01 | 0.00 | 0.00 | 0.01 | 0.02 | 9 |
| LTD0014 | 319.7 | 320 | 0.2 | 0.02 | 0.00 | 0.00 | 0.01 | 0.03 | 9 |
| LTD0014 | 320 | 320.2 | -0.2 | 0.01 | 0.01 | 0.00 | 0.01 | 0.02 | 9 |
| LTD0014 | 320.2 | 321 | 0.3 | 0.03 | 0.00 | 0.00 | 0.01 | 0.04 | 9 |
| LTD0014 | 321 | 322 | 0.4 | 0.07 | 0.00 | 0.00 | 0.01 | 0.04 | 9 |
| LTD0014 | 322 | 323 | 0.6 | 0.04 | 0.01 | 0.03 | 0.08 | 0.16 | 9 |
| LTD0014 | 323 | 323.06 | 1.8 | 0.05 | 0.07 | 0.09 | 0.76 | 1.12 | 9 |
| LTD0015 | 386.45 | 387.3 | 56.7 | 0.82 | 0.18 | 1.59 | 3.13 | 6.62 | 9 |
| LTD0015 | 387.3 | 388 | 4.3 | 0.1 | 0.01 | 0.01 | 0.02 | 0.16 | 9 |
| LTD0015 | 388 | 389 | 14.3 | 0.21 | 0.04 | 0.09 | 0.21 | 0.77 | 9 |
| LTD0015 | 389 | 390 | 6.9 | 0.06 | 0.02 | 0.12 | 0.18 | 0.54 | 9 |
| LTD0015 | 390 | 391 | 25.8 | 0.04 | 0.07 | 0.42 | 0.85 | 2.11 | 9 |
| LTD0015 | 391 | 392 | 21.5 | 0.03 | 0.05 | 0.42 | 0.62 | 1.70 | 9 |
| LTD0015 | 392 | 393 | 4.8 | 0.07 | 0.07 | 0.37 | 0.67 | 1.35 | 9 |
| LTD0015 | 393 | 394 | 2.5 | 0.06 | 0.01 | 0.08 | 0.20 | 0.38 | 9 |
| LTD0015 | 394 | 395 | 1.4 | 0.08 | 0.01 | 0.09 | 0.36 | 0.52 | 9 |
| LTD0015 | 395 | 395.4 | 3 | 0.19 | 0.03 | 0.21 | 1.21 | 1.57 | 9 |
| LTD0015 | 395.4 | 396 | 9.6 | 0.28 | 0.03 | 0.27 | 4.80 | 5.39 | 9 |
| LTD0015 | 396 | 396.5 | 15 | 0.1 | 0.26 | 2.47 | 2.06 | 5.51 | 9 |
| LTD0015 | 396.5 | 397 | 6.8 | 0.19 | 0.06 | 0.68 | 3.76 | 4.74 | 9 |
| LTD0015 | 397 | 397.5 | 6.6 | 0.14 | 0.10 | 1.35 | 3.61 | 5.34 | 9 |
| LTD0015 | 397.5 | 398 | 11.2 | 0.14 | 0.28 | 1.66 | 3.93 | 6.65 | 9 |
| LTD0015 | 398 | 399 | 7.2 | 0.1 | 0.14 | 0.97 | 2.23 | 3.75 | 9 |
| LTD0015 | 399 | 399.45 | 1.2 | 0.02 | 0.00 | 0.06 | 0.24 | 0.34 | 9 |
| LTD0016 | 428.6 | 429.6 | 3.8 | 0.19 | 0.06 | 0.42 | 2.04 | 2.73 | 9 |
| LTD0016 | 429.6 | 430.5 | 3.9 | 0.1 | 0.09 | 0.15 | 2.59 | 3.11 | 9 |
| LTD0016 | 430.5 | 431 | 3.6 | 0.07 | 0.07 | 0.24 | 2.45 | 2.98 | 9 |
| LTD0016 | 431 | 432 | 1.4 | 0.04 | 0.01 | 0.07 | 0.57 | 0.70 | 9 |
| LTD0016 | 432 | 432.9 | 1.2 | 0.02 | 0.06 | 0.11 | 0.60 | 0.92 | 9 |
| LTD0016 | 432.9 | 433.9 | 5.9 | 0.05 | 0.51 | 1.07 | 2.90 | 5.70 | 9 |
| LTD0017 | 300.89 | 301 | 26.4 | 0.62 | 0.01 | 0.06 | 0.07 | 0.86 | 9 |
| LTD0017 | 301 | 302 | 48.6 | 0.15 | 0.08 | 0.55 | 1.22 | 3.21 | 9 |
| LTD0017 | 302 | 303 | 11.7 | 0.09 | 0.03 | 0.15 | 0.33 | 0.85 | 9 |
| LTD0017 | 303 | 304 | 46.8 | 0.14 | 0.28 | 1.55 | 2.68 | 6.16 | 9 |
| LTD0017 | 304 | 304.95 | 13.5 | 0.07 | 0.04 | 0.29 | 0.64 | 1.37 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LTD0018 | 123 | 124 | 2.9 | 0.07 | 0.07 | 0.31 | 1.94 | 2.51 | 9 |
| LTD0018 | 124 | 125 | 2.7 | 0.06 | 0.03 | 0.38 | 1.44 | 1.93 | 9 |
| LTD0018 | 125 | 126 | 8.2 | 0.09 | 0.26 | 1.17 | 2.71 | 4.83 | 9 |
| LTD0018 | 126 | 127 | 3 | 0.06 | 0.04 | 0.47 | 1.53 | 2.16 | 9 |
| LTD0018 | 127 | 128 | 3.7 | 0.07 | 0.03 | 0.63 | 1.73 | 2.50 | 9 |
| LTD0018 | 128 | 129 | 12.4 | 0.11 | 0.24 | 1.82 | 7.71 | 10.44 | 9 |
| LTD0018 | 129 | 130 | 4.2 | 0.08 | 0.07 | 0.63 | 3.83 | 4.74 | 9 |
| LTD0018 | 130 | 131 | 1.1 | 0.03 | 0.01 | 0.12 | 0.45 | 0.61 | 9 |
| LTD0018 | 131 | 132 | 8 | 0.15 | 0.72 | 1.35 | 10.90 | 14.70 | 9 |
| LTD0018 | 132 | 133 | 3.4 | 0.07 | 0.09 | 0.51 | 3.45 | 4.30 | 9 |
| LTD0018 | 133 | 134 | 1.5 | 0.03 | 0.01 | 0.18 | 0.89 | 1.13 | 9 |
| LTD0018 | 134 | 135 | 2.1 | 0.05 | 0.04 | 0.40 | 2.12 | 2.65 | 9 |
| LTD0018 | 135 | 136 | 1.6 | 0.03 | 0.02 | 0.24 | 0.91 | 1.22 | 9 |
| LTD0019 | 159 | 160 | 8.1 | 0.12 | 0.31 | 1.49 | 6.01 | 8.58 | 9 |
| LTD0019 | 160 | 160.5 | 4.6 | 0.08 | 0.24 | 0.18 | 3.40 | 4.47 | 9 |
| LTD0019 | 160.5 | 161 | 5.1 | 0.13 | 0.10 | 0.31 | 3.11 | 3.85 | 9 |
| LTD0019 | 161 | 162 | 3.7 | 0.09 | 0.07 | 0.17 | 3.82 | 4.31 | 9 |
| LTD0019 | 162 | 163 | 4.4 | 0.07 | 0.07 | 0.38 | 2.54 | 3.23 | 9 |
| LTD0019 | 163 | 163.5 | 4.5 | 0.05 | 0.04 | 0.19 | 0.94 | 1.35 | 9 |
| LTD0019 | 163.5 | 164.5 | 5.9 | 0.1 | 0.08 | 0.65 | 4.69 | 5.69 | 9 |
| LTD0020 | 232 | 233 | 86.5 | 0.45 | 0.37 | 2.40 | 4.65 | 10.23 | 9 |
| LTD0020 | 233 | 234 | 90.1 | 0.3 | 0.34 | 2.57 | 4.90 | 10.61 | 9 |
| LTD0020 | 234 | 235 | 100 | 2.02 | 0.69 | 3.36 | 8.19 | 16.10 | 9 |
| LTD0020 | 235 | 236 | 71.3 | 0.62 | 0.48 | 3.87 | 8.44 | 15.31 | 9 |
| LTD0020 | 236 | 236.5 | 19.1 | 0.28 | 0.23 | 1.44 | 3.68 | 6.24 | 9 |
| LTD0021 | 377.8 | 379.1 | 19.8 | 0.09 | 0.47 | 2.33 | 8.93 | 13.09 | 9 |
| LTD0021 | 379.1 | 379.75 | 14.3 | 0.14 | 0.51 | 1.00 | 1.00 | 3.94 | 9 |
| LTD0021 | 379.75 | 380.5 | 1.5 | 0.02 | 0.01 | 0.20 | 0.79 | 1.05 | 9 |
| LTD0021 | 380.5 | 381.5 | 0.7 | 0.02 | 0.01 | 0.05 | 0.22 | 0.31 | 9 |
| LTD0021 | 381.5 | 382.5 | 1.3 | 0.02 | 0.01 | 0.13 | 0.37 | 0.56 | 9 |
| LTD0021 | 382.5 | 383 | 3.8 | 0.04 | 0.04 | 0.57 | 1.00 | 1.74 | 9 |
| LTD0021 | 383 | 383.5 | 21.3 | 0.03 | 0.12 | 0.43 | 0.86 | 2.19 | 9 |
| LTD0023 | 161.6 | 162.5 | | 0.16 | 0.14 | 1.19 | 3.22 | 4.76 | 9 |
| LTD0023 | 162.5 | 163 | | 0.5 | 0.41 | 2.50 | 6.75 | 10.38 | 9 |
| LTD0023 | 163 | 164 | | 0.95 | 0.58 | 5.36 | 18.40 | 25.19 | 9 |
| LTD0023 | 164 | 164.5 | | 10.1 | 0.75 | 5.94 | 17.30 | 25.63 | 9 |
| LTD0023 | 164.5 | 165 | | 0.35 | 0.42 | 3.26 | 9.93 | 14.27 | 9 |
| LTD0023 | 165 | 165.5 | | 0.92 | 0.43 | 2.35 | 9.90 | 13.49 | 9 |
| LTD0023 | 165.5 | 166 | | 0.15 | 0.11 | 0.61 | 6.49 | 7.41 | 9 |
| LTD0023 | 166 | 166.5 | | 0.12 | 0.13 | 0.62 | 4.77 | 5.75 | 9 |
| LTD0023 | 166.5 | 167 | | 0.07 | 0.21 | 0.44 | 3.51 | 4.60 | 9 |
| LTD0023 | 167 | 167.5 | | 0.14 | 0.10 | 0.69 | 3.93 | 4.88 | 9 |
| LTD0023 | 167.5 | 168 | | 0.07 | 0.10 | 0.36 | 2.16 | 2.82 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|--------|--------|--------|------|------|-------|--------|------------|
| LTD0023 | 168 | 168.5 | | 0.05 | 0.18 | 0.31 | 4.09 | 4.96 | 9 |
| LTD0023 | 168.5 | 169 | | 0.06 | 0.08 | 0.17 | 1.30 | 1.71 | 9 |
| LTD0023 | 169 | 169.5 | | 0.07 | 0.03 | 0.32 | 1.64 | 2.03 | 9 |
| LTD0025 | 538 | 539 | 3 | 0.1 | 0.00 | 0.14 | 1.44 | 1.66 | 9 |
| LTD0025 | 539 | 540 | 3 | 0.12 | 0.01 | 0.08 | 2.78 | 2.97 | 9 |
| LTD0025 | 540 | 541 | 5 | 0.11 | 0.02 | 0.15 | 2.11 | 2.44 | 9 |
| LTD0025 | 541 | 542 | 9 | 0.09 | 0.04 | 0.34 | 2.07 | 2.74 | 9 |
| LTD0025 | 542 | 543 | 5 | 0.04 | 0.05 | 1.02 | 2.06 | 3.28 | 9 |
| LTD0025 | 543 | 544 | 8 | 0.06 | 0.15 | 1.78 | 3.15 | 5.46 | 9 |
| LTD0025 | 544 | 545 | 2 | 0.04 | 0.00 | 0.29 | 0.30 | 0.63 | 9 |
| LTD0025 | 545 | 546 | 3 | 0.1 | 0.13 | 0.08 | 1.10 | 1.67 | 9 |
| LTD0025 | 546 | 546.5 | 3 | 0.08 | 0.11 | 0.15 | 1.55 | 2.12 | 9 |
| LTD0025 | 546.5 | 547 | 2 | 0.06 | 0.12 | 0.14 | 1.84 | 2.43 | 9 |
| LTD0025 | 547 | 548 | 5 | 0.11 | 0.56 | 0.13 | 4.63 | 6.73 | 9 |
| LTD0025 | 548 | 548.7 | 2 | 0.06 | 0.04 | 0.13 | 1.24 | 1.54 | 9 |
| LTD0025 | 548.7 | 549.22 | 3 | 0.06 | 0.03 | 0.35 | 0.93 | 1.43 | 9 |
| LTD0026 | 161 | 162 | 82 | 0.31 | 0.10 | 0.76 | 1.63 | 4.70 | 9 |
| LTD0026 | 162 | 163 | 222 | 3.36 | 0.70 | 8.25 | 13.70 | 29.15 | 9 |
| LTD0026 | 163 | 163.7 | 150 | 1.07 | 0.60 | 6.51 | 13.00 | 24.64 | 9 |
| LTD0026 | 163.7 | 164.3 | 6 | 0.05 | 0.04 | 0.18 | 0.74 | 1.19 | 9 |
| LTD0026 | 164.3 | 165 | 3 | 0.04 | 0.02 | 0.10 | 0.22 | 0.45 | 9 |
| LTD0026 | 165 | 166 | 2 | 0.04 | 0.07 | 0.03 | 0.15 | 0.47 | 9 |
| LTD0026 | 166 | 167.1 | 21 | 0.11 | 1.66 | 0.16 | 1.16 | 7.31 | 9 |
| LTD0036 | 160 | 160.8 | 25 | 0.39 | 0.15 | 0.90 | 3.78 | 5.74 | 9 |
| LTD0036 | 160.8 | 161.2 | 49 | 0.21 | 0.36 | 1.88 | 5.09 | 9.21 | 9 |
| LTD0036 | 161.2 | 161.8 | 142 | 0.63 | 0.47 | 2.81 | 5.44 | 13.09 | 9 |
| LTD0036 | 161.8 | 162.5 | 104 | 0.52 | 0.45 | 4.14 | 8.53 | 16.37 | 9 |
| LTD0036 | 162.5 | 163 | 2 | 0.04 | 0.04 | 0.07 | 0.33 | 0.56 | 9 |
| LTD0036 | 163 | 164 | 3 | 0.04 | 0.02 | 0.09 | 0.41 | 0.62 | 9 |
| LTD0036 | 164 | 165 | 3 | 4.22 | 0.13 | 0.05 | 0.14 | 0.91 | 9 |
| LTD0036 | 165 | 166 | 41 | 0.16 | 0.21 | 1.81 | 4.03 | 7.39 | 9 |
| LTD0036 | 166 | 167 | 35 | 0.22 | 0.18 | 1.99 | 4.05 | 7.33 | 9 |
| LTD0036 | 167 | 168 | 24 | 0.21 | 0.11 | 0.68 | 2.20 | 3.80 | 9 |
| LTD0036 | 168 | 169 | 7 | 0.04 | 0.07 | 0.18 | 0.60 | 1.17 | 9 |
| LTD0036 | 169 | 170 | 7 | 0.04 | 0.07 | 0.24 | 1.70 | 2.30 | 9 |
| LTD0036 | 170 | 171 | 9 | 0.08 | 0.22 | 0.29 | 2.25 | 3.47 | 9 |
| LTD0036 | 171 | 172 | 12 | 0.11 | 0.14 | 0.37 | 3.43 | 4.51 | 9 |
| LTD0036 | 172 | 173 | 13 | 0.1 | 0.25 | 0.88 | 4.77 | 6.72 | 9 |
| LTD0036 | 173 | 174 | 2 | 3.96 | 0.13 | 0.04 | 0.13 | 0.83 | 9 |
| LTD0036 | 174 | 175 | 5 | 0.05 | 0.10 | 0.23 | 2.35 | 3.00 | 9 |
| LTD0036 | 175 | 176 | 5 | 0.05 | 0.08 | 0.20 | 1.97 | 2.54 | 9 |
| LTD0036 | 176 | 177 | 4 | 0.08 | 0.06 | 0.20 | 2.42 | 2.91 | 9 |
| LTD0036 | 177 | 178 | 3 | 0.06 | 0.02 | 0.20 | 2.39 | 2.73 | 9 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|------|--------|------------|
| LTD0036 | 178 | 179 | 2 | 0.06 | 0.02 | 0.05 | 0.33 | 0.50 | 9 |
| LTD0036 | 179 | 180 | 3 | 0.07 | 0.02 | 0.09 | 0.43 | 0.65 | 9 |
| LTD0036 | 180 | 181 | 2 | 0.06 | 0.01 | 0.08 | 0.43 | 0.58 | 9 |
| LTD0036 | 181 | 182 | 4 | 0.11 | 0.09 | 0.28 | 2.58 | 3.22 | 9 |
| LTD0040 | 118 | 119 | 2 | 0.03 | 0.02 | 0.18 | 0.50 | 0.77 | 9 |
| LTD0040 | 119 | 120 | 2 | 0.05 | 0.03 | 0.31 | 0.50 | 0.93 | 9 |
| LTD0040 | 120 | 121 | 7 | 0.05 | 0.18 | 0.50 | 0.50 | 1.73 | 9 |
| LTD0040 | 121 | 122 | 5 | 0.09 | 0.22 | 0.33 | 0.50 | 1.65 | 9 |
| LTD0040 | 122 | 123 | 7 | 0.05 | 0.10 | 0.47 | 0.50 | 1.42 | 9 |
| LTD0040 | 123 | 124 | 3 | 0.07 | 0.07 | 0.14 | 0.42 | 0.84 | 9 |
| LTD0040 | 124 | 125 | 5 | 0.06 | 0.06 | 0.26 | 0.50 | 1.05 | 9 |
| LTD0040 | 125 | 126 | 7 | 0.06 | 0.16 | 0.15 | 0.34 | 1.16 | 9 |
| LTD0040 | 126 | 127 | 23 | 0.03 | 0.50 | 0.15 | 0.50 | 2.86 | 9 |
| LTD0040 | 127 | 128 | 50 | 0.13 | 0.50 | 0.50 | 0.50 | 3.86 | 9 |
| LLD002 | 51.82 | 53.34 | | | 0.14 | 0.01 | 0.18 | 0.64 | 8 |
| LLD002 | 53.34 | 54.86 | | | 0.92 | 0.11 | 1.31 | 4.43 | 8 |
| LLD003 | 60.35 | 60.66 | | | 0.54 | 0.01 | 0.46 | 2.25 | 8 |
| LLD003 | 60.66 | 60.96 | | | 1.59 | 0.00 | 1.73 | 6.98 | 8 |
| LLD003 | 60.96 | 61.26 | | | 0.94 | 0.01 | 0.97 | 4.08 | 8 |
| LLD003 | 61.26 | 61.57 | | | 0.15 | 0.01 | 0.22 | 0.70 | 8 |
| LLD003 | 61.57 | 61.87 | | | 0.16 | 0.00 | 0.18 | 0.70 | 8 |
| LLD003 | 61.87 | 62.18 | | | 0.24 | 0.00 | 0.85 | 1.64 | 8 |
| LLD003 | 62.18 | 62.48 | | | 2.01 | 0.00 | 1.15 | 7.79 | 8 |
| LLD003 | 62.48 | 62.79 | | | 1.78 | 0.00 | 0.67 | 6.55 | 8 |
| LLD003 | 62.79 | 63.09 | | | 0.74 | 0.00 | 0.37 | 2.80 | 8 |
| LLD003 | 63.09 | 63.4 | | | 0.10 | 0.00 | 0.16 | 0.50 | 8 |
| LLD003 | 63.4 | 63.7 | | | 0.62 | 0.00 | 0.24 | 2.29 | 8 |
| LLD003 | 63.7 | 64.01 | | | 0.70 | 0.00 | 0.26 | 2.57 | 8 |
| LLD003 | 64.01 | 64.31 | | | 0.71 | 0.00 | 0.29 | 2.64 | 8 |
| LLD003 | 64.31 | 64.62 | | | 0.40 | 0.00 | 0.45 | 1.78 | 8 |
| LLD003 | 64.62 | 65.53 | | | 0.96 | 0.17 | 0.89 | 4.19 | 8 |
| LLD003 | 65.53 | 67.06 | | | 0.79 | 0.02 | 1.94 | 4.57 | 8 |
| LLD004 | 57.81 | 63.39 | | | | | | | 8 |
| LLD005 | 55.53 | 59.26 | | | | | | | 8 |
| LLD006 | 62.18 | 62.48 | | | 1.24 | 0.36 | 1.31 | 5.73 | 8 |
| LLD006 | 62.48 | 62.79 | | | 1.11 | 0.79 | 4.35 | 8.72 | 8 |
| LLD006 | 62.79 | 63.09 | | | | | | 0.00 | 8 |
| LLD006 | 63.09 | 63.4 | | | 0.34 | 0.21 | 1.28 | 2.59 | 8 |
| LLD006 | 63.4 | 63.7 | | | 4.35 | 0.79 | 9.70 | 24.77 | 8 |
| LLD006 | 63.7 | 64.01 | | | 4.35 | 1.60 | 5.60 | 21.40 | 8 |
| LLD006 | 64.01 | 64.31 | | | 2.01 | 2.36 | 0.25 | 9.01 | 8 |
| LLD006 | 64.31 | 64.62 | | | 5.00 | 1.44 | 9.15 | 26.95 | 8 |
| LLD006 | 64.62 | 64.92 | | | 1.73 | 1.34 | 2.87 | 9.79 | 8 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD006 | 64.92 | 65.23 | | | 1.11 | 0.45 | 1.88 | 5.95 | 8 |
| LLD007 | 117.04 | 117.35 | | | 0.11 | 0.00 | 1.00 | 1.35 | 8 |
| LLD007 | 117.35 | 117.65 | | | 0.07 | 0.01 | 0.29 | 0.52 | 8 |
| LLD007 | 117.65 | 117.96 | | | 0.04 | 0.00 | 0.24 | 0.37 | 8 |
| LLD007 | 117.96 | 118.26 | | | 0.52 | 0.01 | 4.65 | 6.37 | 8 |
| LLD007 | 118.26 | 118.57 | | | 2.77 | 0.20 | 4.70 | 14.02 | 8 |
| LLD007 | 118.57 | 118.72 | | | 5.75 | 0.40 | 10.60 | 29.94 | 8 |
| LLD007 | 118.72 | 120.55 | | | 2.51 | 0.30 | 21.90 | 30.45 | 8 |
| LLD007 | 120.55 | 120.7 | | | 5.63 | 0.80 | 5.74 | 25.04 | 8 |
| LLD007 | 120.7 | 121.01 | | | 2.96 | 0.40 | 8.65 | 18.77 | 8 |
| LLD007 | 121.01 | 121.31 | | | 1.42 | 0.03 | 9.15 | 13.86 | 8 |
| LLD007 | 121.31 | 121.62 | | | 0.66 | 0.01 | 3.31 | 5.51 | 8 |
| LLD007 | 121.62 | 121.92 | | | 0.89 | 0.01 | 3.26 | 6.21 | 8 |
| LLD007 | 121.92 | 122.07 | | | 2.48 | 0.03 | 5.28 | 13.49 | 8 |
| LLD007 | 122.07 | 122.22 | | | 1.32 | 0.02 | 0.89 | 5.26 | 8 |
| LLD007 | 122.22 | 122.53 | | | 0.54 | 0.02 | 0.65 | 2.45 | 8 |
| LLD007 | 122.53 | 122.83 | | | 0.20 | 0.02 | 0.35 | 1.02 | 8 |
| LLD007 | 122.83 | 123.14 | | | 0.22 | 0.03 | 0.12 | 0.86 | 8 |
| LLD008 | 53.26 | 53.34 | 0 | 0 | 0.01 | 0.12 | 0.33 | 0.47 | 8 |
| LLD008 | 53.34 | 54.86 | | | 0.40 | 0.06 | 2.76 | 4.14 | 8 |
| LLD008 | 54.86 | 56.39 | | | 0.28 | 0.04 | 0.47 | 1.44 | 8 |
| LLD008 | 56.39 | 56.69 | | | 0.47 | 0.09 | 1.50 | 3.15 | 8 |
| LLD008 | 56.69 | 57 | | | 0.82 | 0.08 | 1.83 | 4.61 | 8 |
| LLD008 | 57 | 57.3 | | | 0.28 | 0.03 | 0.40 | 1.36 | 8 |
| LLD008 | 57.3 | 57.61 | | | 0.38 | 0.03 | 1.15 | 2.42 | 8 |
| LLD008 | 57.61 | 57.91 | | | 0.43 | 0.03 | 0.77 | 2.23 | 8 |
| LLD008 | 57.91 | 58.22 | | | 0.40 | 0.06 | 0.95 | 2.33 | 8 |
| LLD008 | 58.22 | 58.52 | | | 0.20 | 0.64 | 0.93 | 2.17 | 8 |
| LLD008 | 58.52 | 58.83 | | | 0.82 | 0.62 | 1.83 | 5.09 | 8 |
| LLD008 | 58.83 | 59.13 | | | 1.24 | 0.28 | 3.51 | 7.85 | 8 |
| LLD008 | 59.13 | 59.44 | | | 3.09 | 0.28 | 17.55 | 28.00 | 8 |
| LLD008 | 59.44 | 59.74 | | | 3.78 | 0.61 | 11.50 | 24.52 | 8 |
| LLD008 | 59.74 | 60.05 | | | 3.90 | 1.01 | 13.80 | 27.58 | 8 |
| LLD008 | 60.05 | 60.35 | | | 2.96 | 1.19 | 11.30 | 22.14 | 8 |
| LLD008 | 60.35 | 60.66 | | | 7.90 | 0.59 | 4.56 | 31.16 | 8 |
| LLD008 | 60.66 | 60.96 | | | 8.70 | 1.95 | 3.20 | 33.67 | 8 |
| LLD008 | 60.96 | 61.26 | | | 2.62 | 0.31 | 4.00 | 12.93 | 8 |
| LLD008 | 61.26 | 61.57 | | | 2.11 | 0.44 | 2.59 | 9.95 | 8 |
| LLD008 | 61.57 | 61.87 | | | 1.45 | 0.50 | 3.36 | 8.60 | 8 |
| LLD008 | 61.87 | 62.18 | | | 2.00 | 0.05 | 3.90 | 10.55 | 8 |
| LLD008 | 62.18 | 62.48 | | | 2.48 | 0.18 | 0.55 | 8.90 | 8 |
| LLD009 | 50.94 | 51.82 | 0 | 0 | 0.01 | 0.06 | 0.32 | 0.41 | 8 |
| LLD010 | 56.39 | 57.3 | | | 1.91 | 0.37 | 2.41 | 9.04 | 8 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|-------|--------|------------|
| LLD010 | 57.3 | 57.61 | | | | | | 0.00 | 8 |
| LLD010 | 57.61 | 57.91 | | | 0.36 | 0.02 | 0.12 | 1.33 | 8 |
| LLD010 | 57.91 | 58.22 | | | 1.22 | 0.11 | 1.28 | 5.40 | 8 |
| LLD010 | 58.22 | 58.52 | | | 0.75 | 0.06 | 0.72 | 3.25 | 8 |
| LLD010 | 58.52 | 59.13 | | | 2.55 | 0.30 | 0.87 | 9.55 | 8 |
| LLD010 | 59.13 | 59.44 | | | 0.34 | 0.05 | 0.65 | 1.81 | 8 |
| LLD010 | 59.44 | 59.74 | | | 0.36 | 0.05 | 0.70 | 1.92 | 8 |
| LLD010 | 59.74 | 60.96 | | | 0.25 | 0.03 | 0.30 | 1.15 | 8 |
| LLD010 | 60.96 | 61.87 | | | 0.64 | 0.05 | 0.29 | 2.43 | 8 |
| LLD010 | 61.87 | 62.18 | | | 1.08 | 0.41 | 1.40 | 5.33 | 8 |
| LLD010 | 62.18 | 62.48 | | | 0.58 | 0.19 | 0.64 | 2.71 | 8 |
| LLD010 | 62.48 | 62.79 | | | 2.16 | 0.19 | 1.00 | 8.30 | 8 |
| LLD010 | 62.79 | 63.09 | | | 0.17 | 0.06 | 0.18 | 0.81 | 8 |
| LLD010 | 63.09 | 63.4 | | | 0.65 | 0.11 | 1.78 | 4.02 | 8 |
| LLD010 | 63.4 | 63.7 | | | 1.56 | 0.08 | 1.20 | 6.42 | 8 |
| LLD010 | 63.7 | 64.01 | | | 3.73 | 0.28 | 1.78 | 14.34 | 8 |
| LLD010 | 64.01 | 64.31 | | | 1.58 | 0.13 | 0.82 | 6.15 | 8 |
| LLD010 | 64.31 | 65.23 | | | 0.53 | 0.07 | 1.00 | 2.81 | 8 |
| LLD011 | 50.29 | 51.82 | | | 0.44 | 0.01 | 0.13 | 1.59 | 8 |
| LLD011 | 51.82 | 52.73 | | | 0.31 | 0.37 | 12.80 | 14.15 | 8 |
| LLD011 | 52.73 | 53.04 | | | 4.57 | 0.27 | 2.84 | 18.17 | 8 |
| LLD011 | 53.04 | 53.34 | | | 3.27 | 0.24 | 1.24 | 12.25 | 8 |
| LLD011 | 53.34 | 53.64 | | | 3.78 | 0.35 | 2.55 | 15.34 | 8 |
| LLD011 | 53.64 | 53.95 | | | 4.18 | 0.37 | 2.84 | 16.97 | 8 |
| LLD011 | 53.95 | 54.86 | | | 0.50 | 0.05 | 1.08 | 2.78 | 8 |
| LLD011 | 54.86 | 56.39 | | | | | | 0.00 | 8 |
| LLD011 | 56.39 | 57.91 | | | 0.32 | 0.06 | 0.49 | 1.61 | 8 |
| LLD011 | 57.91 | 59.44 | | | 0.55 | 0.13 | 0.49 | 2.43 | 8 |
| LLD011 | 59.44 | 60.66 | | | 1.58 | 0.28 | 1.15 | 6.62 | 8 |
| LLD011 | 60.66 | 60.96 | | | 3.09 | 0.53 | 1.94 | 12.61 | 8 |
| LLD012 | 42.67 | 44.2 | | | 0.05 | 0.31 | 1.28 | 1.71 | 8 |
| LLD012 | 44.2 | 45.72 | | | 0.09 | 0.47 | 4.00 | 4.73 | 8 |
| LLD012 | 45.72 | 47.24 | | | 0.20 | 0.40 | 2.48 | 3.50 | 8 |
| LLD012 | 47.24 | 50.29 | | | 0.10 | 0.47 | 1.13 | 1.88 | 8 |
| LLD012 | 50.29 | 51.82 | | | 0.55 | 0.55 | 4.88 | 7.19 | 8 |
| LLD013 | 54.86 | 56.39 | | | 0.28 | 0.04 | 0.31 | 1.26 | 8 |
| LLD013 | 56.39 | 57.91 | | | 1.06 | 0.06 | 1.48 | 5.03 | 8 |
| LLD013 | 57.91 | 58.22 | | | 1.83 | 0.19 | 4.00 | 10.21 | 8 |
| LLD013 | 58.22 | 58.83 | | | 2.22 | 0.11 | 2.38 | 9.81 | 8 |
| LLD013 | 58.83 | 59.13 | | | 2.48 | 0.09 | 2.59 | 10.85 | 8 |
| LLD013 | 59.13 | 59.44 | | | 0.72 | 0.07 | 1.50 | 3.94 | 8 |
| LLD013 | 59.44 | 59.74 | | | 0.30 | 0.03 | 0.36 | 1.38 | 8 |
| LLD013 | 59.74 | 60.35 | | | 0.62 | 0.02 | 0.29 | 2.36 | 8 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|------|--------|------------|
| LLD013 | 60.35 | 60.66 | | | 1.73 | 0.07 | 0.28 | 6.05 | 8 |
| LLD013 | 60.66 | 60.96 | | | 4.33 | 0.05 | 0.81 | 15.14 | 8 |
| LLD013 | 60.96 | 61.26 | | | 5.20 | 0.15 | 1.00 | 18.29 | 8 |
| LLD013 | 61.26 | 62.18 | | | 1.86 | 0.06 | 0.29 | 6.48 | 8 |
| LLD013 | 62.18 | 62.48 | | | 0.24 | 0.01 | 0.08 | 0.89 | 8 |
| LLD014 | 47.78 | 48.77 | 0 | 0 | 0.01 | 0.02 | 0.48 | 0.54 | 8 |
| LLD014 | 48.77 | 50.29 | | | 0.01 | 0.00 | 0.32 | 0.35 | 8 |
| LLD014 | 50.29 | 51.82 | | | 0.26 | 0.01 | 0.56 | 1.41 | 8 |
| LLD014 | 51.82 | 54.86 | | | 2.00 | 2.58 | 8.70 | 17.62 | 8 |
| LLD014 | 54.86 | 56.39 | | | 3.78 | 5.24 | 5.52 | 22.71 | 8 |
| LLD014 | 56.39 | 57.91 | | | 3.90 | 2.30 | 4.32 | 19.26 | 8 |
| LLD014 | 57.91 | 58.54 | | | 0.96 | 0.65 | 0.95 | 4.70 | 8 |
| LLD015 | 54.86 | 56.39 | | | 0.17 | 0.15 | 0.87 | 1.58 | 8 |
| LLD015 | 56.39 | 57.91 | | | 0.87 | 0.51 | 2.76 | 6.09 | 8 |
| LLD015 | 57.91 | 59.44 | | | 0.89 | 0.75 | 6.20 | 9.81 | 8 |
| LLD015 | 59.44 | 60.96 | | | 0.40 | 0.27 | 1.54 | 3.11 | 8 |
| LLD015 | 60.96 | 61.57 | | | 1.20 | 0.36 | 0.96 | 5.24 | 8 |
| LLD015 | 61.57 | 61.87 | | | 3.32 | 0.42 | 1.28 | 12.61 | 8 |
| LLD015 | 61.87 | 62.18 | | | 3.00 | 1.08 | 1.86 | 12.73 | 8 |
| LLD015 | 62.18 | 62.79 | | | 2.29 | 4.10 | 4.81 | 16.06 | 8 |
| LLD015 | 62.79 | 64.01 | | | 0.45 | 1.24 | 2.05 | 4.63 | 8 |
| LLD015 | 64.01 | 65.53 | | | 0.43 | 0.43 | 0.98 | 2.79 | 8 |
| LLD015 | 65.53 | 67.06 | | | 0.18 | 0.13 | 0.44 | 1.14 | 8 |
| LLD015 | 67.06 | 68.58 | | | 0.16 | 0.02 | 0.28 | 0.82 | 8 |
| LLD016 | 60.05 | 60.96 | | | 1.24 | 0.02 | 0.40 | 4.51 | 8 |
| LLD016 | 60.96 | 61.26 | | | 2.29 | 1.20 | 1.81 | 10.45 | 8 |
| LLD016 | 61.26 | 61.57 | | | 0.26 | 0.14 | 0.25 | 1.22 | 8 |
| LLD016 | 61.57 | 62.48 | | | 0.09 | 0.04 | 0.17 | 0.50 | 8 |
| LLD016 | 62.48 | 63.09 | | | 0.27 | 0.11 | 0.42 | 1.41 | 8 |
| LLD016 | 63.09 | 63.4 | | | 0.43 | 0.18 | 0.56 | 2.14 | 8 |
| LLD016 | 63.4 | 63.7 | | | 0.31 | 0.41 | 1.86 | 3.23 | 8 |
| LLD016 | 63.7 | 64.01 | | | 0.77 | 1.88 | 6.80 | 11.03 | 8 |
| LLD016 | 64.01 | 64.31 | | | 1.32 | 1.92 | 9.80 | 15.88 | 8 |
| LLD016 | 64.31 | 65.53 | | | 0.42 | 0.55 | 2.76 | 4.62 | 8 |
| LLD016 | 65.53 | 65.84 | | | 0.85 | 0.23 | 1.91 | 4.90 | 8 |
| LLD016 | 65.84 | 66.14 | | | 1.71 | 0.07 | 0.91 | 6.62 | 8 |
| LLD016 | 66.14 | 66.45 | | | 0.11 | 0.02 | 0.15 | 0.53 | 8 |
| LLD016 | 66.45 | 66.75 | | | 0.07 | 0.03 | 0.15 | 0.40 | 8 |
| LLD016 | 66.75 | 67.06 | | | 0.56 | 0.11 | 0.45 | 2.39 | 8 |
| LLD016 | 67.06 | 67.36 | | | 0.07 | 0.01 | 0.06 | 0.29 | 8 |
| LLD016 | 67.36 | 67.67 | | | 4.15 | 0.09 | 1.61 | 15.39 | 8 |
| LLD016 | 67.67 | 67.97 | | | 1.48 | 0.05 | 0.55 | 5.47 | 8 |
| LLD016 | 67.97 | 68.58 | | | 0.19 | 0.02 | 0.50 | 1.13 | 8 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD016 | 68.58 | 70.1 | | | 0.96 | 0.76 | 2.08 | 5.93 | 8 |
| LLD016 | 70.1 | 71.63 | | | 0.42 | 0.43 | 1.15 | 2.90 | 8 |
| LLD016 | 71.63 | 71.93 | | | 0.05 | 0.11 | 0.38 | 0.66 | 8 |
| LLD016 | 71.93 | 73.15 | | | 0.30 | 0.45 | 1.06 | 2.45 | 8 |
| LLD016 | 73.15 | 74.68 | | | 0.03 | 0.11 | 0.38 | 0.57 | 8 |
| LLD016 | 74.68 | 75.59 | | | 0.04 | 0.65 | 1.83 | 2.56 | 8 |
| LLD016 | 75.59 | 75.9 | | | 0.09 | 0.63 | 1.28 | 2.14 | 8 |
| LLD016 | 75.9 | 76.2 | | | 0.10 | 0.68 | 1.08 | 2.02 | 8 |
| LLD016 | 76.2 | 77.72 | | | 0.56 | 2.40 | 5.00 | 9.01 | 8 |
| LLD018 | 60.35 | 60.96 | | | 0.61 | 0.00 | 0.23 | 2.22 | 8 |
| LLD018 | 60.96 | 62.48 | | | 0.21 | 0.01 | 0.19 | 0.89 | 8 |
| LLD105 | 92.8 | 93.8 | 76 | 11.5 | 4.03 | 3.58 | 12.00 | 31.00 | 8 |
| LLD105 | 93.8 | 94.8 | 42 | 10.2 | 3.06 | 0.57 | 3.70 | 15.87 | 8 |
| LLD105 | 94.8 | 95.8 | 59 | 36.2 | 1.81 | 2.65 | 10.80 | 22.44 | 8 |
| LLD106 | 47.2 | 48.2 | 1 | 0.9 | 0.16 | 0.01 | 0.96 | 1.58 | 8 |
| LLD106 | 48.2 | 49.2 | 0 | 0.092 | 0.04 | 0.01 | 0.04 | 0.17 | 8 |
| LLD106 | 49.2 | 50.2 | 9 | 27.5 | 1.13 | 0.33 | 2.45 | 8.08 | 8 |
| LLD108 | 271.75 | 272.75 | 1 | 0.022 | 0.37 | 0.02 | 0.03 | 1.30 | 8 |
| LLD108 | 272.75 | 273.75 | 13 | 0.075 | 4.72 | 0.02 | 0.05 | 15.97 | 8 |
| LLD108 | 273.75 | 274.75 | 1 | 0.022 | 0.31 | 0.01 | 0.04 | 1.10 | 8 |
| LLD108 | 274.75 | 275.75 | 7 | 0.052 | 1.83 | 0.02 | 0.33 | 6.56 | 8 |
| LLD108 | 275.75 | 276.75 | 2 | 0.022 | 0.24 | 0.02 | 0.09 | 0.95 | 8 |
| LLD108 | 276.75 | 277.75 | 1 | 0.033 | 0.26 | 0.01 | 0.29 | 1.18 | 8 |
| LLD108 | 277.75 | 278.75 | 0 | 0.062 | 0.21 | 0.02 | 0.30 | 0.99 | 8 |
| LLD108 | 278.75 | 279.75 | 0 | 0.027 | 0.14 | 0.01 | 0.05 | 0.50 | 8 |
| LLD108 | 279.75 | 280.75 | 5 | 0.112 | 1.33 | 0.09 | 1.71 | 6.31 | 8 |
| LLD108 | 280.75 | 281.75 | 1 | 0.028 | 0.09 | 0.08 | 0.66 | 1.04 | 8 |
| LLD109 | 101.8 | 102.8 | 14 | 12.9 | 1.65 | 1.23 | 3.10 | 10.65 | 8 |
| LLD109 | 102.8 | 103.8 | 3 | 0.183 | 0.20 | 0.04 | 0.14 | 0.91 | 8 |
| LLD109 | 103.8 | 104.8 | 0 | 0.027 | 0.02 | 0.01 | 0.08 | 0.13 | 8 |
| LLD109 | 104.8 | 105.8 | 0 | 0.025 | 0.09 | 0.01 | 0.08 | 0.35 | 8 |
| LLD109 | 105.8 | 106.8 | 0 | 0.053 | 0.05 | 0.03 | 0.07 | 0.24 | 8 |
| LLD109 | 106.8 | 107.8 | 26 | 6.37 | 1.21 | 0.82 | 0.88 | 6.58 | 8 |
| LLD109 | 107.8 | 108.8 | 21 | 22.8 | 2.14 | 0.42 | 1.70 | 10.80 | 8 |
| LLD109 | 108.8 | 109.8 | 3 | 1.82 | 0.50 | 0.03 | 0.13 | 1.97 | 8 |
| LLD109 | 109.8 | 110.8 | 48 | 8.55 | 2.60 | 2.07 | 7.44 | 19.51 | 8 |
| LLD109 | 110.8 | 111.8 | 19 | 3.3 | 0.89 | 1.07 | 2.53 | 7.07 | 8 |
| LLD109 | 111.8 | 112.8 | 9 | 0.085 | 0.90 | 0.30 | 1.58 | 5.05 | 8 |
| LLD109 | 112.8 | 113.8 | 2 | 0.213 | 0.18 | 0.06 | 0.62 | 1.32 | 8 |
| LLD109 | 113.8 | 114.8 | 2 | 0.08 | 0.12 | 0.16 | 1.03 | 1.61 | 8 |
| LLD113 | 112.6 | 113.6 | 11 | 0.183 | 0.13 | 1.03 | 1.16 | 2.80 | 8 |
| LLD113 | 113.6 | 114.6 | 3 | 0.138 | 0.40 | 0.27 | 2.53 | 4.17 | 8 |
| LLD113 | 114.6 | 115.6 | 3 | 0.163 | 0.21 | 0.17 | 4.05 | 4.98 | 8 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|-------|-------|-------|--------|------------|
| LLD113 | 115.6 | 116.6 | 0 | 0.057 | -0.01 | -0.01 | 0.03 | -0.03 | 8 |
| LLD113 | 116.6 | 117.6 | 0 | 0.135 | 0.03 | -0.01 | 0.20 | 0.27 | 8 |
| LLD113 | 117.6 | 118.6 | 0 | 0.075 | 0.01 | 0.02 | 0.08 | 0.11 | 8 |
| LLD113 | 118.6 | 119.6 | 5 | 0.53 | 0.58 | 0.10 | 0.99 | 3.15 | 8 |
| LLD113 | 119.6 | 120.6 | 3 | 0.138 | 0.30 | 0.08 | 0.11 | 1.25 | 8 |
| LLD113 | 120.6 | 121.6 | 1 | 0.075 | 0.19 | 0.11 | 0.28 | 1.03 | 8 |
| LLD113 | 121.6 | 122.6 | 24 | 2.51 | 1.36 | 3.15 | 10.70 | 18.75 | 8 |
| LLRC075 | 54 | 55 | 1 | 0.12 | 1.60 | 0.01 | 1.00 | 6.32 | 8 |
| LLRC075 | 55 | 56 | 0 | 0.04 | 0.29 | 0.02 | 0.28 | 1.21 | 8 |
| LLRC075 | 56 | 57 | 1 | 0.75 | 0.33 | 0.03 | 0.72 | 1.89 | 8 |
| LLRC075 | 57 | 58 | 0 | 0.02 | 0.06 | 0.01 | 0.12 | 0.32 | 8 |
| LLRC075 | 58 | 59 | 1 | 0.18 | 0.81 | 0.04 | 0.25 | 2.98 | 8 |
| LLRC075 | 59 | 60 | 1 | 0.41 | 0.85 | 0.04 | 0.24 | 3.13 | 8 |
| LLRC075 | 60 | 61 | 1 | 0.15 | 0.27 | 0.03 | 0.19 | 1.15 | 8 |
| LRC018 | 18 | 19 | 11 | 0.25 | 2.90 | 0.28 | 0.27 | 10.38 | 8 |
| LRC018 | 19 | 20 | 5 | 0.7 | 4.70 | 0.82 | 0.81 | 17.22 | 8 |
| LRC018 | 20 | 21 | 8 | 125 | 0.63 | 0.31 | 0.12 | 8.92 | 8 |
| LRC018 | 21 | 22 | 8 | 6.35 | 0.26 | 0.17 | 0.03 | 1.55 | 8 |
| LRC018 | 22 | 23 | 2 | 7.25 | 0.24 | 0.17 | 0.03 | 1.38 | 8 |
| LRC018 | 23 | 24 | 3 | 0.45 | 0.41 | 0.33 | 0.06 | 1.81 | 8 |
| LRC018 | 24 | 25 | 1 | 0.6 | 0.23 | 0.20 | 0.06 | 1.05 | 8 |
| LRC019 | 31 | 32 | 2 | 0.25 | 0.21 | 0.20 | 0.04 | 0.98 | 8 |
| LRC019 | 32 | 33 | 5 | 1.25 | 2.20 | 0.42 | 0.06 | 7.89 | 8 |
| LRC020 | 17 | 18 | 2 | 0.55 | 0.46 | 0.68 | 0.02 | 2.23 | 8 |
| LRC020 | 18 | 19 | 6 | 0.45 | 2.50 | 0.57 | 0.05 | 8.98 | 8 |
| LRC023 | 14 | 15 | 8 | 0.2 | 5.90 | 0.01 | 0.01 | 19.69 | 8 |
| LRC023 | 15 | 16 | 5 | 0.25 | 6.00 | 0.01 | 0.01 | 19.96 | 8 |
| LRC023 | 16 | 17 | 3 | 0.15 | 0.30 | 0.01 | 0.01 | 1.09 | 8 |
| LTD0034 | 190 | 191 | 4 | 0.05 | 0.49 | 0.03 | 1.44 | 3.17 | 8 |
| LTD0034 | 191 | 192 | 0 | 0.03 | 0.09 | 0.03 | 0.10 | 0.39 | 8 |
| LTD0034 | 192 | 193 | 9 | 0.04 | 0.54 | 0.17 | 0.65 | 2.81 | 8 |
| LTD0034 | 193 | 194 | 6 | 0.06 | 1.12 | 0.09 | 2.93 | 6.86 | 8 |
| LTD0034 | 194 | 195.35 | 2 | 0.07 | 0.65 | 0.04 | 4.47 | 6.70 | 8 |
| LTD0034 | 195.35 | 195.8 | 13 | 0.66 | 1.03 | 0.33 | 2.71 | 6.76 | 8 |
| LTD0034 | 195.8 | 196.45 | 4 | 0.67 | 0.44 | 0.14 | 1.58 | 3.27 | 8 |
| LTD0034 | 196.45 | 196.95 | 18 | 0.66 | 0.89 | 0.82 | 9.10 | 13.26 | 8 |
| LLD006 | 95.4 | 95.71 | | | 0.68 | 0.10 | 4.80 | 7.13 | 7 |
| LLD006 | 95.71 | 96.01 | | | 0.15 | 0.00 | 1.83 | 2.31 | 7 |
| LLD006 | 96.01 | 96.62 | | | 0.21 | 0.07 | 2.64 | 3.39 | 7 |
| LLD006 | 96.62 | 96.93 | | | 0.20 | 0.15 | 8.15 | 8.95 | 7 |
| LLD006 | 96.93 | 97.54 | | | 0.06 | 0.07 | 1.28 | 1.52 | 7 |
| LLD008 | 90.09 | 91.44 | 0 | 0 | 0.02 | 0.01 | 0.08 | 0.14 | 7 |
| LLD008 | 91.44 | 92.96 | | | 0.01 | 0.01 | 0.06 | 0.08 | 7 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD008 | 92.96 | 93.06 | | | 0.03 | 0.01 | 0.26 | 0.36 | 7 |
| LLD010 | 92.99 | 94.49 | 0 | 0 | 0.07 | 0.02 | 0.36 | 0.59 | 7 |
| LLD010 | 94.49 | 96.01 | | | 0.23 | 0.06 | 0.91 | 1.70 | 7 |
| LLD010 | 96.01 | 96.45 | | | 0.04 | 0.02 | 0.20 | 0.36 | 7 |
| LLD011 | 86.87 | 88.39 | | | 0.12 | 0.01 | 0.17 | 0.59 | 7 |
| LLD011 | 88.39 | 89.92 | | | 0.54 | 0.29 | 3.66 | 5.70 | 7 |
| LLD011 | 89.92 | 91.44 | | | 0.15 | 0.02 | 0.55 | 1.06 | 7 |
| LLD013 | 90.45 | 91.44 | 0 | 0 | 0.05 | 0.01 | 0.07 | 0.25 | 7 |
| LLD013 | 91.44 | 92.96 | | | 0.05 | 0.01 | 0.04 | 0.22 | 7 |
| LLD013 | 92.96 | 93.8 | | | 0.04 | 0.01 | 0.22 | 0.36 | 7 |
| LLD013 | 93.8 | 94.18 | | | 0.02 | 0.01 | 0.11 | 0.16 | 7 |
| LLD013 | 94.18 | 94.49 | | | 1.24 | 0.08 | 4.16 | 8.32 | 7 |
| LLD014 | 73.15 | 74.68 | | | 0.38 | 1.71 | 3.00 | 5.81 | 7 |
| LLD014 | 74.68 | 74.98 | | | 1.20 | 5.09 | 13.20 | 21.74 | 7 |
| LLD014 | 74.98 | 75.9 | | | 0.07 | 0.16 | 0.53 | 0.90 | 7 |
| LLD014 | 75.9 | 76.2 | | | 4.57 | 0.22 | 3.09 | 18.37 | 7 |
| LLD014 | 76.2 | 76.5 | | | 2.84 | 0.19 | 0.79 | 10.33 | 7 |
| LLD014 | 76.5 | 77.72 | | | 1.00 | 0.14 | 0.53 | 3.95 | 7 |
| LLD014 | 77.72 | 79.25 | | | 0.12 | 0.47 | 0.55 | 1.38 | 7 |
| LLD014 | 79.25 | 80.77 | | | 0.12 | 0.88 | 0.46 | 1.66 | 7 |
| LLD014 | 80.77 | 81.08 | | | 0.20 | 1.18 | 1.83 | 3.55 | 7 |
| LLD014 | 81.08 | 81.38 | | | 0.98 | 5.03 | 19.10 | 26.86 | 7 |
| LLD014 | 81.38 | 81.69 | | | 1.58 | 3.77 | 16.60 | 25.21 | 7 |
| LLD014 | 81.69 | 81.99 | | | 0.13 | 1.00 | 1.54 | 2.86 | 7 |
| LLD014 | 81.99 | 82.3 | | | 0.16 | 0.40 | 0.46 | 1.35 | 7 |
| LLD014 | 82.3 | 83.82 | | | 0.29 | 0.28 | 1.52 | 2.74 | 7 |
| LLD015 | 89.92 | 91.44 | | | 1.00 | 0.04 | 0.40 | 3.74 | 7 |
| LLD015 | 91.44 | 92.96 | | | 1.43 | 0.03 | 0.31 | 5.06 | 7 |
| LLD015 | 92.96 | 94.49 | | | 1.06 | 0.05 | 0.34 | 3.89 | 7 |
| LLD015 | 94.49 | 96.01 | | | 0.30 | 0.08 | 0.28 | 1.34 | 7 |
| LLD015 | 96.01 | 97.54 | | | 0.19 | 0.15 | 0.41 | 1.18 | 7 |
| LLD015 | 97.54 | 99.06 | | | 0.50 | 1.16 | 3.31 | 6.01 | 7 |
| LLD015 | 99.06 | 100.58 | | | 0.27 | 0.31 | 1.08 | 2.25 | 7 |
| LLD015 | 100.58 | 102.11 | | | 0.10 | 0.10 | 0.30 | 0.72 | 7 |
| LLD015 | 102.11 | 103.63 | | | 0.35 | 0.06 | 1.00 | 2.20 | 7 |
| LLD015 | 103.63 | 105.16 | | | 0.35 | 0.30 | 1.76 | 3.19 | 7 |
| LLD015 | 105.16 | 106.68 | | | 0.23 | 0.13 | 0.52 | 1.40 | 7 |
| LLD015 | 106.68 | 108.2 | | | 0.27 | 0.03 | 0.36 | 1.28 | 7 |
| LLD015 | 108.2 | 109.73 | | | 0.17 | 0.08 | 0.38 | 1.01 | 7 |
| LLD016 | 115.82 | 117.35 | | | 0.12 | 0.05 | 0.91 | 1.36 | 7 |
| LLD016 | 117.35 | 118.11 | | | 0.17 | 0.05 | 0.87 | 1.49 | 7 |
| LLD016 | 118.11 | 118.87 | | | 0.10 | 0.01 | 0.44 | 0.78 | 7 |
| LLD018 | 114.55 | 115.82 | 0 | 0 | 0.02 | 0.01 | 0.14 | 0.21 | 7 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|------|--------|------------|
| LLD018 | 115.82 | 117.12 | | | 0.05 | 0.02 | 0.06 | 0.24 | 7 |
| LLD019 | 102.72 | 103.63 | | | 0.34 | 0.01 | 0.09 | 1.21 | 7 |
| LLD019 | 103.63 | 103.94 | | | 7.00 | 0.02 | 0.31 | 23.42 | 7 |
| LLD019 | 103.94 | 105.16 | | | 2.45 | 0.01 | 0.29 | 8.38 | 7 |
| LLD019 | 105.16 | 106.68 | | | 0.45 | 0.00 | 0.08 | 1.55 | 7 |
| LLD021 | 105.16 | 106.68 | | | 0.93 | 0.01 | 0.10 | 3.18 | 7 |
| LLD021 | 106.68 | 108.2 | | | 0.24 | 0.01 | 0.02 | 0.83 | 7 |
| LLD021 | 108.2 | 109.73 | | | 0.24 | 0.00 | 0.11 | 0.91 | 7 |
| LLD021 | 109.73 | 111.25 | | | 0.27 | 0.01 | 0.08 | 1.00 | 7 |
| LLD022 | 90.53 | 91.44 | | | 1.16 | 0.01 | 0.05 | 3.89 | 7 |
| LLD022 | 91.44 | 92.96 | | | 0.19 | 0.01 | 0.04 | 0.66 | 7 |
| LLD022 | 92.96 | 94.49 | | | 1.00 | 0.02 | 0.05 | 3.37 | 7 |
| LLD023 | 88.39 | 89.92 | | | 0.21 | 0.00 | 0.02 | 0.71 | 7 |
| LLD023 | 89.92 | 91.44 | | | 0.07 | 0.00 | 0.02 | 0.25 | 7 |
| LLD023 | 91.44 | 92.35 | | | 0.06 | 0.00 | 0.02 | 0.22 | 7 |
| LLD023 | 92.35 | 92.66 | | | 0.10 | 0.00 | 0.01 | 0.34 | 7 |
| LLD023 | 92.66 | 92.96 | | | 0.82 | 0.00 | 0.01 | 2.70 | 7 |
| LLD023 | 92.96 | 93.27 | | | 0.29 | 0.00 | 0.01 | 0.96 | 7 |
| LLD023 | 93.27 | 93.57 | | | 0.14 | 0.00 | 0.01 | 0.46 | 7 |
| LLD023 | 93.57 | 93.88 | | | 0.06 | 0.00 | 0.01 | 0.21 | 7 |
| LLD023 | 93.88 | 94.18 | | | 0.11 | 0.00 | 0.01 | 0.39 | 7 |
| LLD023 | 94.18 | 94.49 | | | 0.24 | 0.00 | 0.02 | 0.80 | 7 |
| LLD023 | 94.49 | 94.64 | | | 0.58 | 0.00 | 0.01 | 1.91 | 7 |
| LLD023 | 94.64 | 94.95 | | | 1.28 | 0.00 | 0.04 | 4.27 | 7 |
| LLD023 | 94.95 | 95.1 | | | 1.31 | 0.01 | 0.08 | 4.41 | 7 |
| LLD023 | 95.1 | 95.27 | | | 0.89 | 0.00 | 0.04 | 2.98 | 7 |
| LLD024 | 115.82 | 116.13 | | | 1.86 | 0.34 | 0.33 | 6.76 | 7 |
| LLD024 | 116.13 | 116.43 | | | 1.78 | 2.23 | 2.44 | 10.32 | 7 |
| LLD024 | 116.43 | 116.74 | | | 2.01 | 0.03 | 0.08 | 6.74 | 7 |
| LLD024 | 116.74 | 117.04 | | | 1.89 | 0.15 | 0.20 | 6.57 | 7 |
| LLD024 | 117.04 | 117.35 | | | 1.15 | 0.05 | 0.17 | 4.01 | 7 |
| LLD024 | 117.35 | 118.87 | | | 1.21 | 0.08 | 0.17 | 4.23 | 7 |
| LLD024 | 118.87 | 120.4 | | | 0.17 | 0.01 | 0.03 | 0.59 | 7 |
| LLD024 | 120.4 | 121.31 | | | 0.18 | 0.03 | 0.02 | 0.65 | 7 |
| LLD024 | 121.31 | 121.62 | | | 0.70 | 0.00 | 0.02 | 2.33 | 7 |
| LLD024 | 121.62 | 121.92 | | | 0.26 | 0.00 | 0.01 | 0.89 | 7 |
| LLD024 | 121.92 | 123.14 | | | 0.41 | 0.00 | 0.02 | 1.37 | 7 |
| LLD024 | 123.14 | 123.44 | | | 5.20 | 0.01 | 0.04 | 17.21 | 7 |
| LLD024 | 123.44 | 124.97 | | | 1.00 | 0.00 | 0.03 | 3.33 | 7 |
| LLD024 | 124.97 | 126.49 | | | 0.82 | 0.01 | 0.03 | 2.72 | 7 |
| LLD026 | 106.68 | 108.2 | | | 1.26 | 0.07 | 0.68 | 4.90 | 7 |
| LLD026 | 108.2 | 109.73 | | | 0.04 | 0.26 | 0.45 | 0.82 | 7 |
| LLD027 | 110.95 | 111.25 | | | 0.87 | 0.01 | 0.01 | 2.87 | 7 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|-------|-------|--------|------------|
| LLD027 | 111.25 | 112.78 | | | 0.05 | 0.01 | 0.01 | 0.18 | 7 |
| LLD027 | 112.78 | 113.08 | | | 2.60 | 0.01 | 0.01 | 8.60 | 7 |
| LLD027 | 113.08 | 113.39 | | | 2.29 | 0.01 | 0.01 | 7.57 | 7 |
| LLD028 | 123.44 | 123.75 | | | 0.44 | 0.17 | 0.10 | 1.71 | 7 |
| LLD028 | 123.75 | 124.05 | | | 0.11 | 0.03 | 0.06 | 0.45 | 7 |
| LLD028 | 124.05 | 124.97 | | | 1.04 | 0.14 | 0.50 | 4.06 | 7 |
| LLD028 | 124.97 | 126.49 | | | 0.24 | 0.03 | 0.05 | 0.86 | 7 |
| LLD028 | 126.49 | 126.8 | | | 0.11 | 0.02 | 0.03 | 0.40 | 7 |
| LLD106 | 84.2 | 85.2 | 2 | 5.2 | 0.33 | 0.05 | 0.50 | 1.93 | 7 |
| LLD106 | 85.2 | 86.2 | 6 | 7.78 | 0.74 | 0.40 | 2.29 | 5.63 | 7 |
| LLD109 | 36.8 | 37.8 | 18 | 0.565 | 5.41 | 0.89 | 0.37 | 19.50 | 7 |
| LLD109 | 37.8 | 38.8 | 26 | 0.46 | 4.64 | 6.09 | 0.33 | 21.80 | 7 |
| LLD109 | 38.8 | 39.8 | 23 | 0.293 | 0.18 | 0.24 | 0.06 | 1.46 | 7 |
| LLD109 | 39.8 | 39.88 | 20 | 0.14 | 0.25 | 0.17 | 0.07 | 1.54 | 7 |
| LLD112 | 96.49 | 96.6 | 2 | 4.07 | 0.59 | 0.02 | 0.08 | 2.30 | 7 |
| LLD112 | 96.6 | 97.6 | 0 | 0.052 | 0.01 | 0.00 | 0.02 | 0.03 | 7 |
| LLD112 | 97.6 | 98.6 | 0 | 0.038 | 0.02 | 0.00 | 0.01 | 0.04 | 7 |
| LLD115 | 217.4 | 218.4 | 1 | 0.028 | 0.63 | -0.01 | -0.01 | 2.09 | 7 |
| LLD115 | 218.4 | 219.4 | 2 | 0.039 | 1.88 | 0.01 | 0.02 | 6.28 | 7 |
| LLD115 | 219.4 | 220.4 | 6 | 0.165 | 5.64 | 0.01 | 0.04 | 18.82 | 7 |
| LLD116 | 221.7 | 222.7 | 0 | 0.028 | 0.03 | 0.52 | 1.04 | 1.58 | 7 |
| LLD116 | 222.7 | 223.7 | 1 | 0.063 | 0.02 | 0.81 | 1.11 | 1.93 | 7 |
| LLRC075 | 88 | 89 | 1 | 0.05 | 0.05 | 0.03 | 0.45 | 0.67 | 7 |
| LLRC075 | 89 | 90 | 2 | 0.05 | 0.14 | 0.06 | 0.76 | 1.32 | 7 |
| LLRC075 | 90 | 91 | 3 | 0.11 | 0.63 | 0.16 | 1.79 | 4.09 | 7 |
| LLRC075 | 91 | 92 | 2 | 0.05 | 0.25 | 0.03 | 0.23 | 1.13 | 7 |
| LLRC075 | 92 | 93 | 3 | 0.07 | 0.26 | 0.06 | 0.60 | 1.58 | 7 |
| LLRC075 | 93 | 93.72 | 2 | 0.05 | 0.16 | 0.05 | 0.29 | 0.91 | 7 |
| LRC001 | 50 | 51 | | 3.85 | 0.46 | 0.01 | 0.19 | 1.91 | 7 |
| LRC001 | 51 | 52 | | 9.7 | 0.32 | 0.01 | 0.23 | 1.78 | 7 |
| LRC001 | 52 | 53 | 4 | 10.5 | 1.90 | 0.04 | 0.28 | 7.21 | 7 |
| LRC001 | 53 | 54 | | | | | | 0.00 | 7 |
| LRC001 | 54 | 55 | | 0.65 | 0.13 | 0.02 | 0.07 | 0.55 | 7 |
| LRC001 | 55 | 56 | 19 | 12.2 | 5.00 | 0.34 | 2.10 | 19.99 | 7 |
| LRC001 | 56 | 57 | 9 | 25 | 1.09 | 0.20 | 0.49 | 5.74 | 7 |
| LRC001 | 57 | 58 | 1 | 0.65 | 0.30 | 0.02 | 0.11 | 1.17 | 7 |
| LRC001 | 58 | 59 | 3 | 0.7 | 0.80 | 0.04 | 0.10 | 2.88 | 7 |
| LRC001 | 59 | 60 | 3 | 0.8 | 1.05 | 0.05 | 0.11 | 3.73 | 7 |
| LRC001 | 60 | 61 | | 1.3 | 0.71 | 0.79 | 0.79 | 3.91 | 7 |
| LRC001 | 61 | 62 | 2 | 0.15 | 0.15 | 0.21 | 0.79 | 1.53 | 7 |
| LRC001 | 62 | 63 | 1 | | 0.04 | 0.20 | 0.79 | 1.13 | 7 |
| LRC002 | 22 | 23 | 6 | 3.1 | 3.10 | 0.15 | 0.16 | 10.83 | 7 |
| LRC002 | 23 | 24 | 4 | 0.45 | 1.67 | 0.23 | 0.08 | 5.92 | 7 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|----|--------|--------|-------|-------|-------|--------|------------|
| LRC002 | 24 | 25 | 3 | 0.65 | 9.05 | 0.16 | 0.07 | 30.19 | 7 |
| LRC002 | 25 | 26 | 4 | 0.65 | 1.54 | 0.36 | 0.07 | 5.61 | 7 |
| LRC002 | 26 | 27 | 3 | 1.85 | 1.45 | 0.19 | 0.09 | 5.21 | 7 |
| LRC002 | 27 | 28 | 15 | 1.35 | 3.37 | 0.61 | 0.24 | 12.35 | 7 |
| LRC002 | 28 | 29 | 3 | 0.25 | 0.54 | 0.11 | 0.05 | 2.02 | 7 |
| LRC002 | 29 | 30 | 3 | | 0.26 | 0.07 | 0.05 | 1.04 | 7 |
| LRC004 | 38 | 39 | | 2.4 | | | 1.01 | 1.13 | 7 |
| LRC004 | 39 | 40 | 23 | 2.95 | 6.02 | 0.35 | 1.01 | 21.91 | 7 |
| LRC004 | 40 | 41 | | 0.4 | 0.37 | 0.14 | 1.01 | 2.38 | 7 |
| LRC004 | 41 | 42 | 1 | | 1.23 | 0.10 | 0.11 | 4.29 | 7 |
| LRC004 | 42 | 43 | | | 0.41 | 0.10 | 0.07 | 1.51 | 7 |
| LRC005 | 75 | 76 | 4 | 0.2 | 0.11 | 0.79 | 2.13 | 3.31 | 7 |
| LRC005 | 76 | 77 | 3 | 0.2 | 0.23 | 0.70 | 1.56 | 3.03 | 7 |
| LRC005 | 77 | 78 | 6 | 0.55 | 0.16 | 0.84 | 2.53 | 3.99 | 7 |
| LRC005 | 78 | 79 | 1 | 0.1 | | 0.09 | 0.25 | 0.36 | 7 |
| LRC006 | 47.84 | 48 | 0 | 0 | -1.00 | -1.00 | 1.80 | 1.80 | 7 |
| LRC006 | 48 | 49 | | | | | 1.80 | 1.80 | 7 |
| LRC006 | 49 | 50 | | | 0.01 | | 1.80 | 1.83 | 7 |
| LRC008 | 51 | 52 | 5 | | 0.09 | 0.02 | 1.14 | 1.56 | 7 |
| LRC008 | 52 | 53 | 3 | | 0.09 | 0.02 | 1.61 | 2.00 | 7 |
| LRC008 | 53 | 54 | 24 | 0.7 | 0.14 | 2.18 | 7.20 | 10.25 | 7 |
| LRC008 | 54 | 55 | 48 | 0.7 | 0.48 | 5.87 | 9.00 | 17.10 | 7 |
| LRC008 | 55 | 56 | 37 | 1.4 | 0.46 | 5.13 | 7.80 | 14.93 | 7 |
| LRC008 | 56 | 57 | 26 | 0.4 | 0.20 | 5.45 | 9.80 | 16.03 | 7 |
| LRC008 | 57 | 58 | 24 | 0.85 | 0.40 | 5.39 | 9.80 | 16.61 | 7 |
| LRC008 | 58 | 59 | 7 | 0.1 | 0.03 | 1.00 | 2.12 | 3.30 | 7 |
| LRC008 | 59 | 60 | 14 | 0.15 | 0.22 | 2.71 | 3.37 | 6.89 | 7 |
| LRC008 | 60 | 61 | 39 | 1 | 0.74 | 7.42 | 15.00 | 25.15 | 7 |
| LRC008 | 61 | 62 | 8 | 0.25 | 0.09 | 1.09 | 2.60 | 4.07 | 7 |
| LRC008 | 62 | 63 | 4 | | 0.02 | 0.30 | 0.72 | 1.17 | 7 |
| LRC015 | 29 | 30 | 4 | 6.65 | 0.16 | 0.23 | 0.04 | 1.20 | 7 |
| LRC015 | 30 | 31 | 3 | 2.45 | 0.21 | 0.15 | 0.04 | 1.07 | 7 |
| LRC015 | 31 | 32 | 4 | 2.15 | 0.58 | 0.37 | 0.10 | 2.55 | 7 |
| LRC015 | 32 | 33 | 7 | 2.85 | 0.42 | 0.26 | 0.09 | 2.02 | 7 |
| LRC015 | 33 | 34 | 3 | 2.2 | 0.30 | 0.04 | 0.02 | 1.23 | 7 |
| LRC015 | 34 | 35 | 1 | 0.25 | 0.21 | 0.04 | 0.02 | 0.79 | 7 |
| LRC015 | 35 | 36 | 9 | 0.3 | 0.21 | 0.06 | 0.02 | 1.01 | 7 |
| LRC015 | 36 | 37 | 5 | 0.35 | 0.16 | 0.24 | 0.02 | 0.90 | 7 |
| LRC015 | 37 | 38 | 3 | 0.25 | 0.24 | 0.11 | 0.03 | 1.01 | 7 |
| LRC015 | 38 | 39 | 3 | 0.15 | 0.36 | 0.15 | 0.03 | 1.44 | 7 |
| LRC016 | 46 | 47 | 5 | 0.25 | 0.92 | 0.03 | 0.04 | 3.25 | 7 |
| LRC016 | 47 | 48 | 2 | 0.2 | 0.52 | 0.02 | 0.02 | 1.81 | 7 |
| LRC016 | 48 | 49 | 2 | 0.8 | 0.78 | 0.03 | 0.02 | 2.71 | 7 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|-------|------|------|--------|------------|
| LRC016 | 49 | 50 | 3 | 0.15 | 0.35 | 0.02 | 0.02 | 1.28 | 7 |
| LRC016 | 50 | 51 | 4 | 0.15 | 0.48 | 0.02 | 0.02 | 1.73 | 7 |
| LRC016 | 51 | 52 | 24 | 0.45 | 9.20 | 0.12 | 0.24 | 31.32 | 7 |
| LRC016 | 52 | 53 | 11 | 0.2 | 3.20 | 0.09 | 0.10 | 11.03 | 7 |
| LRC016 | 53 | 54 | 4 | 0.15 | 0.74 | 0.04 | 0.03 | 2.62 | 7 |
| LRC016 | 54 | 55 | 8 | 0.2 | 0.73 | 0.10 | 0.02 | 2.73 | 7 |
| LRC016 | 55 | 56 | 41 | 0.45 | 5.60 | 0.05 | 0.19 | 19.76 | 7 |
| LRC016 | 56 | 57 | 11 | 0.35 | 1.42 | 0.02 | 0.03 | 5.03 | 7 |
| LRC016 | 57 | 58 | 2 | 0.15 | 0.42 | 0.02 | 0.02 | 1.49 | 7 |
| LRC017 | 36 | 37 | 2 | 0.05 | 0.07 | 0.12 | 0.03 | 0.41 | 7 |
| LRC017 | 37 | 38 | 2 | 0.1 | 0.12 | 0.12 | 0.04 | 0.60 | 7 |
| LRC017 | 38 | 39 | 3 | 0.25 | 0.15 | 0.27 | 0.06 | 0.89 | 7 |
| LRC019 | 56 | 57 | 9 | 0.15 | 0.54 | 0.65 | 3.90 | 6.50 | 7 |
| LRC019 | 57 | 58 | 18 | 0.35 | 1.67 | 1.58 | 4.30 | 11.70 | 7 |
| LRC019 | 58 | 59 | 4 | 0.1 | 0.30 | 0.66 | 1.95 | 3.64 | 7 |
| LRC019 | 59 | 60 | 5 | 0.2 | 0.27 | 0.91 | 2.10 | 3.95 | 7 |
| LRC019 | 60 | 61 | 4 | 0.05 | 0.20 | 0.57 | 1.22 | 2.50 | 7 |
| LRC019 | 61 | 62 | 1 | 0.05 | 0.06 | 0.20 | 0.60 | 1.00 | 7 |
| LRC019 | 62 | 63 | 1 | 0.05 | 0.06 | 0.20 | 0.76 | 1.17 | 7 |
| LRC021 | 9 | 10 | 8 | 0.15 | 5.20 | 0.11 | 0.08 | 17.54 | 7 |
| LRC021 | 10 | 11 | 24 | 0.5 | 16.00 | 0.29 | 0.50 | 54.19 | 7 |
| LRC021 | 11 | 13 | | | | | | 0.00 | 7 |
| LRC021 | 13 | 14 | 4 | 0.45 | 3.90 | 0.21 | 0.11 | 13.29 | 7 |
| LRC021 | 14 | 15 | 4 | 0.25 | 2.70 | 0.18 | 0.09 | 9.27 | 7 |
| LRC021 | 15 | 16 | | 0.2 | 1.09 | 0.12 | 0.07 | 3.79 | 7 |
| LRC021 | 16 | 17 | | 0.1 | 0.43 | 0.05 | 0.04 | 1.51 | 7 |
| LRC021 | 17 | 18 | | 0.05 | 0.27 | 0.04 | 0.03 | 0.95 | 7 |
| LRC021 | 18 | 19 | | 0.05 | 0.23 | 0.06 | 0.04 | 0.85 | 7 |
| LRC021 | 19 | 20 | 3 | 0.9 | 0.86 | 0.11 | 0.09 | 3.15 | 7 |
| LRC021 | 20 | 21 | 6 | 0.4 | 1.98 | 0.17 | 0.15 | 7.01 | 7 |
| LRC021 | 21 | 22 | 1 | 0.3 | 0.40 | 0.15 | 0.05 | 1.54 | 7 |
| LRC022 | 36 | 37 | 2 | 0.15 | 1.27 | 0.08 | 0.05 | 4.38 | 7 |
| LRC022 | 37 | 38 | 4 | 0.2 | 0.45 | 0.13 | 0.05 | 1.76 | 7 |
| LRC037 | 71 | 72 | 1 | 0.15 | 0.11 | 0.01 | 1.45 | 1.85 | 7 |
| LRC037 | 72 | 73 | 3 | 0.25 | 0.15 | 0.02 | 5.00 | 5.61 | 7 |
| LRC037 | 73 | 74 | 7 | 0.2 | 0.59 | 0.02 | 5.30 | 7.45 | 7 |
| LRC037 | 74 | 75 | 5 | 0.1 | 0.29 | 0.01 | 4.48 | 5.58 | 7 |
| LRC037 | 75 | 76 | 3 | 0.1 | 0.06 | 0.01 | 1.07 | 1.36 | 7 |
| LRC037 | 76 | 77 | 3 | 0.1 | 0.12 | 0.02 | 1.49 | 1.99 | 7 |
| LRC037 | 77 | 78 | 2 | 0.15 | 0.01 | 0.01 | 0.59 | 0.69 | 7 |
| LRC037 | 78 | 79 | 1 | 0.1 | 0.01 | 0.02 | 1.09 | 1.18 | 7 |
| LRC037 | 79 | 80 | 2 | 0.2 | 0.01 | 0.02 | 0.52 | 0.63 | 7 |
| LRC037 | 80 | 81 | 3 | 0.15 | 0.05 | 0.01 | 1.24 | 1.49 | 7 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|-------|-------|-------|--------|------------|
| LRC037 | 81 | 82 | 5 | 0.1 | 0.10 | 1.23 | 3.86 | 5.43 | 7 |
| LRC037 | 82 | 83 | 9 | 0.2 | 0.26 | 3.11 | 5.60 | 9.49 | 7 |
| LRC037 | 83 | 84 | 5 | 0.1 | 0.15 | 1.10 | 2.54 | 4.15 | 7 |
| LRC037 | 84 | 85 | 3 | 0.15 | 0.11 | 0.27 | 2.11 | 2.80 | 7 |
| LRC048 | 39 | 40 | 4 | 0.2 | 0.14 | 0.01 | 0.70 | 1.27 | 7 |
| LRC048 | 40 | 41 | 3 | 0.2 | 0.09 | 0.03 | 1.17 | 1.57 | 7 |
| LRC048 | 41 | 42 | 1 | 0.15 | 0.62 | 0.01 | 0.01 | 2.09 | 7 |
| LRC048 | 42 | 43 | 2 | 0.1 | 0.74 | 0.01 | 0.08 | 2.59 | 7 |
| LRC048 | 43 | 44 | 2 | 0.2 | 0.77 | 0.07 | 0.04 | 2.70 | 7 |
| LRC048 | 44 | 45 | 9 | 0.4 | 1.54 | 1.36 | 0.07 | 6.62 | 7 |
| LRC048 | 45 | 46 | 7 | 0.55 | 0.32 | 0.05 | 0.02 | 1.33 | 7 |
| LRC048 | 46 | 47 | 5 | 0.15 | 0.14 | 0.03 | 0.03 | 0.65 | 7 |
| LRC048 | 47 | 48 | 6 | 0.2 | 0.34 | 0.02 | 0.54 | 1.84 | 7 |
| LRC048 | 48 | 49 | 5 | 0.15 | 1.88 | 0.02 | 0.34 | 6.69 | 7 |
| LRC048 | 49 | 50 | 3 | 0.15 | 0.25 | 0.02 | 0.02 | 0.95 | 7 |
| LRC048 | 50 | 51 | 3 | 0.2 | 0.37 | 0.02 | 0.05 | 1.36 | 7 |
| LRC048 | 51 | 52 | 2 | | 0.16 | 0.01 | 0.02 | 0.59 | 7 |
| LRC048 | 52 | 53 | 3 | | 1.17 | 0.01 | 0.04 | 3.99 | 7 |
| LRC049 | 60 | 61 | 3 | 0.15 | 0.02 | 0.01 | 1.04 | 1.20 | 7 |
| LRC049 | 61 | 62 | 4 | 0.1 | 0.05 | 0.02 | 2.28 | 2.57 | 7 |
| LRC049 | 62 | 63 | 14 | 4.5 | 0.12 | 2.07 | 4.82 | 7.67 | 7 |
| LRC049 | 63 | 64 | 18 | 0.45 | 0.56 | 4.81 | 14.38 | 21.03 | 7 |
| LRC049 | 64 | 65 | 8 | 0.25 | 0.14 | 1.40 | 2.87 | 4.80 | 7 |
| LRC049 | 65 | 66 | 3 | 0.15 | 0.09 | 0.50 | 1.63 | 2.44 | 7 |
| LRC049 | 66 | 67 | 3 | 0.15 | 0.05 | 0.38 | 1.31 | 1.91 | 7 |
| LRC049 | 67 | 68 | 5 | 0.15 | 0.16 | 2.47 | 6.10 | 8.98 | 7 |
| LRC049 | 68 | 69 | 2 | 0.15 | 0.06 | 0.10 | 2.06 | 2.42 | 7 |
| LRC049 | 69 | 70 | 2 | 0.15 | 0.07 | 0.08 | 0.73 | 1.08 | 7 |
| LTD0036 | 281 | 282 | 2 | 0.01 | 0.45 | 0.01 | 0.03 | 1.57 | 7 |
| LTD0036 | 282 | 283 | 11 | 0.08 | 3.93 | 0.02 | 0.04 | 13.30 | 7 |
| LTD0036 | 283 | 284 | 1 | -0.01 | 0.35 | 0.00 | 0.02 | 1.21 | 7 |
| LLD023 | 58.5 | 66.62 | 0 | 0 | -1.00 | -1.00 | -1.00 | 0.00 | 6 |
| LLD023 | 72.61 | 73.15 | 0 | 0 | 0.02 | 0.01 | 0.05 | 0.14 | 6 |
| LLD023 | 73.15 | 74.07 | | | 0.14 | 0.01 | 0.04 | 0.51 | 6 |
| LLD023 | 74.07 | 74.37 | | | 1.64 | 0.01 | 0.02 | 5.42 | 6 |
| LLD023 | 74.37 | 74.68 | | | 1.58 | 0.01 | 0.04 | 5.26 | 6 |
| LLD023 | 74.68 | 74.98 | | | 2.81 | 0.02 | 0.08 | 9.38 | 6 |
| LLD023 | 74.98 | 76.2 | | | 0.10 | 0.00 | 0.02 | 0.34 | 6 |
| LLD023 | 76.2 | 76.5 | | | 0.15 | 0.00 | 0.02 | 0.52 | 6 |
| LLD023 | 76.5 | 77.72 | | | 0.04 | 0.00 | 0.17 | 0.29 | 6 |
| LLD023 | 77.72 | 79.25 | | | 0.24 | 0.00 | 0.04 | 0.84 | 6 |
| LLD023 | 79.25 | 79.55 | | | 0.29 | 0.00 | 0.06 | 1.01 | 6 |
| LLD023 | 79.55 | 79.86 | | | 4.80 | 0.01 | 0.52 | 16.37 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|-------|--------|------------|
| LLD023 | 79.86 | 80.16 | | | 9.85 | 0.01 | 0.22 | 32.74 | 6 |
| LLD023 | 80.16 | 80.47 | | | 4.00 | 0.02 | 0.19 | 13.41 | 6 |
| LLD023 | 80.47 | 80.77 | | | 0.15 | 0.00 | 0.15 | 0.64 | 6 |
| LLD023 | 80.77 | 81.08 | | | 2.70 | 0.00 | 0.08 | 8.99 | 6 |
| LLD023 | 81.08 | 82.3 | | | 0.28 | 0.00 | 0.03 | 0.96 | 6 |
| LLD023 | 82.3 | 82.6 | | | 0.24 | 0.00 | 0.02 | 0.82 | 6 |
| LLD023 | 82.6 | 82.91 | | | 0.29 | 0.00 | 0.01 | 0.96 | 6 |
| LLD023 | 82.91 | 83.21 | | | 0.85 | 0.01 | 0.02 | 2.82 | 6 |
| LLD023 | 83.21 | 83.52 | | | 2.46 | 0.02 | 0.06 | 8.20 | 6 |
| LLD023 | 83.52 | 83.82 | | | 2.37 | 0.02 | 0.06 | 7.90 | 6 |
| LLD023 | 83.82 | 84.12 | | | 2.88 | 0.04 | 0.24 | 9.77 | 6 |
| LLD023 | 84.12 | 84.43 | | | 1.08 | 0.01 | 0.09 | 3.67 | 6 |
| LLD023 | 84.43 | 84.73 | | | 0.05 | 0.00 | 0.03 | 0.21 | 6 |
| LLD024 | 57.91 | 59.44 | | | 0.02 | 0.28 | 0.94 | 1.27 | 6 |
| LLD024 | 59.44 | 60.05 | | | 0.13 | 2.27 | 0.66 | 3.14 | 6 |
| LLD024 | 60.05 | 60.35 | | | 0.52 | 8.70 | 18.30 | 27.85 | 6 |
| LLD024 | 60.35 | 60.66 | | | 0.63 | 0.50 | 26.40 | 28.93 | 6 |
| LLD024 | 60.66 | 60.96 | | | 0.49 | 3.40 | 18.55 | 23.23 | 6 |
| LLD024 | 60.96 | 61.26 | | | 0.42 | 1.75 | 15.90 | 18.87 | 6 |
| LLD024 | 61.26 | 61.57 | | | 0.42 | 2.36 | 14.20 | 17.72 | 6 |
| LLD024 | 61.57 | 61.87 | | | 0.39 | 0.36 | 21.60 | 23.19 | 6 |
| LLD024 | 61.87 | 62.48 | | | 0.12 | 3.40 | 14.20 | 17.66 | 6 |
| LLD024 | 62.48 | 64.01 | | | 0.03 | 0.23 | 0.50 | 0.81 | 6 |
| LLD024 | 67.06 | 68.58 | | | 0.06 | 0.58 | 1.50 | 2.22 | 6 |
| LLD024 | 68.58 | 70.1 | | | 0.22 | 1.59 | 3.60 | 5.75 | 6 |
| LLD024 | 70.1 | 71.63 | | | 0.11 | 0.66 | 2.76 | 3.72 | 6 |
| LLD024 | 71.63 | 72.24 | | | 0.05 | 0.27 | 1.68 | 2.09 | 6 |
| LLD024 | 72.24 | 73.15 | | | 0.07 | 0.40 | 1.76 | 2.35 | 6 |
| LLD024 | 73.15 | 74.68 | | | 0.20 | 0.62 | 3.85 | 5.07 | 6 |
| LLD024 | 74.68 | 74.98 | | | 0.07 | 0.06 | 1.67 | 1.95 | 6 |
| LLD025 | 64.01 | 65.53 | | | 0.03 | 0.40 | 0.96 | 1.41 | 6 |
| LLD025 | 65.53 | 67.06 | | | 0.15 | 1.54 | 3.75 | 5.62 | 6 |
| LLD025 | 67.06 | 68.58 | | | 0.06 | 0.77 | 1.63 | 2.50 | 6 |
| LLD025 | 68.58 | 70.1 | | | 0.06 | 1.39 | 2.44 | 3.90 | 6 |
| LLD025 | 70.1 | 71.63 | | | 0.10 | 1.49 | 2.50 | 4.18 | 6 |
| LLD025 | 71.63 | 72.24 | | | 0.12 | 1.20 | 1.42 | 2.91 | 6 |
| LLD025 | 72.24 | 73.15 | | | 0.11 | 1.25 | 1.68 | 3.18 | 6 |
| LLD025 | 73.15 | 74.68 | | | 0.15 | 1.20 | 2.33 | 3.89 | 6 |
| LLD025 | 74.68 | 76.2 | | | 0.14 | 0.70 | 2.28 | 3.36 | 6 |
| LLD025 | 76.2 | 77.72 | | | 0.07 | 0.15 | 2.64 | 3.00 | 6 |
| LLD025 | 77.72 | 79.25 | | | 0.04 | 0.02 | 1.73 | 1.88 | 6 |
| LLD025 | 79.25 | 80.77 | | | 0.03 | 0.01 | 0.97 | 1.06 | 6 |
| LLD026 | 62.48 | 64.01 | | | 0.02 | 0.00 | 1.45 | 1.50 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|-------|--------|------------|
| LLD026 | 64.01 | 65.53 | | | 0.01 | 0.03 | 0.96 | 1.02 | 6 |
| LLD026 | 65.53 | 67.06 | | | 0.05 | 1.12 | 3.22 | 4.39 | 6 |
| LLD026 | 67.06 | 68.58 | | | 0.07 | 1.96 | 4.74 | 6.72 | 6 |
| LLD026 | 68.58 | 70.1 | | | 0.09 | 2.20 | 4.81 | 7.08 | 6 |
| LLD026 | 70.1 | 71.63 | | | 0.03 | 0.70 | 2.11 | 2.85 | 6 |
| LLD026 | 71.63 | 72.39 | | | 0.04 | 0.72 | 2.00 | 2.79 | 6 |
| LLD026 | 72.39 | 73.15 | | | 0.31 | 1.50 | 3.09 | 5.47 | 6 |
| LLD026 | 73.15 | 74.68 | | | 0.15 | 2.40 | 7.20 | 9.87 | 6 |
| LLD026 | 74.68 | 76.2 | | | 0.27 | 2.68 | 5.74 | 9.03 | 6 |
| LLD026 | 76.2 | 77.72 | | | 0.05 | 0.49 | 2.19 | 2.80 | 6 |
| LLD026 | 77.72 | 79.25 | | | 0.02 | 0.16 | 0.87 | 1.07 | 6 |
| LLD026 | 79.25 | 80.77 | | | 0.01 | 0.07 | 0.95 | 1.05 | 6 |
| LLD027 | 71.63 | 73.15 | | | 0.02 | 0.68 | 1.28 | 1.95 | 6 |
| LLD027 | 73.15 | 74.07 | | | 0.02 | 1.29 | 1.42 | 2.65 | 6 |
| LLD027 | 74.07 | 74.37 | | | 0.12 | 5.24 | 7.25 | 12.38 | 6 |
| LLD027 | 74.37 | 74.68 | | | 0.07 | 3.84 | 3.95 | 7.65 | 6 |
| LLD027 | 74.68 | 74.98 | | | 0.12 | 4.75 | 6.20 | 10.88 | 6 |
| LLD027 | 74.98 | 75.29 | | | 0.40 | 8.94 | 5.45 | 14.82 | 6 |
| LLD027 | 75.29 | 75.59 | | | 0.41 | 7.12 | 4.60 | 12.36 | 6 |
| LLD027 | 75.59 | 76.2 | | | 0.26 | 5.28 | 6.40 | 12.00 | 6 |
| LLD027 | 76.2 | 76.5 | | | 0.25 | 9.84 | | 9.68 | 6 |
| LLD027 | 76.5 | 76.81 | | | 0.44 | 1.01 | 1.75 | 4.09 | 6 |
| LLD027 | 76.81 | 77.72 | | | 0.23 | 7.59 | 1.45 | 9.04 | 6 |
| LLD027 | 77.72 | 79.25 | | | 0.07 | 4.39 | 2.60 | 6.78 | 6 |
| LLD027 | 79.25 | 80.77 | | | 0.03 | 0.23 | 0.26 | 0.55 | 6 |
| LLD027 | 80.77 | 81.08 | | | 0.01 | 0.42 | 0.10 | 0.51 | 6 |
| LLD027 | 81.08 | 81.38 | | | 0.02 | 0.77 | 0.29 | 1.04 | 6 |
| LLD027 | 81.38 | 81.69 | | | 0.08 | 1.42 | 2.25 | 3.79 | 6 |
| LLD027 | 81.69 | 82.3 | | | 0.05 | 2.54 | 2.82 | 5.27 | 6 |
| LLD027 | 82.3 | 83.82 | | | 0.15 | 2.26 | 1.11 | 3.63 | 6 |
| LLD027 | 83.82 | 84.73 | | | 0.21 | 4.82 | 7.00 | 12.02 | 6 |
| LLD027 | 84.73 | 85.04 | | | 0.41 | 6.01 | 10.55 | 17.31 | 6 |
| LLD027 | 85.04 | 85.34 | | | 0.40 | 7.75 | 6.50 | 14.80 | 6 |
| LLD027 | 85.34 | 86.87 | | | 0.12 | 2.03 | 1.38 | 3.59 | 6 |
| LLD027 | 86.87 | 87.17 | | | 0.04 | 1.39 | 0.62 | 2.00 | 6 |
| LLD028 | 68.58 | 70.1 | | | 0.00 | 0.02 | 0.81 | 0.84 | 6 |
| LLD028 | 70.1 | 71.63 | | | 0.05 | 0.41 | 0.95 | 1.47 | 6 |
| LLD028 | 71.63 | 73.15 | | | 0.01 | 0.18 | 0.50 | 0.70 | 6 |
| LLD028 | 73.15 | 74.68 | | | 0.07 | 0.71 | 1.48 | 2.34 | 6 |
| LLD028 | 74.68 | 80.16 | | | 0.28 | 3.40 | 3.05 | 7.02 | 6 |
| LLD028 | 80.16 | 80.77 | | | 0.19 | 3.13 | 4.44 | 7.87 | 6 |
| LLD028 | 80.77 | 82.3 | | | 0.13 | 2.00 | 3.05 | 5.27 | 6 |
| LLD028 | 82.3 | 83.82 | | | 0.03 | 0.39 | 0.68 | 1.12 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD029 | 71.68 | 73.15 | 0 | 0 | 0.03 | 0.30 | 0.68 | 1.05 | 6 |
| LLD029 | 73.15 | 74.68 | | | 0.04 | 0.63 | 1.83 | 2.51 | 6 |
| LLD029 | 74.68 | 76.2 | | | 0.02 | 0.39 | 0.87 | 1.28 | 6 |
| LLD029 | 76.2 | 77.72 | | | 0.02 | 0.24 | 0.42 | 0.71 | 6 |
| LLD029 | 77.72 | 79.25 | | | 0.03 | 0.37 | 0.96 | 1.38 | 6 |
| LLD029 | 79.25 | 80.77 | | | 0.15 | 2.00 | 3.18 | 5.46 | 6 |
| LLD029 | 80.77 | 82.3 | | | 0.45 | 5.50 | 5.20 | 11.62 | 6 |
| LLD029 | 82.3 | 83.82 | | | 0.10 | 2.32 | 2.48 | 4.91 | 6 |
| LLD029 | 83.82 | 85.34 | | | 0.08 | 0.57 | 2.16 | 2.93 | 6 |
| LLD029 | 85.34 | 86.87 | | | 0.08 | 0.21 | 1.54 | 2.00 | 6 |
| LLD030 | 75.69 | 76.2 | 0 | 0 | 0.00 | 0.00 | 0.04 | 0.05 | 6 |
| LLD030 | 76.2 | 76.96 | | | 0.00 | 0.02 | 0.04 | 0.07 | 6 |
| LLD030 | 76.96 | 77.72 | | | 0.01 | 0.04 | 0.54 | 0.61 | 6 |
| LLD030 | 77.72 | 79.25 | | | 0.01 | 0.15 | 0.90 | 1.07 | 6 |
| LLD030 | 79.25 | 80.77 | | | 0.06 | 1.00 | 2.03 | 3.12 | 6 |
| LLD030 | 80.77 | 82.3 | | | 0.08 | 1.50 | 2.52 | 4.13 | 6 |
| LLD030 | 82.3 | 83.52 | | | 0.02 | 0.31 | 0.65 | 0.99 | 6 |
| LLD030 | 83.52 | 83.82 | | | 0.48 | 4.46 | 9.30 | 14.90 | 6 |
| LLD030 | 83.82 | 84.12 | | | 0.61 | 3.60 | 9.45 | 14.69 | 6 |
| LLD030 | 84.12 | 85.34 | | | 0.01 | 0.21 | 0.57 | 0.80 | 6 |
| LLD030 | 85.34 | 86.87 | | | 0.06 | 0.69 | 1.63 | 2.46 | 6 |
| LLD030 | 86.87 | 88.39 | | | 0.09 | 1.24 | 1.88 | 3.30 | 6 |
| LLD030 | 88.39 | 89.31 | | | 0.19 | 1.92 | 1.86 | 4.20 | 6 |
| LLD030 | 89.31 | 89.92 | | | 0.09 | 1.54 | 2.52 | 4.20 | 6 |
| LLD030 | 89.92 | 91.44 | | | 0.04 | 0.85 | 2.00 | 2.90 | 6 |
| LLD032 | 160.02 | 161.54 | | | 0.06 | 0.15 | 1.30 | 1.63 | 6 |
| LLD032 | 161.54 | 163.07 | | | 0.11 | 0.05 | 1.76 | 2.17 | 6 |
| LLD032 | 163.07 | 164.59 | | | 0.14 | 0.12 | 2.27 | 2.84 | 6 |
| LLD032 | 164.59 | 166.12 | | | 0.15 | 0.19 | 2.94 | 3.61 | 6 |
| LLD032 | 166.12 | 167.64 | | | 0.13 | 0.18 | 2.25 | 2.84 | 6 |
| LLD032 | 167.64 | 169.16 | | | 0.14 | 0.00 | 2.66 | 3.12 | 6 |
| LLD032 | 169.16 | 170.69 | | | 0.03 | 0.11 | 0.88 | 1.08 | 6 |
| LLD036 | 73.01 | 73.15 | 0 | 0 | 0.01 | 0.01 | 0.04 | 0.08 | 6 |
| LLD036 | 73.15 | 74.68 | | | 0.01 | 0.01 | 0.04 | 0.07 | 6 |
| LLD036 | 74.68 | 76.2 | | | 0.01 | 0.07 | 0.24 | 0.34 | 6 |
| LLD036 | 76.2 | 77.72 | | | 0.03 | 0.10 | 0.37 | 0.55 | 6 |
| LLD036 | 77.72 | 78.64 | | | 0.22 | 1.58 | 3.51 | 5.65 | 6 |
| LLD036 | 78.64 | 79.25 | | | 0.07 | 1.45 | 3.22 | 4.75 | 6 |
| LLD036 | 79.25 | 80.77 | | | 0.01 | 1.24 | 2.84 | 3.99 | 6 |
| LLD036 | 80.77 | 82.3 | | | 0.23 | 3.13 | 5.40 | 8.96 | 6 |
| LLD036 | 82.3 | 83.82 | | | 0.40 | 1.50 | 3.00 | 5.66 | 6 |
| LLD036 | 83.82 | 85.34 | | | 0.50 | 5.82 | 17.00 | 23.89 | 6 |
| LLD036 | 85.34 | 86.87 | | | 0.88 | 2.00 | 14.75 | 19.45 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|-------|--------|------------|
| LLD036 | 86.87 | 88.39 | | | 0.50 | 0.45 | 15.20 | 17.26 | 6 |
| LLD036 | 88.39 | 89.66 | | | 0.16 | 0.11 | 3.00 | 3.62 | 6 |
| LLD037 | 67.06 | 68.58 | | | 0.01 | 0.45 | 0.77 | 1.21 | 6 |
| LLD037 | 68.58 | 70.1 | | | 0.02 | 0.49 | 0.96 | 1.48 | 6 |
| LLD037 | 70.1 | 71.63 | | | 0.04 | 0.65 | 1.17 | 1.88 | 6 |
| LLD037 | 71.63 | 73.15 | | | 0.05 | 0.76 | 1.36 | 2.21 | 6 |
| LLD037 | 73.15 | 74.68 | | | 0.07 | 3.89 | 2.55 | 6.29 | 6 |
| LLD037 | 74.68 | 75.59 | | | 0.08 | 5.53 | 3.56 | 8.80 | 6 |
| LLD037 | 75.59 | 75.6 | | | | | | 0.00 | 6 |
| LLD037 | 75.6 | 75.9 | | | 0.22 | 3.26 | 20.50 | 24.17 | 6 |
| LLD037 | 75.9 | 76.2 | | | 0.53 | 3.65 | 21.10 | 26.13 | 6 |
| LLD037 | 76.2 | 76.5 | | | 0.38 | 0.38 | 10.80 | 12.39 | 6 |
| LLD037 | 76.5 | 76.81 | | | 0.33 | 1.54 | 10.20 | 12.67 | 6 |
| LLD037 | 76.81 | 77.11 | | | 0.45 | 1.65 | 14.00 | 16.95 | 6 |
| LLD037 | 77.11 | 77.42 | | | 0.37 | 8.86 | 10.20 | 19.40 | 6 |
| LLD037 | 77.42 | 77.72 | | | 0.54 | 1.28 | 23.50 | 26.44 | 6 |
| LLD037 | 77.72 | 78.03 | | | 0.43 | 0.47 | 13.20 | 15.05 | 6 |
| LLD037 | 78.03 | 78.33 | | | 0.44 | 8.78 | 5.52 | 14.87 | 6 |
| LLD037 | 78.33 | 79.25 | | | 0.15 | 4.96 | 1.78 | 6.72 | 6 |
| LLD037 | 79.25 | 80.77 | | | 0.09 | 3.01 | 1.54 | 4.54 | 6 |
| LLD037 | 80.77 | 82.3 | | | 0.42 | 9.02 | 4.56 | 14.06 | 6 |
| LLD037 | 82.3 | 83.82 | | | 0.23 | 5.81 | 5.52 | 11.50 | 6 |
| LLD037 | 83.82 | 85.34 | | | 0.26 | 2.02 | 4.65 | 7.33 | 6 |
| LLD037 | 85.34 | 86.87 | | | 0.13 | 0.53 | 2.55 | 3.46 | 6 |
| LLD038 | 71.63 | 73.15 | | | 0.02 | 0.20 | 0.28 | 0.51 | 6 |
| LLD038 | 73.15 | 74.68 | | | 0.01 | 0.13 | 0.25 | 0.40 | 6 |
| LLD038 | 74.68 | 76.2 | | | 0.02 | 0.43 | 1.22 | 1.66 | 6 |
| LLD038 | 76.2 | 77.72 | | | 0.02 | 0.20 | 0.64 | 0.87 | 6 |
| LLD038 | 77.72 | 79.25 | | | 0.01 | 0.24 | 0.58 | 0.82 | 6 |
| LLD038 | 79.25 | 80.77 | | | 0.06 | 0.57 | 1.58 | 2.30 | 6 |
| LLD038 | 80.77 | 82.3 | | | 0.08 | 1.16 | 2.41 | 3.72 | 6 |
| LLD038 | 82.3 | 83.82 | | | 0.17 | 2.58 | 4.16 | 7.05 | 6 |
| LLD038 | 83.82 | 85.34 | | | 0.89 | 7.90 | 5.28 | 15.33 | 6 |
| LLD038 | 85.34 | 86.87 | | | 0.28 | 1.96 | 7.20 | 9.89 | 6 |
| LLD038 | 86.87 | 88.39 | | | 0.29 | 0.09 | 5.28 | 6.30 | 6 |
| LLD038 | 88.39 | 89.92 | | | 0.28 | 0.07 | 4.56 | 5.53 | 6 |
| LLD038 | 89.92 | 91.44 | | | 0.05 | 0.01 | 1.20 | 1.38 | 6 |
| LLD038 | 91.44 | 92.96 | | | 0.10 | 0.01 | 1.54 | 1.87 | 6 |
| LLD038 | 92.96 | 94.49 | | | 0.12 | 0.01 | 1.78 | 2.18 | 6 |
| LLD041 | 82.3 | 83.82 | | | 0.09 | 0.52 | 1.22 | 2.00 | 6 |
| LLD041 | 83.82 | 84.28 | | | 0.16 | 5.53 | 10.95 | 16.46 | 6 |
| LLD041 | 84.28 | 85.34 | | | 0.42 | 5.53 | 13.40 | 19.75 | 6 |
| LLD041 | 85.34 | 86.87 | | | 0.39 | 2.68 | 6.65 | 10.35 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|-------|-------|--------|------------|
| LLD041 | 86.87 | 88.39 | | | 0.10 | 0.80 | 1.91 | 2.97 | 6 |
| LLD041 | 88.39 | 89.92 | | | 0.06 | 0.40 | 1.06 | 1.60 | 6 |
| LLD041 | 89.92 | 91.44 | | | 0.07 | 0.25 | 2.35 | 2.80 | 6 |
| LLD041 | 91.44 | 92.96 | | | 0.31 | 1.54 | 5.20 | 7.59 | 6 |
| LLD041 | 92.96 | 94.49 | | | 0.34 | 0.43 | 3.76 | 5.25 | 6 |
| LLD042 | 83.59 | 83.82 | 0 | 0 | 0.02 | 0.21 | 0.98 | 1.25 | 6 |
| LLD042 | 83.82 | 85.34 | | | 0.12 | 2.64 | 2.76 | 5.53 | 6 |
| LLD042 | 85.34 | 85.95 | | | 0.23 | 2.55 | 4.74 | 7.80 | 6 |
| LLD042 | 85.95 | 86.56 | | | 1.34 | 8.88 | 22.90 | 35.32 | 6 |
| LLD042 | 86.56 | 86.87 | | | 0.53 | 7.65 | 3.00 | 11.63 | 6 |
| LLD042 | 86.87 | 88.39 | | | 0.43 | 4.87 | 8.00 | 13.79 | 6 |
| LLD042 | 88.39 | 89.92 | | | 0.08 | 1.54 | 1.30 | 2.96 | 6 |
| LLD042 | 89.92 | 91.44 | | | 0.12 | 1.94 | 2.35 | 4.49 | 6 |
| LLD042 | 91.44 | 92.96 | | | 0.11 | 3.31 | 3.09 | 6.43 | 6 |
| LLD042 | 92.96 | 94.49 | | | 0.06 | 0.47 | 1.45 | 2.08 | 6 |
| LLD043 | 80.77 | 82.3 | | | 0.25 | 6.08 | 11.10 | 17.39 | 6 |
| LLD043 | 82.3 | 82.91 | | | 0.28 | 5.14 | 13.60 | 19.15 | 6 |
| LLD043 | 82.91 | 83.21 | | | 0.49 | 3.60 | 26.20 | 31.06 | 6 |
| LLD043 | 83.21 | 83.52 | | | 0.43 | 0.40 | 21.60 | 23.39 | 6 |
| LLD043 | 83.52 | 83.82 | | | 0.53 | 2.00 | 8.80 | 12.35 | 6 |
| LLD043 | 83.82 | 85.34 | | | 0.21 | 0.64 | 2.48 | 3.73 | 6 |
| LLD043 | 85.34 | 86.87 | | | 0.11 | 0.07 | 2.16 | 2.59 | 6 |
| LLD043 | 86.87 | 88.39 | | | 0.06 | 0.05 | 0.98 | 1.21 | 6 |
| LLD044 | 83.82 | 85.04 | | | 0.00 | 0.01 | 0.21 | 0.23 | 6 |
| LLD044 | 85.04 | 85.34 | | | 0.01 | 0.01 | 0.08 | 0.11 | 6 |
| LLD044 | 85.34 | 86.87 | | | 0.03 | 0.31 | 0.50 | 0.89 | 6 |
| LLD044 | 86.87 | 87.48 | | | 0.14 | 0.29 | 5.28 | 6.02 | 6 |
| LLD044 | 87.48 | 87.78 | | | 0.38 | 5.76 | 16.60 | 23.04 | 6 |
| LLD044 | 87.78 | 88.09 | | | 0.18 | 12.16 | 27.60 | 39.12 | 6 |
| LLD044 | 88.09 | 88.39 | | | 0.95 | 27.60 | 17.30 | 45.27 | 6 |
| LLD044 | 88.39 | 89.92 | | | 0.36 | 3.84 | 4.62 | 9.25 | 6 |
| LLD044 | 89.92 | 90.83 | | | 0.16 | 0.33 | 2.35 | 3.17 | 6 |
| LLD044 | 90.83 | 91.44 | | | 0.08 | 0.19 | 1.20 | 1.64 | 6 |
| LLD044 | 91.44 | 92.96 | | | 0.03 | 0.03 | 0.50 | 0.63 | 6 |
| LLD044 | 92.96 | 94.49 | | | 0.01 | 0.03 | 0.93 | 0.99 | 6 |
| LLD044 | 94.49 | 96.01 | | | 0.01 | 0.04 | 0.50 | 0.58 | 6 |
| LLD044 | 96.01 | 96.3 | | | 0.00 | 0.01 | 0.31 | 0.33 | 6 |
| LLD045 | 81.75 | 82.3 | 0 | 0 | 0.07 | 0.47 | 1.01 | 1.65 | 6 |
| LLD045 | 82.3 | 82.6 | | | 0.43 | 5.82 | 9.10 | 15.74 | 6 |
| LLD045 | 82.6 | 82.91 | | | 0.18 | 12.00 | 17.30 | 28.70 | 6 |
| LLD045 | 82.91 | 83.21 | | | 0.47 | 9.50 | 28.80 | 38.91 | 6 |
| LLD045 | 83.21 | 83.52 | | | 3.51 | 7.90 | 25.50 | 44.19 | 6 |
| LLD045 | 83.52 | 83.82 | | | 2.19 | 8.50 | 24.45 | 39.33 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|-------|-------|--------|------------|
| LLD045 | 83.82 | 84.12 | | | 2.62 | 13.60 | 28.40 | 49.29 | 6 |
| LLD045 | 84.12 | 84.43 | | | 1.81 | 13.60 | 26.60 | 44.81 | 6 |
| LLD045 | 84.43 | 84.73 | | | 0.50 | 5.07 | 10.10 | 16.32 | 6 |
| LLD045 | 84.73 | 85.04 | | | 0.34 | 3.55 | 6.35 | 10.65 | 6 |
| LLD045 | 85.04 | 85.34 | | | 0.37 | 4.25 | 10.20 | 15.24 | 6 |
| LLD045 | 85.34 | 85.65 | | | 0.24 | 2.40 | 5.40 | 8.35 | 6 |
| LLD045 | 85.65 | 85.95 | | | 0.16 | 1.08 | 2.62 | 4.11 | 6 |
| LLD045 | 85.95 | 86.26 | | | 0.36 | 2.54 | 5.63 | 9.09 | 6 |
| LLD045 | 86.26 | 86.56 | | | 0.25 | 5.46 | 12.40 | 18.13 | 6 |
| LLD045 | 86.56 | 86.87 | | | 0.28 | 5.30 | 12.00 | 17.71 | 6 |
| LLD045 | 86.87 | 87.17 | | | 0.79 | 1.00 | 25.50 | 29.01 | 6 |
| LLD045 | 87.17 | 88.39 | | | 0.47 | 4.46 | 1.10 | 6.68 | 6 |
| LLD045 | 88.39 | 89.92 | | | 0.28 | 4.20 | 0.20 | 4.89 | 6 |
| LLD045 | 89.92 | 91.44 | | | 0.20 | 2.30 | 4.44 | 7.17 | 6 |
| LLD045 | 91.44 | 91.74 | | | 0.06 | 0.72 | 1.58 | 2.43 | 6 |
| LLD045 | 91.74 | 91.9 | | | 0.05 | 0.34 | 0.55 | 1.01 | 6 |
| LLD046 | 82.85 | 82.91 | 0 | 0 | 1.24 | 10.80 | 17.80 | 31.61 | 6 |
| LLD046 | 82.91 | 83.21 | | | 1.63 | 15.80 | 33.60 | 53.20 | 6 |
| LLD046 | 83.21 | 83.52 | | | 1.28 | 2.30 | 32.60 | 38.89 | 6 |
| LLD046 | 83.52 | 83.82 | | | 1.54 | 4.15 | 23.50 | 32.32 | 6 |
| LLD046 | 83.82 | 85.04 | | | 1.61 | 6.60 | 13.80 | 25.05 | 6 |
| LLD046 | 85.04 | 85.34 | | | 0.53 | 8.00 | 19.70 | 28.65 | 6 |
| LLD046 | 85.34 | 85.65 | | | 1.45 | 13.20 | 27.00 | 43.67 | 6 |
| LLD046 | 85.65 | 85.95 | | | 1.83 | 7.80 | 27.30 | 40.36 | 6 |
| LLD046 | 85.95 | 86.26 | | | 0.43 | 5.74 | 9.80 | 16.39 | 6 |
| LLD046 | 86.26 | 86.87 | | | 0.07 | 0.72 | 1.94 | 2.81 | 6 |
| LLD046 | 86.87 | 88.39 | | | 0.03 | 0.25 | 1.58 | 1.89 | 6 |
| LLD046 | 88.39 | 89.92 | | | 0.10 | 0.14 | 4.50 | 4.95 | 6 |
| LLD046 | 89.92 | 90.29 | | | 0.16 | 0.03 | 1.83 | 2.38 | 6 |
| LLD047 | 83.82 | 85.34 | | | 0.06 | 4.60 | 5.19 | 9.53 | 6 |
| LLD047 | 85.34 | 86.26 | | | 1.62 | 9.07 | 15.24 | 28.75 | 6 |
| LLD047 | 86.26 | 86.56 | | | 2.90 | 11.66 | 25.51 | 45.58 | 6 |
| LLD047 | 86.56 | 86.87 | | | 2.36 | 10.57 | 22.11 | 39.42 | 6 |
| LLD047 | 86.87 | 87.17 | | | 2.95 | 10.84 | 25.91 | 45.40 | 6 |
| LLD047 | 87.17 | 87.48 | | | 2.32 | 10.28 | 20.66 | 37.58 | 6 |
| LLD047 | 87.48 | 87.78 | | | 2.15 | 9.11 | 19.98 | 35.28 | 6 |
| LLD047 | 87.78 | 88.09 | | | 2.86 | 8.20 | 24.39 | 41.19 | 6 |
| LLD047 | 88.09 | 88.39 | | | 2.71 | 10.00 | 24.44 | 42.39 | 6 |
| LLD047 | 88.39 | 88.7 | | | 3.30 | 10.24 | 30.52 | 50.62 | 6 |
| LLD047 | 88.7 | 89 | | | 3.42 | 12.89 | 31.19 | 54.06 | 6 |
| LLD047 | 89 | 89.31 | | | 1.71 | 11.86 | 14.33 | 30.64 | 6 |
| LLD047 | 89.31 | 89.61 | | | 1.73 | 7.14 | 14.21 | 26.35 | 6 |
| LLD047 | 89.61 | 89.92 | | | 2.03 | 8.43 | 17.34 | 31.62 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|-------|-------|--------|------------|
| LLD047 | 89.92 | 90.22 | | | 2.86 | 10.51 | 25.17 | 44.06 | 6 |
| LLD047 | 90.22 | 90.53 | | | 2.89 | 10.51 | 25.60 | 44.59 | 6 |
| LLD047 | 90.53 | 90.83 | | | 2.11 | 8.14 | 18.41 | 32.70 | 6 |
| LLD047 | 90.83 | 91.44 | | | 2.68 | 8.47 | 20.91 | 37.38 | 6 |
| LLD047 | 91.44 | 91.74 | | | 2.83 | 10.29 | 24.67 | 43.27 | 6 |
| LLD047 | 91.74 | 92.05 | | | 1.54 | 7.94 | 14.89 | 27.11 | 6 |
| LLD047 | 92.05 | 92.35 | | | 1.53 | 7.57 | 12.81 | 24.67 | 6 |
| LLD047 | 92.35 | 92.96 | | | 0.84 | 4.92 | 7.01 | 14.21 | 6 |
| LLD047 | 92.96 | 94.49 | | | 0.38 | 1.23 | 3.54 | 5.90 | 6 |
| LLD047 | 94.49 | 94.79 | | | 0.76 | 0.48 | 6.90 | 9.84 | 6 |
| LLD047 | 94.79 | 95.1 | | | 0.57 | 1.35 | 4.36 | 7.46 | 6 |
| LLD047 | 95.1 | 95.4 | | | 0.59 | 1.78 | 5.06 | 8.61 | 6 |
| LLD047 | 95.4 | 95.71 | | | 0.16 | 0.81 | 1.65 | 2.91 | 6 |
| LLD047 | 95.71 | 96.01 | | | 0.05 | 0.35 | 0.43 | 0.91 | 6 |
| LLD047 | 96.01 | 96.32 | | | 0.13 | 0.20 | 1.38 | 1.99 | 6 |
| LLD047 | 96.32 | 96.62 | | | 0.26 | 1.16 | 1.88 | 3.78 | 6 |
| LLD047 | 96.62 | 96.93 | | | 0.07 | 0.29 | 0.37 | 0.87 | 6 |
| LLD047 | 96.93 | 97.54 | | | 0.06 | 0.55 | 0.53 | 1.22 | 6 |
| LLD047 | 97.54 | 97.84 | | | 0.41 | 0.18 | 2.91 | 4.43 | 6 |
| LLD047 | 97.84 | 98.15 | | | 0.14 | 0.15 | 0.77 | 1.37 | 6 |
| LLD047 | 98.15 | 98.45 | | | 1.03 | 0.31 | 7.72 | 11.39 | 6 |
| LLD047 | 98.45 | 98.76 | | | 3.65 | 0.42 | 31.91 | 44.33 | 6 |
| LLD047 | 98.76 | 99.06 | | | 1.30 | 0.46 | 9.62 | 14.33 | 6 |
| LLD047 | 99.06 | 99.36 | | | 1.00 | 0.15 | 7.41 | 10.85 | 6 |
| LLD047 | 99.36 | 99.67 | | | 0.02 | 0.04 | 0.00 | 0.10 | 6 |
| LLD048 | 73.15 | 75.9 | | | 0.06 | 2.88 | 3.18 | 5.98 | 6 |
| LLD048 | 75.9 | 76.2 | | | 0.16 | 3.93 | 7.70 | 11.76 | 6 |
| LLD048 | 76.2 | 76.5 | | | 0.17 | 3.72 | 4.44 | 8.36 | 6 |
| LLD048 | 76.5 | 76.81 | | | 0.17 | 3.60 | 5.52 | 9.33 | 6 |
| LLD048 | 76.81 | 77.11 | | | 0.20 | 5.14 | 12.40 | 17.68 | 6 |
| LLD048 | 77.11 | 77.42 | | | 1.45 | 9.00 | 26.20 | 39.09 | 6 |
| LLD048 | 77.42 | 77.72 | | | 0.50 | 7.20 | 14.00 | 22.13 | 6 |
| LLD048 | 77.72 | 78.03 | | | 0.21 | 2.00 | 3.61 | 6.09 | 6 |
| LLD048 | 78.03 | 79.25 | | | 0.15 | 1.24 | 2.16 | 3.78 | 6 |
| LLD048 | 79.25 | 81.69 | | | 0.17 | 1.66 | 2.73 | 4.78 | 6 |
| LLD048 | 81.69 | 81.99 | | | 0.19 | 6.26 | 12.00 | 18.27 | 6 |
| LLD048 | 81.99 | 82.3 | | | 0.09 | 9.00 | 20.50 | 28.89 | 6 |
| LLD048 | 82.3 | 82.6 | | | 0.09 | 11.60 | 22.20 | 32.93 | 6 |
| LLD048 | 82.6 | 82.91 | | | 0.49 | 7.20 | 15.40 | 23.50 | 6 |
| LLD048 | 82.91 | 83.21 | | | 0.37 | 7.40 | 22.90 | 30.77 | 6 |
| LLD048 | 83.21 | 83.52 | | | 0.15 | 1.84 | 5.52 | 7.65 | 6 |
| LLD048 | 83.52 | 83.82 | | | 0.04 | 1.66 | 3.88 | 5.51 | 6 |
| LLD048 | 83.82 | 84.43 | | | 0.09 | 0.64 | 1.94 | 2.82 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|-------|-------|--------|------------|
| LLD048 | 84.43 | 84.73 | | | 0.89 | 11.60 | 22.90 | 36.28 | 6 |
| LLD048 | 84.73 | 85.04 | | | 0.56 | 7.40 | 21.10 | 29.62 | 6 |
| LLD048 | 85.04 | 85.34 | | | 0.65 | 8.50 | 2.35 | 12.15 | 6 |
| LLD048 | 85.34 | 85.65 | | | 0.47 | 5.90 | 14.50 | 21.37 | 6 |
| LLD048 | 85.65 | 86.26 | | | 0.55 | 1.84 | 16.90 | 20.36 | 6 |
| LLD048 | 86.26 | 92.6 | | | | | | 0.00 | 6 |
| LLD049 | 167.03 | 167.34 | | | 0.01 | 0.01 | 0.01 | 0.04 | 6 |
| LLD049 | 167.34 | 167.64 | | | 0.01 | 0.02 | 0.03 | 0.08 | 6 |
| LLD049 | 167.64 | 167.94 | | | 0.14 | 1.05 | 2.56 | 3.95 | 6 |
| LLD049 | 167.94 | 168.25 | | | 0.03 | 0.06 | 0.14 | 0.28 | 6 |
| LLD049 | 168.25 | 168.55 | | | 0.01 | 0.02 | 0.04 | 0.10 | 6 |
| LLD049 | 168.55 | 168.86 | | | 0.01 | 0.01 | 0.03 | 0.06 | 6 |
| LLD049 | 168.86 | 169.16 | | | 0.00 | 0.01 | 0.06 | 0.09 | 6 |
| LLD049 | 169.16 | 169.47 | | | 0.01 | 0.24 | 0.54 | 0.78 | 6 |
| LLD049 | 169.47 | 169.77 | | | 0.01 | 0.11 | 0.29 | 0.41 | 6 |
| LLD049 | 169.77 | 170.08 | | | 0.01 | 0.12 | 0.22 | 0.35 | 6 |
| LLD049 | 170.08 | 170.38 | | | 0.03 | 0.36 | 1.59 | 2.00 | 6 |
| LLD052 | 82.19 | 82.3 | 0 | 0 | 0.03 | 0.33 | 1.15 | 1.54 | 6 |
| LLD052 | 82.3 | 83.82 | | | 0.06 | 0.25 | 1.22 | 1.64 | 6 |
| LLD052 | 83.82 | 85.34 | | | 0.04 | 0.06 | 0.24 | 0.41 | 6 |
| LLD052 | 85.34 | 86.87 | | | 0.03 | 0.33 | 1.08 | 1.48 | 6 |
| LLD052 | 86.87 | 87.17 | | | 0.11 | 0.62 | 5.20 | 6.14 | 6 |
| LLD052 | 87.17 | 88.06 | | | | | | 0.00 | 6 |
| LLD052 | 88.06 | 88.39 | | | 0.00 | 0.02 | 0.09 | 0.12 | 6 |
| LLD052 | 88.39 | 89.92 | | | 0.06 | 0.18 | 0.33 | 0.68 | 6 |
| LLD052 | 89.92 | 91.44 | | | 0.15 | 0.68 | 0.73 | 1.83 | 6 |
| LLD052 | 91.44 | 92.96 | | | 0.08 | 0.40 | 0.75 | 1.37 | 6 |
| LLD052 | 92.96 | 94.49 | | | 0.04 | 0.36 | 0.92 | 1.39 | 6 |
| LLD052 | 94.49 | 95.1 | | | 0.01 | 0.09 | 0.29 | 0.40 | 6 |
| LLD053 | 57.91 | 59.44 | | | 0.03 | 0.25 | 1.88 | 2.21 | 6 |
| LLD053 | 59.44 | 60.96 | | | 0.02 | 0.12 | 1.42 | 1.59 | 6 |
| LLD053 | 60.96 | 62.48 | | | 0.02 | 0.07 | 0.70 | 0.84 | 6 |
| LLD053 | 62.48 | 64.01 | | | 0.09 | 0.46 | 2.26 | 2.98 | 6 |
| LLD053 | 64.01 | 65.53 | | | 0.12 | 0.09 | 1.57 | 2.06 | 6 |
| LLD054 | 73.76 | 74.07 | | | 0.22 | 0.40 | 0.89 | 1.97 | 6 |
| LLD054 | 74.07 | 74.37 | | | 5.55 | 1.75 | 8.15 | 28.04 | 6 |
| LLD054 | 74.37 | 74.68 | | | 6.60 | 1.20 | 8.90 | 31.76 | 6 |
| LLD054 | 74.68 | 74.98 | | | 1.83 | 11.50 | 6.60 | 22.99 | 6 |
| LLD054 | 74.98 | 75.29 | | | 1.66 | 2.43 | 2.22 | 9.89 | 6 |
| LLD054 | 75.29 | 75.59 | | | 0.37 | 0.12 | 0.60 | 1.92 | 6 |
| LLD054 | 75.59 | 75.9 | | | 0.59 | 0.13 | 0.66 | 2.71 | 6 |
| LLD054 | 75.9 | 76.2 | | | 0.56 | 0.13 | 0.66 | 2.60 | 6 |
| LLD054 | 76.2 | 76.5 | | | 0.21 | 0.08 | 0.26 | 1.02 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|------|--------|------------|
| LLD054 | 76.5 | 76.81 | | | 0.09 | 0.09 | 0.28 | 0.65 | 6 |
| LLD054 | 76.81 | 77.11 | | | 0.17 | 0.06 | 0.22 | 0.82 | 6 |
| LLD054 | 77.11 | 77.42 | | | 0.94 | 0.15 | 0.28 | 3.51 | 6 |
| LLD054 | 77.42 | 77.72 | | | 0.45 | 0.40 | 1.54 | 3.36 | 6 |
| LLD054 | 77.72 | 78.03 | | | 0.35 | 0.26 | 0.66 | 2.05 | 6 |
| LLD054 | 78.03 | 78.33 | | | 0.33 | 0.22 | 0.82 | 2.09 | 6 |
| LLD054 | 78.33 | 78.64 | | | 0.15 | 0.08 | 0.29 | 0.85 | 6 |
| LLD054 | 78.64 | 78.94 | | | 0.15 | 0.13 | 0.29 | 0.90 | 6 |
| LLD054 | 78.94 | 79.25 | | | 2.19 | 0.43 | 1.63 | 9.24 | 6 |
| LLD054 | 79.25 | 79.55 | | | 0.68 | 0.18 | 0.68 | 3.09 | 6 |
| LLD054 | 79.55 | 79.86 | | | 0.16 | 0.11 | 0.45 | 1.08 | 6 |
| LLD054 | 79.86 | 80.16 | | | 0.08 | 0.15 | 0.23 | 0.63 | 6 |
| LLD054 | 80.16 | 80.47 | | | 0.06 | 0.13 | 0.41 | 0.72 | 6 |
| LLD054 | 80.47 | 80.77 | | | 0.04 | 0.14 | 0.28 | 0.53 | 6 |
| LLD054 | 80.77 | 81.08 | | | 0.06 | 0.12 | 0.28 | 0.59 | 6 |
| LLD054 | 81.08 | 81.38 | | | 0.06 | 0.14 | 0.41 | 0.73 | 6 |
| LLD054 | 81.38 | 81.69 | | | 0.60 | 0.98 | 0.89 | 3.75 | 6 |
| LLD054 | 81.69 | 81.99 | | | 0.37 | 0.68 | 0.66 | 2.48 | 6 |
| LLD054 | 81.99 | 82.3 | | | 1.50 | 0.44 | 1.83 | 7.17 | 6 |
| LLD054 | 82.3 | 82.6 | | | 0.40 | 0.27 | 0.73 | 2.27 | 6 |
| LLD054 | 82.6 | 82.91 | | | 1.01 | 0.24 | 0.70 | 4.25 | 6 |
| LLD054 | 82.91 | 83.21 | | | 0.67 | 0.25 | 0.73 | 3.16 | 6 |
| LLD054 | 83.21 | 83.52 | | | 1.31 | 0.25 | 0.82 | 5.37 | 6 |
| LLD054 | 83.52 | 83.82 | | | 0.77 | 0.19 | 0.68 | 3.39 | 6 |
| LLD054 | 83.82 | 84.12 | | | 0.87 | 0.19 | 0.66 | 3.68 | 6 |
| LLD054 | 84.12 | 84.43 | | | 0.48 | 0.25 | 0.62 | 2.43 | 6 |
| LLD054 | 84.43 | 84.73 | | | 0.82 | 0.25 | 1.00 | 3.91 | 6 |
| LLD054 | 84.73 | 85.04 | | | 1.31 | 0.75 | 1.14 | 6.14 | 6 |
| LLD054 | 85.04 | 85.34 | | | 2.01 | 0.75 | 1.31 | 8.62 | 6 |
| LLD054 | 85.34 | 85.65 | | | 1.73 | 0.60 | 1.24 | 7.49 | 6 |
| LLD054 | 85.65 | 85.95 | | | 1.31 | 0.26 | 0.85 | 5.40 | 6 |
| LLD054 | 85.95 | 86.26 | | | 1.20 | 0.25 | 0.82 | 5.00 | 6 |
| LLD054 | 86.26 | 86.56 | | | 0.46 | 0.13 | 0.36 | 1.98 | 6 |
| LLD054 | 86.56 | 86.87 | | | 0.20 | 0.09 | 0.50 | 1.24 | 6 |
| LLD054 | 86.87 | 87.17 | | | 0.26 | 0.08 | 0.28 | 1.21 | 6 |
| LLD054 | 87.17 | 87.48 | | | 1.57 | 0.22 | 0.92 | 6.29 | 6 |
| LLD054 | 87.48 | 87.78 | | | 0.04 | 0.07 | 0.18 | 0.38 | 6 |
| LLD054 | 87.78 | 88.09 | | | 0.05 | 0.09 | 0.23 | 0.48 | 6 |
| LLD054 | 88.09 | 88.39 | | | 0.11 | 0.18 | 0.56 | 1.06 | 6 |
| LLD054 | 88.39 | 88.7 | | | 0.10 | 0.13 | 0.28 | 0.72 | 6 |
| LLD054 | 88.7 | 89 | | | 0.25 | 0.27 | 0.68 | 1.74 | 6 |
| LLD054 | 89 | 89.31 | | | 0.22 | 0.23 | 0.60 | 1.52 | 6 |
| LLD054 | 89.31 | 89.61 | | | 0.03 | 0.12 | 0.44 | 0.64 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|-------|--------|------------|
| LLD054 | 89.61 | 89.92 | | | 0.05 | 0.15 | 0.64 | 0.95 | 6 |
| LLD054 | 89.92 | 90.22 | | | 0.18 | 0.87 | 2.76 | 4.12 | 6 |
| LLD054 | 90.22 | 90.53 | | | 0.45 | 0.32 | 2.08 | 3.84 | 6 |
| LLD054 | 90.53 | 90.83 | | | 0.25 | 0.32 | 1.38 | 2.49 | 6 |
| LLD054 | 90.83 | 91.14 | | | 0.22 | 0.92 | 2.40 | 3.96 | 6 |
| LLD054 | 91.14 | 91.44 | | | 0.14 | 0.35 | 2.08 | 2.87 | 6 |
| LLD054 | 91.44 | 91.74 | | | 0.39 | 0.44 | 2.22 | 3.88 | 6 |
| LLD054 | 91.74 | 92.05 | | | 0.50 | 1.00 | 7.50 | 10.05 | 6 |
| LLD054 | 92.05 | 92.35 | | | 0.86 | 0.12 | 1.24 | 4.17 | 6 |
| LLD054 | 92.35 | 92.52 | | | 0.44 | 0.12 | 1.88 | 3.42 | 6 |
| LLD055 | 89.92 | 90.07 | | | 0.02 | 0.85 | 1.94 | 2.77 | 6 |
| LLD055 | 90.07 | 90.22 | | | 0.26 | 3.04 | 9.27 | 12.85 | 6 |
| LLD055 | 90.22 | 90.53 | | | 0.23 | 6.60 | 13.50 | 20.21 | 6 |
| LLD055 | 90.53 | 90.83 | | | 0.10 | 0.22 | 6.80 | 7.32 | 6 |
| LLD055 | 90.83 | 90.98 | | | 0.04 | 0.73 | 2.04 | 2.83 | 6 |
| LLD055 | 90.98 | 91.14 | | | 0.05 | 0.30 | 3.60 | 4.02 | 6 |
| LLD055 | 91.14 | 91.29 | | | 0.11 | 0.66 | 2.40 | 3.37 | 6 |
| LLD055 | 91.29 | 91.44 | | | 0.05 | 0.23 | 1.50 | 1.89 | 6 |
| LLD055 | 91.44 | 92.05 | | | 0.01 | 0.02 | 0.05 | 0.08 | 6 |
| LLD055 | 92.05 | 92.35 | | | 0.00 | 0.03 | 0.12 | 0.15 | 6 |
| LLD055 | 92.35 | 92.51 | | | 0.04 | 0.36 | 2.00 | 2.45 | 6 |
| LLD055 | 92.51 | 92.66 | | | 0.15 | 3.20 | 1.94 | 5.32 | 6 |
| LLD055 | 92.66 | 92.96 | | | 0.14 | 2.43 | 5.65 | 8.28 | 6 |
| LLD055 | 92.96 | 93.57 | | | 0.11 | 3.30 | 5.75 | 9.07 | 6 |
| LLD055 | 93.57 | 93.88 | | | 0.10 | 1.20 | 2.70 | 4.10 | 6 |
| LLD055 | 93.88 | 94.18 | | | 0.15 | 2.30 | 4.02 | 6.60 | 6 |
| LLD055 | 94.18 | 94.49 | | | 0.10 | 1.29 | 4.10 | 5.58 | 6 |
| LLD055 | 94.49 | 94.79 | | | 0.06 | 0.08 | 6.50 | 6.75 | 6 |
| LLD055 | 94.79 | 95.1 | | | 0.06 | 0.17 | 2.08 | 2.42 | 6 |
| LLD055 | 95.1 | 95.4 | | | 0.05 | 1.49 | 1.61 | 3.11 | 6 |
| LLD055 | 95.4 | 95.71 | | | 0.15 | 1.80 | 3.60 | 5.70 | 6 |
| LLD055 | 95.71 | 96.01 | | | 0.12 | 0.75 | 2.64 | 3.70 | 6 |
| LLD055 | 96.01 | 96.32 | | | 0.14 | 0.20 | 2.16 | 2.80 | 6 |
| LLD055 | 96.32 | 96.62 | | | 0.07 | 0.28 | 1.55 | 2.03 | 6 |
| LLD055 | 96.62 | 96.93 | | | 0.04 | 0.15 | 0.88 | 1.13 | 6 |
| LLD055 | 96.93 | 97.23 | | | 0.05 | 0.07 | 2.11 | 2.34 | 6 |
| LLD055 | 97.23 | 97.54 | | | 0.07 | 0.03 | 1.03 | 1.28 | 6 |
| LLD055 | 97.54 | 97.84 | | | 0.11 | 0.01 | 2.11 | 2.50 | 6 |
| LLD055 | 97.84 | 98.15 | | | 0.04 | 0.00 | 1.70 | 1.85 | 6 |
| LLD055 | 98.15 | 98.45 | | | 0.02 | 0.01 | 0.19 | 0.28 | 6 |
| LLD055 | 98.45 | 98.76 | | | 0.10 | 0.01 | 1.51 | 1.84 | 6 |
| LLD055 | 98.76 | 99.06 | | | 0.11 | 0.01 | 1.97 | 2.34 | 6 |
| LLD055 | 99.06 | 99.36 | | | 0.08 | 0.01 | 2.01 | 2.28 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|-------|--------|------------|
| LLD055 | 99.36 | 99.67 | | | 0.08 | 0.01 | 0.45 | 0.72 | 6 |
| LLD055 | 99.67 | 99.97 | | | 0.01 | 0.01 | 0.09 | 0.14 | 6 |
| LLD055 | 99.97 | 100.28 | | | 0.02 | 0.01 | 0.38 | 0.45 | 6 |
| LLD055 | 100.28 | 100.58 | | | 0.09 | 0.01 | 6.90 | 7.21 | 6 |
| LLD055 | 100.58 | 100.89 | | | 0.07 | 0.01 | 4.07 | 4.30 | 6 |
| LLD055 | 100.89 | 101.19 | | | 0.04 | 0.01 | 1.80 | 1.92 | 6 |
| LLD055 | 101.19 | 101.5 | | | 0.07 | 0.00 | 1.47 | 1.70 | 6 |
| LLD055 | 101.5 | 101.8 | | | 0.11 | 0.00 | 3.50 | 3.88 | 6 |
| LLD055 | 101.8 | 102.11 | | | 0.14 | 0.00 | 4.38 | 4.83 | 6 |
| LLD055 | 102.11 | 102.41 | | | 0.15 | 0.00 | 4.12 | 4.62 | 6 |
| LLD055 | 102.41 | 102.57 | | | 0.09 | | 0.87 | 1.15 | 6 |
| LLD055 | 102.57 | 102.72 | | | 0.04 | | 0.58 | 0.71 | 6 |
| LLD055 | 102.72 | 102.87 | | | 0.10 | | 1.73 | 2.06 | 6 |
| LLD055 | 102.87 | 103.02 | | | 0.02 | | 0.23 | 0.29 | 6 |
| LLD055 | 103.02 | 103.17 | | | 0.02 | | 0.24 | 0.30 | 6 |
| LLD055 | 103.17 | 103.33 | | | 0.06 | | 0.54 | 0.72 | 6 |
| LLD055 | 103.33 | 103.48 | | | 0.02 | | 0.29 | 0.36 | 6 |
| LLD055 | 103.48 | 103.63 | | | 0.01 | | 0.17 | 0.21 | 6 |
| LLD055 | 103.63 | 103.78 | | | 0.04 | | 0.28 | 0.41 | 6 |
| LLD055 | 103.78 | 103.94 | | | 0.14 | | 0.82 | 1.28 | 6 |
| LLD055 | 103.94 | 104.09 | | | 0.82 | | 4.35 | 7.04 | 6 |
| LLD055 | 104.09 | 104.24 | | | 1.95 | | 10.80 | 17.24 | 6 |
| LLD055 | 104.24 | 104.55 | | | 1.24 | | 6.80 | 10.89 | 6 |
| LLD055 | 104.55 | 104.85 | | | 3.15 | | 7.00 | 17.40 | 6 |
| LLD055 | 104.85 | 105.16 | | | 1.89 | | 2.76 | 9.00 | 6 |
| LLD055 | 105.16 | 105.46 | | | 0.79 | | 1.63 | 4.24 | 6 |
| LLD055 | 105.46 | 105.77 | | | 0.68 | | 2.44 | 4.68 | 6 |
| LLD055 | 105.77 | 105.92 | | | 0.94 | | 4.65 | 7.75 | 6 |
| LLD055 | 105.92 | 106.07 | | | 3.30 | | 5.87 | 16.76 | 6 |
| LLD055 | 106.07 | 106.22 | | | 1.08 | | 1.88 | 5.44 | 6 |
| LLD055 | 106.22 | 106.38 | | | 0.58 | | 7.00 | 8.90 | 6 |
| LLD055 | 106.38 | 106.53 | | | 1.18 | | 9.55 | 13.43 | 6 |
| LLD055 | 106.53 | 106.68 | | | 0.77 | | 10.00 | 12.54 | 6 |
| LLD055 | 106.68 | 106.83 | | | 0.89 | | 17.30 | 20.24 | 6 |
| LLD055 | 106.83 | 107.14 | | | 0.66 | | 19.70 | 21.88 | 6 |
| LLD055 | 107.14 | 107.59 | | | 0.60 | | 20.80 | 22.78 | 6 |
| LLD055 | 107.59 | 107.75 | | | 0.87 | | 27.00 | 29.85 | 6 |
| LLD055 | 107.75 | 107.9 | | | 0.56 | | 27.00 | 28.83 | 6 |
| LLD055 | 107.9 | 108.05 | | | 0.41 | | 19.40 | 20.75 | 6 |
| LLD055 | 108.05 | 108.2 | | | 0.52 | | 18.80 | 20.52 | 6 |
| LLD055 | 108.2 | 108.36 | | | 0.28 | | 16.55 | 17.48 | 6 |
| LLD055 | 108.36 | 108.51 | | | 0.23 | | 12.75 | 13.52 | 6 |
| LLD055 | 108.51 | 108.66 | | | 0.15 | | 9.27 | 9.75 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|-------|-------|--------|------------|
| LLD055 | 108.66 | 108.81 | | | 0.12 | | 6.60 | 6.98 | 6 |
| LLD055 | 108.81 | 108.97 | | | 0.14 | | 4.45 | 4.93 | 6 |
| LLD055 | 108.97 | 109.12 | | | 0.06 | | 4.10 | 4.29 | 6 |
| LLD055 | 109.12 | 109.27 | | | 0.08 | | 1.97 | 2.22 | 6 |
| LLD055 | 109.27 | 109.42 | | | 0.07 | | 2.60 | 2.84 | 6 |
| LLD057 | 53.34 | 54.86 | | | 0.03 | 0.24 | 0.07 | 0.39 | 6 |
| LLD057 | 54.86 | 55.47 | | | 0.03 | 0.34 | 0.09 | 0.48 | 6 |
| LLD057 | 55.47 | 56.39 | | | 0.03 | 0.30 | 0.26 | 0.63 | 6 |
| LLD057 | 56.39 | 57.91 | | | 0.01 | 0.07 | 0.22 | 0.32 | 6 |
| LLD057 | 57.91 | 59.44 | | | 0.01 | 0.06 | 0.70 | 0.79 | 6 |
| LLD057 | 59.44 | 59.74 | | | 0.01 | 0.03 | 0.36 | 0.42 | 6 |
| LLD057 | 59.74 | 60.05 | | | 0.01 | 0.05 | 0.85 | 0.93 | 6 |
| LLD057 | 60.05 | 60.35 | | | 0.02 | 0.05 | 1.16 | 1.26 | 6 |
| LLD057 | 60.35 | 60.66 | | | 0.03 | 0.07 | 1.42 | 1.57 | 6 |
| LLD057 | 60.66 | 60.96 | | | 0.04 | 0.06 | 2.04 | 2.24 | 6 |
| LLD057 | 60.96 | 61.26 | | | 0.08 | 0.06 | 5.46 | 5.76 | 6 |
| LLD057 | 61.26 | 61.57 | | | 0.07 | 0.14 | 3.76 | 4.11 | 6 |
| LLD057 | 61.57 | 61.87 | | | 0.15 | 0.23 | 7.52 | 8.24 | 6 |
| LLD057 | 61.87 | 62.18 | | | 0.19 | 0.17 | 8.48 | 9.25 | 6 |
| LLD057 | 62.18 | 62.48 | | | 0.06 | 0.16 | 4.22 | 4.58 | 6 |
| LLD057 | 62.48 | 62.79 | | | 0.04 | 0.46 | 1.09 | 1.65 | 6 |
| LLD057 | 62.79 | 63.09 | | | 0.09 | 10.80 | 2.35 | 12.37 | 6 |
| LLD057 | 63.09 | 63.4 | | | 0.05 | 1.74 | 3.82 | 5.54 | 6 |
| LLD057 | 63.4 | 63.7 | | | 0.06 | 2.10 | 6.72 | 8.81 | 6 |
| LLD057 | 63.7 | 64.01 | | | 0.12 | 2.45 | 14.43 | 17.03 | 6 |
| LLD057 | 64.01 | 64.31 | | | 0.14 | 0.66 | 13.80 | 14.85 | 6 |
| LLD057 | 64.31 | 64.62 | | | 0.11 | 1.32 | 8.40 | 9.94 | 6 |
| LLD057 | 64.62 | 64.92 | | | 0.06 | 2.25 | 9.00 | 11.21 | 6 |
| LLD057 | 64.92 | 65.23 | | | 0.04 | 1.92 | 6.08 | 7.94 | 6 |
| LLD057 | 65.23 | 65.53 | | | 0.03 | 0.28 | 6.65 | 7.01 | 6 |
| LLD057 | 65.53 | 65.84 | | | 0.05 | 0.83 | 10.40 | 11.31 | 6 |
| LLD057 | 65.84 | 66.14 | | | 0.04 | 1.65 | 10.80 | 12.41 | 6 |
| LLD057 | 66.14 | 66.45 | | | 0.03 | 0.79 | 9.85 | 10.64 | 6 |
| LLD057 | 66.45 | 66.75 | | | 0.02 | 1.10 | 10.00 | 11.06 | 6 |
| LLD057 | 66.75 | 67.06 | | | 0.01 | 0.10 | 1.70 | 1.80 | 6 |
| LLD057 | 67.06 | 68.58 | | | 0.01 | 0.30 | 3.20 | 3.50 | 6 |
| LLD057 | 68.58 | 70.1 | | | 0.07 | 0.81 | 6.20 | 7.15 | 6 |
| LLD057 | 70.1 | 71.63 | | | 0.04 | 0.33 | 6.20 | 6.63 | 6 |
| LLD057 | 71.63 | 72.85 | | | 0.01 | 0.07 | 0.80 | 0.88 | 6 |
| LLD101 | 80.4 | 81 | 9 | 0.019 | 0.00 | 0.45 | 0.84 | 1.48 | 6 |
| LLD101 | 81 | 82 | 345 | 13.5 | 1.03 | 15.10 | 28.60 | 54.89 | 6 |
| LLD101 | 82 | 83 | 228 | 7.3 | 0.30 | 2.31 | 5.47 | 14.60 | 6 |
| LLD101 | 83 | 84 | 430 | 9.12 | 1.19 | 14.00 | 28.20 | 55.93 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|--------|--------|--------|------|------|-------|--------|------------|
| LLD101 | 84 | 85 | 545 | 12.8 | 0.48 | 6.38 | 13.00 | 34.59 | 6 |
| LLD101 | 85 | 86 | 45 | 0.949 | 0.14 | 2.41 | 5.35 | 9.15 | 6 |
| LLD101 | 86 | 87 | 23 | 0.813 | 0.26 | 0.24 | 7.92 | 9.61 | 6 |
| LLD101 | 87 | 88 | 8 | 0.11 | 0.17 | 0.02 | 3.85 | 4.63 | 6 |
| LLD101 | 88 | 89 | 6 | 0.327 | 0.07 | 0.01 | 4.59 | 5.00 | 6 |
| LLD102 | 72.8 | 73.8 | 7 | 0.07 | 0.02 | 0.48 | 1.29 | 1.95 | 6 |
| LLD102 | 73.8 | 74.8 | 53 | 0.187 | 0.05 | 1.46 | 3.03 | 5.84 | 6 |
| LLD102 | 74.8 | 75.8 | 4 | 0.104 | 0.00 | 0.07 | 0.35 | 0.53 | 6 |
| LLD102 | 75.8 | 76.8 | 7 | 0.123 | 0.01 | 0.03 | 0.07 | 0.30 | 6 |
| LLD102 | 76.8 | 77.8 | 4 | 0.073 | 0.00 | 0.26 | 0.44 | 0.78 | 6 |
| LLD102 | 77.8 | 78.8 | 4 | 0.301 | 0.01 | 0.40 | 1.05 | 1.57 | 6 |
| LLD102 | 78.8 | 79.8 | 17 | 1.48 | 0.27 | 3.09 | 4.15 | 8.32 | 6 |
| LLD102 | 79.8 | 80.8 | 4 | 0.13 | 0.10 | 1.37 | 1.34 | 3.01 | 6 |
| LLD102 | 80.8 | 81.8 | 3 | 0.113 | 0.05 | 0.53 | 1.86 | 2.57 | 6 |
| LLD102 | 81.8 | 82.8 | 5 | 0.127 | 0.08 | 0.70 | 1.31 | 2.34 | 6 |
| LLD102 | 82.8 | 83.8 | 3 | 0.13 | 0.13 | 0.41 | 2.06 | 2.93 | 6 |
| LLD102 | 83.8 | 84.8 | 1 | 0.043 | 0.01 | 0.02 | 2.16 | 2.23 | 6 |
| LLD111 | 91.55 | 92.4 | 2 | 0.115 | 0.01 | 0.01 | 0.36 | 0.46 | 6 |
| LLD111 | 92.4 | 93.4 | 1 | 0.07 | 0.01 | 0.00 | 0.25 | 0.33 | 6 |
| LLD111 | 93.4 | 94.4 | 0 | 0.017 | 0.02 | 0.00 | 0.93 | 0.98 | 6 |
| LLD111 | 94.4 | 95.4 | 0 | 0.023 | 0.01 | 0.00 | 0.03 | 0.03 | 6 |
| LLD111 | 95.4 | 96.4 | 1 | 0.027 | 0.00 | 0.00 | 0.08 | 0.11 | 6 |
| LLD111 | 96.4 | 97.4 | 1 | 0.028 | 0.00 | 0.00 | 0.24 | 0.28 | 6 |
| LLD111 | 97.4 | 98.4 | 0 | 0.02 | 0.01 | 0.00 | 0.24 | 0.25 | 6 |
| LLD111 | 98.4 | 99.4 | 1 | 0.127 | 0.23 | 0.01 | 4.85 | 5.66 | 6 |
| LLD111 | 99.4 | 100.4 | 1 | 0.393 | 0.02 | 0.03 | 0.63 | 0.76 | 6 |
| LLD111 | 100.4 | 101.4 | 2 | 0.248 | 0.00 | 0.01 | 0.06 | 0.13 | 6 |
| LLD111 | 101.4 | 102.4 | 4 | 0.29 | 0.00 | 0.00 | 0.02 | 0.15 | 6 |
| LLD111 | 102.4 | 103.4 | 2 | 0.143 | 0.00 | 0.00 | 0.02 | 0.09 | 6 |
| LLD111 | 103.4 | 104.4 | 1 | 0.132 | 0.00 | 0.00 | 0.03 | 0.07 | 6 |
| LLD111 | 104.4 | 105.38 | 1 | 0.065 | 0.00 | 0.00 | 0.01 | 0.04 | 6 |
| LLD112 | 61.6 | 62.6 | 3 | 0.097 | 0.06 | 1.06 | 3.00 | 4.24 | 6 |
| LLD112 | 62.6 | 63.6 | 25 | 0.457 | 1.18 | 7.31 | 15.50 | 26.62 | 6 |
| LLD112 | 63.6 | 64.6 | 9 | 0.448 | 0.27 | 3.53 | 5.20 | 9.52 | 6 |
| LLD112 | 64.6 | 65.6 | 5 | 0.202 | 0.14 | 2.05 | 2.82 | 5.26 | 6 |
| LLD112 | 65.6 | 66.6 | 11 | 0.207 | 0.29 | 2.57 | 5.70 | 9.24 | 6 |
| LLD112 | 66.6 | 67.6 | 3 | 0.05 | 0.04 | 0.12 | 1.37 | 1.69 | 6 |
| LLD112 | 67.6 | 68.6 | 2 | 0.055 | 0.04 | 0.11 | 1.30 | 1.56 | 6 |
| LLD112 | 68.6 | 69.6 | 0 | 0.07 | 0.02 | 0.17 | 0.92 | 1.11 | 6 |
| LLD112 | 69.6 | 70.6 | 7 | 0.197 | 0.31 | 3.41 | 6.10 | 10.38 | 6 |
| LLD112 | 76.6 | 77.6 | 1 | 0.057 | 0.02 | 0.22 | 1.05 | 1.35 | 6 |
| LLD112 | 77.6 | 78.6 | 0 | 0.052 | 0.04 | 0.01 | 1.02 | 1.13 | 6 |
| LLD112 | 78.6 | 79.6 | 0 | 0.055 | 0.00 | 0.00 | 0.05 | 0.03 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|-------|-------|--------|------------|
| LLD112 | 79.6 | 80.6 | 2 | 0.08 | 0.07 | 0.27 | 0.81 | 1.35 | 6 |
| LLD112 | 80.6 | 81.6 | 2 | 0.116 | 0.06 | 0.53 | 1.83 | 2.54 | 6 |
| LLD112 | 81.6 | 82.6 | 2 | 0.11 | 0.02 | 0.01 | 0.11 | 0.23 | 6 |
| LLD112 | 82.6 | 83.6 | 2 | 0.138 | 0.00 | 0.01 | 0.01 | 0.08 | 6 |
| LLD112 | 83.6 | 84.6 | 2 | 0.232 | 0.01 | 0.01 | 0.02 | 0.11 | 6 |
| LLD112 | 84.6 | 84.76 | 1 | 0.115 | 0.12 | 0.00 | 0.02 | 0.45 | 6 |
| LLD114 | 163.83 | 164.8 | 0 | 0.124 | 0.01 | 0.00 | 0.03 | 0.03 | 6 |
| LLD114 | 164.8 | 165.8 | 1 | 0.192 | 0.01 | 0.01 | 0.09 | 0.16 | 6 |
| LLD114 | 165.8 | 166.8 | 0 | 0.037 | 0.00 | 0.00 | 0.02 | 0.01 | 6 |
| LLD114 | 166.8 | 167.8 | 0 | -0.008 | 0.00 | 0.00 | 0.25 | 0.23 | 6 |
| LLD114 | 167.8 | 168.01 | 0 | 0.013 | 0.00 | 0.00 | 0.03 | 0.01 | 6 |
| LLD119 | 211 | 212 | 3 | 0.228 | 0.30 | 0.43 | 5.95 | 7.43 | 6 |
| LLD119 | 212 | 213 | 1 | 0.047 | 0.22 | 0.03 | 1.42 | 2.19 | 6 |
| LLD119 | 213 | 214 | 0 | 0.05 | 0.16 | 0.01 | 3.06 | 3.56 | 6 |
| LLD119 | 214 | 215 | 0 | 0.067 | 0.25 | 0.01 | 2.36 | 3.17 | 6 |
| LLD119 | 215 | 216 | 2 | 0.1 | 0.28 | 0.03 | 5.11 | 6.10 | 6 |
| LLD119 | 216 | 217 | 1 | 0.088 | 0.03 | 0.02 | 2.27 | 2.43 | 6 |
| LLD119 | 217 | 218 | 3 | 0.155 | 0.07 | 0.07 | 6.90 | 7.29 | 6 |
| LLD119 | 218 | 219 | 1 | 0.047 | 0.25 | 0.01 | 2.56 | 3.41 | 6 |
| LLD119 | 219 | 220 | 1 | 0.197 | 0.35 | 0.01 | 6.45 | 7.65 | 6 |
| LLD119 | 220 | 221 | 1 | 0.2 | 0.08 | 0.01 | 1.62 | 1.94 | 6 |
| LLD119 | 221 | 222 | 0 | 0.195 | 0.34 | 0.04 | 6.20 | 7.32 | 6 |
| LLD119 | 222 | 223 | 10 | 1.03 | 0.55 | 7.60 | 19.60 | 28.54 | 6 |
| LLD119 | 223 | 224 | 16 | 0.372 | 0.47 | 11.30 | 22.30 | 34.44 | 6 |
| LLD119 | 224 | 225 | 2 | 0.143 | 0.04 | 1.33 | 2.13 | 3.52 | 6 |
| LLD120 | 215 | 216 | 12 | 0.353 | 7.95 | 0.02 | 0.24 | 26.81 | 6 |
| LLD120 | 216 | 217 | 4 | 0.06 | 2.34 | 0.00 | 0.08 | 7.91 | 6 |
| LLD122 | 209 | 210 | 0 | 0.054 | 0.46 | 0.02 | 0.03 | 1.54 | 6 |
| LLD122 | 210 | 211 | 1 | 0.287 | 0.38 | 0.10 | 0.81 | 2.20 | 6 |
| LLD122 | 211 | 212 | 56 | 32.8 | 3.72 | 7.63 | 7.92 | 30.10 | 6 |
| LLD122 | 212 | 213 | 9 | 21.8 | 1.18 | 0.16 | 0.91 | 6.26 | 6 |
| LLD132 | 62 | 63 | 25 | 0.73 | 0.04 | 0.65 | 1.71 | 3.09 | 6 |
| LLD132 | 63 | 64 | 98 | 1.22 | 0.40 | 3.82 | 5.86 | 13.12 | 6 |
| LLD132 | 64 | 65 | 104 | 0.8 | 0.48 | 3.97 | 4.19 | 12.00 | 6 |
| LLD132 | 65 | 66 | 18 | 0.62 | 0.04 | 0.78 | 0.41 | 1.72 | 6 |
| LLD132 | 66 | 67 | 4 | 0.15 | 0.02 | 0.01 | 0.15 | 0.32 | 6 |
| LLD132 | 67 | 68 | 1 | 0.76 | 0.05 | 0.27 | 0.50 | 0.97 | 6 |
| LLD132 | 68 | 69 | 74 | 1.11 | 0.08 | 0.66 | 2.00 | 4.76 | 6 |
| LLD132 | 69 | 70 | 62 | 1.24 | 0.30 | 3.23 | 6.49 | 12.00 | 6 |
| LLD132 | 70 | 71 | 78 | 1.29 | 0.56 | 5.97 | 12.40 | 21.64 | 6 |
| LLD132 | 71 | 72 | 66 | 0.99 | 0.37 | 5.26 | 13.49 | 21.14 | 6 |
| LLD132 | 72 | 73 | 15 | 0.48 | 0.07 | 1.16 | 8.59 | 10.26 | 6 |
| LLD132 | 73 | 74 | 32 | 0.4 | 0.12 | 2.47 | 12.33 | 15.77 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|-------|--------|--------|------|------|-------|--------|------------|
| LLD132 | 74 | 74.63 | 1 | 0.13 | 0.06 | 0.04 | 2.30 | 2.57 | 6 |
| LLD134 | 81 | 82 | 6 | 0.45 | 0.04 | 0.01 | 3.18 | 3.51 | 6 |
| LLD134 | 82 | 83 | 4 | 0.11 | 0.03 | 0.01 | 2.10 | 2.29 | 6 |
| LLD134 | 83 | 84 | 6 | 0.26 | 0.04 | 0.01 | 2.59 | 2.88 | 6 |
| LLD134 | 84 | 85 | 16 | 0.3 | 0.05 | 0.01 | 3.41 | 3.99 | 6 |
| LLD134 | 85 | 86 | 6 | 0.07 | 0.01 | 0.01 | 0.43 | 0.63 | 6 |
| LLD134 | 86 | 87 | 5 | 0.07 | 0.05 | 0.00 | 0.68 | 0.98 | 6 |
| LLD134 | 87 | 88 | 7 | 0.23 | 0.10 | 0.01 | 3.84 | 4.37 | 6 |
| LLD134 | 88 | 89 | 6 | 0.18 | 0.01 | 0.01 | 0.82 | 1.03 | 6 |
| LLD134 | 89 | 90 | 5 | 0.59 | 0.01 | 0.01 | 0.97 | 1.17 | 6 |
| LLD134 | 90 | 91 | 3 | 0.02 | 0.00 | 0.00 | 0.30 | 0.38 | 6 |
| LLD134 | 91 | 92 | 3 | 0.01 | 0.00 | 0.00 | 0.39 | 0.48 | 6 |
| LLD134 | 92 | 93 | 5 | 0.17 | 0.06 | 0.00 | 2.77 | 3.11 | 6 |
| LLD134 | 93 | 94 | 3 | 0.1 | 0.01 | 0.00 | 1.89 | 2.01 | 6 |
| LLD134 | 94 | 95 | 3 | 0.02 | 0.01 | 0.00 | 2.06 | 2.17 | 6 |
| LLD134 | 95 | 96 | 4 | 0.09 | 0.00 | 0.00 | 0.70 | 0.81 | 6 |
| LLD134 | 96 | 97 | 3 | 0.06 | 0.06 | 0.00 | 2.10 | 2.38 | 6 |
| LLD134 | 97 | 98 | 2 | 0.13 | 0.06 | 0.00 | 2.49 | 2.76 | 6 |
| LLD134 | 98 | 99 | 3 | 0.26 | 0.04 | 0.01 | 0.77 | 0.99 | 6 |
| LLD134 | 99 | 100 | 9 | 0.58 | 0.49 | 0.03 | 6.54 | 8.45 | 6 |
| LLD134 | 100 | 101 | 1 | 0.08 | 0.08 | 0.01 | 0.35 | 0.65 | 6 |
| LLD134 | 101 | 102 | 1 | 0.005 | 0.01 | 0.00 | 0.07 | 0.11 | 6 |
| LLD134 | 102 | 103 | 1 | 0.26 | 0.14 | 0.01 | 0.06 | 0.57 | 6 |
| LLD134 | 103 | 104 | 3 | 0.24 | 0.67 | 0.00 | 0.03 | 2.32 | 6 |
| LLD134 | 104 | 105 | 2 | 0.06 | 0.58 | 0.00 | 0.04 | 2.00 | 6 |
| LLD135 | 114 | 115 | 37 | 0.92 | 0.23 | 9.19 | 23.90 | 33.90 | 6 |
| LLD135 | 115 | 116 | 15 | 4.87 | 0.57 | 5.52 | 9.85 | 17.31 | 6 |
| LLD135 | 116 | 117 | 7 | 1.56 | 0.36 | 1.65 | 3.08 | 6.01 | 6 |
| LLD135 | 117 | 118 | 8 | 1.15 | 0.14 | 1.54 | 2.75 | 4.84 | 6 |
| LLD135 | 118 | 119 | 9 | 0.63 | 0.20 | 0.22 | 3.06 | 4.18 | 6 |
| LLD135 | 119 | 120 | 7 | 0.42 | 0.06 | 1.39 | 2.33 | 3.98 | 6 |
| LLD135 | 120 | 121 | 18 | 0.25 | 0.12 | 2.99 | 5.94 | 9.48 | 6 |
| LLD135 | 121 | 122 | 33 | 37.4 | 0.31 | 7.28 | 12.45 | 22.72 | 6 |
| LLD135 | 122 | 123 | 24 | 4.26 | 0.22 | 2.82 | 5.16 | 9.24 | 6 |
| LLD135 | 123 | 124 | 21 | 2.45 | 0.11 | 1.81 | 3.77 | 6.42 | 6 |
| LLD135 | 124 | 125 | 53 | 9.41 | 0.40 | 4.39 | 6.22 | 13.29 | 6 |
| LLD135 | 125 | 126 | 88 | 14.3 | 0.37 | 5.01 | 9.29 | 17.94 | 6 |
| LLD135 | 126 | 127 | 17 | 0.24 | 0.09 | 1.25 | 2.31 | 4.15 | 6 |
| LLD135 | 127 | 128 | 21 | 0.22 | 0.07 | 1.24 | 1.63 | 3.49 | 6 |
| LLD135 | 128 | 129 | 10 | 0.09 | 0.05 | 0.18 | 2.08 | 2.65 | 6 |
| LLD135 | 129 | 130 | 6 | 0.07 | 0.05 | 0.45 | 1.84 | 2.56 | 6 |
| LLD135 | 130 | 131 | 6 | 0.1 | 0.02 | 0.32 | 2.32 | 2.81 | 6 |
| LLD135 | 131 | 132 | 5 | 0.08 | 0.03 | 0.32 | 1.61 | 2.14 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|-----|--------|--------|------|------|-------|--------|------------|
| LLD135 | 132 | 133 | 3 | 0.05 | 0.01 | 0.03 | 0.53 | 0.66 | 6 |
| LLD135 | 133 | 134 | 4 | 0.06 | 0.00 | 0.02 | 0.12 | 0.25 | 6 |
| LLD135 | 134 | 135 | 5 | 0.03 | 0.03 | 0.06 | 2.08 | 2.36 | 6 |
| LLD135 | 135 | 136 | 9 | 0.1 | 0.07 | 0.09 | 4.88 | 5.41 | 6 |
| LLD135 | 136 | 137 | 12 | 0.08 | 0.11 | 0.58 | 6.88 | 8.07 | 6 |
| LLD135 | 137 | 138 | 10 | 0.03 | 0.04 | 0.05 | 9.04 | 9.47 | 6 |
| LLD136 | 164 | 165 | 7 | 0.26 | 0.08 | 2.30 | 5.08 | 7.60 | 6 |
| LLD136 | 165 | 166 | 30 | 1.5 | 0.43 | 6.39 | 20.09 | 28.09 | 6 |
| LLD136 | 166 | 167 | 35 | 0.58 | 0.53 | 7.67 | 22.50 | 32.04 | 6 |
| LLD136 | 167 | 168 | 11 | 0.23 | 0.10 | 4.35 | 8.59 | 13.13 | 6 |
| LLD136 | 168 | 169 | 7 | 0.16 | 0.01 | 2.93 | 5.67 | 8.54 | 6 |
| LLD136 | 169 | 170 | 4 | 0.24 | 0.10 | 1.07 | 4.77 | 6.19 | 6 |
| LLD136 | 170 | 171 | 4 | 0.11 | 0.15 | 0.17 | 4.43 | 5.18 | 6 |
| LLD136 | 171 | 172 | 1 | 0.15 | 0.11 | 0.09 | 5.20 | 5.68 | 6 |
| LLD136 | 172 | 173 | 3 | 0.13 | 0.08 | 0.04 | 6.13 | 6.51 | 6 |
| LLD136 | 173 | 174 | 16 | 0.23 | 0.23 | 3.34 | 9.39 | 13.57 | 6 |
| LLD136 | 174 | 175 | 8 | 0.13 | 0.20 | 1.40 | 7.41 | 9.53 | 6 |
| LLD136 | 175 | 176 | 1 | 0.03 | 0.10 | 0.02 | 1.90 | 2.28 | 6 |
| LLD136 | 176 | 177 | 1 | 0.05 | 0.02 | 0.01 | 0.97 | 1.06 | 6 |
| LLD136 | 177 | 178 | 5 | 0.12 | 0.06 | 0.09 | 10.95 | 11.35 | 6 |
| LLD136 | 178 | 179 | 4 | 0.06 | 0.02 | 0.13 | 0.84 | 1.12 | 6 |
| LLD136 | 179 | 180 | 5 | 0.07 | 0.01 | 0.11 | 0.29 | 0.56 | 6 |
| LLD136 | 180 | 181 | 4 | 0.05 | 0.00 | 0.04 | 0.20 | 0.34 | 6 |
| LLD136 | 181 | 182 | 4 | 0.05 | 0.00 | 0.02 | 0.41 | 0.55 | 6 |
| LLD136 | 182 | 183 | 6 | 0.05 | 0.04 | 0.95 | 2.08 | 3.23 | 6 |
| LLD136 | 183 | 184 | 4 | 0.07 | 0.02 | 0.73 | 5.60 | 6.43 | 6 |
| LLD136 | 184 | 185 | 5 | 0.06 | 0.02 | 0.20 | 4.40 | 4.78 | 6 |
| LLD136 | 185 | 186 | 1 | 0.02 | 0.00 | 0.11 | 0.35 | 0.47 | 6 |
| LLD136 | 186 | 187 | 2 | 0.04 | 0.00 | 0.01 | 0.41 | 0.47 | 6 |
| LLD136 | 187 | 188 | 3 | 0.05 | 0.01 | 0.00 | 3.84 | 3.94 | 6 |
| LLD136 | 188 | 189 | 2 | 0.08 | 0.01 | 0.00 | 2.56 | 2.64 | 6 |
| LLD137 | 261 | 262 | 1 | 0.005 | 0.20 | 0.00 | 0.02 | 0.71 | 6 |
| LLD137 | 262 | 263 | 5 | 0.005 | 1.68 | 0.02 | 0.08 | 5.77 | 6 |
| LLD137 | 263 | 264 | 1 | 0.005 | 0.16 | 0.00 | 0.02 | 0.56 | 6 |
| LLD137 | 264 | 265 | 1 | 0.005 | 0.04 | 0.00 | 0.01 | 0.15 | 6 |
| LLRC069 | 66 | 67 | 11 | 1.65 | 0.13 | 0.23 | 5.90 | 6.88 | 6 |
| LLRC069 | 67 | 68 | 8 | 0.08 | 0.14 | 0.58 | 4.85 | 6.05 | 6 |
| LLRC069 | 68 | 69 | 16 | 4.82 | 0.10 | 0.28 | 3.20 | 4.42 | 6 |
| LLRC069 | 69 | 70 | 9 | 1.36 | 0.04 | 0.26 | 0.54 | 1.19 | 6 |
| LLRC069 | 70 | 71 | 10 | 0.14 | 0.04 | 0.22 | 0.58 | 1.18 | 6 |
| LLRC069 | 71 | 72 | 5 | 0.17 | 0.04 | 0.22 | 0.95 | 1.42 | 6 |
| LLRC069 | 72 | 73 | 5 | 0.52 | 0.11 | 0.67 | 3.91 | 5.02 | 6 |
| LLRC069 | 73 | 74 | 8 | 0.59 | 0.31 | 0.51 | 4.52 | 6.25 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|------|-------|--------|------------|
| LLRC069 | 74 | 75 | 5 | 0.18 | 0.35 | 0.19 | 10.16 | 11.62 | 6 |
| LLRC069 | 75 | 76 | 3 | 0.08 | 0.07 | 0.09 | 2.00 | 2.38 | 6 |
| LLRC069 | 76 | 77 | 5 | 0.2 | 0.08 | 0.50 | 1.63 | 2.48 | 6 |
| LLRC069 | 77 | 78 | 3 | 0.41 | 0.08 | 0.64 | 3.31 | 4.24 | 6 |
| LLRC069 | 78 | 79 | 4 | 0.1 | 0.02 | 0.51 | 1.94 | 2.56 | 6 |
| LLRC070 | 78 | 79 | 3 | 0.03 | 0.33 | 0.01 | 7.80 | 8.96 | 6 |
| LLRC070 | 79 | 80 | 2 | 0.03 | 0.05 | 0.00 | 0.54 | 0.78 | 6 |
| LLRC070 | 80 | 81 | 3 | 0.15 | 0.43 | 0.01 | 4.80 | 6.31 | 6 |
| LLRC070 | 81 | 82 | 3 | 0.07 | 0.23 | 0.01 | 4.90 | 5.75 | 6 |
| LLRC070 | 82 | 83 | 2 | 0.02 | 0.11 | 0.01 | 2.40 | 2.82 | 6 |
| LLRC070 | 83 | 84 | 1 | 0.03 | 0.04 | 0.01 | 0.68 | 0.84 | 6 |
| LLRC071 | 65 | 66 | 8 | 0.04 | 0.24 | 2.72 | 6.15 | 9.61 | 6 |
| LLRC071 | 66 | 67 | 3 | 0.03 | 0.04 | 0.90 | 4.41 | 5.41 | 6 |
| LLRC071 | 67 | 68 | 2 | 0.06 | 0.08 | 0.50 | 4.19 | 4.95 | 6 |
| LLRC071 | 68 | 69 | 3 | 0.05 | 0.06 | 0.92 | 5.80 | 6.91 | 6 |
| LLRC071 | 69 | 70 | 3 | 0.06 | 0.11 | 0.42 | 3.45 | 4.27 | 6 |
| LLRC072 | 79 | 80 | 3 | 0.01 | 0.20 | 0.07 | 1.20 | 2.00 | 6 |
| LLRC072 | 80 | 81 | 4 | 0.14 | 0.65 | 0.03 | 10.00 | 12.26 | 6 |
| LLRC072 | 81 | 82 | 2 | 0.1 | 0.03 | 0.02 | 0.67 | 0.83 | 6 |
| LLRC072 | 82 | 83 | 2 | -0.01 | 0.06 | 0.02 | 5.70 | 5.96 | 6 |
| LLRC072 | 83 | 84 | 5 | -0.01 | 0.06 | 0.02 | 2.10 | 2.43 | 6 |
| LLRC072 | 84 | 85 | 3 | 0.08 | 0.23 | 0.01 | 2.90 | 3.73 | 6 |
| LLRC072 | 85 | 86 | 2 | 0.04 | 0.06 | 0.03 | 2.30 | 2.56 | 6 |
| LLRC072 | 86 | 87 | 2 | 0.03 | 0.05 | 0.02 | 1.90 | 2.14 | 6 |
| LLRC072 | 87 | 88 | 2 | 0.01 | 0.05 | 0.02 | 0.81 | 1.03 | 6 |
| LLRC072 | 88 | 89 | 2 | 0.03 | 0.07 | 0.03 | 0.19 | 0.50 | 6 |
| LLRC072 | 89 | 90 | 2 | 0.01 | 0.08 | 0.03 | 0.09 | 0.43 | 6 |
| LLRC072 | 90 | 91 | 3 | 0.03 | 0.54 | 0.04 | 0.11 | 2.00 | 6 |
| LLRC074 | 51 | 52 | 3 | 0.33 | 0.24 | 0.27 | 0.07 | 1.19 | 6 |
| LLRC074 | 52 | 53 | 30 | 0.71 | 0.66 | 1.74 | 1.18 | 5.70 | 6 |
| LLRC074 | 53 | 54 | 14 | 0.44 | 0.16 | 2.54 | 7.80 | 10.98 | 6 |
| LLRC074 | 54 | 55 | 12 | 0.62 | 0.34 | 6.02 | 14.60 | 21.48 | 6 |
| LLRC074 | 55 | 56 | 20 | 1.16 | 0.39 | 3.06 | 7.50 | 12.09 | 6 |
| LLRC074 | 56 | 57 | 8 | 0.56 | 0.20 | 0.36 | 9.30 | 10.50 | 6 |
| LLRC074 | 57 | 58 | 3 | 0.56 | 0.17 | 0.06 | 5.50 | 6.21 | 6 |
| LLRC074 | 58 | 59 | 4 | 0.52 | 0.25 | 0.05 | 7.80 | 8.78 | 6 |
| LLRC074 | 59 | 60 | 15 | 0.4 | 0.27 | 0.06 | 7.80 | 9.13 | 6 |
| LLRC074 | 60 | 61 | 15 | 1.39 | 0.41 | 0.07 | 11.50 | 13.37 | 6 |
| LLRC074 | 61 | 62 | 8 | 0.77 | 0.36 | 0.04 | 11.80 | 13.25 | 6 |
| LLRC074 | 62 | 63 | 8 | 0.95 | 0.26 | 0.06 | 7.90 | 9.06 | 6 |
| LLRC074 | 63 | 64 | 4 | 0.78 | 0.25 | 0.04 | 7.40 | 8.41 | 6 |
| LLRC074 | 64 | 65 | 8 | 1.13 | 0.16 | 0.04 | 5.80 | 6.63 | 6 |
| LLRC074 | 65 | 66 | 17 | 1.44 | 0.15 | 0.04 | 6.70 | 7.71 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|-----|--------|--------|------|------|-------|--------|------------|
| LLRC074 | 66 | 67 | 8 | 0.54 | 0.08 | 0.03 | 4.40 | 4.90 | 6 |
| LLRC074 | 67 | 68 | 3 | 0.2 | 0.08 | 0.02 | 6.40 | 6.76 | 6 |
| LLRC074 | 68 | 69 | 6 | 0.27 | 0.07 | 0.10 | 6.20 | 6.68 | 6 |
| LLRC074 | 69 | 70 | 6 | 0.28 | 0.21 | 0.17 | 4.60 | 5.61 | 6 |
| LLRC074 | 70 | 71 | 4 | 0.25 | 0.20 | 0.33 | 10.30 | 11.36 | 6 |
| LLRC074 | 71 | 72 | 6 | 0.22 | 0.49 | 0.10 | 2.80 | 4.66 | 6 |
| LLRC074 | 72 | 73 | 12 | 0.46 | 0.09 | 0.04 | 7.10 | 7.75 | 6 |
| LLRC074 | 73 | 74 | 3 | 0.26 | 0.23 | 0.07 | 8.30 | 9.19 | 6 |
| LLRC074 | 74 | 75 | 7 | 0.26 | 0.27 | 0.24 | 9.50 | 10.79 | 6 |
| LLRC074 | 75 | 76 | 4 | 0.32 | 0.28 | 0.18 | 2.90 | 4.09 | 6 |
| LLRC074 | 76 | 77 | 4 | 0.29 | 0.05 | 0.11 | 3.50 | 3.89 | 6 |
| LLRC074 | 77 | 78 | 4 | 0.22 | 0.10 | 0.35 | 2.90 | 3.66 | 6 |
| LLRC074 | 78 | 79 | 3 | 0.49 | 0.04 | 0.19 | 2.50 | 2.91 | 6 |
| LLRC074 | 79 | 80 | 5 | 0.7 | 0.03 | 0.11 | 2.60 | 2.98 | 6 |
| LLRC074 | 80 | 81 | 2 | 0.36 | 0.13 | 0.07 | 1.00 | 1.55 | 6 |
| LLRC074 | 81 | 82 | 1 | 0.18 | 0.10 | 0.13 | 1.41 | 1.90 | 6 |
| LLRC074 | 82 | 83 | 2 | 0.2 | 0.20 | 0.27 | 1.17 | 2.12 | 6 |
| LLRC076 | 56 | 57 | 3 | -0.01 | 0.02 | 0.13 | 1.04 | 1.28 | 6 |
| LLRC076 | 57 | 58 | 5 | -0.01 | 0.01 | 0.07 | 5.00 | 5.23 | 6 |
| LLRC076 | 58 | 59 | 91 | 0.59 | 0.03 | 0.42 | 3.60 | 6.38 | 6 |
| LLRC076 | 59 | 60 | 29 | 0.48 | 0.05 | 0.65 | 2.20 | 3.68 | 6 |
| LLRC076 | 60 | 61 | 5 | 0.2 | 0.01 | 0.14 | 1.12 | 1.43 | 6 |
| LLRC076 | 61 | 62 | 4 | 0.04 | 0.01 | 0.07 | 1.00 | 1.19 | 6 |
| LLRC076 | 62 | 63 | 3 | 0.06 | 0.01 | 0.03 | 0.22 | 0.36 | 6 |
| LLRC076 | 63 | 64 | 4 | 0.05 | 0.01 | 0.03 | 0.17 | 0.32 | 6 |
| LLRC076 | 64 | 65 | 23 | 1.3 | 0.17 | 2.80 | 5.50 | 9.21 | 6 |
| LLRC076 | 65 | 66 | 18 | 4.77 | 0.20 | 3.47 | 7.70 | 12.17 | 6 |
| LLRC076 | 66 | 67 | 7 | 0.2 | 0.06 | 0.94 | 2.00 | 3.24 | 6 |
| LLRC076 | 67 | 68 | 12 | 0.65 | 0.23 | 2.78 | 4.50 | 8.10 | 6 |
| LLRC076 | 68 | 69 | 9 | 0.1 | 0.10 | 1.51 | 3.00 | 4.90 | 6 |
| LLRC076 | 69 | 70 | 9 | 0.13 | 0.12 | 1.56 | 4.60 | 6.62 | 6 |
| LLRC076 | 70 | 71 | 8 | 0.09 | 0.10 | 1.02 | 3.50 | 4.97 | 6 |
| LLRC076 | 71 | 72 | 7 | 0.12 | 0.21 | 2.36 | 4.30 | 7.29 | 6 |
| LLRC081 | 90 | 91 | 4 | 0.25 | 1.62 | 0.37 | 14.00 | 19.78 | 6 |
| LLRC081 | 91 | 92 | 5 | 0.39 | 0.38 | 0.78 | 8.40 | 10.51 | 6 |
| LLRC081 | 92 | 93 | 4 | 0.24 | 0.30 | 0.30 | 6.50 | 7.87 | 6 |
| LLRC081 | 93 | 94 | 3 | 0.16 | 0.41 | 0.14 | 15.20 | 16.77 | 6 |
| LLRC081 | 94 | 95 | 2 | 0.17 | 0.12 | 0.03 | 13.20 | 13.67 | 6 |
| LLRC081 | 95 | 96 | 1 | 0.05 | 0.06 | 0.03 | 4.70 | 4.97 | 6 |
| LLRC081 | 96 | 97 | 0 | 0.09 | 0.08 | 0.06 | 3.20 | 3.51 | 6 |
| LLRC081 | 97 | 98 | 1 | 0.03 | 0.16 | 0.05 | 6.30 | 6.90 | 6 |
| LLRC081 | 98 | 99 | 1 | -0.01 | 0.06 | 0.01 | 3.40 | 3.62 | 6 |
| LLRC082 | 129 | 130 | 4 | 0.17 | 0.28 | 2.09 | 4.00 | 6.90 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|-----|--------|--------|------|------|-------|--------|------------|
| LLRC082 | 130 | 131 | 3 | 0.14 | 0.25 | 2.43 | 4.80 | 7.89 | 6 |
| LLRC082 | 131 | 132 | 41 | 24.3 | 0.80 | 6.93 | 17.50 | 28.60 | 6 |
| LLRC082 | 132 | 133 | 10 | 1.98 | 0.11 | 1.70 | 4.90 | 7.16 | 6 |
| LLRC082 | 133 | 134 | 18 | 12.2 | 0.40 | 6.06 | 11.70 | 19.52 | 6 |
| LLRC082 | 134 | 135 | 12 | 9.56 | 0.53 | 7.87 | 14.00 | 23.60 | 6 |
| LLRC082 | 135 | 136 | 27 | 4.61 | 0.26 | 5.07 | 10.10 | 16.44 | 6 |
| LLRC082 | 136 | 137 | 10 | 0.33 | 0.26 | 2.48 | 5.50 | 8.84 | 6 |
| LLRC082 | 137 | 138 | 9 | 0.19 | 0.13 | 0.77 | 3.40 | 4.76 | 6 |
| LLRC082 | 138 | 139 | 4 | 0.09 | 0.08 | 0.14 | 2.40 | 2.90 | 6 |
| LLRC082 | 139 | 140 | 7 | 0.43 | 0.07 | 0.62 | 3.10 | 4.08 | 6 |
| LLRC082 | 140 | 141 | 8 | 0.45 | 0.15 | 0.56 | 3.90 | 5.13 | 6 |
| LLRC082 | 141 | 142 | 5 | 0.18 | 0.09 | 0.24 | 4.20 | 4.84 | 6 |
| LLRC082 | 142 | 143 | 6 | 0.09 | 0.06 | 0.23 | 1.08 | 1.64 | 6 |
| LLRC082 | 143 | 144 | 4 | 0.04 | 0.02 | 0.13 | 0.82 | 1.11 | 6 |
| LLRC082 | 144 | 145 | 5 | 0.09 | 0.03 | 0.11 | 4.00 | 4.33 | 6 |
| LLRC082 | 145 | 146 | 3 | 0.06 | 0.02 | 0.09 | 2.30 | 2.54 | 6 |
| LLRC083 | 68 | 69 | 3 | 0.22 | 1.45 | 0.28 | 1.83 | 6.95 | 6 |
| LLRC083 | 69 | 70 | 16 | 0.39 | 1.32 | 3.40 | 1.48 | 9.32 | 6 |
| LLRC083 | 70 | 71 | 14 | 1.21 | 1.69 | 3.38 | 5.90 | 14.93 | 6 |
| LLRC083 | 71 | 72 | 3 | 0.19 | 0.47 | 2.02 | 3.90 | 7.36 | 6 |
| LLRC083 | 72 | 73 | 2 | 0.06 | 0.26 | 0.25 | 0.26 | 1.39 | 6 |
| LLRC083 | 73 | 74 | 1 | 0.1 | 0.19 | 0.17 | 0.14 | 0.97 | 6 |
| LLRC083 | 74 | 75 | 1 | 0.21 | 0.18 | 0.16 | 0.21 | 1.00 | 6 |
| LLRC083 | 75 | 76 | 17 | 0.1 | 0.96 | 0.39 | 0.67 | 4.63 | 6 |
| LLRC083 | 76 | 77 | 7 | 0.04 | 0.90 | 0.15 | 0.39 | 3.67 | 6 |
| LLRC083 | 77 | 78 | 2 | 0.07 | 1.19 | 0.11 | 0.18 | 4.26 | 6 |
| LLRC084 | 65 | 66 | 3 | 0.49 | 0.70 | 0.15 | 5.40 | 7.94 | 6 |
| LLRC084 | 66 | 67 | 1 | 0.31 | 0.27 | 0.06 | 2.40 | 3.40 | 6 |
| LLRC084 | 67 | 68 | 1 | 0.27 | 0.10 | 0.06 | 3.70 | 4.12 | 6 |
| LLRC084 | 68 | 69 | 3 | 0.19 | 0.19 | 0.18 | 2.90 | 3.77 | 6 |
| LLRC084 | 69 | 70 | 1 | 1.02 | 0.90 | 1.05 | 4.90 | 8.89 | 6 |
| LLRC084 | 70 | 71 | 5 | 0.5 | 0.48 | 0.75 | 4.30 | 6.72 | 6 |
| LLRC090 | 95 | 96 | 2 | 0.03 | 0.02 | 0.19 | 0.73 | 1.02 | 6 |
| LLRC090 | 96 | 97 | 1 | 0.04 | 0.03 | 0.20 | 0.79 | 1.10 | 6 |
| LLRC090 | 97 | 98 | 3 | 0.05 | 0.06 | 0.58 | 1.67 | 2.47 | 6 |
| LLRC090 | 98 | 99 | 3 | 0.02 | 0.52 | 0.07 | 0.81 | 2.67 | 6 |
| LLRC090 | 99 | 100 | 2 | 0.02 | 0.06 | 0.03 | 0.14 | 0.42 | 6 |
| LLRC091 | 98 | 99 | 780 | 12.4 | 0.06 | 0.65 | 2.40 | 23.31 | 6 |
| LLRC091 | 99 | 100 | 490 | 1.74 | 0.03 | 0.30 | 1.00 | 13.70 | 6 |
| LLRC091 | 100 | 101 | 153 | 1.11 | 0.03 | 0.57 | 1.09 | 5.59 | 6 |
| LLRC091 | 101 | 102 | 222 | 9.44 | 0.01 | 0.23 | 0.30 | 6.58 | 6 |
| LLRC091 | 102 | 103 | 106 | 6.98 | 0.01 | 0.33 | 0.94 | 4.27 | 6 |
| LLRC091 | 103 | 104 | 23 | 2.2 | 0.03 | 0.52 | 1.12 | 2.37 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|--------|--------|--------|------|------|------|--------|------------|
| LLRC091 | 104 | 105 | 24 | 1.7 | 0.10 | 1.00 | 2.67 | 4.58 | 6 |
| LLRC092 | 109 | 110 | 4 | 0.14 | 0.04 | 0.32 | 0.87 | 1.39 | 6 |
| LLRC092 | 110 | 111 | 5 | 0.09 | 0.01 | 0.31 | 1.00 | 1.45 | 6 |
| LLRC092 | 111 | 112 | 3 | 0.12 | 0.24 | 0.07 | 5.70 | 6.64 | 6 |
| LLRC092 | 112 | 113 | 3 | 0.05 | 0.07 | 0.08 | 3.25 | 3.62 | 6 |
| LLRC092 | 113 | 114 | 4 | 0.07 | 0.01 | 0.03 | 1.66 | 1.83 | 6 |
| LLRC092 | 114 | 115 | 4 | 0.16 | 0.02 | 0.02 | 4.80 | 4.98 | 6 |
| LLRC092 | 115 | 116 | 5 | 0.09 | 0.01 | 0.01 | 1.41 | 1.57 | 6 |
| LLRC092 | 116 | 117 | 6 | 0.12 | 0.10 | 0.29 | 3.21 | 3.96 | 6 |
| LLRC092 | 117 | 118 | 3 | 0.1 | 0.18 | 0.02 | 0.72 | 1.40 | 6 |
| LLRC093 | 112 | 113 | 22 | 1.02 | 0.19 | 0.41 | 5.67 | 7.27 | 6 |
| LLRC093 | 113 | 114 | 72 | 1.11 | 0.07 | 0.22 | 1.13 | 3.42 | 6 |
| LLRC093 | 114 | 115 | 20 | 0.21 | 0.19 | 0.18 | 1.77 | 3.06 | 6 |
| LLRC093 | 115 | 116 | 38 | 0.28 | 0.54 | 0.62 | 6.44 | 9.73 | 6 |
| LLRC093 | 116 | 117 | 47 | 0.42 | 0.44 | 0.56 | 5.48 | 8.63 | 6 |
| LLRC093 | 117 | 118 | 11 | 0.09 | 0.06 | 0.13 | 2.15 | 2.73 | 6 |
| LLRC093 | 118 | 119 | 5 | 0.05 | 0.02 | 0.04 | 1.95 | 2.18 | 6 |
| LLRC093 | 119 | 120 | 4 | 0.03 | 0.01 | 0.02 | 0.88 | 1.04 | 6 |
| LLRC094 | 105 | 106 | 22 | 4.42 | 0.23 | 3.03 | 8.24 | 12.50 | 6 |
| LLRC094 | 106 | 107 | 15 | 0.6 | 0.10 | 0.41 | 1.47 | 2.58 | 6 |
| LLRC094 | 107 | 108 | 47 | 0.23 | 0.02 | 0.11 | 0.37 | 1.72 | 6 |
| LLRC094 | 108 | 109 | 114 | 0.55 | 0.02 | 0.16 | 0.86 | 3.96 | 6 |
| LLRC094 | 109 | 110 | 680 | 0.18 | 0.10 | 0.51 | 0.90 | 18.68 | 6 |
| LLRC094 | 110 | 111 | 54 | 0.08 | 0.02 | 0.59 | 1.25 | 3.21 | 6 |
| LLRC094 | 111 | 112 | 15 | 0.41 | 0.04 | 0.80 | 1.93 | 3.18 | 6 |
| LLRC094 | 112 | 113 | 14 | 0.22 | 0.17 | 0.94 | 9.60 | 11.35 | 6 |
| LLRC094 | 113 | 114 | 6 | 0.09 | 0.03 | 0.07 | 9.12 | 9.43 | 6 |
| LLRC094 | 114 | 115 | 6 | 0.01 | 0.01 | 0.02 | 3.31 | 3.51 | 6 |
| LLRC094 | 115 | 116 | 5 | 0.11 | 0.11 | 0.03 | 9.03 | 9.54 | 6 |
| LLRC094 | 116 | 117 | 4 | 0.07 | 0.22 | 0.03 | 7.52 | 8.37 | 6 |
| LLRC094 | 117 | 118 | 10 | 0.07 | 0.12 | 4.45 | 7.83 | 12.49 | 6 |
| LLRC094 | 118 | 119 | 6 | 0.05 | 0.06 | 0.95 | 5.55 | 6.75 | 6 |
| LLRC094 | 119 | 120 | 4 | 0.04 | 0.04 | 0.07 | 3.94 | 4.22 | 6 |
| LLRC094 | 120 | 121 | 4 | 0.05 | 0.04 | 0.02 | 9.46 | 9.72 | 6 |
| LLRC094 | 121 | 122 | 6 | 0.13 | 0.23 | 0.32 | 4.85 | 6.05 | 6 |
| LLRC094 | 122 | 123 | 3 | 0.05 | 0.03 | 0.05 | 1.48 | 1.69 | 6 |
| LLRC094 | 123 | 124 | 4 | 0.03 | 0.10 | 0.01 | 1.55 | 1.98 | 6 |
| LLRC094 | 124 | 125 | 3 | 0.18 | 0.22 | 0.01 | 2.83 | 3.65 | 6 |
| LLRC094 | 125 | 125.41 | 3 | 0.12 | 0.33 | 0.01 | 5.19 | 6.37 | 6 |
| LLRC095 | 110 | 111 | 2 | 0.01 | 0.05 | 0.02 | 3.76 | 3.98 | 6 |
| LLRC095 | 111 | 112 | 1 | 0.005 | 0.02 | 0.04 | 0.99 | 1.11 | 6 |
| LLRC095 | 112 | 113 | 2 | 0.005 | 0.01 | 0.24 | 0.62 | 0.92 | 6 |
| LLRC095 | 113 | 114 | 1 | 0.005 | 0.01 | 0.33 | 0.75 | 1.10 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|--------|--------|--------|------|------|-------|--------|------------|
| LLRC095 | 114 | 115 | 2 | 0.01 | 0.02 | 0.26 | 0.67 | 1.01 | 6 |
| LLRC095 | 115 | 116 | 2 | 0.12 | 0.01 | 0.11 | 0.56 | 0.76 | 6 |
| LLRC095 | 116 | 117 | 4 | 0.95 | 0.06 | 0.46 | 2.00 | 2.75 | 6 |
| LLRC095 | 117 | 118 | 9 | 0.72 | 0.03 | 0.81 | 1.59 | 2.68 | 6 |
| LLRC095 | 118 | 119 | 5 | 0.4 | 0.05 | 0.67 | 2.08 | 2.98 | 6 |
| LLRC095 | 119 | 120 | 3 | 0.16 | 0.06 | 0.23 | 2.48 | 2.97 | 6 |
| LLRC095 | 120 | 121 | 1 | 0.08 | 0.14 | 0.06 | 0.78 | 1.32 | 6 |
| LLRC095 | 121 | 122 | 1 | 0.07 | 0.07 | 0.03 | 0.63 | 0.92 | 6 |
| LLRC095 | 122 | 123 | 2 | 0.07 | 0.09 | 0.02 | 1.39 | 1.76 | 6 |
| LLRC095 | 123 | 124 | 1 | 0.08 | 0.06 | 0.02 | 0.32 | 0.55 | 6 |
| LLRC095 | 124 | 125 | 2 | 0.09 | 0.04 | 0.01 | 0.21 | 0.40 | 6 |
| LLRC095 | 125 | 125.64 | 1 | 0.09 | 0.14 | 0.04 | 0.50 | 1.03 | 6 |
| LLRC096 | 113 | 114 | 5 | 0.54 | 0.16 | 0.27 | 3.92 | 4.84 | 6 |
| LLRC096 | 114 | 115 | 2 | 0.2 | 0.10 | 0.14 | 2.08 | 2.59 | 6 |
| LLRC096 | 115 | 116 | 3 | 0.25 | 0.11 | 0.14 | 3.28 | 3.86 | 6 |
| LLRC096 | 116 | 117 | 3 | 0.38 | 0.19 | 0.13 | 4.72 | 5.54 | 6 |
| LLRC096 | 117 | 118 | 6 | 0.71 | 0.88 | 2.19 | 11.70 | 16.76 | 6 |
| LLRC096 | 118 | 119 | 4 | 0.67 | 0.57 | 0.47 | 4.88 | 7.32 | 6 |
| LLRC096 | 119 | 120 | 1 | 0.16 | 0.04 | 0.08 | 0.38 | 0.62 | 6 |
| LLRC096 | 120 | 121 | 2 | 0.07 | 0.02 | 0.04 | 1.92 | 2.08 | 6 |
| LLRC096 | 121 | 122 | 2 | 0.09 | 0.02 | 0.04 | 1.84 | 1.99 | 6 |
| LLRC097 | 119 | 120 | 1 | 0.03 | 0.23 | 0.01 | 0.34 | 1.15 | 6 |
| LLRC098 | 62 | 63 | 5 | 0.58 | 0.15 | 0.03 | 1.67 | 2.35 | 6 |
| LLRC098 | 63 | 64 | 3 | 0.08 | 0.01 | 0.01 | 1.59 | 1.70 | 6 |
| LLRC098 | 64 | 65 | 6 | 1.25 | 0.02 | 0.01 | 1.59 | 1.90 | 6 |
| LLRC098 | 65 | 66 | 3 | 0.2 | 0.01 | 0.02 | 0.55 | 0.67 | 6 |
| LLRC098 | 66 | 67 | 4 | 0.13 | 0.32 | 0.04 | 10.00 | 11.18 | 6 |
| LLRC098 | 67 | 68 | 4 | 0.39 | 0.10 | 0.03 | 11.00 | 11.46 | 6 |
| LLRC098 | 68 | 69 | 4 | 0.21 | 0.08 | 0.01 | 4.72 | 5.09 | 6 |
| LLRC098 | 69 | 70 | 3 | 0.21 | 0.05 | 0.01 | 2.96 | 3.21 | 6 |
| LLRC098 | 70 | 71 | 3 | 0.2 | 0.12 | 0.01 | 2.48 | 2.98 | 6 |
| LLRC099 | 125 | 126 | 2 | 0.13 | 0.05 | 0.17 | 0.13 | 0.52 | 6 |
| LLRC099 | 126 | 127 | 1 | 0.04 | 0.07 | 0.30 | 0.06 | 0.60 | 6 |
| LLRC099 | 127 | 128 | 1 | 0.03 | 0.06 | 0.27 | 0.06 | 0.53 | 6 |
| LLRC100 | 148 | 149 | 12 | 7.96 | 0.43 | 0.94 | 0.37 | 3.34 | 6 |
| LLRC100 | 149 | 150 | 2 | 3.87 | 0.13 | 0.06 | 0.06 | 0.79 | 6 |
| LLRC100 | 150 | 151 | 1 | 0.59 | 0.29 | 0.06 | 0.05 | 1.10 | 6 |
| LLRC100 | 151 | 152 | 3 | 0.39 | 1.54 | 0.06 | 0.10 | 5.33 | 6 |
| LLRC100 | 152 | 153 | 21 | 10.3 | 2.07 | 1.59 | 4.96 | 14.26 | 6 |
| LLRC100 | 153 | 154 | 4 | 0.28 | 0.77 | 0.07 | 0.34 | 3.07 | 6 |
| LRC004 | 29 | 30 | 22 | 3.55 | 0.07 | 0.97 | 0.03 | 1.86 | 6 |
| LRC004 | 30 | 31 | 4 | 0.45 | 0.05 | 0.47 | 0.03 | 0.74 | 6 |
| LRC004 | 31 | 32 | 3 | 0.6 | 0.05 | 0.45 | 0.03 | 0.70 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|------|-------|--------|------------|
| LRC004 | 32 | 33 | 2 | 0.3 | 0.06 | 0.56 | 0.03 | 0.79 | 6 |
| LRC004 | 33 | 34 | 5 | 2.45 | 0.19 | 0.82 | 0.03 | 1.64 | 6 |
| LRC005 | 24 | 25 | 12 | 0.55 | 0.20 | 1.01 | 0.04 | 1.94 | 6 |
| LRC005 | 25 | 26 | 44 | 5.95 | 0.77 | 1.13 | 0.04 | 4.99 | 6 |
| LRC005 | 26 | 27 | 28 | 3.5 | 0.44 | 0.58 | 0.04 | 2.89 | 6 |
| LRC005 | 27 | 28 | 40 | 15.4 | 0.99 | 0.98 | 0.04 | 5.96 | 6 |
| LRC005 | 28 | 29 | 48 | 4.7 | 4.20 | 0.86 | 17.90 | 33.97 | 6 |
| LRC005 | 29 | 30 | 40 | 4.1 | 1.50 | 0.60 | 21.20 | 27.90 | 6 |
| LRC005 | 30 | 31 | 18 | 1.1 | 0.71 | 0.81 | 12.40 | 15.98 | 6 |
| LRC005 | 31 | 32 | 23 | 0.3 | 1.01 | 0.78 | 10.90 | 15.53 | 6 |
| LRC005 | 32 | 33 | 7 | 0.15 | 0.11 | 1.16 | 3.08 | 4.67 | 6 |
| LRC005 | 33 | 34 | 13 | 0.8 | 0.15 | 0.09 | 4.17 | 5.11 | 6 |
| LRC005 | 34 | 35 | 17 | 0.3 | 0.14 | 0.97 | 7.80 | 9.58 | 6 |
| LRC005 | 35 | 36 | 9 | 0.4 | 0.10 | 0.95 | 6.12 | 7.55 | 6 |
| LRC005 | 36 | 37 | 16 | 0.25 | 0.27 | 0.95 | 4.85 | 7.01 | 6 |
| LRC005 | 37 | 38 | 11 | 1 | 0.48 | 0.87 | 6.18 | 8.87 | 6 |
| LRC005 | 38 | 39 | 8 | 0.15 | 0.33 | 0.89 | 7.60 | 9.70 | 6 |
| LRC005 | 39 | 40 | 12 | 0.15 | 0.42 | 0.93 | 5.58 | 8.11 | 6 |
| LRC005 | 40 | 41 | 4 | 0.15 | 0.15 | 0.80 | 7.40 | 8.72 | 6 |
| LRC005 | 41 | 42 | 4 | 0.15 | 0.10 | 0.62 | 9.30 | 10.30 | 6 |
| LRC005 | 42 | 43 | 3 | | 0.14 | 0.93 | 2.86 | 4.23 | 6 |
| LRC005 | 43 | 44 | 19 | 4.85 | 0.64 | 0.82 | 13.00 | 16.57 | 6 |
| LRC005 | 44 | 45 | 2 | | 0.04 | 0.34 | 0.69 | 1.18 | 6 |
| LRC005 | 45 | 46 | | | 0.01 | 0.15 | 0.42 | 0.59 | 6 |
| LRC005 | 46 | 47 | 3 | 0.2 | 0.09 | 0.67 | 3.01 | 4.00 | 6 |
| LRC005 | 47 | 48 | | | 0.10 | 0.33 | 2.09 | 2.72 | 6 |
| LRC005 | 48 | 49 | | | 0.04 | 0.08 | 2.09 | 2.29 | 6 |
| LRC005 | 49 | 50 | | | | 0.07 | 2.09 | 2.15 | 6 |
| LRC005 | 50 | 51 | | | 0.01 | 0.05 | 2.09 | 2.17 | 6 |
| LRC005 | 51 | 52 | | | 0.02 | 0.04 | 2.09 | 2.19 | 6 |
| LRC005 | 52 | 53 | | | 0.02 | 0.05 | 2.09 | 2.20 | 6 |
| LRC005 | 53 | 54 | | | 0.03 | 0.02 | 2.09 | 2.21 | 6 |
| LRC005 | 54 | 55 | 2 | | 0.11 | 0.05 | 2.09 | 2.55 | 6 |
| LRC005 | 55 | 56 | 4 | 0.1 | 0.48 | 0.04 | 0.28 | 2.00 | 6 |
| LRC005 | 56 | 57 | 3 | | 0.30 | 0.02 | 0.15 | 1.24 | 6 |
| LRC007 | 27 | 28 | 14 | 0.1 | 0.10 | 0.85 | 0.04 | 1.49 | 6 |
| LRC007 | 28 | 29 | 11 | 0.1 | 0.15 | 0.89 | 0.04 | 1.61 | 6 |
| LRC007 | 29 | 30 | 28 | 0.35 | 0.37 | 0.31 | 0.04 | 2.25 | 6 |
| LRC007 | 30 | 31 | 16 | 0.2 | 0.25 | 0.71 | 0.04 | 1.91 | 6 |
| LRC007 | 31 | 32 | 35 | 0.65 | 0.88 | 0.82 | 0.04 | 4.59 | 6 |
| LRC008 | 20 | 21 | 27 | 7.2 | 0.10 | 3.10 | 0.35 | 4.52 | 6 |
| LRC008 | 21 | 22 | 11 | 0.25 | 0.14 | 1.20 | 0.38 | 2.20 | 6 |
| LRC008 | 22 | 23 | 37 | 0.65 | 0.12 | 2.10 | 0.28 | 3.53 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|------|-------|--------|------------|
| LRC008 | 23 | 24 | 22 | 0.15 | 0.04 | 0.75 | 0.08 | 1.43 | 6 |
| LRC008 | 24 | 25 | 10 | 0.25 | 0.06 | 1.54 | 0.10 | 1.95 | 6 |
| LRC008 | 25 | 26 | 76 | 1.05 | 0.02 | 2.70 | 0.04 | 4.48 | 6 |
| LRC008 | 26 | 27 | 27 | 0.35 | 0.01 | 1.47 | 0.02 | 2.06 | 6 |
| LRC008 | 27 | 28 | 27 | 0.4 | 0.01 | 2.40 | 0.02 | 2.91 | 6 |
| LRC008 | 28 | 29 | 38 | 0.6 | 0.01 | 5.00 | 0.03 | 5.54 | 6 |
| LRC008 | 29 | 30 | 17 | 0.7 | 0.08 | 2.90 | 0.04 | 3.37 | 6 |
| LRC008 | 30 | 31 | 21 | 0.55 | 0.33 | 3.30 | 3.40 | 8.01 | 6 |
| LRC008 | 31 | 32 | 19 | 0.45 | 0.55 | 2.50 | 4.10 | 8.66 | 6 |
| LRC008 | 32 | 33 | 7 | | 0.15 | 0.34 | 4.80 | 5.77 | 6 |
| LRC008 | 33 | 34 | 4 | | 0.02 | 0.07 | 1.47 | 1.69 | 6 |
| LRC008 | 34 | 35 | 2 | | 0.01 | 0.03 | 1.71 | 1.83 | 6 |
| LRC008 | 35 | 36 | 3 | | 0.03 | 0.03 | 3.82 | 4.01 | 6 |
| LRC008 | 36 | 37 | 2 | | 0.09 | 0.03 | 4.61 | 5.00 | 6 |
| LRC008 | 37 | 38 | | | 0.01 | 0.02 | 0.40 | 0.43 | 6 |
| LRC008 | 38 | 39 | | | 0.00 | 0.03 | 0.38 | 0.42 | 6 |
| LRC008 | 39 | 40 | 12 | | 0.11 | 3.55 | 4.14 | 7.99 | 6 |
| LRC008 | 40 | 41 | 17 | 1.2 | 0.15 | 2.62 | 4.80 | 8.12 | 6 |
| LRC008 | 41 | 42 | 5 | | 0.03 | 0.43 | 1.57 | 2.19 | 6 |
| LRC008 | 42 | 43 | 10 | | 0.11 | 2.58 | 2.02 | 4.94 | 6 |
| LRC008 | 43 | 44 | 4 | | 0.03 | 0.05 | 1.08 | 1.31 | 6 |
| LRC008 | 44 | 45 | 4 | | 0.05 | 0.03 | 0.64 | 0.94 | 6 |
| LRC008 | 45 | 46 | 4 | | 0.10 | 0.03 | 1.84 | 2.30 | 6 |
| LRC008 | 46 | 47 | 10 | | 0.10 | 0.43 | 2.49 | 3.44 | 6 |
| LRC008 | 47 | 48 | 4 | | 0.16 | 0.02 | 1.86 | 2.52 | 6 |
| LRC008 | 48 | 49 | 4 | | 0.20 | 0.02 | 2.43 | 3.20 | 6 |
| LRC010 | 23 | 24 | 36 | 0.15 | 0.16 | 4.30 | 0.10 | 5.39 | 6 |
| LRC010 | 24 | 25 | 13 | 0.15 | 0.08 | 1.74 | 0.08 | 2.24 | 6 |
| LRC010 | 25 | 26 | 35 | 0.95 | 0.02 | 1.20 | 0.02 | 2.11 | 6 |
| LRC010 | 26 | 27 | 24 | 0.45 | 0.01 | 1.71 | 0.01 | 2.21 | 6 |
| LRC027 | 18 | 19 | 10 | 0.1 | 0.37 | 0.35 | 0.44 | 2.23 | 6 |
| LRC027 | 19 | 20 | 2 | | 0.14 | 0.08 | 0.15 | 0.72 | 6 |
| LRC028 | 32 | 33 | 12 | 0.3 | 0.81 | 3.60 | 9.28 | 15.51 | 6 |
| LRC028 | 33 | 34 | 2 | 0.05 | 0.05 | 0.01 | 0.09 | 0.32 | 6 |
| LRC029 | 33 | 34 | 22 | | 4.10 | 4.20 | 37.40 | 55.26 | 6 |
| LRC029 | 34 | 35 | 22 | 0.1 | 0.87 | 6.10 | 21.10 | 30.02 | 6 |
| LRC029 | 35 | 36 | 9 | | 1.85 | 2.20 | 13.70 | 22.01 | 6 |
| LRC029 | 36 | 37 | 2 | 0.05 | 0.02 | 0.10 | 0.12 | 0.33 | 6 |
| LRC029 | 37 | 38 | 3 | 0.05 | 0.01 | 0.16 | 0.02 | 0.28 | 6 |
| LRC029 | 38 | 39 | 8 | 0.05 | 0.02 | 0.29 | 0.02 | 0.56 | 6 |
| LRC029 | 39 | 40 | 9 | 0.05 | 1.40 | 0.57 | 0.20 | 5.56 | 6 |
| LRC029 | 40 | 41 | 14 | 0.1 | 1.20 | 0.25 | 0.21 | 4.75 | 6 |
| LRC029 | 41 | 42 | 12 | 0.1 | 0.41 | 0.24 | 0.07 | 1.94 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|------|-------|--------|------------|
| LRC029 | 42 | 43 | 5 | 0.1 | 0.49 | 0.16 | 0.07 | 1.96 | 6 |
| LRC031 | 19 | 20 | 3 | 1 | 0.28 | 1.33 | 0.04 | 2.29 | 6 |
| LRC031 | 20 | 21 | 3 | 0.3 | 1.94 | 1.03 | 0.10 | 7.52 | 6 |
| LRC031 | 21 | 22 | 4 | 0.5 | 1.96 | 0.30 | 0.11 | 6.98 | 6 |
| LRC031 | 22 | 23 | 3 | 0.45 | 0.62 | 0.32 | 0.06 | 2.49 | 6 |
| LRC032 | 49 | 50 | 4 | 0.8 | 0.21 | 0.13 | 0.09 | 1.04 | 6 |
| LRC032 | 50 | 51 | 13 | 0.15 | 0.27 | 2.06 | 0.43 | 3.51 | 6 |
| LRC032 | 51 | 52 | 3 | 0.4 | 0.14 | 0.48 | 0.04 | 1.03 | 6 |
| LRC033 | 8 | 9 | 2 | 0.85 | 0.10 | 0.68 | 0.53 | 1.57 | 6 |
| LRC033 | 9 | 10 | 4 | 0.4 | 0.06 | 0.70 | 0.23 | 1.19 | 6 |
| LRC033 | 10 | 11 | 3 | 0.15 | 0.05 | 0.52 | 0.20 | 0.91 | 6 |
| LRC033 | 11 | 12 | 2 | 0.1 | 0.05 | 0.56 | 0.09 | 0.81 | 6 |
| LRC033 | 12 | 13 | 6 | 0.05 | 0.05 | 0.48 | 0.09 | 0.83 | 6 |
| LRC033 | 13 | 14 | | 0.05 | 0.04 | 0.38 | 0.07 | 0.54 | 6 |
| LRC033 | 14 | 15 | | 0.15 | 0.03 | 0.48 | 0.05 | 0.59 | 6 |
| LRC033 | 15 | 16 | 5 | 0.2 | 0.01 | 0.18 | 0.02 | 0.35 | 6 |
| LRC033 | 16 | 17 | 11 | 0.4 | 0.01 | 0.46 | 0.02 | 0.76 | 6 |
| LRC034 | 15 | 16 | 66 | 0.85 | 0.09 | 0.53 | 0.05 | 2.52 | 6 |
| LRC034 | 16 | 17 | 90 | 1 | 0.14 | 1.68 | 0.06 | 4.32 | 6 |
| LRC034 | 17 | 18 | 213 | 1.9 | 0.18 | 0.86 | 0.09 | 6.89 | 6 |
| LRC034 | 18 | 19 | 23 | 1.35 | 0.18 | 0.85 | 0.08 | 2.07 | 6 |
| LRC035 | 30 | 31 | 2 | 0.25 | 0.02 | 0.20 | 0.14 | 0.46 | 6 |
| LRC035 | 31 | 32 | 8 | 0.2 | 0.00 | 0.13 | 0.04 | 0.38 | 6 |
| LRC035 | 32 | 33 | 38 | 0.4 | 0.21 | 2.40 | 2.70 | 6.52 | 6 |
| LRC035 | 33 | 34 | 308 | 0.4 | 1.40 | 5.70 | 20.10 | 37.57 | 6 |
| LRC035 | 34 | 35 | 238 | 12.7 | 0.16 | 2.90 | 7.80 | 17.53 | 6 |
| LRC035 | 35 | 36 | 331 | 6.1 | 0.22 | 5.90 | 15.70 | 30.32 | 6 |
| LRC035 | 36 | 37 | 18 | 6.65 | 0.06 | 1.02 | 2.70 | 4.58 | 6 |
| LRC035 | 37 | 38 | 50 | 1.7 | 0.06 | 0.98 | 3.08 | 5.49 | 6 |
| LRC035 | 38 | 39 | 15 | 0.95 | 0.03 | 0.38 | 0.93 | 1.80 | 6 |
| LRC035 | 39 | 40 | 23 | 1.55 | 0.09 | 1.32 | 3.10 | 5.23 | 6 |
| LRC035 | 40 | 41 | 25 | 0.6 | 0.10 | 1.25 | 3.00 | 5.11 | 6 |
| LRC035 | 41 | 42 | 10 | 0.25 | 0.04 | 0.41 | 1.42 | 2.17 | 6 |
| LRC036 | 37 | 38 | 12 | 0.2 | 0.01 | 0.09 | 0.56 | 0.97 | 6 |
| LRC036 | 38 | 39 | 138 | 1.25 | 0.06 | 0.32 | 1.05 | 5.05 | 6 |
| LRC036 | 39 | 40 | 81 | 1.3 | 0.01 | 0.19 | 0.77 | 3.05 | 6 |
| LRC036 | 40 | 41 | 185 | 2.15 | 0.01 | 0.20 | 0.77 | 5.70 | 6 |
| LRC036 | 41 | 42 | 12 | 0.85 | 0.02 | 0.12 | 0.33 | 0.85 | 6 |
| LRC036 | 42 | 43 | 160 | 5 | 0.13 | 1.73 | 3.67 | 9.89 | 6 |
| LRC036 | 43 | 44 | 84 | 1.1 | 0.13 | 0.16 | 3.32 | 6.05 | 6 |
| LRC036 | 44 | 45 | 192 | 1.55 | 0.02 | 0.55 | 1.03 | 6.48 | 6 |
| LRC036 | 45 | 46 | 119 | 1.25 | 0.03 | 0.10 | 0.27 | 3.48 | 6 |
| LRC036 | 46 | 47 | 185 | 1.4 | 0.02 | 0.11 | 0.21 | 5.05 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|------|------|--------|------------|
| LRC036 | 47 | 48 | 14 | 0.15 | 0.01 | 0.02 | 0.04 | 0.43 | 6 |
| LRC036 | 48 | 49 | 6 | 0.1 | 0.00 | 0.01 | 0.03 | 0.20 | 6 |
| LRC036 | 49 | 50 | 10 | 0.15 | 0.01 | 0.01 | 0.03 | 0.31 | 6 |
| LRC036 | 50 | 51 | 14 | 0.15 | 0.01 | 0.02 | 0.04 | 0.46 | 6 |
| LRC036 | 51 | 52 | 185 | 0.4 | 0.01 | 0.17 | 0.29 | 5.12 | 6 |
| LRC036 | 52 | 53 | 120 | 0.2 | 0.02 | 0.13 | 0.24 | 3.42 | 6 |
| LRC036 | 53 | 54 | 70 | 0.2 | 0.03 | 0.04 | 0.04 | 1.94 | 6 |
| LRC036 | 54 | 55 | 162 | 2.9 | 0.05 | 0.52 | 1.02 | 5.84 | 6 |
| LRC036 | 55 | 56 | 164 | 3.2 | 0.14 | 1.87 | 3.92 | 10.34 | 6 |
| LRC036 | 56 | 57 | 169 | 1.6 | 0.13 | 2.44 | 5.34 | 12.28 | 6 |
| LRC036 | 57 | 58 | 43 | 0.4 | 0.14 | 0.95 | 2.18 | 4.58 | 6 |
| LRC036 | 58 | 59 | 12 | 0.2 | 0.01 | 0.22 | 0.40 | 0.93 | 6 |
| LRC036 | 59 | 60 | 11 | 0.15 | 0.01 | 0.31 | 0.26 | 0.85 | 6 |
| LRC036 | 60 | 61 | 11 | 0.15 | 0.04 | 0.67 | 1.31 | 2.33 | 6 |
| LRC036 | 61 | 62 | 21 | 0.15 | 0.09 | 2.54 | 4.20 | 7.32 | 6 |
| LRC036 | 62 | 63 | 9 | 0.4 | 0.02 | 1.10 | 2.28 | 3.56 | 6 |
| LRC036 | 63 | 64 | 5 | 0.15 | 0.01 | 0.40 | 0.93 | 1.45 | 6 |
| LRC036 | 64 | 65 | 4 | 0.15 | 0.00 | 0.05 | 0.59 | 0.76 | 6 |
| LRC036 | 65 | 66 | 3 | 0.15 | 0.01 | 0.04 | 1.04 | 1.20 | 6 |
| LRC036 | 66 | 67 | 3 | 0.15 | 0.09 | 0.03 | 1.30 | 1.71 | 6 |
| LRC036 | 67 | 68 | 10 | 0.4 | 0.43 | 1.93 | 7.20 | 10.63 | 6 |
| LRC036 | 68 | 69 | 10 | 0.3 | 0.29 | 3.20 | 5.70 | 9.80 | 6 |
| LRC036 | 69 | 70 | 7 | 0.4 | 0.14 | 1.57 | 2.53 | 4.59 | 6 |
| LRC036 | 70 | 71 | 7 | 0.4 | 0.14 | 1.97 | 3.60 | 6.02 | 6 |
| LRC036 | 71 | 72 | 10 | 0.3 | 0.27 | 3.20 | 5.70 | 9.74 | 6 |
| LRC036 | 72 | 73 | 8 | 0.2 | 0.09 | 0.76 | 1.62 | 2.79 | 6 |
| LRC036 | 73 | 74 | 6 | 0.2 | 0.26 | 0.08 | 0.51 | 1.60 | 6 |
| LRC037 | 49 | 50 | 14 | 0.25 | 0.00 | 0.26 | 1.47 | 2.08 | 6 |
| LRC037 | 50 | 51 | 14 | 0.3 | 0.01 | 0.37 | 1.42 | 2.13 | 6 |
| LRC037 | 51 | 52 | 36 | 0.35 | 0.01 | 0.42 | 1.89 | 3.21 | 6 |
| LRC037 | 52 | 53 | 21 | 0.35 | 0.01 | 0.71 | 1.75 | 2.95 | 6 |
| LRC037 | 53 | 54 | 15 | 0.15 | 0.01 | 1.09 | 2.11 | 3.49 | 6 |
| LRC037 | 54 | 55 | 18 | 0.25 | 0.01 | 1.38 | 4.52 | 6.24 | 6 |
| LRC037 | 55 | 56 | 4 | 0.2 | 0.01 | 0.14 | 1.34 | 1.59 | 6 |
| LRC037 | 56 | 57 | 8 | 0.35 | 0.24 | 0.86 | 4.29 | 6.07 | 6 |
| LRC037 | 57 | 58 | 5 | 0.2 | 0.04 | 0.33 | 1.37 | 1.93 | 6 |
| LRC038 | 36 | 37 | 6 | 0.25 | 0.05 | 1.53 | 1.32 | 3.03 | 6 |
| LRC038 | 37 | 38 | 6 | 0.2 | 0.05 | 0.86 | 1.54 | 2.63 | 6 |
| LRC038 | 38 | 39 | 9 | 0.15 | 0.11 | 0.25 | 1.43 | 2.25 | 6 |
| LRC038 | 39 | 40 | 68 | 2.8 | 0.23 | 3.23 | 7.37 | 12.88 | 6 |
| LRC038 | 40 | 41 | 142 | 1 | 0.08 | 1.57 | 3.83 | 9.10 | 6 |
| LRC038 | 41 | 42 | 8 | 0.55 | 0.01 | 0.12 | 0.28 | 0.65 | 6 |
| LRC038 | 42 | 43 | 21 | 0.55 | 0.03 | 1.09 | 2.36 | 3.99 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|------|-------|--------|------------|
| LRC038 | 43 | 44 | 39 | 0.35 | 0.42 | 2.63 | 5.60 | 10.35 | 6 |
| LRC038 | 44 | 45 | 4 | 0.15 | 0.01 | 0.20 | 1.22 | 1.55 | 6 |
| LRC038 | 45 | 46 | 5 | 0.4 | 0.01 | 0.09 | 0.43 | 0.68 | 6 |
| LRC038 | 46 | 47 | 2 | 0.3 | 0.00 | 0.03 | 0.05 | 0.16 | 6 |
| LRC038 | 47 | 48 | 3 | 0.3 | 0.01 | 0.06 | 0.07 | 0.24 | 6 |
| LRC038 | 48 | 49 | 12 | 0.3 | 0.05 | 1.87 | 2.30 | 4.46 | 6 |
| LRC038 | 49 | 50 | 29 | 0.55 | 0.23 | 2.93 | 6.42 | 10.57 | 6 |
| LRC038 | 50 | 51 | 22 | 0.2 | 0.24 | 2.61 | 4.85 | 8.55 | 6 |
| LRC038 | 51 | 52 | 13 | 0.2 | 0.15 | 1.19 | 2.08 | 3.99 | 6 |
| LRC038 | 52 | 53 | 9 | 0.3 | 0.07 | 0.86 | 1.72 | 2.95 | 6 |
| LRC038 | 53 | 54 | 37 | 1.05 | 0.12 | 4.41 | 11.02 | 16.37 | 6 |
| LRC038 | 54 | 55 | 37 | 0.7 | 0.41 | 4.78 | 7.98 | 14.60 | 6 |
| LRC038 | 55 | 56 | 23 | 0.2 | 0.44 | 3.07 | 4.10 | 8.90 | 6 |
| LRC038 | 56 | 57 | 13 | 0.3 | 0.51 | 1.89 | 2.57 | 6.29 | 6 |
| LRC038 | 57 | 58 | 4 | 0.1 | 0.05 | 0.83 | 0.60 | 1.62 | 6 |
| LRC038 | 58 | 59 | 8 | 0.2 | 1.19 | 1.43 | | 5.42 | 6 |
| LRC038 | 59 | 60 | 4 | 0.1 | 0.04 | 0.16 | 0.66 | 1.03 | 6 |
| LRC038 | 60 | 61 | 4 | 0.1 | 0.04 | 0.16 | 0.66 | 1.03 | 6 |
| LRC038 | 61 | 62 | 13 | 0.3 | 0.22 | 0.66 | 5.80 | 7.46 | 6 |
| LRC038 | 62 | 63 | 20 | 0.8 | 0.42 | 2.50 | 7.30 | 11.48 | 6 |
| LRC038 | 63 | 64 | 13 | 1.65 | 0.57 | 2.20 | 6.10 | 10.37 | 6 |
| LRC038 | 64 | 65 | 4 | 0.3 | 0.33 | 0.17 | 4.20 | 5.56 | 6 |
| LRC038 | 65 | 66 | 7 | 0.2 | 0.22 | 1.83 | 4.40 | 6.96 | 6 |
| LRC038 | 66 | 67 | 9 | 0.25 | 0.06 | 3.60 | 6.40 | 10.08 | 6 |
| LRC038 | 67 | 68 | 8 | 0.2 | 0.15 | 2.50 | 5.50 | 8.47 | 6 |
| LRC038 | 68 | 69 | 3 | 0.2 | 0.06 | 0.47 | 1.23 | 1.93 | 6 |
| LRC038 | 69 | 70 | 2 | 0.25 | 0.10 | 0.65 | 2.60 | 3.57 | 6 |
| LRC038 | 70 | 71 | 3 | 0.15 | 0.09 | 0.59 | 2.40 | 3.31 | 6 |
| LRC038 | 71 | 72 | 2 | 0.15 | 0.01 | 0.05 | 0.75 | 0.88 | 6 |
| LRC038 | 72 | 73 | 14 | 0.3 | 0.06 | 0.90 | 5.00 | 6.36 | 6 |
| LRC038 | 73 | 74 | 52 | 2.5 | 0.19 | 3.90 | 6.80 | 12.35 | 6 |
| LRC038 | 74 | 75 | 9 | 0.15 | 0.08 | 0.83 | 1.33 | 2.58 | 6 |
| LRC038 | 75 | 76 | 8 | 0.1 | 0.20 | 2.20 | 4.80 | 7.63 | 6 |
| LRC038 | 76 | 77 | 6 | 0.15 | 0.11 | 2.70 | 5.20 | 8.15 | 6 |
| LRC038 | 77 | 78 | 3 | 0.15 | 0.03 | 2.20 | 2.70 | 4.85 | 6 |
| LRC038 | 78 | 79 | 1 | 0.15 | 0.02 | 0.82 | 2.60 | 3.44 | 6 |
| LRC038 | 79 | 80 | 3 | 0.25 | 0.04 | 1.31 | 3.20 | 4.60 | 6 |
| LRC038 | 80 | 81 | 4 | 0.15 | 0.02 | 1.03 | 2.60 | 3.70 | 6 |
| LRC038 | 81 | 82 | 5 | 0.45 | 0.05 | 1.13 | 2.60 | 3.91 | 6 |
| LRC038 | 82 | 83 | 3 | 0.15 | 0.06 | 0.59 | 1.85 | 2.65 | 6 |
| LRC038 | 83 | 84 | 9 | 0.25 | 0.18 | 2.30 | 6.20 | 9.10 | 6 |
| LRC038 | 84 | 85 | 3 | 0.1 | 0.03 | 0.29 | 1.24 | 1.69 | 6 |
| LRC038 | 85 | 86 | 2 | 0.15 | 0.20 | 0.22 | 4.70 | 5.60 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|------|------|--------|------------|
| LRC038 | 86 | 87 | 2 | 0.2 | 0.17 | 0.08 | 2.30 | 2.98 | 6 |
| LRC039 | 58 | 59 | | 0.2 | 0.00 | 0.01 | 1.50 | 1.53 | 6 |
| LRC039 | 59 | 60 | 19 | 0.15 | 0.10 | 0.33 | 7.60 | 8.71 | 6 |
| LRC039 | 60 | 61 | 14 | 0.3 | 0.02 | 0.38 | 2.00 | 2.77 | 6 |
| LRC039 | 61 | 62 | 19 | 0.6 | 0.03 | 0.39 | 1.94 | 2.89 | 6 |
| LRC039 | 62 | 63 | 46 | 1.35 | 0.13 | 1.78 | 5.80 | 9.03 | 6 |
| LRC039 | 63 | 64 | 18 | 0.55 | 0.06 | 0.63 | 1.63 | 2.87 | 6 |
| LRC039 | 64 | 65 | 7 | 0.35 | 0.04 | 0.28 | 0.86 | 1.42 | 6 |
| LRC039 | 65 | 66 | | | | | | 0.00 | 6 |
| LRC039 | 66 | 67 | 8 | 0.3 | 0.25 | 2.03 | 6.40 | 9.27 | 6 |
| LRC039 | 67 | 68 | 14 | 0.2 | 0.27 | 2.25 | 6.80 | 10.08 | 6 |
| LRC039 | 68 | 69 | 10 | 0.1 | 0.23 | 4.30 | 8.00 | 12.88 | 6 |
| LRC039 | 69 | 70 | 4 | 0.1 | 0.05 | 1.21 | 3.00 | 4.36 | 6 |
| LRC039 | 70 | 71 | 6 | 0.15 | 0.04 | 0.58 | 1.80 | 2.60 | 6 |
| LRC039 | 71 | 72 | 6 | 0.2 | 0.03 | 0.13 | 0.27 | 0.65 | 6 |
| LRC039 | 72 | 73 | 6 | 0.1 | 0.02 | 1.00 | 0.71 | 1.83 | 6 |
| LRC039 | 73 | 74 | 4 | 0.4 | 0.02 | 0.02 | 0.47 | 0.68 | 6 |
| LRC039 | 74 | 75 | 6 | 0.05 | 0.10 | 3.70 | 2.10 | 5.90 | 6 |
| LRC040 | 41 | 42 | 17 | 7.4 | 0.26 | 1.89 | 4.60 | 7.95 | 6 |
| LRC040 | 42 | 43 | 17 | 1.1 | 0.07 | 1.32 | 2.20 | 4.09 | 6 |
| LRC040 | 43 | 44 | 8 | 0.85 | 0.10 | 1.00 | 1.63 | 3.11 | 6 |
| LRC040 | 44 | 45 | 6 | 2.8 | 0.19 | 1.21 | 2.50 | 4.49 | 6 |
| LRC040 | 45 | 46 | 6 | 1.05 | 0.06 | 1.65 | 2.40 | 4.27 | 6 |
| LRC040 | 46 | 47 | 111 | 10.6 | 0.14 | 1.89 | 4.60 | 10.06 | 6 |
| LRC040 | 47 | 48 | 12 | 0.7 | 0.27 | 2.00 | 5.90 | 8.93 | 6 |
| LRC040 | 48 | 49 | 9 | 0.3 | 0.26 | 2.10 | 5.30 | 8.29 | 6 |
| LRC040 | 49 | 50 | 4 | 0.15 | 0.02 | 0.04 | 2.50 | 2.70 | 6 |
| LRC040 | 50 | 51 | 6 | 0.15 | 0.06 | 0.04 | 3.70 | 4.09 | 6 |
| LRC040 | 51 | 52 | 5 | 0.2 | 0.15 | 0.04 | 5.80 | 6.47 | 6 |
| LRC040 | 52 | 53 | 4 | 0.2 | 0.26 | 0.02 | 6.40 | 7.39 | 6 |
| LRC040 | 53 | 54 | 3 | 0.15 | 0.09 | 0.02 | 1.66 | 2.04 | 6 |
| LRC040 | 54 | 55 | 5 | 0.15 | 0.23 | 0.04 | 2.40 | 3.32 | 6 |
| LRC040 | 55 | 56 | 2 | | 0.09 | 0.04 | 1.17 | 1.55 | 6 |
| LRC040 | 56 | 57 | 4 | | 0.16 | 0.59 | 2.50 | 3.66 | 6 |
| LRC040 | 57 | 58 | 10 | 0.15 | 0.61 | 3.60 | 8.20 | 13.71 | 6 |
| LRC040 | 58 | 59 | 16 | 0.2 | 0.65 | 5.90 | 9.10 | 16.97 | 6 |
| LRC040 | 59 | 60 | 3 | | 0.04 | 0.68 | 1.50 | 2.33 | 6 |
| LRC040 | 60 | 61 | 3 | 0.05 | 0.01 | 0.87 | 0.84 | 1.72 | 6 |
| LRC040 | 61 | 62 | 3 | | 0.02 | 2.30 | 2.70 | 4.92 | 6 |
| LRC040 | 62 | 63 | 2 | | 0.45 | 0.39 | 0.00 | 1.89 | 6 |
| LRC040 | 63 | 64 | 1 | | 0.78 | 0.24 | 0.00 | 2.82 | 6 |
| LRC040 | 64 | 65 | 2 | | 0.09 | 0.04 | | 0.38 | 6 |
| LRC040 | 65 | 66 | 2 | 0.15 | 0.29 | 0.02 | 0.03 | 1.06 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|-------|-------|--------|------------|
| LRC040 | 66 | 67 | 5 | 0.55 | 3.00 | 1.17 | 0.13 | 11.24 | 6 |
| LRC040 | 67 | 68 | 1 | 0.1 | 0.29 | 1.36 | 0.01 | 2.22 | 6 |
| LRC041 | 78 | 79 | 8 | 0.65 | 0.06 | 0.44 | 1.09 | 1.92 | 6 |
| LRC041 | 79 | 80 | 8 | 0.7 | 0.05 | 6.50 | 1.81 | 8.05 | 6 |
| LRC042 | 44 | 45 | 2 | 0.05 | 1.40 | 0.12 | 0.01 | 4.79 | 6 |
| LRC042 | 45 | 46 | 1 | 0.1 | 1.35 | 0.12 | 0.00 | 4.60 | 6 |
| LRC042 | 46 | 47 | 42 | 1.05 | 0.31 | 1.25 | 0.10 | 3.35 | 6 |
| LRC042 | 47 | 48 | 24 | 1.75 | 0.27 | 0.59 | 0.03 | 2.14 | 6 |
| LRC042 | 48 | 49 | 12 | 0.55 | 1.20 | 0.07 | 0.01 | 4.36 | 6 |
| LRC042 | 49 | 50 | 8 | 0.3 | 0.01 | 0.02 | 0.21 | 0.47 | 6 |
| LRC042 | 50 | 51 | 4 | 0.2 | 0.01 | 0.02 | 0.29 | 0.43 | 6 |
| LRC042 | 51 | 52 | 4 | 0.25 | 1.23 | 0.36 | 0.01 | 4.50 | 6 |
| LRC042 | 52 | 53 | 2 | 0.1 | 0.10 | 1.05 | 0.00 | 1.33 | 6 |
| LRC042 | 53 | 54 | 1 | 0.1 | 0.03 | 0.51 | 0.00 | 0.59 | 6 |
| LRC042 | 54 | 55 | 4 | 0.1 | 0.20 | 1.09 | 0.01 | 1.74 | 6 |
| LRC042 | 55 | 56 | 37 | 0.5 | 0.50 | 1.39 | 0.04 | 3.89 | 6 |
| LRC042 | 56 | 57 | 114 | 0.4 | 0.26 | 0.54 | 0.04 | 4.25 | 6 |
| LRC042 | 57 | 58 | 17 | 0.95 | 0.63 | 1.41 | 0.05 | 3.87 | 6 |
| LRC042 | 58 | 59 | 11 | 0.85 | 1.14 | 1.93 | 0.06 | 5.87 | 6 |
| LRC042 | 59 | 60 | 16 | 0.6 | 0.24 | 27.10 | 3.90 | 29.51 | 6 |
| LRC042 | 60 | 61 | 10 | 0.65 | 0.16 | 5.40 | 0.28 | 5.93 | 6 |
| LRC042 | 61 | 62 | 7 | 0.3 | 0.09 | 4.60 | 0.16 | 4.77 | 6 |
| LRC042 | 62 | 63 | 5 | 0.15 | 0.68 | 3.70 | 0.24 | 5.95 | 6 |
| LRC042 | 63 | 64 | 6 | 0.15 | 0.29 | 0.50 | 0.50 | 2.06 | 6 |
| LRC042 | 64 | 65 | 5 | 0.1 | 0.04 | 1.31 | 0.05 | 1.48 | 6 |
| LRC042 | 65 | 66 | 2 | | 0.10 | 1.21 | 0.02 | 1.50 | 6 |
| LRC042 | 66 | 67 | 2 | 0.05 | 1.30 | 1.39 | 0.05 | 5.64 | 6 |
| LRC042 | 67 | 68 | 3 | 0.05 | 1.07 | 0.28 | 0.14 | 4.00 | 6 |
| LRC042 | 68 | 69 | 2 | 0.05 | 0.12 | 2.50 | 0.17 | 2.88 | 6 |
| LRC042 | 69 | 70 | 6 | 0.1 | 0.20 | 13.50 | 4.00 | 16.97 | 6 |
| LRC042 | 70 | 71 | 4 | 0.15 | 0.02 | 0.25 | 1.84 | 2.25 | 6 |
| LRC042 | 71 | 72 | 2 | | 0.11 | 2.60 | 0.02 | 2.76 | 6 |
| LRC043 | 78 | 79 | 24 | 0.15 | 0.05 | 0.87 | 2.70 | 4.26 | 6 |
| LRC043 | 79 | 80 | 129 | 4.25 | 0.24 | 2.99 | 6.57 | 13.49 | 6 |
| LRC044 | 7 | 8 | 2 | 0.4 | 0.19 | 0.71 | 0.71 | 2.06 | 6 |
| LRC044 | 8 | 9 | 2 | 1.5 | 0.29 | 0.99 | 0.99 | 2.96 | 6 |
| LRC044 | 9 | 10 | 9 | 2.7 | 0.11 | 0.91 | 0.41 | 1.96 | 6 |
| LRC044 | 10 | 11 | 4 | 1.25 | 0.03 | 0.31 | 0.95 | 1.49 | 6 |
| LRC045 | 67 | 68 | 5 | 0.15 | 1.76 | 0.92 | 0.13 | 6.89 | 6 |
| LRC045 | 68 | 69 | 8 | 0.3 | 0.10 | 1.79 | 3.81 | 5.97 | 6 |
| LRC045 | 69 | 70 | 16 | 0.1 | 4.70 | 1.42 | 0.10 | 17.30 | 6 |
| LRC045 | 70 | 71 | 2 | 1.15 | 0.73 | 0.77 | 17.90 | 21.11 | 6 |
| LRC045 | 71 | 72 | 69 | 2.3 | 0.48 | 2.33 | 5.24 | 10.76 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|-------|------|--------|------------|
| LRC045 | 72 | 73 | 27 | 0.5 | 0.10 | 0.53 | 1.21 | 2.71 | 6 |
| LRC045 | 73 | 74 | 24 | 1.55 | 0.13 | 0.23 | 2.90 | 4.20 | 6 |
| LRC045 | 74 | 75 | 13 | 0.9 | 0.04 | 0.67 | 1.38 | 2.49 | 6 |
| LRC045 | 75 | 76 | 15 | 2.1 | 0.04 | 0.37 | 0.95 | 1.90 | 6 |
| LRC045 | 76 | 77 | 13 | 0.9 | 0.06 | 0.58 | 1.57 | 2.67 | 6 |
| LRC045 | 77 | 78 | 6 | 0.35 | 0.03 | 0.21 | 1.05 | 1.49 | 6 |
| LRC045 | 78 | 79 | 16 | 0.15 | 2.60 | 2.70 | 0.21 | 11.63 | 6 |
| LRC045 | 79 | 80 | 9 | 0.25 | 0.20 | 1.97 | 4.06 | 6.74 | 6 |
| LRC045 | 80 | 81 | 7 | 0.35 | 0.40 | 1.32 | 6.21 | 8.91 | 6 |
| LRC045 | 81 | 82 | 7 | 0.15 | 0.14 | 1.15 | 2.40 | 4.09 | 6 |
| LRC045 | 82 | 83 | 13 | 0.2 | 0.48 | 3.71 | 6.96 | 12.22 | 6 |
| LRC045 | 83 | 84 | 4 | 0.75 | 2.00 | 0.57 | 0.10 | 7.35 | 6 |
| LRC045 | 84 | 85 | 6 | 0.2 | 0.33 | 0.78 | 1.70 | 3.65 | 6 |
| LRC045 | 85 | 86 | 4 | 0.15 | 0.12 | 0.83 | 1.48 | 2.73 | 6 |
| LRC045 | 86 | 87 | 4 | 0.15 | 0.09 | 0.96 | 1.35 | 2.62 | 6 |
| LRC045 | 87 | 88 | 9 | 0.15 | 8.17 | 3.20 | 0.04 | 30.11 | 6 |
| LRC045 | 88 | 89 | 7 | 0.15 | 0.02 | 2.54 | 5.48 | 8.01 | 6 |
| LRC045 | 89 | 90 | 4 | 0.4 | 2.20 | 1.09 | 0.04 | 8.40 | 6 |
| LRC045 | 90 | 91 | 6 | 0.2 | 0.03 | 0.48 | 2.34 | 3.03 | 6 |
| LRC045 | 91 | 92 | 3 | 0.15 | 0.02 | 0.16 | 4.65 | 4.94 | 6 |
| LRC046 | 34 | 35 | 2 | 0.2 | 0.22 | 0.76 | 0.05 | 1.52 | 6 |
| LRC046 | 35 | 36 | 69 | 0.85 | 0.58 | 1.97 | 0.08 | 5.53 | 6 |
| LRC046 | 36 | 37 | 50 | 1.2 | 0.67 | 0.91 | 0.17 | 4.51 | 6 |
| LRC046 | 37 | 38 | 16 | 1.8 | 4.30 | 4.40 | 0.13 | 18.77 | 6 |
| LRC046 | 38 | 39 | 8 | 3.25 | 2.80 | 1.54 | 0.11 | 11.10 | 6 |
| LRC046 | 39 | 40 | 20 | 0.7 | 9.00 | 5.60 | 0.25 | 35.53 | 6 |
| LRC046 | 40 | 41 | 12 | 0.15 | 4.20 | 2.20 | 0.15 | 16.30 | 6 |
| LRC046 | 41 | 42 | 6 | 0.2 | 2.70 | 1.34 | 0.05 | 10.33 | 6 |
| LRC046 | 42 | 43 | 11 | 0.5 | 5.00 | 2.20 | 0.07 | 18.85 | 6 |
| LRC046 | 43 | 44 | 9 | 0.3 | 4.10 | 2.30 | 0.17 | 16.01 | 6 |
| LRC046 | 44 | 45 | 8 | 0.2 | 4.70 | 1.30 | 0.21 | 17.10 | 6 |
| LRC046 | 45 | 46 | 6 | 0.55 | 1.76 | 0.99 | 0.11 | 6.99 | 6 |
| LRC046 | 46 | 47 | 12 | 0.2 | 0.37 | 30.00 | 7.80 | 36.33 | 6 |
| LRC046 | 47 | 48 | 4 | 0.2 | 0.13 | 1.28 | 1.80 | 3.49 | 6 |
| LRC046 | 48 | 49 | 4 | 0.2 | 0.12 | 0.44 | 4.90 | 5.80 | 6 |
| LRC046 | 49 | 50 | 4 | 0.2 | 0.23 | 0.14 | 7.80 | 8.79 | 6 |
| LRC046 | 50 | 51 | 5 | 0.2 | 0.18 | 0.85 | 4.50 | 6.00 | 6 |
| LRC046 | 51 | 52 | 10 | 0.2 | 0.33 | 4.20 | 8.50 | 13.63 | 6 |
| LRC046 | 52 | 53 | 13 | 0.2 | 0.22 | 2.60 | 6.30 | 9.70 | 6 |
| LRC046 | 53 | 54 | 10 | 0.2 | 0.28 | 3.60 | 6.70 | 11.12 | 6 |
| LRC046 | 54 | 55 | 5 | 0.15 | 0.06 | 1.28 | 2.12 | 3.60 | 6 |
| LRC046 | 55 | 56 | 8 | 0.15 | 0.08 | 2.80 | 4.40 | 7.40 | 6 |
| LRC046 | 56 | 57 | 7 | 0.15 | 0.18 | 1.69 | 5.90 | 8.19 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|------|----|--------|--------|------|-------|------|--------|------------|
| LRC046 | 57 | 58 | 3 | 0.15 | 0.04 | 0.72 | 2.77 | 3.62 | 6 |
| LRC046 | 58 | 59 | 3 | | 0.05 | 0.41 | 1.24 | 1.86 | 6 |
| LRC046 | 59 | 60 | | | 0.00 | 5.20 | 0.25 | 4.94 | 6 |
| LRC046 | 60 | 61 | 5 | 0.15 | 0.03 | 0.75 | 1.62 | 2.53 | 6 |
| LRC046 | 61 | 62 | 12 | 0.2 | 0.22 | 2.50 | 5.50 | 8.79 | 6 |
| LRC046 | 62 | 63 | 12 | 1.15 | 0.50 | 4.40 | 7.10 | 13.07 | 6 |
| LRC046 | 63 | 64 | 7 | 0.15 | 0.22 | 1.52 | 6.20 | 8.48 | 6 |
| LRC046 | 64 | 65 | 4 | 0.2 | 0.06 | 0.19 | 1.77 | 2.24 | 6 |
| LRC046 | 65 | 66 | 2 | 0.2 | 0.05 | 0.06 | 0.23 | 0.50 | 6 |
| LRC046 | 66 | 67 | 2 | 0.2 | 0.36 | 0.05 | 0.24 | 1.54 | 6 |
| LRC046 | 67 | 68 | 5 | 1.25 | 0.52 | 0.33 | 0.91 | 3.11 | 6 |
| LRC048 | 11 | 12 | 38 | 0.9 | 0.10 | 2.58 | 0.22 | 3.85 | 6 |
| LRC048 | 12 | 13 | 73 | 25.85 | 0.13 | 16.23 | 0.16 | 18.30 | 6 |
| LRC048 | 13 | 14 | 52 | 12.85 | 0.16 | 4.15 | 0.25 | 6.45 | 6 |
| LRC048 | 14 | 15 | 17 | 1.1 | 0.07 | 1.62 | 0.12 | 2.28 | 6 |
| LRC048 | 15 | 16 | 13 | 0.4 | 0.04 | 0.55 | 0.07 | 1.04 | 6 |
| LRC048 | 16 | 17 | 33 | 0.45 | 0.00 | 0.18 | 0.05 | 1.06 | 6 |
| LRC048 | 17 | 18 | 113 | 0.45 | 0.01 | 0.24 | 0.04 | 3.15 | 6 |
| LRC048 | 18 | 19 | 167 | 0.15 | 0.03 | 0.32 | 0.06 | 4.62 | 6 |
| LRC048 | 19 | 20 | 50 | 0.3 | 0.02 | 0.83 | 0.06 | 2.14 | 6 |
| LRC048 | 20 | 21 | 21 | 0.9 | 0.02 | 0.91 | 0.05 | 1.50 | 6 |
| LRC048 | 21 | 22 | 24 | 0.3 | 0.01 | 0.85 | 0.05 | 1.48 | 6 |
| LRC048 | 22 | 23 | 56 | 0.45 | 0.02 | 4.20 | 0.05 | 5.33 | 6 |
| LRC048 | 23 | 24 | 39 | 0.35 | 0.03 | 1.06 | 0.01 | 2.07 | 6 |
| LRC048 | 24 | 25 | 47 | 5.85 | 0.08 | 4.72 | 0.04 | 6.03 | 6 |
| LRC048 | 25 | 26 | 54 | 0.5 | 0.06 | 1.75 | 0.04 | 3.19 | 6 |
| LRC048 | 26 | 27 | 47 | 6.45 | 0.41 | 3.84 | 0.13 | 6.43 | 6 |
| LRC048 | 27 | 28 | 23 | 2.7 | 0.56 | 1.29 | 0.13 | 3.85 | 6 |
| LRC048 | 28 | 29 | 39 | 0.65 | 0.27 | 0.63 | 0.05 | 2.51 | 6 |
| LRC048 | 29 | 30 | 113 | 1.3 | 0.02 | 2.57 | 0.06 | 5.32 | 6 |
| LRC048 | 30 | 31 | 188 | 2.5 | 0.02 | 4.58 | 0.05 | 9.07 | 6 |
| LRC048 | 31 | 32 | 36 | 0.5 | 0.01 | 1.05 | 0.04 | 1.96 | 6 |
| LRC048 | 32 | 33 | 11 | 0.4 | 0.02 | 0.45 | 1.81 | 2.59 | 6 |
| LRC048 | 33 | 34 | 7 | 0.2 | 0.10 | 0.38 | 1.44 | 2.30 | 6 |
| LRC049 | 42 | 43 | 8 | 0.15 | 0.00 | 0.02 | 0.83 | 1.07 | 6 |
| LRC049 | 43 | 44 | 72 | 0.35 | 0.01 | 0.15 | 2.70 | 4.68 | 6 |
| LRC049 | 44 | 45 | 64 | 2 | 0.07 | 0.90 | 5.20 | 7.95 | 6 |
| LRC049 | 45 | 46 | 15 | 0.3 | 0.02 | 0.68 | 2.20 | 3.26 | 6 |
| LRC049 | 46 | 47 | 9 | 0.35 | 0.04 | 1.05 | 2.60 | 3.90 | 6 |
| LRC049 | 47 | 48 | 8 | 0.25 | 0.03 | 0.93 | 2.10 | 3.25 | 6 |
| LRC049 | 48 | 49 | 6 | 0.25 | 0.09 | 1.44 | 3.00 | 4.75 | 6 |
| LRC049 | 49 | 50 | 3 | 0.1 | 0.08 | 0.80 | 2.20 | 3.25 | 6 |
| LRC049 | 50 | 51 | 9 | 0.15 | 0.23 | 4.20 | 7.30 | 12.07 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|----|--------|--------|------|-------|-------|--------|------------|
| LRC049 | 51 | 52 | 2 | 0.15 | 0.03 | 0.50 | 3.10 | 3.71 | 6 |
| LRC049 | 52 | 53 | 3 | 0.25 | 0.11 | 0.11 | 1.14 | 1.71 | 6 |
| LRC050 | 19 | 20 | 38 | 2.3 | 0.10 | 0.66 | 0.31 | 2.29 | 6 |
| LRC050 | 20 | 21 | 38 | 2.8 | 0.07 | 0.59 | 0.24 | 2.08 | 6 |
| LRC050 | 21 | 22 | 48 | 1.25 | 0.07 | 0.63 | 0.25 | 2.30 | 6 |
| LRC050 | 22 | 23 | 28 | 0.3 | 0.07 | 0.39 | 0.29 | 1.57 | 6 |
| LRC050 | 23 | 24 | 26 | 1.45 | 0.09 | 0.87 | 0.43 | 2.24 | 6 |
| LRC050 | 24 | 25 | 80 | 3.85 | 0.07 | 0.37 | 0.13 | 2.87 | 6 |
| LRC050 | 25 | 26 | 226 | 2.8 | 0.07 | 1.18 | 0.26 | 7.35 | 6 |
| LRC050 | 26 | 27 | 380 | 4.95 | 0.01 | 2.82 | 0.34 | 12.67 | 6 |
| LRC050 | 27 | 28 | 172 | 3.3 | 0.04 | 1.20 | 0.13 | 5.81 | 6 |
| LRC050 | 28 | 29 | 82 | 1.72 | 0.01 | 0.87 | 0.04 | 3.00 | 6 |
| LRC050 | 29 | 30 | 77 | 3.55 | 0.11 | 0.82 | 0.18 | 3.37 | 6 |
| LRC050 | 30 | 31 | 40 | 2.1 | 0.10 | 0.85 | 0.61 | 2.82 | 6 |
| LRC050 | 31 | 32 | 38 | 2.3 | 0.12 | 1.60 | 3.75 | 6.65 | 6 |
| LRC050 | 32 | 33 | 18 | 2.05 | 0.06 | 0.75 | 2.49 | 3.91 | 6 |
| LRC050 | 33 | 34 | 120 | 0.2 | 1.29 | 9.43 | 17.88 | 33.63 | 6 |
| LRC050 | 34 | 35 | 120 | 0.2 | 0.87 | 10.13 | 17.50 | 32.50 | 6 |
| LRC050 | 35 | 36 | 98 | 0.45 | 0.32 | 6.86 | 13.88 | 23.58 | 6 |
| LRC050 | 36 | 37 | 40 | 0.45 | 0.24 | 2.28 | 3.79 | 7.66 | 6 |
| LRC050 | 37 | 38 | 22 | 0.25 | 0.15 | 0.03 | 1.88 | 2.95 | 6 |
| LRC050 | 38 | 39 | 38 | 0.35 | 0.28 | 2.11 | 3.57 | 7.36 | 6 |
| LRC050 | 39 | 40 | 80 | 13.4 | 0.56 | 6.30 | 12.70 | 22.89 | 6 |
| LRC050 | 40 | 41 | 64 | 3.95 | 0.57 | 8.10 | 14.70 | 25.67 | 6 |
| LRC050 | 41 | 42 | 40 | 5.85 | 0.26 | 4.30 | 8.70 | 14.72 | 6 |
| LRC050 | 42 | 43 | 18 | 0.7 | 0.11 | 1.34 | 4.20 | 6.25 | 6 |
| LRC050 | 43 | 44 | 20 | 0.5 | 0.20 | 2.10 | 5.60 | 8.68 | 6 |
| LRC050 | 44 | 45 | 27 | 1.05 | 0.18 | 3.10 | 5.90 | 10.01 | 6 |
| LRC050 | 45 | 46 | 62 | 2.8 | 0.13 | 2.40 | 5.40 | 9.67 | 6 |
| LRC050 | 46 | 47 | 58 | 4.55 | 0.13 | 1.66 | 4.00 | 7.60 | 6 |
| LTD0001 | 75.57 | 76 | 1.2 | 0.3 | 0.00 | 0.02 | 0.07 | 0.13 | 6 |
| LTD0001 | 76 | 77 | 4.5 | 0.32 | 0.03 | 0.17 | 0.37 | 0.76 | 6 |
| LTD0001 | 77 | 78 | 6.9 | 0.2 | 0.08 | 1.18 | 2.88 | 4.38 | 6 |
| LTD0001 | 78 | 79 | 20.3 | 0.16 | 0.02 | 2.43 | 4.40 | 7.17 | 6 |
| LTD0001 | 79 | 80 | 32.3 | 0.65 | 0.14 | 2.09 | 5.45 | 8.64 | 6 |
| LTD0001 | 80 | 81 | 1.8 | 0.02 | 0.01 | 0.04 | 0.12 | 0.23 | 6 |
| LTD0001 | 81 | 82 | 2.1 | 0.02 | 0.01 | 0.07 | 0.11 | 0.24 | 6 |
| LTD0001 | 82 | 83 | 3 | 0.06 | 0.02 | 0.12 | 0.13 | 0.37 | 6 |
| LTD0001 | 83 | 84 | 3.8 | 0.08 | 0.00 | 0.03 | 0.07 | 0.22 | 6 |
| LTD0001 | 84 | 85 | 278 | 3.91 | 0.12 | 1.15 | 2.23 | 10.79 | 6 |
| LTD0001 | 85 | 86 | 158 | 0.7 | 0.05 | 0.51 | 0.95 | 5.58 | 6 |
| LTD0001 | 86 | 87 | 25.3 | 0.7 | 0.01 | 0.06 | 0.32 | 1.07 | 6 |
| LTD0001 | 87 | 88 | 133 | 0.46 | 0.02 | 0.18 | 0.31 | 3.89 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|------|--------|------------|
| LTD0001 | 88 | 89 | 17.1 | 0.08 | 0.01 | 0.04 | 0.15 | 0.64 | 6 |
| LTD0001 | 89 | 90 | 109 | 0.09 | 0.01 | 0.24 | 0.50 | 3.49 | 6 |
| LTD0001 | 90 | 91 | 144 | 0.22 | 0.01 | 0.18 | 0.52 | 4.33 | 6 |
| LTD0001 | 91 | 92 | 32.5 | 3.02 | 0.02 | 0.41 | 0.70 | 2.11 | 6 |
| LTD0001 | 92 | 92.31 | 4.4 | 0.04 | 0.00 | 0.04 | 0.07 | 0.23 | 6 |
| LTD0005 | 99.86 | 100 | -0.2 | 0.01 | 0.00 | 0.00 | 0.06 | 0.06 | 6 |
| LTD0005 | 100 | 101 | -0.2 | 0.01 | 0.00 | 0.00 | 0.07 | 0.07 | 6 |
| LTD0005 | 101 | 102 | 0.2 | 0.01 | 0.00 | 0.00 | 0.02 | 0.03 | 6 |
| LTD0005 | 102 | 103 | -0.2 | -0.01 | 0.00 | 0.00 | 0.05 | 0.05 | 6 |
| LTD0005 | 103 | 104 | 0.3 | 0.01 | 0.00 | 0.00 | 0.30 | 0.31 | 6 |
| LTD0005 | 104 | 105 | 1.2 | 0.07 | 0.33 | 0.00 | 4.42 | 5.54 | 6 |
| LTD0005 | 105 | 105.5 | 0.3 | 0.15 | 0.03 | 0.00 | 1.10 | 1.22 | 6 |
| LTD0005 | 105.5 | 106 | 0.3 | 0.05 | 0.01 | 0.00 | 0.09 | 0.14 | 6 |
| LTD0005 | 106 | 107 | -0.2 | 0.01 | 0.01 | 0.00 | 0.12 | 0.15 | 6 |
| LTD0005 | 107 | 108 | -0.2 | 0.01 | 0.10 | 0.00 | 0.13 | 0.44 | 6 |
| LTD0005 | 108 | 109 | 0.3 | 0.02 | 0.05 | 0.00 | 1.03 | 1.19 | 6 |
| LTD0005 | 109 | 110 | -0.2 | 0.01 | 0.00 | 0.00 | 0.22 | 0.22 | 6 |
| LTD0005 | 110 | 111 | -0.2 | 0.01 | 0.00 | 0.00 | 0.22 | 0.22 | 6 |
| LTD0005 | 111 | 112 | -0.2 | 0.01 | 0.00 | 0.00 | 0.03 | 0.03 | 6 |
| LTD0005 | 112 | 113 | -0.2 | -0.01 | 0.00 | 0.00 | 0.01 | 0.01 | 6 |
| LTD0005 | 113 | 114 | -0.2 | 0.02 | 0.00 | 0.00 | 0.03 | 0.03 | 6 |
| LTD0005 | 114 | 115 | -0.2 | 0.01 | 0.00 | 0.00 | 0.02 | 0.02 | 6 |
| LTD0005 | 115 | 116 | -0.2 | -0.01 | 0.04 | 0.00 | 0.03 | 0.16 | 6 |
| LTD0005 | 116 | 117 | 0.7 | 0.02 | 0.27 | 0.00 | 0.04 | 0.96 | 6 |
| LTD0005 | 117 | 118 | 0.5 | 0.01 | 0.21 | 0.00 | 0.03 | 0.74 | 6 |
| LTD0005 | 118 | 119 | 0.3 | 0.01 | 0.13 | 0.00 | 0.04 | 0.49 | 6 |
| LTD0005 | 119 | 120 | -0.2 | -0.01 | 0.01 | 0.00 | 0.14 | 0.16 | 6 |
| LTD0005 | 120 | 121 | -0.2 | -0.01 | 0.00 | 0.00 | 0.02 | 0.02 | 6 |
| LTD0005 | 121 | 122 | -0.2 | -0.01 | 0.00 | 0.00 | 0.01 | 0.01 | 6 |
| LTD0005 | 122 | 123 | -0.2 | -0.01 | 0.00 | 0.00 | 0.01 | 0.01 | 6 |
| LTD0005 | 123 | 124 | -0.2 | -0.01 | 0.00 | 0.00 | 0.27 | 0.27 | 6 |
| LTD0005 | 124 | 125 | -0.2 | -0.01 | 0.00 | 0.00 | 0.03 | 0.02 | 6 |
| LTD0005 | 125 | 126 | -0.2 | -0.01 | 0.00 | 0.00 | 0.03 | 0.03 | 6 |
| LTD0005 | 126 | 127 | 1.3 | -0.01 | 0.00 | 0.00 | 0.02 | 0.06 | 6 |
| LTD0005 | 127 | 128 | 0.6 | -0.01 | 0.09 | 0.00 | 0.02 | 0.34 | 6 |
| LTD0005 | 128 | 129 | 0.6 | 0.01 | 0.08 | 0.01 | 0.04 | 0.32 | 6 |
| LTD0005 | 129 | 130 | 0.4 | 0.01 | 0.04 | 0.00 | 0.01 | 0.14 | 6 |
| LTD0005 | 130 | 131 | 0.5 | -0.01 | 0.11 | 0.00 | 0.63 | 0.99 | 6 |
| LTD0005 | 131 | 132 | 1.8 | 0.01 | 1.10 | 0.01 | 0.91 | 4.59 | 6 |
| LTD0006 | 78.36 | 79 | 0.6 | -0.01 | 0.00 | 0.01 | 0.09 | 0.12 | 6 |
| LTD0006 | 79 | 80 | 0.4 | -0.01 | 0.00 | 0.01 | 0.06 | 0.10 | 6 |
| LTD0006 | 80 | 81 | 0.3 | -0.01 | 0.00 | 0.00 | 0.04 | 0.06 | 6 |
| LTD0006 | 81 | 82 | 0.3 | -0.01 | 0.00 | 0.00 | 0.05 | 0.07 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|------|--------|------------|
| LTD0006 | 82 | 83 | 0.2 | -0.01 | 0.00 | 0.00 | 0.02 | 0.03 | 6 |
| LTD0006 | 83 | 83.7 | 19.2 | 0.06 | 0.01 | 0.19 | 0.37 | 1.06 | 6 |
| LTD0006 | 83.7 | 84.1 | 6.5 | 0.05 | 0.00 | 0.11 | 0.25 | 0.52 | 6 |
| LTD0006 | 84.1 | 85 | 1.1 | -0.01 | 0.01 | 0.12 | 0.25 | 0.42 | 6 |
| LTD0006 | 85 | 86 | 0.5 | -0.01 | 0.00 | 0.04 | 0.09 | 0.15 | 6 |
| LTD0006 | 86 | 87 | 47.2 | 1.86 | 0.23 | 2.18 | 4.12 | 8.12 | 6 |
| LTD0006 | 87 | 88 | 13.5 | 5.18 | 0.13 | 1.98 | 4.90 | 7.71 | 6 |
| LTD0006 | 88 | 89 | 13.7 | 16.45 | 0.48 | 4.72 | 7.40 | 14.38 | 6 |
| LTD0006 | 89 | 89.9 | 12.1 | 2.84 | 0.43 | 4.47 | 5.03 | 10.91 | 6 |
| LTD0006 | 89.9 | 90.5 | 4.6 | 0.58 | 0.16 | 1.79 | 3.36 | 5.64 | 6 |
| LTD0006 | 90.5 | 91 | 4.5 | 0.2 | 0.28 | 1.82 | 3.45 | 6.12 | 6 |
| LTD0006 | 91 | 92 | 6.9 | 0.1 | 0.31 | 3.46 | 4.78 | 9.08 | 6 |
| LTD0006 | 92 | 93 | 1.9 | 0.04 | 0.05 | 0.87 | 1.97 | 2.97 | 6 |
| LTD0006 | 93 | 94 | 0.9 | 0.02 | 0.07 | 0.51 | 0.94 | 1.63 | 6 |
| LTD0006 | 94 | 95 | 5.9 | 0.2 | 0.30 | 1.74 | 5.24 | 7.94 | 6 |
| LTD0006 | 95 | 95.82 | 2.7 | 0.08 | 0.16 | 0.24 | 3.60 | 4.41 | 6 |
| LTD0008 | 153.71 | 154.05 | 5.7 | 0.94 | 0.16 | 1.89 | 2.48 | 4.88 | 6 |
| LTD0008 | 154.05 | 155.05 | 6.3 | 0.11 | 0.17 | 1.34 | 2.51 | 4.44 | 6 |
| LTD0008 | 155.05 | 156.05 | 3.5 | 0.08 | 0.22 | 0.33 | 3.05 | 4.16 | 6 |
| LTD0008 | 156.05 | 157.05 | 2.3 | 0.03 | 0.01 | 0.03 | 0.99 | 1.13 | 6 |
| LTD0008 | 157.05 | 158.05 | 3.7 | 0.04 | 0.02 | 0.03 | 0.97 | 1.14 | 6 |
| LTD0008 | 158.05 | 159.05 | 3.2 | 0.06 | 0.01 | 0.02 | 1.80 | 1.93 | 6 |
| LTD0008 | 159.05 | 159.42 | 3.1 | 0.05 | 0.01 | 0.00 | 1.67 | 1.78 | 6 |
| LTD0010 | 186 | 187 | 4.4 | 0.17 | 0.20 | 0.19 | 6.34 | 7.28 | 6 |
| LTD0010 | 187 | 188 | 5.3 | 0.24 | 0.11 | | 2.40 | 2.89 | 6 |
| LTD0010 | 188 | 189 | 1.5 | 0.1 | 0.02 | 0.02 | 1.49 | 1.62 | 6 |
| LTD0010 | 189 | 190 | 6.8 | 0.1 | 0.36 | 1.17 | 2.55 | 4.95 | 6 |
| LTD0010 | 190 | 191 | 1.3 | 0.09 | 0.14 | 0.00 | 0.06 | 0.55 | 6 |
| LTD0010 | 191 | 192 | 0.5 | 0.05 | 0.00 | 0.00 | 0.02 | 0.05 | 6 |
| LTD0010 | 192 | 193 | 0.8 | 0.06 | 0.01 | 0.01 | 0.04 | 0.08 | 6 |
| LTD0010 | 193 | 194 | 2.1 | 0.08 | 0.08 | 0.00 | 0.33 | 0.64 | 6 |
| LTD0011 | 130.55 | 131.1 | 2.7 | 0.05 | 0.08 | 0.09 | 6.61 | 7.04 | 6 |
| LTD0011 | 131.1 | 132 | 2.4 | 0.06 | 0.06 | 0.15 | 0.82 | 1.22 | 6 |
| LTD0011 | 132 | 133 | 2.4 | 0.42 | 0.02 | 0.44 | 0.82 | 1.37 | 6 |
| LTD0011 | 133 | 134 | 2.9 | 0.26 | 0.04 | 1.13 | 1.72 | 2.95 | 6 |
| LTD0011 | 134 | 135 | 1.2 | 0.37 | 0.05 | 0.53 | 1.55 | 2.24 | 6 |
| LTD0011 | 135 | 135.65 | 0.5 | 0.08 | 0.05 | 0.03 | 1.25 | 1.45 | 6 |
| LTD0011 | 135.65 | 136.2 | 5.8 | 0.13 | 0.12 | 1.91 | 5.55 | 7.82 | 6 |
| LTD0011 | 136.2 | 137 | 6.5 | 0.28 | 0.08 | 1.73 | 3.63 | 5.64 | 6 |
| LTD0011 | 137 | 138 | 1.3 | 0.05 | 0.08 | 0.05 | 3.51 | 3.85 | 6 |
| LTD0011 | 138 | 139 | 1.9 | 0.06 | 0.02 | 0.00 | 0.60 | 0.73 | 6 |
| LTD0011 | 139 | 140 | 0.8 | 0.12 | 0.00 | 0.01 | 0.13 | 0.18 | 6 |
| LTD0011 | 140 | 141 | 0.8 | 0.07 | 0.00 | 0.01 | 0.03 | 0.06 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|-------|-------|--------|--------|------|------|-------|--------|------------|
| LTD0011 | 141 | 142 | 0.6 | 0.02 | 0.00 | 0.00 | 0.02 | 0.03 | 6 |
| LTD0011 | 142 | 142.8 | 1 | 0.04 | 0.02 | 0.00 | 0.36 | 0.43 | 6 |
| LTD0011 | 142.8 | 143.7 | 1.3 | 0.03 | 0.09 | 0.00 | 2.06 | 2.38 | 6 |
| LTD0012 | 238.5 | 239.5 | -0.2 | -0.01 | 0.00 | 0.00 | 0.02 | 0.03 | 6 |
| LTD0012 | 239.5 | 240 | 3.2 | 0.03 | 2.22 | 0.00 | 0.04 | 7.45 | 6 |
| LTD0012 | 240 | 240.6 | 4.9 | 0.04 | 1.71 | 0.01 | 0.12 | 5.90 | 6 |
| LTD0018 | 181 | 182 | 35.4 | 0.72 | 0.77 | 9.51 | 26.70 | 38.70 | 6 |
| LTD0018 | 182 | 183 | 4.6 | 0.32 | 0.06 | 0.97 | 2.33 | 3.54 | 6 |
| LTD0018 | 183 | 184 | 18.8 | 0.86 | 0.30 | 5.78 | 9.20 | 15.90 | 6 |
| LTD0018 | 184 | 185 | 12.7 | 0.58 | 0.41 | 4.25 | 5.77 | 11.28 | 6 |
| LTD0018 | 185 | 186 | 2.9 | 0.14 | 0.56 | 0.12 | 6.95 | 8.97 | 6 |
| LTD0018 | 186 | 187 | 3.5 | 0.11 | 0.58 | 0.24 | 9.64 | 11.87 | 6 |
| LTD0018 | 187 | 188 | 6.1 | 0.13 | 0.40 | 0.08 | 7.35 | 8.91 | 6 |
| LTD0018 | 188 | 189 | 3 | 0.04 | 0.06 | 0.05 | 2.18 | 2.50 | 6 |
| LTD0018 | 189 | 190 | 4.2 | 0.04 | 0.02 | | 3.04 | 3.22 | 6 |
| LTD0018 | 190 | 191 | 2.5 | 0.01 | 0.00 | 0.02 | 0.66 | 0.76 | 6 |
| LTD0018 | 191 | 192 | 0.9 | 0.02 | 0.00 | 0.01 | 0.83 | 0.87 | 6 |
| LTD0018 | 192 | 193 | 4.5 | 0.11 | 0.14 | 0.02 | 15.05 | 15.64 | 6 |
| LTD0018 | 193 | 194 | 2 | 0.02 | 0.01 | 0.01 | 2.46 | 2.56 | 6 |
| LTD0019 | 218 | 219 | 3.5 | 0.1 | 0.06 | 0.60 | 1.34 | 2.18 | 6 |
| LTD0019 | 219 | 220 | 12 | 0.21 | 0.25 | 1.89 | 8.27 | 11.09 | 6 |
| LTD0019 | 220 | 221 | 2 | 0.07 | 0.33 | 0.02 | 5.25 | 6.40 | 6 |
| LTD0019 | 221 | 222 | 2.3 | 0.04 | 0.01 | 0.03 | 1.99 | 2.12 | 6 |
| LTD0019 | 222 | 223 | 1.5 | 0.02 | 0.01 | 0.01 | 0.49 | 0.56 | 6 |
| LTD0019 | 223 | 224 | 1.9 | 0.05 | 0.05 | 0.01 | 1.89 | 2.12 | 6 |
| LTD0019 | 224 | 225 | 2.3 | 0.05 | 0.08 | 0.01 | 2.51 | 2.83 | 6 |
| LTD0019 | 225 | 226 | 3 | 0.09 | 0.23 | 0.02 | 9.33 | 10.17 | 6 |
| LTD0019 | 226 | 227 | 7.7 | 0.12 | 0.37 | 0.89 | 10.30 | 12.51 | 6 |
| LTD0019 | 227 | 228 | 5.1 | 0.08 | 0.32 | 0.28 | 6.01 | 7.45 | 6 |
| LTD0019 | 228 | 229 | 3.1 | 0.09 | 0.05 | 0.06 | 4.95 | 5.24 | 6 |
| LTD0019 | 229 | 230 | 5.2 | 0.06 | 0.18 | 0.08 | 3.95 | 4.75 | 6 |
| LTD0019 | 230 | 230.5 | 0.4 | -0.01 | 0.01 | 0.01 | 0.29 | 0.33 | 6 |
| LTD0019 | 230.5 | 231 | 0.8 | 0.02 | 0.01 | 0.01 | 0.98 | 1.03 | 6 |
| LTD0019 | 231 | 232 | 1.6 | 0.05 | 0.12 | 0.01 | 4.29 | 4.73 | 6 |
| LTD0019 | 232 | 233 | 0.9 | 0.02 | 0.02 | 0.01 | 0.52 | 0.61 | 6 |
| LTD0019 | 233 | 233.4 | 0.4 | 0.01 | 0.01 | 0.00 | 0.15 | 0.20 | 6 |
| LTD0019 | 233.4 | 234 | 0.9 | 0.02 | 0.09 | 0.01 | 1.40 | 1.72 | 6 |
| LTD0019 | 234 | 235 | 2.9 | 0.07 | 0.60 | 0.01 | 3.86 | 5.91 | 6 |
| LTD0020 | 291 | 291.5 | 1 | 0.04 | 0.00 | 0.07 | 1.33 | 1.43 | 6 |
| LTD0020 | 291.5 | 292 | 2.2 | 0.06 | 0.51 | 0.12 | 2.71 | 4.56 | 6 |
| LTD0020 | 292 | 293 | 1.6 | 0.04 | 0.19 | 0.15 | 2.94 | 3.75 | 6 |
| LTD0023 | 209 | 209.5 | | 0.08 | 0.05 | 0.72 | 1.50 | 2.32 | 6 |
| LTD0023 | 209.5 | 210 | | 0.05 | 0.06 | 0.73 | 1.18 | 2.05 | 6 |

| Hole_ID | From | To | Ag_ppm | Au_ppm | Cu% | Pb% | Zn% | Zn_Eq% | Ore Domain |
|---------|--------|--------|--------|--------|------|------|------|--------|------------|
| LTD0023 | 210 | 211 | | 0.04 | 0.07 | 1.08 | 2.07 | 3.29 | 6 |
| LTD0023 | 211 | 211.94 | | 0.02 | 0.04 | 0.23 | 0.64 | 0.97 | 6 |
| LTD0027 | 177 | 177.6 | 2 | 0.83 | 0.41 | 0.24 | 0.55 | 2.21 | 6 |
| LTD0027 | 177.6 | 178.2 | 79 | 10.6 | 5.25 | 5.96 | 7.46 | 32.65 | 6 |
| LTD0027 | 178.2 | 179 | 0 | 3.39 | 0.04 | 0.01 | 0.03 | 0.33 | 6 |
| LTD0027 | 179 | 180 | 0 | 0.17 | 0.50 | 0.00 | 0.12 | 1.75 | 6 |
| LTD0033 | 318 | 319 | 4 | 0.11 | 0.77 | 0.04 | 0.13 | 2.81 | 6 |
| LTD0033 | 319 | 320 | 39 | 2.95 | 5.30 | 0.81 | 2.03 | 21.37 | 6 |
| LTD0033 | 320 | 321 | 13 | 1.63 | 2.28 | 0.17 | 1.40 | 9.48 | 6 |
| LTD0033 | 321 | 322 | 0 | 0.03 | 0.17 | 0.00 | 0.02 | 0.54 | 6 |
| LTD0033 | 322 | 323 | 0 | 0.03 | 0.17 | 0.01 | 0.05 | 0.60 | 6 |
| LTD0033 | 323 | 324 | 7 | 0.21 | 1.04 | 0.07 | 0.41 | 4.09 | 6 |
| LLD007 | 160.93 | 161.24 | | | 0.25 | 0.01 | 0.08 | 0.90 | 3 |
| LLD007 | 161.24 | 161.54 | | | 0.11 | 0.02 | 0.15 | 0.54 | 3 |
| LLD007 | 161.54 | 161.85 | | | 0.10 | 0.02 | 0.12 | 0.47 | 3 |
| LLD007 | 161.85 | 162.15 | | | 0.26 | 0.02 | 0.23 | 1.10 | 3 |
| LLD007 | 162.15 | 162.31 | | | 1.83 | 0.01 | 4.24 | 10.29 | 3 |
| LLD007 | 162.31 | 162.46 | | | 2.09 | 0.01 | 4.32 | 11.23 | 3 |
| LLD007 | 162.46 | 162.76 | | | 0.52 | 0.01 | 1.15 | 2.88 | 3 |
| LLD007 | 162.76 | 163.07 | | | 0.14 | 0.01 | 0.29 | 0.74 | 3 |
| LLD007 | 163.07 | 164.59 | | | 0.08 | 0.01 | 0.26 | 0.53 | 3 |
| LLD007 | 164.59 | 166.12 | | | 0.05 | 0.00 | 0.19 | 0.35 | 3 |
| LLD007 | 166.12 | 166.42 | | | 0.03 | 0.01 | 1.08 | 1.19 | 3 |
| LLD007 | 166.42 | 167.03 | | | 0.03 | 0.01 | 1.20 | 1.29 | 3 |
| LLD007 | 167.03 | 167.18 | | | 0.12 | 0.01 | 0.82 | 1.22 | 3 |
| LLD007 | 167.18 | 167.34 | | | 0.48 | 0.05 | 1.00 | 2.63 | 3 |
| LLD007 | 167.34 | 167.49 | | | 1.54 | 0.01 | 0.70 | 5.79 | 3 |
| LLD007 | 167.49 | 167.64 | | | 0.38 | 0.01 | 0.18 | 1.43 | 3 |
| LLD007 | 167.64 | 168.25 | | | 0.11 | 0.01 | 0.11 | 0.50 | 3 |
| LLD007 | 168.25 | 169.16 | | | 1.07 | 0.12 | 3.95 | 7.59 | 3 |
| LTD0034 | 219 | 220 | 11 | 0.12 | 3.06 | 0.03 | 1.55 | 11.96 | 3 |
| LTD0034 | 220 | 221 | 7 | 0.08 | 2.16 | 0.02 | 0.43 | 7.76 | 3 |
| LTD0034 | 221 | 222 | 11 | 0.1 | 2.44 | 0.04 | 0.82 | 9.18 | 3 |
| LTD0034 | 222 | 223 | 0 | -0.01 | 0.02 | 0.00 | 0.02 | 0.07 | 3 |
| LTD0034 | 223 | 224 | 0 | 0.02 | 0.02 | 0.00 | 0.04 | 0.07 | 3 |
| LTD0034 | 224 | 225 | 4 | 0.06 | 0.37 | 0.06 | 1.93 | 3.32 | 3 |
| LTD0034 | 225 | 226 | 13 | 0.15 | 0.87 | 0.39 | 6.45 | 10.00 | 3 |
| LTD0034 | 226 | 227 | 14 | 0.06 | 1.50 | 0.24 | 5.09 | 10.61 | 3 |

APPENDIX 4

LIONTOWN - DRILLHOLE COLLAR PLAN

